

INTERNATIONAL STANDARD

ISO
4600

Second edition
1992-08-15

Plastics — Determination of environmental stress cracking (ESC) — Ball or pin impression method

*Plastiques — Détermination de la fissuration sous contrainte dans un
environnement donné (ESC) — Méthode par enfoncement de billes ou
de goupilles*



Reference number
ISO 4600:1992(E)

AVA **Documents**
Document Sharing Hub

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 4600 was prepared by Technical Committee ISO/TC 61, *Plastics*, Sub-Committee SC 6, *Ageing, chemical and environmental resistance*.

This second edition cancels and replaces the first edition (ISO 4600:1981), of which it constitutes a technical revision.

© ISO 1992

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

Environmental stress cracking is exhibited by many materials, including plastics. When a plastic material is stressed or strained in air below its yield point, stress cracking can occur after a period of time, which may be very long. These stresses may be internal or external, or a combination of both. Exposure to a chemical medium simultaneously with the same stress or strain may result in a dramatic shortening of the time to failure. This phenomenon is referred to as environmental stress cracking (ESC). The permissible long-term stress or strain may be reduced considerably by this phenomenon.

The cracks produced may penetrate completely through the thickness of the material, separating it into two or more pieces, or they may be arrested on reaching regions of lower stress or different material morphology.

The determination of ESC is complex because it is influenced by many parameters, including:

- test specimen dimensions;
- test specimen state (orientation, structure, internal stresses);
- stress and strain;
- temperature of test;
- duration of test;
- chemical medium;
- test method;
- failure criterion.

By keeping all but one parameter constant, the influence of the variable parameter on ESC can be assessed. The main objective of ESC measurements is to determine the effect of chemical media (environment) on plastics (test specimens and articles). The measurements may also be used to evaluate the influence of the moulding conditions upon the quality of an article when the failure mode corresponds to that obtained in actual service. It may not be possible, however, to establish any direct correlation between the results of short-duration ESC measurements on test specimens and the actual service behaviour of articles, because the behaviour of the latter is likely to be more complex than that of test specimens.

Plastics — Determination of environmental stress cracking (ESC) — Ball or pin impression method

1 Scope

This International Standard specifies methods for the determination of environmental stress cracking (ESC) of plastics by means of a constant-strain test.

The test is applicable to finished products and to test specimens, prepared by moulding and/or machining, and can be used for the assessment of both ESC of a plastic product or material exposed to different environments, and for the determination of ESC of different plastics materials exposed to a specific environment.

NOTE 1 An alternative method for the determination of environmental stress cracking by means of a constant-strain test is specified in ISO 4599. A method for the determination of environmental stress cracking by means of a constant-stress test is specified in ISO 6252.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 178:1975, *Plastics — Determination of flexural properties of rigid plastics*.

ISO 291:1977, *Plastics — Standard atmospheres for conditioning and testing*.

ISO 293:1986, *Plastics — Compression moulding test specimens of thermoplastic materials*.

ISO 294:1975, *Plastics — Injection moulding test specimens of thermoplastic materials*.

ISO 468:1982, *Surface roughness — Parameters, their values and general rules for specifying requirements*.

ISO/R 527:1966, *Plastics — Determination of tensile properties*.

ISO 2557-1:1989, *Plastics — Amorphous thermoplastics — Preparation of test specimens with a specified maximum reversion — Part 1: Bars*.

ISO 2818:1980, *Plastics — Preparation of test specimens by machining*.

ISO 3167:1983, *Plastics — Preparation and use of multipurpose test specimens*.

ISO 4599:1986, *Plastics — Determination of resistance to environmental stress cracking (ESC) — Bent strip method*.

ISO 6252:1992, *Plastics — Determination of environmental stress cracking (ESC) — Constant-tensile-stress method*.

3 Definitions

For the purposes of this International Standard, the following definitions apply.

3.1 oversize (d_d): The difference between the diameter of an impressed steel ball or pin (d_b) and the diameter of the hole (d_h) drilled into the test specimen.

$$d_d = d_b - d_h$$

3.2 deformation step: A determination made at a defined oversize.

3.3 deformation step zero: A determination made using test specimens that are drilled and reamed only, i.e. without impressing a ball or pin.