

INTERNATIONAL STANDARD

**ISO
625**

Second edition
1996-02-15

Solid mineral fuels — Determination of carbon and hydrogen — Liebig method

*Combustibles minéraux solides — Dosage du carbone et de
l'hydrogène — Méthode de Liebig*



Reference number
ISO 625:1996
AVA Documents
Document Sharing Hub

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 625 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This second edition cancels and replaces the first edition (ISO 625:1975), which has been technically revised.

Annex A of this International Standard is for information only.

© ISO 1996

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

An alternative method to that specified in this International Standard is given in ISO 609:1996, *Solid mineral fuels — Determination of carbon and hydrogen — High temperature combustion method*.

Solid mineral fuels — Determination of carbon and hydrogen — Liebig method

1 Scope

This International Standard specifies a method of determining the total carbon and the total hydrogen in hard coal, brown coal and lignite, and coke, by the Liebig method.

The results include the carbon in the carbonates and the hydrogen combined in the moisture and in the water of constitution of silicates. A determination of moisture is carried out at the same time, and an appropriate correction is applied to the hydrogen value obtained by combustion. A determination of carbon dioxide may also be made and the total carbon value corrected for the presence of mineral carbonates.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 331:1983, *Coal — Determination of moisture in the analysis sample — Direct gravimetric method.*

ISO 687:1974, *Coke — Determination of moisture in the analysis sample.*

ISO 925:1980, *Solid mineral fuels — Determination of carbon dioxide content — Gravimetric method.*

ISO 1015:1992, *Brown coals and lignites — Determination of moisture content — Direct volumetric method.*

ISO 1170:1977, *Coal and coke — Calculation of analyses to different bases.*

ISO 1988:1975, *Hard coal — Sampling.*

ISO 2309:1980, *Coke — Sampling.*

ISO 5068:1983, *Brown coals and lignites — Determination of moisture content — Indirect gravimetric method.*

ISO 5069-2:1983, *Brown coals and lignites — Principles of sampling — Part 2: Sample preparation for determination of moisture content and for general analysis.*

3 Principle

A known mass of coal or coke is burnt in a current of oxygen in a tube impervious to gases, the products of the incomplete combustion being further burnt over copper oxide; all the hydrogen is converted to water and all the carbon to carbon dioxide. These products are absorbed by suitable reagents and determined gravimetrically. Oxides of sulfur are retained by lead chromate, chlorine by a silver gauze roll and oxides of nitrogen by granular manganese dioxide.

4 Reagents and materials

WARNING — Care should be exercised when handling reagents, many of which are toxic.

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.1 Magnesium perchlorate, anhydrous, less than 1,2 mm in size and preferably within the size range 1,2 mm to 0,7 mm.

WARNING — Due regard must be taken of local regulations when disposing of exhausted magnesium perchlorate. Regeneration of magnesium perchlorate must not be attempted, owing to the risk of explosion.

4.2 Sodium hydroxide on an inert base, preferably of a coarse grading, for example 3,0 mm to 1,5 mm, but not finer than the grading 1,2 mm to 0,7 mm, and preferably of the self-indicating type.

4.3 Manganese dioxide, granular, 1,2 mm to 0,7 mm.

Manganese dioxide in the granular form and the size required can be prepared as follows.

Dissolve manganese sulfate in water and boil the solution. Make the solution alkaline with ammonium hydroxide and add solid ammonium persulfate, in small portions, to the boiling solution until precipitation is complete. Filter through a hardened fast-filter paper, wash with water by decantation, then with dilute sulfuric acid and finally with water until acid-free. Transfer the moist precipitate to a mortar and place in an oven until most of the water has evaporated, but the powder is still damp. Press the mass into a cake with a pestle, using firm pressure. Complete the drying, break up the cake cautiously and sieve to separate the 1,2 mm to 0,7 mm size.

4.4 Copper gauze, of mesh approximately 1 mm and 10 mm wide.

4.5 Copper oxide, wire form, chopped to particles approximately 3 mm long with a diameter of approximately 0,2 mm.

4.6 Lead chromate, fused, size range 2,4 mm to 1,2 mm.

4.7 Pure silver gauze, of mesh approximately 1 mm, made of wire approximately 0,3 mm in diameter.

4.8 Oxygen, hydrogen-free, preferably prepared from liquid air and not by electrolysis. Electrolytically prepared oxygen shall be passed over red-hot copper oxide before use to remove any trace of hydrogen.

4.9 Glass wool.

5 Apparatus

5.1 Analytical balance, capable of weighing to the nearest 0,1 mg.

5.2 Purification train, for absorbing water vapour and carbon dioxide from the oxygen used for the combustion. Assemble the train using a series of U-tubes containing the following reagents in the order stated, in the direction of flow:

- magnesium perchlorate (4.1) for absorbing water;
- sodium hydroxide on an inert base (4.2) for absorbing carbon dioxide;
- magnesium perchlorate for absorbing the water evolved in the reaction between carbon dioxide and sodium hydroxide.

The purification train shall be large enough to render frequent recharging unnecessary, even with continuous use.

5.3 Combustion assembly

5.3.1 Furnaces. The combustion tube is heated by three furnaces. For the 1,25 mm combustion tube described in clause 6, the following approximate lengths are appropriate:

- furnace No. 1 (to heat the boat and its contents to 925 °C) — 250 mm;
- furnace No. 2 (to keep the entire copper oxide section of the tube heated to 800 °C) — 500 mm;
- furnace No. 3 (to cover the lead chromate and the roll of pure silver gauze and to heat the former to about 500 °C) — 200 mm.

5.3.2 Combustion tube, of fused silica or suitable hard glass. The diameter of the tube shall be 12 mm to 15 mm. A suitable length is 1,25 m.

5.3.3 Combustion boat, of platinum, porcelain or fused silica, approximately 70 mm long.

5.4 Absorption train, for absorbing the water and carbon dioxide evolved by the combustion of the sample. Assemble the train using the following reagents in the order stated, in the direction of flow.

- magnesium perchlorate (4.1) for absorbing the water evolved during the combustion;