

INTERNATIONAL STANDARD

**ISO
683-9**

First edition
1988-12-01



INTERNATIONAL ORGANIZATION FOR STANDARDIZATION
ORGANISATION INTERNATIONALE DE NORMALISATION
МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ

Heat-treatable steels, alloy steels and free-cutting steels —

Part 9 : Wrought free-cutting steels

Aciers pour traitement thermique, aciers alliés et aciers pour décolletage —

Partie 9: Aciers corroyés pour décolletage

Reference number
ISO 683-9:1988 (E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 683-9 was prepared by Technical Committee ISO/TC 17, *Steel*.

It cancels and replaces ISO Recommendation R 683-9 : 1970, of which it constitutes a technical revision.

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.

Heat-treatable steels, alloy steels and free-cutting steels —

Part 9 : Wrought free-cutting steels

0 Introduction

When preparing this part of ISO 683, it was very difficult to come to international agreements on chemical composition of free-cutting steels. The types of steel given in this part of ISO 683 are typical grades only and other grades may be covered by national standards.

1 Scope and field of application

1.1 This part of ISO 683 gives the technical delivery requirements for

- semi-finished products, e.g. blooms, billets, slabs,
- bars,
- wire rod and
- bright steel

manufactured from the free-cutting steels listed in table 3 and supplied in one of the treatment conditions given for the different types of products in table 1, lines 2 and 3, and in one of the surface conditions given in table 2.

This part of ISO 683 covers three groups of wrought free-cutting steels for mechanical purposes as listed in table 3, namely

- a) not intended for heat treatment,
- b) suitable for case-hardening,
- c) suitable for quenching and tempering.

NOTE — Related International Standards are given in annex C.

1.2 In special cases, variations in these technical delivery requirements or additions to them may form the subject of an agreement at the time of enquiry and order (see annex B).

1.3 In addition to this part of ISO 683, the general technical delivery requirements of ISO 404 are applicable.

2 References

ISO 377, *Wrought steel — Selection and preparation of samples and test pieces.*

ISO 404, *Steel and steel products — General technical delivery requirements.*

ISO 683, *Heat-treatable steels, alloy steels and free-cutting steels*

— *Part 1: Direct-hardening unalloyed and low-alloyed wrought steel in form of different black products.*

— *Part 11: Wrought case-hardening steels.*

ISO 1035, *Hot-rolled steel bars*

— *Part 1: Dimensions of round bars.*

— *Part 2: Dimensions of square bars.*

— *Part 3: Dimensions of flat bars.*

— *Part 4: Tolerances.*

ISO 6506, *Metallic materials — Hardness test — Brinell test.*

ISO 6892, *Metallic materials — Tensile testing.*

ISO 6929, *Steel products — Definitions and classification.*

3 Definitions

3.1 product forms: See ISO 6929.

3.2 free-cutting steels: In the sense of this part of ISO 683, steels characterized by good machinability, i.e. high metal removal rate, essentially obtained by higher than normal contents of sulfur, or sulfur and lead.

4 Ordering and designation

The designation of the product in an order shall cover the following:

- a) the designation of the product form (bloom, bar, wire rod, etc.) followed by
 - either the designation of the dimensional standard and the dimensions and tolerances selected from this (see 5.5),
 - or the designation of the drawing or any other document covering the dimensions and tolerances required for the product;
- b) if a surface condition other than "hot worked" or a special surface quality is required:
 - the surface condition (see table 2) and
 - the surface quality (see 5.4);
- c) a description of the steel comprising
 - 1) a reference to this part of ISO 683;
 - 2) the designation of the steel type given in table 3;
 - 3) if a treatment condition other than the untreated condition is required, the symbol for this other condition (see table 1, column 3);
 - 4) if a document is required, the symbol for the required type of document (see table 10);
 - 5) if any supplementary requirements are to be complied with, the symbol and, where necessary, the details of each supplementary requirement (see annex B).

Example:

To be ordered are:

Hot-rolled round bars,

according to ISO 1035-1,

with a nominal diameter of 40,0 mm,

with a nominal length of 8 000 mm,

with a diameter tolerance of $\pm 0,40$ mm (= class S of ISO 1035-4),

with a length tolerance of $+100^0$ mm (= class L2 of ISO 1035-4),

all other tolerances as given in ISO 1035-4, for normal cases.

Surface

peeled (symbol PE, see table 2).

Steel

according to this part of ISO 683,

type 35 S 20 (see table 3),

treatment condition: untreated (no symbol or U, see table 1),

with an inspection certificate of type IC (see table 10).

Designation:

Rounds: ISO 1035-1 – 40,0 S × 8 000 L2

Surface: PE

Steel: ISO 683-9 – 35 S 20 – U – IC

5 Requirements

5.1 Manufacturing process

5.1.1 The manufacturing process for the steel and for the products is, with the restrictions given by the requirements in 5.1.2 to 5.1.3, left to the discretion of the manufacturer.

5.1.2 Treatment and surface condition at delivery

In accordance with the agreements at the time of enquiry and order, the products shall be delivered in one of the treatment and surface conditions listed in tables 1 and 2 respectively.

5.1.3 Cast separation

The steels shall be delivered separated by casts.

5.2 Chemical composition, hardness and mechanical properties

5.2.1 Table 1 gives a survey of combinations of usual treatment conditions at delivery, product forms and requirements according to the tables 3 to 7 (chemical composition, maximum hardness, mechanical properties).

5.2.2 Mechanical properties for reference test bars of case-hardening steels in the simulated case-hardened condition are given in table 6 for guidance.

5.3 Technological properties

5.3.1 Machinability

The steels covered by this part of ISO 683 have good machinability and chip-breaking characteristics. However, the machinability decreases with increasing carbon, silicon and manganese contents, while cold-reduction improves the machinability of the steels not intended for heat-treatment and steels 10 S 20 and 10 SPb 20.

5.3.2 Weldability

Because of their high sulfur and phosphorus content, free-cutting steels are not normally recommended for welding.

5.4 Surface quality

5.4.1 All products shall have a workmanlike finish.

5.4.2 Minor surface imperfections, which may also occur under normal manufacturing conditions, such as scores originating in the case of black steel from rolled-in scale, are not to be regarded as defects.

5.4.3 As long as no International Standard on the surface quality of steel products is available, detailed requirements referring to this characteristic shall, where appropriate, be agreed at the time of enquiry and order.

NOTES

1 For bars and wire rod included in this part of ISO 683, a separate International Standard on surface quality is under consideration.

2 It is more difficult to detect and eliminate surface discontinuities in coiled products than in cut lengths. This should be taken into account when agreements on surface quality are made.

5.4.4 Removal of surface imperfections by welding is not permitted.

Pending publication of a separate International Standard, the kind and permissible depth of surface imperfections for removal should, where appropriate, be agreed at the time of enquiry and order.

5.5 Shape, dimensions and tolerances

The shape, dimensions and tolerances of the products shall comply with the requirements agreed at the time of enquiry and order. The agreements shall, as far as possible, be based on corresponding International Standards, otherwise on suitable national standards.

NOTE — The following International Standard covers dimensions and/or tolerances for products covered by this part of ISO 683 :

— for bars: ISO 1035 parts 1 to 4.

6 Inspection, testing and conformity of products

6.1 Inspection and testing procedures and types of document

6.1.1 Table 10 gives a survey of the inspection procedures and the types of document in ISO 404 which may be agreed at the time of enquiry and order for deliveries according to this part of ISO 683.

6.1.2 If in accordance with the agreements at the time of enquiry and order a test report (TR) is to be provided, this shall include

- a) a statement that the material complies with the requirements of the order, and
- b) the results of the cast analysis for all elements specified for the steel type supplied.

6.1.3 If in accordance with the agreements in the order an inspection certificate (IC or ICP) or an inspection report (IR) (see table 10) is to be provided, the specific inspections and tests described in 6.2 shall be carried out and their results shall be certified in the document.

In addition the document shall include

- a) for all elements specified for the steel type concerned, the results of the cast analysis given by the manufacturer;
- b) the results of all inspections and tests made necessary by supplementary requirements (see annex B);
- c) the symbol letters or numbers relating the test certificates, the test pieces and products to each other.

6.2 Specific inspection and testing

6.2.1 Verification of the hardness and mechanical properties

6.2.1.1 The hardness requirements and/or mechanical properties given for the relevant treatment condition in table 1, column 8, sub-column 2, shall be verified, with the following exception. The requirements given in footnotes 1 and 2 to table 1 (mechanical properties of reference test pieces), shall only be verified if the supplementary requirement given in annex B, clause B.1 or B.2, is invoked.

6.2.1.2 The amount of testing, the sampling conditions and the test methods to be applied for the verification of compliance with the requirements shall be in accordance with the prescriptions in table 11.

6.2.2 Visual and dimensional inspection

A sufficient number of products shall be inspected to ensure compliance with the specification.

6.2.3 Retests

6.2.3.1 Where for one or more test units one or more tests give unsatisfactory results, the manufacturer has the choice of withdrawing the test units concerned (for example for re-treatment or sorting in accordance with ISO 404) or maintaining them. If they are maintained, retests shall be carried out according to the following rules.

6.2.3.2 If — as in the case of product analysis (see annex B, clause B.3) — only one test of the type concerned was carried out on the sample concerned and gave the unsatisfactory result, two new tests of the same type shall be carried out.

6.2.3.3 If the test unit consists of more than one product and if the product from which the unsatisfactory test result stems is not withdrawn from the test unit, one of the two new tests shall be made on test pieces taken from the sample or product originally tested.

6.2.3.4 All retests shall give satisfactory results. Otherwise the test unit concerned shall be rejected.

7 Marking

The manufacturer shall mark the products or bundles or boxes containing the products in a suitable way, so that the identification of the cast, the steel type and the origin of the delivery is possible (see annex B, clause B.4).