



International
Standard

ISO 7054

**Corrosion of metals and alloys —
Wiping method for measurements
of gases and particles on real
structures and equipment**

*Corrosion des métaux et alliages — Méthodes d'essuyage pour
mesurage des gaz et des particules sur structures et équipements
en conditions réelles*

**First edition
2024-10**

Reference number
ISO 7054:2024(en)

Full document details: [ISO 7054-2024](#)

© ISO 2024  **Documents**
Document Sharing Hub



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Introduction of general wiping method	2
5 Preparation	3
6 Wiping procedure	5
6.1 General	5
6.2 Wiping	6
6.3 Cautions for wiping	8
6.4 Extraction	8
7 Analysis	9
7.1 Soluble deposition concentration measurement method by detector tube	9
7.2 Soluble deposition concentration measurement method by ion chromatography	10
7.3 Soluble deposition concentration measurement method by other analysis devices	10
7.4 Insoluble deposition concentration measurement methods	10
8 Expression of results	10
8.1 Units of soluble and insoluble deposition concentrations	10
8.2 Expression of soluble deposition concentration result	10
8.3 Expression of insoluble deposition concentration result	11
9 Test report	11
Annex A (informative) Example of deposition measurement of different parts of real steel structure	13
Annex B (informative) Example of deposition measurement of real steel structures at different sites by season	15
Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Airborne salts, gases and particles deposited on structures and equipment are corrosion and/or degradation factors for metals, alloys and organic materials. Information on the surfaces of these substances is useful for understanding the corrosion conditions or degradation mechanism, the remaining life of these materials and the corrosivity of the environment. The wiping method outlined in this document is an example of a measurement method used to determine the types and concentrations of depositions on real structures and equipment.

Depositions related to corrosion and degradation are classified as soluble and insoluble materials. Soluble depositions collect moisture and retain a thin layer of water on their surfaces. Prolonged wetness accelerates corrosion and degradation because the thin layer of water contains soluble depositions with a high concentration of electrolytes.

Various methods for collecting airborne gases and particles are widely used to categorize corrosivity. However, for example, the accumulation method described in ISO 9225 requires considerable time (over a year), sampling is conducted every month and a kit consisting of clean gauze and a frame is needed to obtain reliable data. The wiping method described in this document is also widely used in all industries, and is a quick, low-cost method to determine the specifications of materials and coatings, the intervals for maintenance and replacement and the progress of corrosion and degradation. Despite these advantages, procedures for deposition sampling and measurement have not yet been established, and measures to prevent contamination and improve measurement quality are also needed to conduct appropriate corrosion and degradation checks.

The deposition concentration obtained by the wiping method is useful for environmental management because it provides information for prioritising environmental degradation factors. Many instantaneous values are used for the deposition concentration, which is expressed by a mass per unit area without a time component.

Corrosion of metals and alloys — Wiping method for measurements of gases and particles on real structures and equipment

1 Scope

This document specifies a method for evaluating depositions on real structures and equipment by wiping. Depositions become corrosion and/or degradation factors for metals, alloys and organic materials, and can be analysed quantitatively to control the corrosion and degradation of real structures and equipment.

The method specified in this document is suitable for evaluating the type and amounts of depositions on real structures and equipment in all industries. This method identifies the type of depositions and gives instantaneous values of the concentrations of water-soluble and insoluble depositions, which are expressed by mass per area without a time component. These values provide information on environmental factors related to corrosion and degradation. The method can be used to detect water-soluble depositions, including chloride ion, sulfate ion and other ions, and can assist users in understanding the synergistic and antagonistic effects that accelerate corrosion.

This document is applicable to:

- metals and their alloys;
- metallic coatings;
- organic coatings;
- concretes and other structural materials.

The method for determining chloride on clean surfaces, which ensures the cleanness of steel substrates after surface preparation such as grinding, polishing, cleaning and rinsing and before the application of paints, is given in ISO 8502-2, ISO 8502-5, ISO 8502-6 and ISO 8502-9.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 8044, *Corrosion of metals and alloys — Basic terms and definitions*

ISO 9225, *Corrosion of metals and alloys — Corrosivity of atmospheres — Measurement of environmental parameters affecting corrosivity of atmospheres*

ISO 11844-1, *Corrosion of metals and alloys — Classification of low corrosivity of indoor atmospheres — Part 1: Determination and estimation of indoor corrosivity*

ISO 11844-2, *Corrosion of metals and alloys — Classification of low corrosivity of indoor atmospheres — Part 2: Determination of corrosion attack in indoor atmospheres*

ISO 11844-3, *Corrosion of metals and alloys — Classification of low corrosivity of indoor atmospheres — Part 3: Measurement of environmental parameters affecting indoor corrosivity*

ISO 7503-1, *Measurement of radioactivity — Measurement and evaluation of surface contamination — Part 1: General principles*

ISO 8502-2, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 2: Laboratory determination of chloride on cleaned surfaces*

ISO 8502-5, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 5: Measurement of chloride on steel surfaces prepared for painting (ion detection tube method)*

ISO 8502-6, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 6: Extraction of water soluble contaminants for analysis (Bresle method)*

ISO 8502-9, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 9: Field method for the conductometric determination of water-soluble salts*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8044, ISO 9225, ISO 11844-1, ISO 11844-2, ISO 11844-3, ISO 7503-1, ISO 8502-2, ISO 8502-5, ISO 8502-6, ISO 8502-9 and ISO 3696 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Introduction of general wiping method

Depositions can be sampled by using the wiping method. The wiping method entails wiping not only the surfaces of metals and alloys, but also organic materials and paint systems of structures and equipment exposed to atmospheric conditions. The concentration of the depositions can also be determined by this method. This document applies to the measurement of gases and particles that affect corrosion and degradation of the surfaces of materials. The concentrations of the soluble and insoluble depositions are expressed by mass per unit area, and the time component is not considered. The risks of corrosion in metals and alloys and the risks of degradation in organic materials can be determined by comparing the concentration of depositions on various parts of the structures and equipment, or at various sites where structures and equipment are located. The wiping method is a powerful, low-cost and easy-to-use method for capturing soluble and insoluble depositions that does not require a fixed time exposures or exchanges of the sampling medium.

The wiping method provides information on the types and concentrations of corrosive chemical depositions. This helps users:

- understand the corrosion of metals and alloys and the degradation of organic materials;
- understand the synergistic and antagonistic effects of environmental degradation agents;
- find better maintenance methods and exchange maintenance cycles for real structures and equipment;
- perform environmental assessments and determine appropriate specifications for construction.

The wiping method can be used widely to measure depositions on various organic and inorganic materials with different surface roughness and water repellency. It is also applicable to various oxides of metals and alloys. The advantages of the wiping method include the following:

- a) it applies to hydrophobic materials, hydrophilic materials and heavily-corroded rusty surfaces, which have different deposition efficiencies from polished surfaces of metals and alloys;
 - b) it provides instantaneous values for the concentration of depositions, which is useful for:
- maintaining structures and equipment;