

INTERNATIONAL STANDARD

**ISO
8225**

Second edition
1995-11-15

Photography — Ammonia-processed diazo photographic film — Specifications for stability

*Photographie — Film photographique diazoïque traité à l'ammoniac —
Spécifications relatives à la stabilité*



Reference number
ISO 8225:1995(E)



Documents
Document Sharing Hub

Contents

	Page
1 Scope	1
2 Normative references	1
3 Definitions	2
4 Safety and hazards	2
5 Requirements for film base	3
6 Requirements for processed film	3
7 Requirements for the emulsion and backing layers of processed film	4
8 Requirements for image stability	4
9 Test methods	5
10 Image test methods	8
11 Classification for reporting	9

Annexes

A Preparation of standard solution of tetrabutylammonium hydroxide	10
B Microfilm image quality	11
C Distinction between film storage copies and work copies ...	13
D Light-fading of diazo images	14
E Bibliography	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 8225 was prepared by Technical Committee ISO/TC 42, *Photography*.

This second edition cancels and replaces the first edition (ISO 8225:1987), which has been technically revised.

Annex A forms an integral part of this International Standard. Annexes B, C, D and E are for information only.

Introduction

Since 1930, great advances have been made in the use of photographic films for the preservation of records. The preservation of records on film by national, state and municipal governments, by banks, insurance companies, industry and other enterprises, has been stimulated by recognition of the resultant economies in storage space, organization, accessibility and ease of reproduction. The safe-keeping of pictorial film records having legal, scientific, industrial, medical, historical, military or other values has also become increasingly important.

The use of film for records having long-term values necessitated the development of International Standards to specify the characteristics of film suitable for this purpose. ISO 10602 specifies the requirements for silver-gelatin films which are suitable for storage. This International Standard (for diazo film) and ISO 9718 (for vesicular film) give the requirements for photographic duplicate films suitable for storage.

The term “archival film” has been discontinued and the new concept of “life expectancy” is introduced. Film life is classified by the LE or life expectancy rating as defined in this International Standard. For example, LE-100 represents film with a life expectancy of 100 years when stored under extended-term storage conditions specified in ISO 5466.

Criteria for properties of LE-10 and LE-100 diazo films are based upon the dark-ageing stability of diazo images. Different dark incubation tests are specified for LE-10 and LE-100 films. All other property and processing requirements for medium and long-term diazo films are identical.

It is recognized that diazo images may show density changes after exposure to light. However, this International Standard covers only films used as storage copies, not as work copies (as defined in annex C). The light-fading requirements specified in this International Standard ensure satisfactory behaviour for storage copies which are not intended to be subjected to frequent light exposure.

In addition to the characterization of films with respect to their expected storage life, diazo films are also separated into two classes (A and B); these classes are dependent upon their intended use. Class A films are those which retain density in both the visual and actinic region (printing) after storage. Such films can be viewed directly or reprinted onto ultra-violet (UV)-sensitive materials. However, some diazo films are not intended to be reprinted onto UV-sensitive materials. Such films require only visual capabilities after storage and are designated as Class B films. Obviously, both Class A and Class B films can fall into the LE-10 and LE-100 categories. The requirements for Class A and Class B films are identical, with the exception of image-stability tests after dark-ageing and after light-fading.

Everyone concerned with the preservation of records on photographic film should realize that specifying the chemical and physical characteristics of the material does not, by itself, assure satisfactory behaviour. It is also

essential to provide the correct storage temperature and humidity, and protection from the hazards of fire, water, light and certain atmospheric pollutants. Conditions for the storage of record films are specified in ISO 5466 and ISO 10214.

This page intentionally left blank

Photography — Ammonia-processed diazo photographic film — Specifications for stability

1 Scope

1.1 This International Standard establishes specifications for the stability of polyester-base safety film which has an ammonia-processed diazo photographic image. It covers photographic film intended for LE-10 and LE-100 records.

1.2 This International Standard applies to photographic film in which the image layer is a discrete layer attached to a transparent support.

1.3 It applies to roll film and sheet film.

1.4 This International Standard characterizes only the inherent keeping behaviour of the film. However, the suitability of a film record after extended storage depends on both the inherent ageing characteristics of the film and the original image quality. The latter is discussed in annex B.

1.5 This International Standard applies only to diazo photographic film intended and used as LE-10 and LE-100 storage copies. Storage copies should be stored in accordance with ISO 5466 and ISO 10214. It does not apply to diazo film records intended and used as "work" or "use" copies (as discussed in annex C).

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements

based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 5-1:1984, *Photography — Density measurements — Part 1: Terms, symbols and notations.*

ISO 5-2:1991, *Photography — Density measurements — Part 2: Geometric conditions for transmission density.*

ISO 5-3:1995, *Photography — Density measurements — Part 3: Spectral conditions.*

ISO 527-3:1995, *Plastics — Determination of tensile properties — Part 3: Test conditions for films and sheets.*

ISO 543:1990, *Photography — Photographic films — Specifications for safety film.*

ISO 5466:1992, *Photography — Processed safety photographic films — Storage practices.*

ISO 6077:1993, *Photography — Photographic films and papers — Wedge test for brittleness.*

ISO 9718:1995, *Photography — Processed vesicular photographic film — Specifications for stability.*

ISO 10214:1991, *Photography — Processed photographic materials — Filing enclosures for storage.*

ISO 10602:1995, *Photography — Processed silver-gelatin type black-and-white film — Specifications for stability.*

3 Definitions

For the purposes of this International Standard, the following definitions apply.

3.1 archival medium: Recording material that can be expected to retain information for ever so that it can be retrieved without significant loss when properly stored.

NOTE 1 There is, however, no such material and it is not a term to be used in International Standards or system specifications.

3.2 life expectancy (LE): Length of time that information is predicted to be retrievable in a system under extended-term storage conditions.

NOTE 2 However, the actual useful life of film is very dependent upon the existing storage conditions (see ISO 5466 and ISO 10214).

3.3 LE designation: Rating for the "life expectancy" of recording materials and associated retrieval systems. The number following the LE symbol is a prediction of the minimum life expectancy, in years, for which information can be retrieved without significant loss when stored under extended-term storage conditions.

NOTE 3 For example, LE-100 indicates that information can be retrieved for at least 100 years' storage.

3.4 extended-term storage conditions: Storage conditions suitable for the preservation of recorded information having permanent value.

3.5 medium-term storage conditions: Storage conditions suitable for the preservation of recorded information for a minimum of 10 years.

3.6 film base: Plastic support for the emulsion and backing layers.

3.7 emulsion layer(s): Image or image-forming layer(s) of photographic films, papers and plates.

3.8 Class A films: Films which are usable both visually and for printing onto ultraviolet-sensitive materials.

3.9 Class B films: Films which are usable visually but do not have any density requirements for printing onto ultraviolet-sensitive materials.

3.10 safety photographic film: Photographic film which passes the ignition time test and burning time test as specified in ISO 543.

3.11 safety poly(ethylene terephthalate) base: Film base composed mainly of a polymer of ethylene glycol and terephthalic acid.

3.12 density: Degree of light absorption, reflection or scattering characteristics of a photographic image, expressed as the logarithm to the base 10 of the ratio of incident radiant flux to the transmitted, reflected or scattered flux. (See ISO 5-3.)

3.13 printing density: Density of a processed photographic image in which the incident and transmitted radiant flux are evaluated by a receiver having the same spectral response as the photographic material on which the sample is to be printed, and the incident radiant flux has the same spectral energy distribution as the printing light source.

3.14 visual diffuse density: Density of a processed photographic image in which the incident and the transmitted or reflected radiant flux are evaluated by the human eye, or by a receiver having the same spectral response as the human eye.

3.15 projection density: Density of a processed photographic image in which the angular distributions of the incident and transmitted radiant flux are equal and specified.

NOTE 4 For microfilm applications, the angular distribution is a nominal half-angle of $6,4^\circ$, which corresponds to an f -number of $f/4,5$ and simulates a microfilm reader.

4 Safety and hazards

4.1 Hazard warnings

Some of the chemicals specified in the test procedures are caustic, toxic or otherwise hazardous. Safe laboratory practice for the handling of chemicals requires the use of safety glasses or goggles, rubber gloves and other protective apparel such as face masks or aprons where appropriate. Specific danger notices are given in the text and footnotes for particularly dangerous materials, but normal precautions are required during the performance of any chemical procedure at all times. The first time that a hazardous material is noted in the test procedure section, the hazard will be indicated by the word "DANGER" followed by a symbol consisting of angle brackets " $\langle \rangle$ " containing a letter which designates the specific hazard. A double bracket " $\langle\langle \rangle\rangle$ " will be used for particu-