

# INTERNATIONAL STANDARD

ISO  
864

Second edition  
1988-12-15



---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION  
ORGANISATION INTERNATIONALE DE NORMALISATION  
МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ

---

## **Arc welding — Solid and tubular cored wires which deposit carbon and carbon manganese steel — Dimensions of wires, spools, rims and coils**

*Soudage à l'arc — Fils nus massifs et fourrés déposant un acier au carbone et un acier au carbone-manganèse — Dimensions des fils, bobines, jantes et couronnes*

Reference number  
ISO 864:1988 (C)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 864 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*.

This second edition cancels and replaces the first edition (ISO 864 : 1975), of which it constitutes a technical revision.

# Arc welding — Solid and tubular cored wires which deposit carbon and carbon manganese steel — Dimensions of wires, spools, rims and coils

## 1 Scope

This International Standard specifies dimensions and tolerances of wires, spools, rims and coils.

It deals with solid and tubular cored wires used for arc welding of non-alloyed steel, with or without gas shielding or with powder flux.

## 2 Dimensions of wires — Nominal diameters and tolerances

The nominal diameters and tolerances of wires are given in table 1.

Table 1

Dimensions in millimetres

| Nominal diameter               | Solid wires          |                       | Tubular cored wires           |                  |                       |
|--------------------------------|----------------------|-----------------------|-------------------------------|------------------|-----------------------|
|                                | Gas-shielded welding | Submerged arc welding | Drawn                         | Rolled           | Submerged arc welding |
|                                |                      |                       | With or without gas shielding |                  |                       |
| Tolerances on nominal diameter |                      |                       |                               |                  |                       |
| 0,6                            | + 0,01<br>− 0,03     | —                     | + 0,02<br>− 0,05              | ± 0,05           | —                     |
| 0,8                            | + 0,01<br>− 0,04     |                       |                               |                  |                       |
| 0,9                            |                      |                       |                               |                  |                       |
| 1,0                            |                      |                       |                               |                  |                       |
| 1,2                            |                      |                       |                               |                  |                       |
| 1,4                            |                      |                       |                               |                  |                       |
| 1,6                            |                      |                       |                               |                  |                       |
| 1,8                            |                      |                       |                               |                  |                       |
| 2,0                            | ± 0,04               | + 0,02<br>− 0,06      | ± 0,08                        | + 0,04<br>− 0,05 |                       |
| 2,4                            |                      |                       |                               |                  |                       |
| 2,5                            |                      |                       |                               |                  |                       |
| 2,8                            |                      |                       |                               |                  |                       |
| 3,0                            |                      |                       |                               |                  |                       |
| 3,2                            |                      |                       |                               |                  |                       |
| 4,0                            |                      |                       |                               |                  |                       |
| 5,0                            | + 0,01<br>− 0,07     | ± 0,06                | + 0,02<br>− 0,07              | —                | + 0,06<br>− 0,08      |
| 6,0                            |                      |                       |                               |                  |                       |