



**International
Standard**

ISO 9073-7

**Nonwovens — Test methods —
Part 7:
Determination of bending length**

Nontissés — Méthodes d'essai —

Partie 7: Détermination de la longueur de flexion

**Second edition
2024-11**

Reference number
ISO 9073-7:2024(en)

Full document details: [ISO 9073-7-2024](#)

© ISO 2024  **Documents**
Document Sharing Hub



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents		Page
Foreword.....		iv
1	Scope.....	1
2	Normative references.....	1
3	Terms and definitions.....	1
4	Principle.....	2
5	Apparatus.....	2
6	Sampling.....	3
7	Preparation and conditioning of test specimens.....	3
8	Procedure.....	4
9	Expression of results.....	4
10	Test report.....	5
Annex A (normative) Flexural rigidity, bending length and overhanging length.....		6
Bibliography.....		8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 248, *Textiles and textile products*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 9073-7:1995), which has been technically revised.

The main changes are as follows:

- the title has been changed from "*Textiles — Test methods for nonwovens — Part 7: Determination of bending length*" to "*Nonwovens — Test methods — Part 7: Determination of bending length*";
- [Figure 1](#) has been corrected according to ISO/IEC Directives, Part 2;
- [Figure A.1](#) has been corrected according to ISO/IEC Directives, Part 2;
- through the document, "test piece" has been replaced by "test specimen";
- numbering of NOTE has been corrected according to ISO/IEC Directives, Part 2;
- Bibliography has been added to list the informative references described in [8.2](#) and [A.3](#).

A list of all parts in the ISO 9073 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Nonwovens — Test methods —

Part 7: Determination of bending length

SAFETY WARNING — This document does not claim to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this document to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. It is expected that the person performing this test has been fully trained in all aspects of this procedure.

1 Scope

This document specifies a method for determining the bending length of a nonwoven. A formula is given for calculating the flexural rigidity of the nonwoven material from the bending length. The method is not applicable to combination-type materials (composites or laminates) in which there can be a natural twist.

NOTE This document describes a test method specific to nonwovens.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 9073-1, *Nonwovens — Test methods — Part 1: Determination of mass per unit area*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 bending length

length of a rectangular strip of nonwoven, fixed at one end and free at the other, that will bend under its own weight to an angle of $7,1^\circ$

3.2 flexural rigidity

ratio of small changes in bending moment per unit width of the material to corresponding small changes in curvature expressed in $\text{mN}\cdot\text{cm}$

Note 1 to entry: Flexural rigidity can be calculated from the bending length.

Note 2 to entry: Flexural rigidity is expressed in $\text{mN}\cdot\text{cm}$.