

Transformed.

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

ISO RECOMMENDATION

R 1460

**DETERMINATION OF THE WEIGHT PER UNIT AREA
OF HOT DIP GALVANIZED COATINGS ON FERROUS MATERIALS
BY CHEMICAL DISSOLUTION OF THE COATING
GRAVIMETRIC METHOD**

1st EDITION

April 1970

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

BRIEF HISTORY

The ISO Recommendation R 1460, *Determination of the weight per unit area of hot dip galvanized coatings on ferrous materials by chemical dissolution of the coating – Gravimetric method*, was drawn up by Technical Committee ISO/TC 107, *Metallic and other non-organic coatings*, the Secretariat of which is held by the Ente Nazionale Italiano di Unificazione (UNI).

Work on this question led to the adoption of Draft ISO Recommendation No. 1460 which was circulated to all the ISO Member Bodies for enquiry in May 1968. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

Australia	India	Portugal
Belgium	Iran	South Africa, Rep. of
Chile	Israel	Spain
Czechoslovakia	Italy	Sweden
Finland	Netherlands	Switzerland
France	New Zealand	Thailand
Germany	Norway	U.A.R.
Hungary	Poland	United Kingdom

The following Member Body opposed the approval of the Draft :

Turkey

This Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided, in April 1970, to accept it as an ISO RECOMMENDATION.