

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

ISO RECOMMENDATION R 807

CHEMICAL ANALYSIS OF MAGNESIUM AND MAGNESIUM ALLOYS

POLAROGRAPHIC DETERMINATION OF ZINC
(Zinc content between 0.1 and 4 %)

1st EDITION
August 1968

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

BRIEF HISTORY

The ISO Recommendation R 807, *Chemical analysis of magnesium and magnesium alloys – Polarographic determination of zinc (Zinc content between 0.1 and 4 %)*, was drawn up by Technical Committee ISO/TC 79, *Light metals and their alloys*, the Secretariat of which is held by the Association Française de Normalisation (AFNOR).

Work on this question by the Technical Committee began in 1957 and led, in 1965, to the adoption of a Draft ISO Recommendation.

In December 1966, this Draft ISO Recommendation (No. 1128) was circulated to all the ISO Member Bodies for enquiry. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

Argentina	India	South Africa,
Austria	Ireland	Rep. of
Belgium	Israel	Spain
Brazil	Italy	Switzerland
Canada	Japan	Sweden
Chile	Korea, Rep. of	Turkey
Czechoslovakia	Netherlands	U.A.R.
France	New Zealand	U.S.A.
Germany	Norway	U.S.S.R.
Hungary	Poland	Yugoslavia

One Member Body opposed the approval of the Draft :

United Kingdom

The Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided, in August 1958, to accept it as an ISO RECOMMENDATION.