



JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS C 6483 : 1997

Copper-clad laminates for printed
wiring boards — Synthetic fiber
fabric base, epoxy resin

ICS 31. 180

Descriptors : laminates, copper, printed circuits, printed-circuit boards, printed-circuit bases, epoxy resins, synthetic fibres

Reference number : JIS C 6483 : 1997 (E)

C 6483 : 1997

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of International Trade and Industry through deliberations at Japanese Industrial Standards Committee in accordance with the Industrial Standardization Law:

Date of Establishment: 1966-04-01

Date of Revision: 1997-02-20

Date of Public Notice in Official Gazette: 1997-02-20

Investigated by: Japanese Industrial Standards Committee
Divisional Council on Electronics

JIS C 6483:1997, First English edition published in 1997-06

Translated and published by: Japanese Standards Association
4-1-24, Akasaka, Minato-ku, Tokyo, 107 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

Copper-clad laminates for printed wiring boards
— Synthetic fiber fabric base, epoxy resin

1 Scope This Japanese Industrial Standard specifies the copper-clad laminates for printed wiring boards using polyester fiber fabric base, epoxy resin (hereafter referred to as "copper-clad laminates").

Remarks: The following standards are cited in this Standard:

JIS C 5603 *Terms and definitions for printed circuits*

JIS C 6480 *General rules of copper-clad laminates for printed wiring boards*

JIS C 6481 *Test methods of copper-clad laminates for printed wiring boards*

2 Definitions For the purpose of this Standard, the principal definitions specified in JIS C 5603 apply.

3 Type designation

3.1 Structure of type designation The type designation shall be formed in the following arrangement:

[Symbol denoting kind of copper- clad laminate]	[Hyphen]	[Symbol denoting base material and resin]	[Symbol denoting charac- teristics]	[Symbol denoting thick- ness and arrange- ment of copper foil]	[Symbol denoting size]
[3.2.1]		[3.2.2]	[3.2.3]	[3.2.4]	[3.2.5]
Example: FCL	—	SE	1F	35/0	A

[Symbol denoting thickness]	[Hyphen]	[Symbol denoting toler- ances on thick- ness]	[Symbol denoting appear- ance]	[Symbol denoting flame re- tardance]
[3.2.6]		[3.2.7]	[3.2.8]	[3.2.9]
Example: 16	—	1	1	V1

3.2 Symbols

3.2.1 Kind of copper-clad laminate The symbol denoting kind of copper-clad laminate shall be English capital letters FCL based on 3.2.1 of JIS C 6480.

3.2.2 Base material and resin The symbol denoting base material and resin shall be English capital letters SE representing "synthetic fiber fabric base, epoxy resin" based on 3.2.2 of JIS C 6480.

3.2.3 Characteristics The symbol denoting characteristics shall be 1 or 1F based on 3.2.2 of JIS C 6480.

3.2.4 Thickness and arrangement of copper foil The symbol denoting thickness of copper foil shall be as shown in Table 1 based on 3.2.3 of JIS C 6480.

The arrangement shall be symbolized in such a way that the symbol denoting thickness of upper copper foil and that of lower copper foil are written in front and behind a slash, and in the case of single-sided copper-clad laminate, 0 is appended to the slash.

When the double-sided copper-clad laminate is formed by copper foil of different thickness, the symbol denoting the thicker copper foil shall be shown in front of the slash.

Table 1 Thickness of copper foil

Unit: mm

Symbol	Thickness
18	0.018
35	0.035
70	0.070

For a thickness other than the above-mentioned, symbols of two or three digits shall be used.

3.2.5 Size The symbol denoting size shall be as shown in Table 2 based on 3.2.4 of JIS C 6480.

Table 2 Size

Unit: mm

Symbol	Size
A	1 000 × 1 000
B	1 000 × 1 200
S	Other than the above-mentioned

3.2.6 Thickness The symbol denoting thickness shall be as shown in Table 3 based on 3.2.5 of JIS C 6480.