



JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS Z 1715 : 2009

(JPIA/JPIF/JSA)

**Biaxially oriented polyethylene
terephthalate (PET) films for packaging**

ICS 55.040 ; 83.140.10

Reference number : JIS Z 1715 : 2009 (E)

PROTECTED BY COPYRIGHT

Date of Establishment: 1997-09-20

Date of Revision: 2009-03-20

Date of Public Notice in Official Gazette: 2009-03-23

Investigated by: Japanese Industrial Standards Committee

Standards Board

Technical Committee on Logistics and Distribution of
Goods

JIS Z 1715 : 2009, First English edition published in 2010-10

Translated and published by: Japanese Standards Association
4-1-24, Akasaka, Minato-ku, Tokyo, 107-8440 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

PROTECTED BY COPYRIGHT

Contents

	Page
Introduction	1
1 Scope	1
2 Normative references	1
3 Classification	2
4 Requirements	2
4.1 Appearance	2
4.2 Dimensions	3
4.3 Performance	4
5 Test methods	4
5.1 Conditioning of specimens and test condition	4
5.2 Appearance	5
5.3 Dimensions	5
5.4 Tensile strength and tensile strain at break	5
5.5 Dimensional change on heating	6
5.6 Coefficient of oxygen transmission	6
5.7 Coefficient of water vapour transmission	6
5.8 Haze	7
5.9 Wetting tension	7
5.10 Physiological behaviour	7
5.11 Rounding of measured values	7
5.12 Test report	7
6 Packaging	7
7 Marking	7
7.1 Marking on products	7
7.2 Marking on packaging	7
Annex JA (informative) Comparison table between of JIS and corresponding International Standard	9

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee as the result of proposal for revision of Japanese Industrial Standard submitted by Japan PET Film Industry Association (JPIA)/The Japan Plastics Industry Federation (JPIF)/Japanese Standards Association (JSA) with the draft being attached, based on the provision of Article 12 Clause 1 of the Industrial Standardization Law applicable to the case of revision by the provision of Article 14.

Consequently **JIS Z 1715 : 1997** is replaced with this Standard.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with a patent right, application for a patent after opening to the public, utility model right or application for registration of utility model after opening to the public which have technical properties. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying the patent right, application for a patent after opening to the public, utility model right or application for registration of utility model after opening to the public which have the said technical properties.

Biaxially oriented polyethylene terephthalate (PET) films for packaging

Introduction

This Japanese Industrial Standard has been prepared based on the first edition of **ISO 15988** published in 2003 with some modifications of the technical contents for the periodic review of 5 years and for conformance to **ISO** standard.

The portions with continuous sidelines or dotted underlines are the matters in which the contents of the corresponding International Standard have been modified. A list of modifications with explanations is given in Annex JA.

1 Scope

This Standard specifies biaxially oriented transparent polyethylene terephthalate (PET) films, mainly used for packaging (hereafter referred to as “films”).

NOTE : The International Standard corresponding to this Standard and the symbol of degree of correspondence are as follows:

ISO 15988 : 2003 *Plastics — Film and sheeting — Biaxially oriented poly (ethylene terephthalate (PET) films* (MOD)

In addition, symbols which denote the degree of correspondence in the contents between the relevant International Standard and **JIS** are IDT (identical), MOD (modified), and NEQ (not equivalent) according to **ISO/IEC Guide 21**.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

JIS B 7503 *Dial gauges*

JIS B 7507 *Vernier, dial and digital callipers*

JIS B 7516 *Metal rules*

JIS K 6768 *Plastics — Film and sheeting — Determination of wetting tension*

NOTE : Corresponding International Standard : **ISO 8296** *Plastics — Film and sheeting — Determination of wetting tension* (IDT)

JIS K 7100 *Plastics — Standard atmospheres for conditioning and testing*

NOTE : Corresponding International Standard : **ISO 291** *Plastics — Standard*

atmospheres for conditioning and testing (MOD)

JIS K 7126-1 *Plastics — Film and sheeting — Determination of gas-transmission rate — Part 1 : Differential-pressure method*

NOTE : Corresponding International Standard : ISO 15105-1 *Plastics — Film and sheeting — Determination of gas-transmission rate — Part 1 : Differential-pressure method (MOD)*

JIS K 7126-2 *Plastics — Film and sheeting — Determination of gas-transmission rate — Part 2 : Equal-pressure method*

NOTE : Corresponding International Standard : ISO 15105-2 *Plastics — Film and sheeting — Determination of gas-transmission rate — Part 2 : Equal-pressure method (IDT)*

JIS K 7127 *Plastics — Determination of tensile properties — Part 3 : Test conditions for films and sheets*

NOTE : Corresponding International Standard : ISO 527-3 *Plastics — Determination of tensile properties — Part 3 : Test conditions for films and sheets (IDT)*

JIS K 7129 *Plastics — Film and sheeting — Determination of water vapour transmission rate — Instrumental method*

JIS K 7130 *Plastics — Film and sheeting — Determination of thickness*

NOTE : Corresponding International Standard : ISO 4593 *Plastics — Film and sheeting — Determination of thickness by mechanical scanning (MOD)*

JIS K 7136 *Plastics — Determination of haze for transparent materials*

NOTE : Corresponding International Standard : ISO 14782 *Plastics — Determination of haze for transparent materials (IDT)*

JIS Z 8401 *Guide to the rounding of numbers*

3 Classification

Films are classified according to the corona discharge treatment as given in table 1.

Table 1 Classification of films

Type
Films subjected to corona discharge treatment
Films not subjected to corona discharge treatment

4 Requirements

4.1 Appearance

The film appearance shall be checked in accordance with 5.2 and the films shall be