

KES

Development Standard for
Lab Aging Mode of Catalyst

KES T – L507

(EST.) 1996 – 07 – 10

Contents

1. Scope of Application
2. Purpose
3. Definition of Term
4. Development Standard for Lab Aging
Mode of Catalyst
5. Condition for Development of Lab
Aging Mode of Catalyst
6. Development Flow for Lab Aging Mode
of Catalyst



1. Scope of application

It shall be applied to purifier catalyst for exhaust gas of vehicle and commercial car.

2. Purpose

This test standard shall be for purifier of vehicle exhaust, in other words, Lab for reducing development period of catalyst. This test shall describe method for aging artificially to confirm catalyst to guaranteed distance through installment (Electric circuit)

Note (1) Catalyst : Coated basic material(Alumina, ceria, zirconia etc)over the metal substrate or ceramic for purifying exhaust product.

3. Definition of term

(1) Conversion efficiency

Values calculated disparity of gas consistency as one-hundredth part before and after catalysis.

$$\text{Conversion Efficiency, \%} = \left(1 - \left(\frac{\text{Cat output}}{\text{Cat input}} \right) \right) \times 100$$

In this Catinput : Gas consistency before catalyst (Vol% or ppm)

Catoutput : Gas consistency after catalyst (Vol% or ppm)

(2) Light -off temperature

Temperature when conversion efficiency of catalyst becomes 50°C when temperature of preceding part of catalyst raises by being injected gas of regular consistency .hereinafter "LOT" marked.

(3) Surface area

Physical characteristic helping promotion of conversion of catalyst and dispersion of precious metal. Characteristic controlled by basic materials (alumina ceria, zirconia) marked above.

(4) Aging

Aging catalyst artificially at electric circuit as taking sample size as more than ϕ 2.54cm x 7cm core.

(5) Poisoning

Chemical aging covering precious metal with Pb, P, S, Si in fuel or engine oil. If poisoning is progressed, conversion efficiency is decreased..

4. Development standard for Lab of catalyst, aging mode

(1) Get basic data about durability and deterioration of catalyst according to catalyst testing