

RAW MATERIALS / FERROUS

FNHA-2-A-404.00

COLD DRAWN ROUND BAR AISI 1018 - METRIC**1. SCOPE**

This specification defines the requirements for Cold Drawn Steel Bar conforming to AISI chemistry specifications and ASTM A29 dimensional tolerances.

2. APPLICATION

This specification includes material requirements, ordering information and quality requirements to be used by Engineering, Purchasing and Manufacturing.

3. DRAWING SPECIFICATIONS

- 3.1 C.D.Round AISI 1018 (Preferred)
- 3.2 C.D.Round AISI 1018 G&P
- 3.3 C.D.Round AISI 10L18 (see Section 8.)

4. RELATED SPECIFICATIONS**4.1 REFERENCE STANDARDS**

ASTM A29 - Standard Specifications for Steel Bar, Carbon and Alloy, Hot Wrought and Cold Finished, General Requirements.

ASTM A108 - Standard Specifications for Steel Bar, Carbon, Cold Finished, Standard Quality.

86050124 (FNHA-2-A-027.00) - General Requirements for Carbon and Alloy Steel Bars, Hot Rolled and Cold Finished.

86599831 (FNHA-2-A-404.01) -
Materials List 9842918

5. ORDERING INFORMATION

- 5.1 AISI 1018 Steel.
- 5.2 Cold Drawn Bar, Standard Quality.
- 5.3 Dimensions (diameter, bar length, and whether cut length or random length).
- 5.4 Condition:
- 5.4.1 Cold drawn, to ISO h11 tolerance, unless otherwise specified.
- 5.4.2 Cold drawn, ground and polished (G&P) to ISO h9 tolerance, unless otherwise specified.

6. CHEMICAL COMPOSITION FOR AISI 1018 STEEL

Carbon, %	0.15 to 0.20
Manganese, %	0.60 to 0.90
Phosphorus, %	0.040 maximum
Sulfur, %	0.050 maximum
Lead - not permitted, unless specified for free-machining properties (see Section 8.).	

7. DIMENSIONAL TOLERANCES

- 7.1 Size tolerances for Cold Drawn Rounds, see Table 1.
- 7.2 Length tolerance for cut lengths -
+ 50mm / - 0, unless otherwise specified by part number drawing.

					NAME	STD 1018 CD RD-M		
					 NEW HOLLAND		ENGINEERING SPECIFICATION	
							FRAME 1	OF 2
							PART NUMBER	
							9842918	
.L	J	RE	113870	9-99	THE INFORMATION HEREON IS THE CONFIDENTIAL AND PROPRIETARY PROPERTY OF NEW HOLLAND N. V. AND/OR ITS SUBSIDIARIES. ANY USE, EXCEPT THAT FOR WHICH IT MAY BE LOANED, IS PROHIBITED.			
FRAME NO.	REV	BY	ECN NO.	DATE				
APP.	DRAWN		TH	7-99				
GES 9-99	CHECKED							

9842918
Documents
Document Sharing Hub

RAW MATERIALS / FERROUS

FNHA-2-A-404.00

8. FREE-MACHINING PROPERTIES

8.1 The use of 10L18, low carbon leaded steel, is being discontinued by New Holland. If free-machining properties are desired, and are not detrimental to the function of the product, AISI 1117 steel should be specified by the engineer, either as the preferred material or as the alternate material to AISI 1018 steel. If 1117 is listed as an alternate material, Manufacturing has the option of specifying 1117 if the reduction in machining cost will offset the increased material cost.

8.2 AISI 1117 should be used with caution under the following conditions, because it is more brittle than AISI 1018:

8.2.1 Impact or shock loading conditions.

8.2.2 Welding the circumference of small diameter shafts (less than 0.75" diameter).

8.2.3 Carburizing or carbonitriding thin cross-sections (less than 0.25").

9. MECHANICAL PROPERTIES

Tensile Strength, psi, typical	64 000
Yield Strength, psi, typical	54 000
Elongation in 2", typical %	15
Reduction in Area, typical %	40
Rockwell B Hardness, typical	72
Brinnell Hardness, typical	126

TABLE 1. Size Tolerance for 1018 C.D. Round

Size, mm	Cold Drawn Tolerance from Specified Size, Minus only, mm (inches)	Cold Drawn, Ground and Polished, Tolerance from Specified Size, Minus only, mm (inches)
To 10, incl.	.090 (.0035)	.036 (.0014)
Over 10 to 18, incl.	.110 (.0040)	.043 (.0017)
Over 18 to 30, incl.	.130 (.0050)	.052 (.0020)
Over 30 to 50, incl.	.160 (.0060)	.062 (.0025)
Over 50 to 80, incl.	.190 (.0075)	.074 (.0030)
Over 80 to 100, incl.	.220 (.0085)	.087 (.0035)

 NEW HOLLAND	NAME				PART NUMBER	
	STD 1018 CD RD-M				9842918	
ENGINEERING SPECIFICATION				REV. J	FRAME 2	OF 2