PD CEN/TR/ISO/ASTM 52912:2020

BSI Standards Publication

Additive manufacturing — Design — Functionally graded additive manufacturing

Documents
Document Sharing Hub

Full document details: PD CEN/TR/ISO/ASTM 52912:2020

National foreword

This Published Document is the UK implementation of CEN/TR/ISO/ASTM 52912:2020. It is identical to ISO/ASTM TR 52912:2020.

The UK participation in its preparation was entrusted to Technical Committee AMT/8, Additive manufacturing.

A list of organizations represented on this committee can be obtained on request to its committee manager.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2020
Published by BSI Standards Limited 2020

ISBN 978 0 580 52325 0

ICS 25.030

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 October 2020.

Amendments/corrigenda issued since publication

Date	Text affected

Documents
Document Sharing Hub

Full document details: PD CEN/TR/ISO/ASTM 52912:2020

TECHNICAL REPORT

RAPPORT TECHNIQUE

TECHNISCHER BERICHT

CEN/TR/ISO/ASTM 52912

October 2020

ICS 25.030

English Version

Additive manufacturing - Design - Functionally graded additive manufacturing (ISO/ASTM/TR 52912:2020)

Fabrication additive - Conception - Fabrication additive à gradient fonctionnel (ISO/ASTM/TR 52912:2020)

Technischer Bericht für die Gestaltung von additiv gefertigten, gradierten Bauteilen (ISO/ASTM/TR 52912:2020)

This Technical Report was approved by CEN on 31 August 2020. It has been drawn up by the Technical Committee CEN/TC 438.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2020 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. CEN/TR/ISO/ASTM 52912:2020 E

Documents
Document Sharing Hub

Full document details: PD CEN/TR/ISO/ASTM 52912:2020

European foreword

This document (CEN/TR/ISO/ASTM 52912:2020) has been prepared by Technical Committee ISO/TC 261 "Additive manufacturing" in collaboration with Technical Committee CEN/TC 438 “Additive Manufacturing” the secretariat of which is held by AFNOR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of ISO/ASTM/TR 52912:2020 has been approved by CEN as CEN/TR/ISO/ASTM 52912:2020 without any modification.

Documents
Document Sharing Hub

Full document details: PD CEN/TR/ISO/ASTM 52912:2020

Contents

Page

Foreword ..... **iv**
Introduction ..... **v**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **1**
4 Abreviations **1**
5 Concept of Functionally Graded Additive Manufacturing (FGAM) **3**
5.1 General 3
5.2 Homogeneous compositions — Single Material FGAM 3
5.3 Heterogeneous compositions — Multi-material FGAM 4
6 Advances of functionally graded additive manufacturing **8**
6.1 General 8
6.2 AM and FGAM process 8
6.3 Material extrusion 9
6.4 Powder bed fusion 12
6.5 Directed energy deposition 13
6.6 Sheet lamination 14
7 Current limitations of FGAM **16**
7.1 General 16
7.2 Material limitations 16
7.2.1 General 16
7.2.2 Defining the optimum material property distribution 17
7.2.3 Predicting the material properties of manufactured components 17
7.2.4 Material selection 17
7.2.5 Understanding differences and defining tolerances 17
7.3 Limitations of current additive manufacturing technologies 17
7.4 CAD Software limitations 18
7.4.1 General 18
7.4.2 Data exchange formats 19
8 Potential applications of FGAM **20**
8.1 General 20
8.2 Biomedical applications 21
8.3 Aerospace applications 21
8.4 Consumer markets 21
9 Summary **22**
Bibliography **23**

© ISO/ASTM International 2020 – All rights reserved

Documents
Document Sharing Hub
Full document details: PD CEN/TR/ISO/ASTM 52912:2020

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by ISO/TC 261, *Additive manufacturing*, in cooperation with ASTM F 42, *Additive manufacturing technologies*, on the basis of a partnership agreement between ISO and ASTM International with the aim to create a common set of ISO/ASTM standards on additive manufacturing and in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 438, *Additive manufacturing*, in accordance with the agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO/ASTM International 2020 – All rights reserved
Documents
Document Sharing Hub
Full document details: PD CEN/TR/ISO/ASTM 52912:2020

Introduction

Functionally Graded Materials (FGMs) were developed in 1984 for a space plane project to sustain high thermal barriers to overcome the shortcomings of traditional composite materials (AZO Materials, 2002). Traditional composites [Figure 1 a)] are homogeneous mixtures, therefore involving a compromise between the desirable properties of the component materials. Functionally Graded Materials (FGMs) are a class of advanced materials with spatially varying composition over a changing dimension, with corresponding changes in material properties built-in[56]. FGMs attain their multifunctional status by mapping performance requirements to strategies of material structuring and allocation [Figure 1 b)].

The manufacturing processes of conventional FGMs include shot peening, ion implantation, thermal spraying, electrophoretic deposition and chemical vapour deposition. Since additive manufacturing processes builds parts by successive addition of material, they provide the possibility to produce products with Functionally Graded properties, thereby introducing the concept often known as Functionally Graded Additive Manufacturing (FGAM). As this area of work is new, driven by academic research, and lacks available standardisation, there have been multiple different names proposed by different researchers in different publications as terms for this area, for example, functionally graded rapid prototyping (FGRP)[56], varied property rapid prototyping (VPRP)[57] and site-specific properties additive manufacturing[72]. However, even if there clearly is a great need for clarification of key terms associated with FGAM, this document does not include any attempts of alignment in terminology. This document is an overview of state of the art and the possibilities for FGAM enabled by present AM process technology and thus a purely informative document. Since this overview is based on available publications, and in order to facilitate cross referencing from these publications, this document has used the terms concerning FGAM as they are used in the original publications.

a) Traditional composite **b) FGM composite**

Figure 1 — Allocation of materials in a traditional composite and an FGM composite

© ISO/ASTM International 2020 – All rights reserved

Documents
Document Sharing Hub
Full document details: PD CEN/TR/ISO/ASTM 52912:2020

Additive manufacturing — Design — Functionally graded additive manufacturing

1 Scope

The use of Additive Manufacturing (AM) enables the fabrication of geometrically complex components by accurately depositing materials in a controlled way. Technological progress in AM hardware, software, as well as the opening of new markets demand for higher flexibility and greater efficiency in today's products, encouraging research into novel materials with functionally graded and high-performance capabilities. This has been termed as Functionally Graded Additive Manufacturing (FGAM), a layer-by-layer fabrication technique that involves gradationally varying the ratio of the material organization within a component to meet an intended function. As research in this field has gained worldwide interest, the interpretations of the FGAM concept requires greater clarification. The objective of this document is to present a conceptual understanding of FGAM. The current-state of art and capabilities of FGAM technology will be reviewed alongside with its challenging technological obstacles and limitations. Here, data exchange formats and some of the recent application is evaluated, followed with recommendations on possible strategies in overcoming barriers and future directions for FGAM to take off.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

4 Abreviations

AM	Additive Manufacturing (see ISO/ASTM 52900)
AMF	Additive Manufacturing Format, see 8.4.2.1 (see ISO/ASTM 52900)
CAD	Computer Aided Design[48]
CAE	Computer Aided Engineering[14]
DED	Directed Energy Deposition, see Clause 6 (see ISO/ASTM 52900)
DMLS	Direct Metal Laser Sintering, the name for laser-based metal powder bed fusion process by EOS Gmbh[40]
EBM	Electron Beam Melting, the name for electron beam based metal powder bed fusion process by Arcam AB[40]
FAV	Fabricatable Voxel, see 8.4.2.2[19]

© ISO/ASTM International 2020 – All rights reserved

Documents
Document Sharing Hub
Full document details: PD CEN/TR/ISO/ASTM 52912:2020

FEA	Finite Element Analysis[48]
FEF	Freeze-form Extrusion Fabrication, a material extrusion process based on the extrusion of feedstock in the form of pastes and application of freeze drying to form a green body which can be consolidated to the desired material properties by sintering. Presently only used for research and development projects.[34]
FEM	Finite Element Method[18]
FDM	Fused Deposition Modelling, name for material extrusion processes by Stratasys Ltd.[39]
FGAM	Functionally Graded Additive Manufacturing[61]
FGMs	Functionally Graded Materials[61]
FGRP	Functionally Graded Rapid Prototyping, name for FGAM used by Neri Oxman in some publications.[56]
LMD	Laser Metal Deposition, a common name for directed energy deposition processes that uses laser as the source of energy to melt and fuse metallic materials as they are being deposited, see Clause 6.[21]
LOM	Laminated Object Manufacturing, name of sheet lamination processes originally developed by Helisys Inc.[42]
MMAM	Multi-Material Additive Manufacturing, name used for AM when using more than one material in the same process.[61]
MM FGAM	Multi-Material Functionally Graded Additive Manufacturing, name for FGAM when the functional grading is based on building parts using more than one material in the same process, and the composition of the different material components is controlled by the computer program.[43]
PBF	Powder Bed Fusion (ISO/ASTM 52900)
SHS	Selective Heat Sintering, name of a powder bed fusion process that fuse polymer powder by means of a thermal printhead instead of the more common laser. The process was originally developed by Blueprinter but has been withdrawn from the market following the bankruptcy of this company.[40]
SLM	Selective Laser Melting, name for laser-based metal powder bed fusion process originally developed in collaboration between F&S Stereolithographietechnik GmbH (Fockele & Schwarze) and Fraunhofer Institute for Laser Technology. This name is a registered trademark of SLM Solutions Group AG and Realizer GmbH.[40]
SLS	Selective Laser Sintering, name for powder bed fusion process originally developed by DTM Corp, but which has been assumed by 3D Systems by the acquisition of this company. Since this was the first powder bed fusion process to be commercialized, it has sometimes been used synonymously for all powder bed fusion processes.[40]
STL	Stereolithography, name for a digital file format for three dimensional solid models originally developed for the Stereolithography process by 3D Systems, hence the name. Since this conversion to this format has been commonly available in several CAD programs this file format has until present times effectively been functioning as a de-facto standard for AM processes. (see ISO/ASTM 52900)
UAM	Ultrasonic Additive Manufacturing, name for a metal sheet lamination process by Fabrisonic LLC. The process fuses thin sheets (or ribbons) of metal by ultrasonic vibrations.[43]

© ISO/ASTM International 2020 – All rights reserved
Documents
Document Sharing Hub
Full document details: PD CEN/TR/ISO/ASTM 52912:2020

VDM	Vague Discrete Modelling[8]
VPRP	Variable Property Rapid Prototyping, name for FGAM used by Neri Oxman in some publications.[57]
3MF	3D Manufacturing Format, a digital file format for three dimensional solid models in additive manufacturing, developed by the 3MF consortium, see 8.4.2.3.[3]

5 Concept of Functionally Graded Additive Manufacturing (FGAM)

5.1 General

Additive Manufacturing (AM) is the process of joining materials to make *parts* from 3D model data, usually *layer* upon layer, as opposed to subtractive manufacturing and formative manufacturing methodologies (ISO/ASTM 52900). AM enables the direct fabrication of fine detailed bespoke components by accurately placing material(s) at set positions within a design domain as a single unit[76]. The use of AM has given opportunity to produce parts using FGM, through a process known as Functionally Graded Additive Manufacturing (FGAM). AM technologies suitable for the fabrication of FGMs include Material Extrusion, Direct-Energy Deposition, Powder Bed Fusion, Sheet Lamination[43] and PolyJet technology.

Functionally Graded Additive Manufacturing (FGAM) is a layer-by-layer fabrication technique that intentionally modify process parameters and gradationally varies the spatial of material(s) organization within one component to meet intended function.

FGAM offers a streamlined path from idea to reality. The emergence of FGAM has the potential to achieve more efficiently engineered structures. The aim of using FGAM is to fabricate performance-based freeform components driven by their graduated material(s) behaviour. In contrast to conventional single-material and multi-material AM which focuses mainly on shape-centric prototyping, FGAM is a material-centric fabrication process that signifies a shift from contour modelling to performance modelling. Having the performance-driven functionality built-in directly into the material is a fundamental advantage and a significant improvement to AM technologies. An example includes highly customizable internal features with integrated functionalities that would be impossible to produce using conventional manufacturing[5]. The amount, volume, shape and location of the reinforcement in the material matrix can be precisely controlled to achieve the desired mechanical properties for a specific application[18].

Reference [57] describes the concept of FGAM as a Variable Property Rapid Prototyping (VPRP) method with the ability to strategically control the density and directionality of material substance in a complex 3D distribution to produce a high level of seamless integration of monolithic structure using the same machine. The material characteristics and properties are altered by changing the composition, phase or microstructure with a pre-determined location. The potential material composition achievable by FGAM can be characterised into 3 types:

a) variable densification within a homogeneous composition;

b) heterogeneous composition through simultaneously combining two or more materials through gradual transition;

c) using a combination of variable densification within a heterogeneous composition.

These three types of characteristics are described in 5.2 and 5.3.

5.2 Homogeneous compositions — Single Material FGAM

FGAM can produce efficiently engineered structures by strategically modulating the spatial position (e.g. density and porosity) and morphology of lattice structures across the volume of the bulk material[43]. We term this as varied densification FGAM (also known as porosity-graded FGAM). Reference [56] proposed this as a biological-inspired rapid fabrication that occurs in nature such as the radial density

© ISO/ASTM International 2020 – All rights reserved

AVA Documents Document Sharing Hub
Full document details: PD CEN/TR/ISO/ASTM 52912:2020

gradients in palm trees, spongy trabecular structure of bone and tissue variation in muscle which is heterogeneous in elasticity and stiffness. The directionality, magnitude and density concentration of material substance in a monolithic anisotropic composite structure contribute to functional deviations to modulate the physical properties, and to create functional shapes through structural hierarchy[54].

Man-made structures such as concrete pillars are typically volumetrically homogeneous[27]. Varied densification single-material FGAM was demonstrated through Steven Keating's work on functionally graded concrete being fabricated by a MakerBot machine with a modified material extruder. The concrete piece showed a functional gradient of density to mimic the cellular structures of a palm tree, from a solid exterior to a porous core. The porosity gradient was achieved by varying the powder particle sizes that were assigned in different locations during the gradation process or by varying the production process parameters[43]. For Reference [27], the density was controlled by aggregating the water ratio of the concrete at a given position, which led to excellent strength-to-weight ratio, making it lighter and yet more efficient and stronger than a solid piece of concrete.

5.3 Heterogeneous compositions — Multi-material FGAM

Multiple-material Additive Manufacturing (MMAM) is achievable using conventional 3D printers with multiple nozzles to deliver different materials to the platform[77]. In powder bed fusion, MMAM can be realized by utilizing a conventional delivery device in combination with a suction module to remove powder after the solidifying process-step[7]. As sharp interfaces exist in most conventional MMAM composites where two materials meet and interact, this creates a brittle phase[72]. Failure is commonly initiated between discrete change of materials properties, such as delamination or cracks caused by the surface tension between two materials[17]. Multi-material (MM) FGAM seeks to improve the interfacial bond by removing the distinct boundaries between dissimilar or incompatible materials. The mechanical stress concentrations and thermal stress caused by different expansion coefficients will be largely reduced[72]. Figures 2, a) and b) explain the approach of voxellization of Multi-material Additive Manufacturing according to Reference [7].

© ISO/ASTM International 2020 – All rights reserved
Documents
Document Sharing Hub
Full document details: PD CEN/TR/ISO/ASTM 52912:2020