PD CLC/TR 50682:2018

BSI Standards Publication

Consideration on the use of OTDRs to measure return loss of single-mode optical fibre connections

Documents
Document Sharing Hub

Full document details: PD CLC/TR 50682:2018

National foreword

This Published Document is the UK implementation of CLC/TR 50682:2018.

The UK participation in its preparation was entrusted to Technical Committee GEL/86/2, Fibre optic interconnecting devices and passive components.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018
Published by BSI Standards Limited 2018

ISBN 978 0 580 51409 8

ICS 33.180.01

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 June 2018.

Amendments/corrigenda issued since publication

Date	Text affected

Documents
Document Sharing Hub

Full document details: PD CLC/TR 50682:2018

TECHNICAL REPORT

RAPPORT TECHNIQUE

TECHNISCHER BERICHT

CLC/TR 50682

June 2018

ICS 33.180.01

English Version

Consideration on the use of OTDRs to measure return loss of single-mode optical fibre connections

Examen de l'utilisation de la réflectométrie optique dans le domaine temporel (OTDR) pour la mesure de l'affaiblissement de réflexion des connexions en unimodal

Überlegungen zur Verwendung von OTDRs zur Messung der Rückflussdämpfung von Einmoden-LWL-Verbindungen

This Technical Report was approved by CENELEC on 2018-04-16.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2018 CENELEC All rights of exploitation in any form and by any means reserved worldwide for CENELEC Members.

Ref. No. CLC/TR 50682:2018 E

AVA Documents Document Sharing Hub

Full document details: PD CLC/TR 50682:2018

Contents

Page

European foreword 3
Introduction 4
1 Scope 5
2 Normative references 5
3 Terms and definitions 5
4 Description of Samples 5
5 Test 6
6 Test results 6
7 Conclusions 12
Annex A (informative) **Test data obtained in the Round Robin** 13
Bibliography 19

Documents
Document Sharing Hub
Full document details: PD CLC/TR 50682:2018

European foreword

This document (CLC/TR 50682:2018) has been prepared by CLC/TC 86BXA "*Fibre optic interconnect, passive and connectorised components*".

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

Documents
Document Sharing Hub

Full document details: PD CLC/TR 50682:2018

Introduction

The introduction of new types of optical fibre (i.e. ITU-T G.657, EN 60793-2-50 B6 type) and the differences between manufacturers' products cause a spread of up to 3 dB in the backscatter values (Bs) of available telecommunications single mode fibre. The variation in this parameter can lead to large differences in measured return loss (RL) of connections. This can give issues in field measurement where the fibre type and manufacturer may be unknown and the Bs may not be updated for each measurement in the OTDR.

To evaluate the real impact of this spread of backscatter vales on return loss measurement, a Round Robin Test (RRT) was designed by CLC TC86BXA in 2015. "Black-box" connections (i.e. closed boxes with a connection of two plugs and fibre with similar or different B_s values) were circulated for testing in 2016 and 2017 around several laboratories. The result of this Round Robin is intended to contribute to future specification of return loss requirements on optical components.

Documents
Document Sharing Hub
Full document details: PD CLC/TR 50682:2018

1 Scope

The purpose of this document is to describe a round robin on return loss of single mode optical fibre connections. This includes the description of the samples, the test procedures and test instrumentation, results and conclusions.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 61300-3-6:2009, *Fibre optic interconnecting devices and passive components - Basic test and measurement procedures - Part 3-6: Examinations and measurements - Return loss*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

3.1
return loss
RL
ratio of the power (Pi) incident on, or entering, the DUT to the total power reflected (Pr) by the DUT, expressed in decibels

3.2
backscatter value
B_s
backscattering level of the OTDR trace is a constant (K) that includes both the Rayleigh backscattering of the fibre and the OTDR pulse duration

4 Description of Samples

The Device Under Test (DUT) was an optical fibre-to-fibre connection, protected by a box, making the connection inaccessible to the user. The patch cords used in the DUTs were provided by different manufacturers to ensure a mix of fibres. The plugs in the connection were either SC/APC or SC/PC style which were terminated on single fibre cable 50 m in length, and the free ends were terminated with SC/APC plugs in order to create input/output ports. All the combinations were chosen in order to have a connection RL between 55 dB and 60 dB. Some of these connections were made by mixing fibres with similar B_S and others using different B_S.

Ten DUTs (black boxes) were made in total. The samples were packed and transported in such a way as to minimize performance changes during the round robin test and retested at the end of the RRT.

In Table 1, the fibre manufacturers, fibre types and mode field diameters (MFD) of the samples used in the RRT are listed, together with the backscatter values at 1 310 nm and 1 550 nm. It can be noted that the difference among B_S values is higher at 1 310 nm (~ 2,6 dB), than at 1 550 nm (~ 0,7 dB).

Documents
Document Sharing Hub
Full document details: PD CLC/TR 50682:2018