



BSI Standards Publication

Environmental testing

Part 3-15: Supporting documentation and guidance —
Vacuum-assisted reflow soldering

National foreword

This Published Document is the UK implementation of IEC TR 60068-3-15:2024.

The UK participation in its preparation was entrusted to Technical Committee EPL/501, Electronic Assembly Technology.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

This publication is not to be regarded as a British Standard.

© The British Standards Institution 2024
Published by BSI Standards Limited 2024

ISBN 978 0 539 29877 2

ICS 19.040; 31.190

Compliance with a Published Document cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 April 2024.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

TECHNICAL REPORT



**Environmental testing –
Part 3-15: Supporting documentation and guidance – Vacuum-assisted reflow
soldering**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 19.040; 31.190

ISBN 978-2-8322-8169-7

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 Voids in solder joints	7
4.1 Type of voids	7
4.2 Reasons for voids	8
4.3 Influence of voiding on solder joint performance	9
5 Vacuum-assisted soldering processes	9
5.1 Purpose	9
5.2 Combination of soldering process with vacuum	9
5.3 Typical temperature-pressure-time curves	10
5.3.1 Convection soldering with vacuum	10
5.3.2 Vapour phase soldering with vacuum.....	11
5.3.3 Contact soldering with vacuum	12
6 Effect of vacuum when reflow soldering.....	13
6.1 General.....	13
6.1.1 General description	13
6.1.2 Physical basics.....	13
6.1.3 Vacuum parameters.....	14
6.1.4 Vapour phase vacuum reflow soldering.....	14
6.2 Components in the vacuum reflow soldering process	15
6.2.1 Influence of pressure differences	15
6.2.2 Influence of temperature, time, and vacuum	18
7 Vacuum equipment restrictions	18
7.1 General.....	18
7.2 Chamber size.....	18
7.3 Time to reach vacuum level	19
7.4 Cycle time.....	19
7.5 Summary	19
8 Typical defects after vacuum-assisted reflow soldering.....	20
8.1 Typical defect modes occurring at components	20
8.2 Component defect modes – summary	24
8.3 Soldering defect modes	24
8.3.1 Dropping of components	24
8.3.2 Bridging.....	25
8.3.3 Splattering	25
Bibliography.....	27
Figure 1 – X-Ray examples of voids in solder joints in different SMD-Components	8
Figure 2 – Reduction of voids with low flux soldering & preforms	8
Figure 3 – Example of a product for vacuum-assisted soldering processes	10
Figure 4 – Typical profile – vacuum-assisted convection soldering.....	11
Figure 5 – Typical profile – vacuum-assisted vapour phase soldering	12

Figure 6 – Typical profile – vacuum-assisted contact soldering	13
Figure 7 – Vapour pressure curve of Galden®	15
Figure 8 – Pressures to be considered	16
Figure 9 – Vapour pressure curve of water.....	17
Figure 10 – Blow Hole Void in/out of metallization.....	20
Figure 11 – Gas bubbles at metallization interface	20
Figure 12 – Gas bubble caused by residues in metallization defect.....	21
Figure 13 – Blow out void in solder meniscus.....	21
Figure 14 – Aluminium electrolytic capacitors with non-solid electrolyte, bulged.....	22
Figure 15 – Composite housing bursts in case of overpressure	22
Figure 16 – Housing mainly made of plastic bursts in case of overpressure	23
Figure 17 – Relay lock (polymer dot) blown off.....	23
Figure 18 – Housing with adhesive joint bursts in case of overpressure	24
Figure 19 – An example of bridging on BGA during vacuum assisted soldering	25
Figure 20 – Optimization with stepwise applying of vacuum to reduce bridging	25
Figure 21 – Splattering due to explosive outgassing from the solder joint.....	26
Table 1 – Combination of soldering processes with vacuum.....	10
Table 2 – Molar mass	17
Table 3 – Combination of soldering processes with vacuum.....	19

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ENVIRONMENTAL TESTING –

**Part 3-15: Supporting documentation and guidance –
Vacuum-assisted reflow soldering**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC TR 60068-3-15 has been prepared by technical committee 91: Electronics assembly technology. It is a Technical Report.

The text of this Technical Report is based on the following documents:

Draft	Report on voting
91/1916/DTR	91/1930/RVDTR

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this Technical Report is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 60068 series, published under the general title *Environmental testing*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

As defined in ISO 857-2, reflow soldering is a joining process using an additional metal (solder) with a liquidus temperature of 450 °C or less, in which solder paste or preforms are reflowed.

Reflow soldering can be carried out with the technical processes of convection (air or nitrogen), condensation (vapour phase), radiation (e.g. infrared) or contact heat.

Sometimes it is not possible to achieve the required void level for an assembly only with methods listed above despite the use of all technical possibilities.

Regarding void-induced asymmetrical stress constellations, a reduction of voiding can lead to a mitigated stress condition within the solder joints.

Various technical requirements only tolerate very small void dimensions. To achieve these requirements, vacuum-assisted soldering can be applied with the above mentioned reflow soldering processes.

In some product applications, a hermetic seal is required. The reliable fulfilment of this requirement is very demanding to the process technology especially complex assemblies. Vacuum-assisted soldering creates significantly more consistency in the results here.

Further benefits of vacuum-assisted soldering are improved thermal management or high frequency performance (contour adaptation, mitigation of blow holes).

Vacuum-assisted soldering, however, requires a different equipment with more complex structure and process control. Since the vacuum process has an impact on the process time, the suitability of the components and solder paste that are used need to be checked.

ENVIRONMENTAL TESTING –

Part 3-15: Supporting documentation and guidance – Vacuum-assisted reflow soldering

1 Scope

This part of IEC 60068 describes vacuum-assisted soldering considering the thermal profiling, soldering methods, suitability of the components and vacuum features of soldering systems. It is based on practical experiences from manufacturers, component, material, and soldering systems suppliers. It supports manufacturers by providing information about the functionality of vacuum and effect of vacuum on components performance.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

4 Voids in solder joints

4.1 Type of voids

After soldering, many different macro and micro disturbances of the solder structure can be detected in the solder joints with e.g. X-Ray inspection, ultrasonic inspection or cross sectioning. Some of them represent the so-called voids which are divided according to their causes and type.

The definitions and classification of different void types can be found for example in IPC-7095, IPC-7093 or IEC TR 61191-8. This document describes the use of vacuum to prevent so-called macro voids. Figure 1 shows examples of macro voids in solder joints of different component types.