PD IEC/TR 62283:2010

BSI Standards Publication

Optical fibres — Guidance for nuclear radiation tests

bsi.

...making excellence a habit.™

Document Sharing Hub

National foreword

This Published Document is the UK implementation of IEC/TR 62283:2010. It supersedes PD IEC/TR 62283:2003 which is withdrawn.

The UK participation in its preparation was entrusted by Technical Committee GEL/86, Fibre optics, to Subcommittee GEL/86/1, Optical fibres and cables.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2010

ISBN 978 0 580 69366 3

ICS 17.240; 33.180.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 July 2010.

Amendments issued since publication

Amd. No.	Date	Text affected

Documents
Document Sharing Hub

Full document details: PD IEC/TR 62283:2010

IEC/TR 62283

Edition 2.0 2010-06

TECHNICAL REPORT

Optical fibres – Guidance for nuclear radiation tests

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE V

ICS 33.180.10

ISBN 978-2-88912-031-4

® Registered trademark of the International Electrotechnical Commission

Documents
Document Sharing Hub

Full document details: PD IEC/TR 62283:2010

CONTENTS

FOREWORD 4
INTRODUCTION 6
1 Scope 7
2 Normative references 7
3 Radiation units, dose calculation 7
4 Radiation shielding 9
5 Radiation environments and exposure 9
5.1 Natural radioactivity 9
5.2 Nuclear reactors (fission) 9
5.3 Fusion reactors 9
5.4 High-energy physics experiments 10
5.5 Space environments 10
5.6 Medicine 10
5.7 Military environments 11
5.8 Industrial environments 11
6 Irradiation facilities and dosimetry 11
6.1 General 11
6.2 Continuous gamma irradiation 12
6.3 Neutron irradiation 12
6.4 Proton irradiation 13
6.5 Electron irradiation 14
6.6 Pulsed irradiation 15
7 Radiation effects on optical fibres 15
8 Radiation-induced transmission loss 16
8.1 Overview 16
8.2 Fibre type 17
8.3 Radiation history 17
8.4 Wavelength dependence 17
8.5 Temperature dependence 18
8.6 Light power dependence, photobleaching 19
8.7 Dose rate dependence 21
8.8 Pulsed irradiations 23
8.9 Radiation type dependence 24
8.10 Loss annealing 25
8.11 Conclusions 25
9 Measurement techniques and quality assurance of attenuation measurements 26
10 Radiation effects on passive fibre optic components 26
10.1 Connectors 26
10.2 Couplers and multiplexers 27
10.3 Fibre Bragg gratings 27
Bibliography 29

Figure 1 – Wavelength dependence of the radiation-induced loss of a Ge-doped graded index fibre (50/125 µm) 17
Figure 2 – Temperature dependence of the radiation-induced loss 18

AVA Documents
Document Sharing Hub
Full document details: PD IEC/TR 62283:2010

Figure 3 – Light power dependence of the radiation-induced loss of an undoped single-mode fibre 20
Figure 4 – Light power dependence of the radiation-induced loss in modern MM SI and SM fibres 20
Figure 5 – Dose rate dependence of the radiation-induced loss; *T* = 22 °C 22
Figure 6 – Annealing of the radiation-induced loss of a Ge-doped GI fibre after pulsed electron irradiation with dose values of 5 Gy(SiO_2), 100 Gy(SiO_2) and 1 000 Gy(SiO_2), respectively 23

Documents
Document Sharing Hub
Full document details: PD IEC/TR 62283:2010

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES – GUIDANCE FOR NUCLEAR RADIATION TESTS

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC 62283, which is a technical report, has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This second edition cancels and replaces the first edition of IEC/TR 62283 published in 2003 and constitutes a technical revision.

The main changes with respect to the previous edition are listed below:

– Clause 5 now also covers Industrial environment.
– a new Clause 9 has been added to deal with "Measurement techniques and quality assurance of attenuation measurements".

Documents
Document Sharing Hub
Full document details: PD IEC/TR 62283:2010

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
86A/1312/DTR	86A/1327/RVC

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

Documents
Document Sharing Hub
Full document details: PD IEC/TR 62283:2010

INTRODUCTION

In order to restrict the test method of IEC 60793-1-54, *Optical fibres – Part 1-54: Measurement methods and test procedures – Gamma irradiation* to a clear, concise listing of instructions, the background knowledge that is necessary to perform correct, relevant and expressive irradiation tests as well as to limit measurement uncertainty is presented here separately as a "guidance document".

Documents
Document Sharing Hub
Full document details: PD IEC/TR 62283:2010

OPTICAL FIBRES – GUIDANCE FOR NUCLEAR RADIATION TESTS

1 Scope

This technical report gives a short summary of the radiation exposure in certain environments and applications and the different radiation effects on fibres. It also describes the most important radiation effect, i.e. the increase of transmission loss, and its strong dependence on a variety of fibre properties and test conditions. These dependencies need to be known in order to perform appropriate tests for each specific application as well as to understand, compare and qualify the test results obtained at different laboratories when performed according to IEC 60793-1-54, *Optical fibres – Part 1-54: Measurement methods and test procedures – Gamma irradiation.*

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-40, *Optical fibres – Part 1- 40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 60793-1-54, *Optical fibres – Part 1-54: Measurement methods and test procedures – Gamma irradiation*

3 Radiation units, dose calculation

The interaction of radiation with matter depends on charge, mass and energy in the case of particle radiation (for example, electrons, protons, neutrons, alphas and heavy ions) and on energy in the case of electromagnetic radiation such as X-rays or gamma quanta. The interaction causes an energy transfer to the respective matter. This leads to ionization and warming up. Additionally structural damage in the material may occur at higher doses, leading to other effects such as changes of refractive index or mechanical properties.

The higher the radiation's energy, the stronger its penetrability and the longer its range. The energy unit is the electron Volt (eV). Usual radiation energies in natural or technical environments range from tens of keV (medical X-rays) to several MeV (fission or fusion reactors and nuclear weapons). Current energies at high-energy physics accelerators vary depending on the type of colliding particles. The highest energy for electron-positron collisions is 100 GeV per beam. For proton-proton collisions the energy per beam is 1 TeV. The new "Large Hadron Collider" (LHC) at CERN uses beams with an energy of 7 TeV. In addition, there are quite a number of other accelerators which operate between these limits.

Note that these energies refer to the colliding particles. The secondary particles, i.e. the ones likely to affect fibres, have much lower energies.

The energy deposited by ionizing radiation in matter is called "energy dose" (or absorbed dose). The old unit is rad, (rd or rad); 1 rad = 100 erg/g (1 erg = 10^{-7} J) but should not be used anymore. The SI unit is the Gray [Gy]; 1 Gy = 1 J/kg = 100 rad.

AVA Documents
Document Sharing Hub

Some dosimeter types measure the charge released in a gas (for example, ionization chambers). This was used to define another type of dose, the "ion dose". The ion dose unit is the röntgen (non-SI unit), [R]; 1 R = 2,58 × 10^{-4} C/kg, with C = charge unit (coulomb). Conversion of ion dose, D', to energy dose, D, can be performed for ^{60}Co gamma rays (about 1,2 MeV) by

$$D = 0{,}879 \frac{\text{Gy(air)}}{\text{R}} \; D' \tag{1}$$

If this unit is used, the values of relevant quantities shall be given in terms of SI units first followed by these non-SI units in parentheses.

The energy transfer of gammas and X-rays to matter depends on their energy as well as on the irradiated material. Therefore, the material has to be added to the dose unit (for example [Gy(Si)], [rad(SiO_2)], [Gy(air)] etc.), and the dose D(d) measured with a dosimeter material d (for example, air) can differ significantly from the dose D(m) deposited in the investigated material m (for example, Si, SiO_2, InGaAs etc.).

The dose ratio between both materials D(m) is given by the ratio of their "photon mass energy absorption coefficient" μ_{en}/ρ:

$$D(m) = \frac{(\mu_{en}/\rho)_m}{(\mu_{en}/\rho)_d} \; D(d) \tag{2}$$

The μ_{en}/ρ-values can differ significantly, especially for materials of high and low atomic number at energies < 300 keV. They are tabulated for various elements and compounds in reference [1][1].

The dose rate, i.e. the dose exposition per time, should be given in units of Gy/h, kGy/h, or Gy/s.

The intensity of particle radiation is usually characterized by the fluence Φ. The unit is particles/cm^2 or only cm^{-2}. The dose of charged particles (in a certain material depth) can be calculated from their fluence and their (energy-dependent) energy loss per unit of length, dE/dx (= stopping power):

$$D = \frac{\Phi}{\rho} \cdot \frac{dE}{dx} \tag{3}$$

with ρ = material density. The stopping power can be calculated with the software package "SRIM"[2], see [2]. The particle fluence per time unit is called flux or flux density. The unit is $cm^{-2}\,s^{-1}$.

The neutron dose D_n can be calculated from its fluence Φ_n and the energy and material dependent "fluence dose conversion factor" or "kerma factor" $k(E_n,\text{Mat.})$:

$$D_n = \Phi_n \cdot k(E_n, Mat.) \tag{4}$$

The kerma-factors are tabulated for a variety of elements and compounds in [3].

---

1) Numbers in square brackets refer to the bibliography.

2) SRIM is the trade name of a product supplied by IBM. This information is given for the convenience of users of this Technical Report and does not constitute an endorsement by IEC of the product named. Equivalent products may be used if they can be shown to lead to the same results.

AVA Documents
Document Sharing Hub
Full document details: PD IEC/TR 62283:2010

4 Radiation shielding

Shielding of optical fibres against (especially gamma) radiation is in most cases not reasonably achievable since, for example, gamma rays of 1 MeV are attenuated to 1/10 of their initial intensity only by 5 cm of lead.

However, buried fibre cables that are layed in at least 1 m depth are shielded against 1 MeV gamma rays by about a factor of 10^4.

5 Radiation environments and exposure

5.1 Natural radioactivity

The predominant radiation type is gamma rays. Typical annual dose value for earth cables or undersea cables is <0,004 Gy. The total dose during an expected cable lifetime of 25 years would thus be <0,1 Gy. Distinctly higher values are possible, for example, above uranium or thorium ore deposits. The dose and dose rates are typical and may vary depending on the specific application.

5.2 Nuclear reactors (fission)

Optical fibres can be exposed to gamma rays as well as to thermal and fast neutrons. Dose and fluence values depend strongly on the place within the reactor building and the operating conditions of the reactor (for example the power delivery, normal operation or accident).

Within the containment area, exposure levels range from 0,001 Gy/h to 0,03 Gy/h up to about 1 Gy/h near the primary coolant lines. The dose rate around the fuel rods is of the order of 10^3 Gy/h. In the early stage of an accident, dose rates as high as 10^4 Gy/h will occur within the containment [4].

The neutron flux (= fluence Φ per unit of time) within the containment can range from about 10 $cm^{-2}s^{-1}$ up to about 10^{12} $cm^{-2}s^{-1}$near the fuel rods.

The dose, dose rates and neutron fluence are typical and may vary depending on the specific application.

5.3 Fusion reactors

The primary radiation emitted after the fusion of deuterium (D) and tritium (T) nuclei are 14 MeV neutrons and ^{4}He nuclei (energy about 3,5 MeV). The ^{4}He ions are very short-ranged and will not reach optical fibres that might be used as sensors or to transfer data, whereas the fast neutrons are very penetrating and will also activate the structural materials around the reaction chamber. These materials then emit high gamma ray intensities also after reactor turn-off.

Again, the total dose and neutron fluence values depend strongly on location and operation conditions.

For the future test facility ITER (International Thermonuclear Experimental Reactor), gamma dose rates at the first wall of about 2×10^2 Gy/s and life dose values of 10^7 Gy to 10^9 Gy are expected. The neutron fluence there could reach values up to 10^{20} cm^{-2}.

At inertial confinement fusion (ICF) facilities such as "Laser Megajoule" (France) or "National Ignition Facility" (USA) diagnostic equipment, comprising also optical fibres, is exposed to pulsed radiation of up to 10^3 Gy at dose rates up to 10^{10} Gy/s.

The dose and dose rates are typical and may vary depending on the specific application.

AVA Documents
Document Sharing Hub
Full document details: PD IEC/TR 62283:2010