PD IEC/TS 60034-27-2:2012

BSI Standards Publication

Rotating electrical machines

Part 27-2: On-line partial discharge measurements on the stator winding insulation of rotating electrical machines

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

raising standards worldwide™

Full document details: PD IEC/TS 60034-27-2:2012

National foreword

This Published Document is the UK implementation of IEC/TS 60034-27-2:2012.

The UK participation in its preparation was entrusted to Technical Committee PEL/2, Rotating electrical machinery.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012

Published by BSI Standards Limited 2012

ISBN 978 0 580 80766 4

ICS 29.160

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 October 2012.

Amendments issued since publication

Amd. No.	Date	Text affected

Documents
Document Sharing Hub

Full document details: PD IEC/TS 60034-27-2:2012

IEC/TS 60034-27-2

Edition 1.0 2012-03

TECHNICAL SPECIFICATION

colour inside

Rotating electrical machines –
Part 27-2: On-line partial discharge measurements on the stator winding insulation of rotating electrical machines

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE XA

ICS 29.160

ISBN 978-2-88912-018-5

Warning! Make sure that you obtained this publication from an authorized distributor.

® Registered trademark of the International Electrotechnical Commission

Documents
Document Sharing Hub

Full document details: PD IEC/TS 60034-27-2:2012

CONTENTS

FOREWORD 5
INTRODUCTION 7
1 Scope 9
2 Normative references 9
3 Terms and definitions 9
4 Nature of PD in rotating machines 11
4.1 Basics of PD 11
4.2 Types of PD in rotating machines 12
4.2.1 General 12
4.2.2 Internal discharges 12
4.2.3 Slot discharges 13
4.2.4 Discharges in the end-winding 13
4.2.5 Conductive particles 13
4.3 Arcing and sparking 14
4.3.1 General 14
4.3.2 Arcing at broken conductors 14
4.3.3 Vibration sparking 14
5 Noise and disturbance 14
5.1 General 14
5.2 Noise and disturbance sources 14
5.3 Frequency domain separation 15
5.4 Time domain separation 16
5.5 Combination of frequency and time domain separation 17
5.6 Gating 17
5.7 Pattern recognition separation 18
6 Measuring techniques and instruments 18
6.1 General 18
6.2 Pulse propagation in windings 19
6.3 Signal transfer characteristics 19
6.4 PD sensors 22
6.4.1 General 22
6.4.2 Design of PD sensors 22
6.4.3 Reliability of PD Sensors 23
6.5 PD measuring device 23
6.6 PD measuring parameters 23
6.6.1 General 23
6.6.2 PD magnitude 23
6.6.3 Additional PD parameters 24
7 Installation of PD on-line measuring systems 24
7.1 General 24
7.2 Installation of PD sensors 24
7.3 Outside access point and cabling 25
7.4 Installation of the PD measuring device 26
7.5 Installation of operational data acquisition systems 26
8 Normalization of measurements 27

AVA Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

8.1 General ... 27
8.2 Normalization for low frequency systems ... 27
8.2.1 General ... 27
8.2.2 Normalization procedure ... 27
8.3 Normalization / sensitivity check for high & very high frequency systems ... 29
8.3.1 Specification for the electronic pulse generation ... 29
8.3.2 Configuration of the machine ... 30
8.3.3 Sensitivity check ... 30
9 Measuring procedures ... 30
9.1 General ... 30
9.2 Machine operating parameters ... 31
9.3 Baseline measurement ... 31
9.3.1 General ... 31
9.3.2 Recommended test procedure ... 31
9.4 Periodic on-line PD measurements ... 32
9.5 Continuous on-line PD measurements ... 33
10 Visualization of measurements ... 33
10.1 General ... 33
10.2 Visualization of trending parameters ... 33
10.3 Visualization of PD patterns ... 34
11 Interpretation of on-line measurements ... 37
11.1 General ... 37
11.2 Evaluation of basic trend parameters ... 37
11.3 Evaluation of PD patterns ... 38
11.3.1 General ... 38
11.3.2 PD pattern interpretation ... 38
11.4 Effect of machine operating factors ... 39
11.4.1 General ... 39
11.4.2 Machine operating factors ... 39
11.4.3 Steady state load conditions ... 39
11.4.4 Transient load conditions ... 40
12 Test report ... 41
Annex A (informative) Examples of Phase Resolved Partial Discharge (PRPD) pattern ... 44
Bibliography ... 55

Figure 1 – Time domain disturbance separation by time of pulse arrival ... 16
Figure 2 – Combined time and frequency domain disturbance separation (TF-map) ... 17
Figure 3 – Idealized frequency response of a PD pulse at the PD source and at the machine terminals; Frequency response of different PD measuring systems: a) low frequency range, b) high frequency range, c) very high frequency range ... 21
Figure 4 – Measuring object, during normalization ... 28
Figure 5 – Arrangement for sensitivity check ... 29
Figure 6 – Recommended test procedure with consecutive load and temperature conditions ... 32
Figure 7 – Example of visualization of trending parameters ... 34
Figure 8 – Example of a Φ-q-n partial discharge pattern, with colour code for the pulse number H(n)/s ... 35

AVA Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

Figure 9 – Example of a three phase, phase shifted Φ-q-n plot 36
Figure A.1 – Stylized examples of PD phase resolved patterns 44
Figure A.2 – Example of internal void discharges PRPD pattern, recorded during laboratory simulation 45
Figure A.3 – Example of internal delamination PRPD pattern, recorded during laboratory simulation 46
Figure A.4 – Example of delamination between conductor and insulation PRPD pattern, recorded during laboratory simulation 47
Figure A.5 – Slot partial discharges activity and corresponding PRPD pattern, recorded during laboratory simulation 47
Figure A.6 – Corona activity at the S/C and stress grading coating, and corresponding PRPD pattern, recorded during laboratory simulation 48
Figure A.7 – Surface tracking activity along the end arm and corresponding PRPD pattern, recorded during laboratory simulation 48
Figure A.8 – Gap type discharge activities and corresponding PRPD patterns, recorded during laboratory simulations 49
Figure A.9 – Example of internal void discharges PRPD pattern, recorded on-line 50
Figure A.10 – Example of internal delamination PRPD pattern, recorded on-line 51
Figure A.11 – Example of delamination between conductor and insulation PRPD pattern, recorded on-line 51
Figure A.12 – Degradation caused by slot partial discharges activity and corresponding PRPD pattern recorded on-line 52
Figure A.13 – Degradation caused by corona activity at the S/C and stress grading coating and corresponding PRPD pattern, recorded on-line 53
Figure A.14 – Surface tracking activity along the end arm and corresponding PRPD pattern, recorded on-line 53
Figure A.15 – Degradation caused by gap type discharges and corresponding PRPD patterns, recorded on-line 54
Figure A.16 – PRPD pattern recorded on-line, illustrating multiple PD sources 54

Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ROTATING ELECTRICAL MACHINES –

Part 27-2: On-line partial discharge measurements on the stator winding insulation of rotating electrical machines

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a technical specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC/TS 60034-27-2, which is a technical specification, has been prepared by IEC technical committee 2: Rotating machinery.

Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

The text of this technical specification is based on the following documents:

Enquiry draft	Report on voting
2/1636/DTS	2/1649/RVC

Full information on the voting for the approval of this technical specification can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

NOTE A table of cross-references of all IEC TC 2 publications can be found on the IEC TC 2 dashboard on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- transformed into an International standard,
- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

Documents
Document Sharing Hub

Full document details: PD IEC/TS 60034-27-2:2012

INTRODUCTION

For many years, the measurement of partial discharges (PD) has been employed as a sensitive means of assessing the quality of new insulation as well as a means of detecting localized sources of PD in used electrical winding insulation arising from operational stresses in service. Compared with other dielectric tests (i.e. the measurement of dissipation factor or insulation resistance) the differentiating character of partial discharge measurements allows localized weak points of the insulation system to be identified. Especially on-line PD measurements are not only sensitive to partial discharges but also to various arcing and sparking phenomena.

With regard to condition assessment of rotating machines, the measurement of partial discharges can provide information on:

– points of weakness in the insulation system;
– degradation processes;
– maintenance measures and intervals between overhauls.

Although the PD testing of rotating machines has gained widespread acceptance, it has emerged from several studies that not only are there many different methods of measurement in existence but also the criteria and methods of analysing and finally assessing the measured data are often very different and not really comparable. Consequently, there is a need to give some guidance to those users who are considering the use of PD measurements to assess the condition of their insulation systems.

Partial discharge testing of stator windings can be divided into two broad groups:

a) off-line measurements, in which the stator winding is isolated from the power system and a separate power supply is employed to energize the winding;
b) on-line measurements, in which the rotating machine is operating normally and connected to the power system.

Both of these approaches have advantages and disadvantages with respect to one another. A detailed discussion of PD off-line testing is provided in IEC/TS 60034-27, whereas this technical specification is confined to on-line techniques. The approach to deal with PD on- and off-line measurement techniques in two different technical specifications is considered necessary to render each specification sufficiently concise to be of use by non-specialists in the field of PD measurement.

PD on-line measurements are recorded with the rotating machine experiencing all of the operating stresses; thermal, electrical, environmental and mechanical. On-line PD testing has the following advantages:

– the voltage distribution across the winding is the same as during operation;
– the measurements are made at operating temperature;
– normal mechanical forces are present.

Due to the realistic stress impact on the winding during measurement and due to the fact that the measurement is performed during normal operation, on-line PD testing has become very popular. Since no service interruption is required, once the PD sensors are installed during a scheduled unit outage, and no external power source is needed, on-line testing is usually cost effective compared to off-line PD measurement. Condition changes of the stator winding insulation system can be identified and evaluated at an early stage based on a real-time condition assessment and thus condition-based and predictive maintenance strategies can be improved.

Empirical limits verified in practice can be used as a basis for evaluating test results. Furthermore, PD trend evaluation and comparisons with machines of similar design and similar

AVA Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

insulation system measured under similar conditions, using the same measuring equipment, are recommended to ensure reliable assessment of the condition of the stator winding insulation.

This technical specification does not deal with online PD measurements on converter driven electrical machines because different measuring techniques are needed to distinguish between noise from the converter and PD from the winding. For this purpose IEC/TS 61934 may apply.

Limitations

On-line PD tests on stator windings produce comparative, rather than absolute measurements. This creates a fundamental limitation for the interpretation of PD data, and implies that simple limits for allowable PD cannot be established unless many precautions are taken. For the same reasons, PD acceptance criteria for new or rewound stator windings cannot be established unless many precautions are taken. The reasons for the difficulty to set absolute limits for PD include:

- There are many types of PD sensors as well as recording and analyzing instruments. Generally they are incompatible and will produce different results for the same PD activity.
- Even with the same measuring system, partial discharges will interact with the winding capacitance, inductance and/or surge impedance to produce different voltage and current pulses. Thus PD measurements from machines with different ratings and/or winding connections may produce different PD results, even though the actual amount of damage may be the same.
- Different types of defects can produce different PD magnitudes, even with the same amount of damage.
- PD may occur close or far from the PD sensor. In general if the PD is physically far from the PD sensor, it will produce a smaller response at the PD sensor due to attenuation.

Users should also be aware that there is no evidence that the time to failure of the stator winding insulation can be estimated using any PD quantity, even in combination with other electrical tests. Also, determining the root cause of an insulation deterioration process using pattern recognition, especially if more than one process is occurring, is still somewhat subjective, although the technology is evolving rapidly.

Noise and disturbance may have a great impact on the detected signals, especially for on-line PD measurements. Cross-coupling of PD and noise on one phase can obscure PD on another phase. With some measuring systems, this can make objective interpretation of the test results difficult.

Users of PD measurement should be aware that, due to the principles of the method, not all insulation-related problems in stator windings can be detected by measuring partial discharges, e.g. insulation failures involving continuous leakage currents due to conductive paths between different elements of the insulation or pulse-less discharge phenomena.

Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

ROTATING ELECTRICAL MACHINES –

Part 27-2: On-line partial discharge measurements on the stator winding insulation of rotating electrical machines

1 Scope

This part of IEC 60034, which is a technical specification, provides a common basis for

– measuring techniques and instruments;
– the arrangement of the installation;
– normalization and sensitivity assessment;
– measuring procedures;
– noise reduction;
– the documentation of results;
– the interpretation of results;

with respect to partial discharge on-line measurements on the stator winding insulation of non-converter driven rotating electrical machines with rated voltage of 3 kV and up. This technical specification covers PD measuring systems and methods detecting electrical PD signals. The same measuring devices and procedures can also be used to detect electrical sparking and arcing phenomena.

NOTE The main differences between on-line measurements and off-line measurements are due to a different voltage distribution along the winding and various thermal and mechanical effects related to the operation, like vibration, contact arcing or temperature gradients between stator copper and stator iron core. Furthermore, especially for hydrogen-cooled machines the gas and the gas pressure is different for off- and on-line PD measurements.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60270:2000, *High-voltage test techniques – Partial discharge measurements*

IEC/TS 60034-27, *Rotating electrical machines – Part 27: Off-line partial discharge measurements on the stator winding insulation of rotating electrical machines*

3 Terms and definitions

For the purposes of this document the general terms and definitions for partial discharge measurements given in IEC 60270 apply, together with the following.

3.1
off-line measurement
measurement taken with the rotating machine at standstill, the machine being disconnected from the power system

Note 1 to entry: The necessary test voltage is applied to the winding from a separate voltage source

AVA Documents
Document Sharing Hub

Full document details: PD IEC/TS 60034-27-2:2012

3.2
on-line measurement
measurement taken with the rotating machine in normal operation

3.3
periodic on-line PD measurement
on-line PD measurement performed on the machine at regular intervals

3.4
continuous on-line PD measurement
on-line PD measurement performed on the machine with a measuring device continuously acquiring PD data

3.5
stress control coating
paint or tape on the surface of the groundwall insulation that extends beyond the conductive slot portion coating in high-voltage stator bars and coils

Note 1 to entry: The stress control coating reduces the electric field stress along the winding overhang to below a critical value that would initiate PD on the surface. The stress control coating overlaps the conductive slot portion coating to provide electrical contact between them.

3.6
conductive slot coating
conductive paint or tape layer in intimate contact with the groundwall insulation in the slot portion of the coil side, often called ‘semiconductive’ coating

Note 1 to entry: This coating together with adequate slot design provides electrical contact to the stator core, without shorting the core laminations.

3.7
corona discharge
visible partial discharge adjacent to the surface of a conductor in gases

3.8
slot discharges
discharges that occur between the outer surface of the slot portion of a coil or bar and the grounded core laminations due to high voltage

3.9
vibration sparking
interrupted surface currents between the outer surface of the slot portion of a bar and the grounded core laminations due to axially induced voltages on the conductive slot coating combined with bar vibrations

3.10
internal discharges
discharges that occur within the insulation system

3.11
surface discharges
discharges that occur on the surface of the insulation or on the surface of winding components in the winding overhang or the active part of the machine winding

3.12
pulse magnitude distribution
number of pulses within a series of equally-spaced windows of pulse magnitude during a predefined measuring time

Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

3.13
pulse phase distribution
number of pulses within a series of equally-spaced windows of phase during a predefined measuring time

3.14
phase resolved partial discharge pattern
PD distribution map of PD magnitude vs. a.c. cycle phase position, for visualization of the PD behaviour during a predefined measuring time

3.15
PD sensor
general type of transducer, which can be used to detect PD signals from the machine winding

Note 1 to entry: A PD sensor typically consists of a high voltage coupling capacitor of low inductance design and a low voltage coupling device in series.

3.16
coupling device
usually an active or passive four-terminal network that converts the input currents to output voltage signals

Note 1 to entry: These signals are transmitted to the measuring device by a transmission system. The frequency response of the coupling device is normally chosen at least so as to efficiently prevent the test voltage frequency and its harmonics from reaching the measuring device.

3.17
resistance temperature detector
RTD
temperature detector inserted into the stator winding, usually between the top and bottom bar or between embedded coil sides in a given slot

3.18
largest repeatedly occurring PD magnitude Q_m
the largest magnitude recorded by a measuring system which has the pulse train response in accordance with 4.3.3 of IEC 60270, or the magnitude associated with a PD pulse repetition rate of a specified number of pulses per second, which can be directly inferred from a pulse magnitude distribution.

Note 1 to entry: A recommended pulse repetition rate is 10 pulses or more per second.

4 Nature of PD in rotating machines

4.1 Basics of PD

Generally, partial discharges (PD) can develop at locations where the dielectric properties of insulating materials are inhomogeneous. At such locations, the local electrical field strength may be enhanced. Due to local electrical over-stressing this may lead to a local, partial breakdown. This partial breakdown is not a total breakdown of the insulation system. PD in general requires a gas volume to develop, e.g. in gas filled voids embedded in the insulation, adjacent to conductors or at insulation interfaces.

A partial discharge can occur when the local field strength exceeds the dielectric strength of the insulating material. This process may result in numerous PD pulses during one cycle of the applied voltage.

The amount of charge transferred in the discharge is closely related to the specific properties of the inhomogeneity such as the dimensions, the actual breakdown voltage and the specific dielectric properties of the materials involved, e.g. surface properties, kind of gas, gas pressure, etc.

AVA Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

Stator winding insulation systems for high voltage machines will normally have some PD activity, but are inherently resistant to partial discharges due to their inorganic mica components. However, significant PD in these machines is usually more a symptom of insulation deficiencies, like manufacturing problems or in-service deterioration, rather than being a direct cause of failure. Nevertheless, depending on the individual processes, PD in machines may also directly attack the insulation and thus influence the ageing process. The time to failure or failure probability may not always correlate with PD levels, but depends significantly on other factors, for example operating temperature, wedging conditions, bar vibrations, degree of contamination, etc.

The measurement and the analysis of the specific PD behaviour can be efficiently used for quality control of new windings and winding components and for early detection of insulation deficiencies caused by thermal, electrical, ambient and mechanical ageing factors in service, which might result in an insulation fault.

The main differences between on-line measurements and off-line measurements are due to a different voltage distribution along the winding and various thermal and mechanical effects related to the operation, like vibration, contact arcing or temperature gradients between stator copper and stator iron core. Furthermore, especially for hydrogen-cooled machines the gas and the gas pressure is different for off- and on-line PD measurements.

4.2 Types of PD in rotating machines

4.2.1 General

Partial discharges may develop throughout the stator winding insulation system due to specific manufacturing technologies, manufacturing deficiencies, normal in-service ageing, or abnormal ageing. Machine design, the nature of the materials used, manufacturing methods, operating conditions, etc. can profoundly affect the quantity, location, characteristics, evolution and the significance of PD. For a given machine, the existing PD sources may be identified and distinguished in many cases by their characteristic PD behaviour.

4.2.2 Internal discharges

4.2.2.1 Internal voids

Although manufacturing processes are designed to minimize internal voids, inevitably there is some void content. For example in a resin impregnated mica tape insulation system, that is commonly used in high voltage rotating machines, the mica in the insulation system prevents the partial discharges from developing into a complete breakdown. As long as internal voids are small and do not significantly enlarge, operational reliability is not reduced.

4.2.2.2 Internal delamination

Internal delamination within the main insulation can be caused by imperfect curing of the insulation system during manufacturing or by mechanical or thermal over-stressing during operation. Large voids may develop over a large surface resulting in discharges of relatively high energy, which may significantly attack the insulation. In particular, delamination will reduce the thermal conductivity of the insulation, which might lead to accelerated ageing or even a thermal runaway. Thus, delamination needs careful consideration when PD activity is being assessed.

4.2.2.3 Delamination between conductors and insulation

Thermal cycling may cause delamination at the interface of the conductor and the main insulation. This delamination can result in partial discharges which can relatively rapidly result in failure especially in multi-turn coils.

Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

4.2.2.4 Electrical treeing

Electrical treeing in machine insulation is an ageing process in which fine erosion channels propagate through the epoxy around the mica barriers and may finally lead to electrical breakdown of the main insulation. Electrical treeing can start at any point of locally enhanced electric field within the insulation, e.g. rough structures of the inner conductor, insulation impurities, gas filled voids or delaminations in the insulation. This process is associated with internal partial discharge activity.

4.2.3 Slot discharges

Slot discharges in high voltage machines will develop when the conductive slot portion coating is damaged due to bar/coil movement in the slot or slot exit area, for example by a loss of wedging pressure due to settlement, erosion of the material, abrasion, chemical attack or manufacturing deficiencies. Higher discharges will develop when serious mechanical damage is already present, which may result in additional damage to the main insulation and eventually in an insulation fault. Slot discharges are generally caused by locally enhanced electric fields, and thus these processes occur only at the higher voltage end of each phase. The absolute time between detection of this phenomenon and final insulation failure is generally unknown. However, compared to other typical deterioration effects this time could be relatively short, especially in the presence of bar/coil vibrations. Thus, reliable detection at an early stage is necessary to decide if appropriate remedial actions are required.

4.2.4 Discharges in the end-winding

4.2.4.1 General

Partial discharges in the end-winding area may occur at several locations with high local electric field strengths. Such discharges usually occur at interfaces between different elements of the stator winding overhang.

4.2.4.2 Surface discharges

Surface discharges generally occur whenever the electrical field along a surface exceeds the breakdown field of the surrounding gas. This may occur if no stress control coating is applied or the stress control coating of the end-winding becomes ineffective because of poorly designed interfaces, contamination, porosity, thermal effects, etc. When reliable field grading is no longer assured surface discharges will develop, which may gradually erode the materials. This is normally a very slow failure mechanism, even though the PD behaviour might be subjected to relatively fast changes due to surface effects. Surface discharges usually result in a phase to ground fault.

4.2.4.3 Phase to phase discharges

PD may occur between phases, for example due to inadequate phase to phase clearances or at elements of the overhang support system like spacers or cords. Depending on specific design details these discharges may have large magnitudes and may either occur as surface discharges or internal discharges and thus the time between detection of this phenomenon and final insulation failure is uncertain. Phase to phase discharges may result in a phase to phase breakdown.

4.2.5 Conductive particles

Conductive particles, especially small particles, for example due to contamination of the winding, may result in a strong local concentration of partial discharges. This may result in a ‘pinhole’ in the insulation.

Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

4.3 Arcing and sparking

4.3.1 General

In contrast to the types of PD described in 4.2, which are caused by locally enhanced electric fields, arcing and sparking phenomena occur due to interruption of currents resulting from the magnetic flux within the stator core. These processes involve higher energy and temperatures, which leads to a faster degradation of the insulation materials. Arcing and sparking lead to transient pulses, which can also be detected by PD measuring systems.

4.3.2 Arcing at broken conductors

Broken conductors, resulting from mechanical vibrations, may lead to intermittent contacts and consequently to arc formation.

4.3.3 Vibration sparking

Due to the magnetic field in the stator core parasitic surface currents will flow axially along the conductive slot coating of a bar. In case the bar vibrates, these currents may be interrupted at a contact point to the core iron, and the interruption of this current will form an arc to the core. If the resistance of the conductive coating is too low, the current will be of significant magnitude and the resulting arc can damage the groundwall insulation by an erosion process. This so called vibration sparking, which is a relatively fast deterioration mechanism, may occur at any point of the winding and thus also at low potential sites, for example close to the neutral of the winding.

5 Noise and disturbance

5.1 General

An important challenge with on-line PD measurement is separating stator-winding PD from electrical noise or disturbances. In contrast to properly set-up off-line PD tests, in most on-line tests electrical disturbance pulses will often be present, and these disturbance pulses may be more frequent and of larger magnitude than the stator winding PD pulses, also the signals may be phase-locked to the AC power frequency voltage. If the disturbances are not adequately suppressed, or the test technician is not able to adequately identify what is a disturbance and what is stator PD, there is a great risk that the disturbance will be classed as stator PD. Consequently the stator may be identified as having serious insulation problems, when in fact the insulation may be in good condition. If too many ‘false positives’ occur, confidence is lost in the test, and future testing may not be routinely done, losing the benefit of on-line PD testing.

5.2 Noise and disturbance sources

Consistent with IEC/TS 60034-27, noise is defined to be non-stator winding signals that clearly are not pulses. Noise may be due to electronic devices within the PD detection system itself, for example thermal noise from semiconductive devices. Noise can also be from radio stations, radio transmitters, mobile telephones, power line carrier signals, etc. This noise is easily separated from pulse-like signals either visually on an oscillographic display or with the use of filters. Thus it is not considered further in this technical specification.

Disturbances are electrical pulses of relatively short duration that may have many of the characteristics of stator winding PD pulses – but in fact are not stator winding PD. Some of these disturbances are synchronized to the AC cycle, and some are not. Sometimes synchronized disturbance pulses can be suppressed based on their position with respect to the AC phase angle.

Examples of synchronized disturbances are:

Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

a) Partial discharges caused by e.g. electrostatic precipitators or bushing discharges
b) Power tool operation such as from arc welding and commutator sparking (may also be unsynchronized)
c) Transients caused by power electronics, for example converter fed motors or excitation systems. This disturbance may also be unsynchronized to the AC cycle
d) Poor electrical connections (leading to contact sparking) on the bus or cable connecting the rotating machine to the power system
e) Poor electrical connections elsewhere in the plant that lead to contact sparking
f) PD in other apparatus connected to the motor or generator terminals, for example output bus, power cable, switchgear and/or transformers
g) Arcing or sparking sources within the motor or generator, such as stator core lamination sparking

Examples of non-synchronized disturbances are:

h) Power tool operation (arc welding and commutator sparking)
i) Transients caused by power electronics, for example converter fed motors or static excitation systems
j) Slip ring sparking on the machine rotor
k) Overhead crane power rail sparking

All of these disturbances create electrical pulses that the unwary may confuse with stator winding PD. With disturbances d), e), f), and g), the operator normally wants to know if such activity is occurring, because it may indicate other problems (beyond stator insulation problems) that may lead to equipment failure. Thus some users may not class these examples as a disturbance, but rather as signals to be identified.

To reduce the risk of false indications of the stator winding insulation condition, many methods have been developed to help users to manually and/or automatically separate stator winding PD from disturbances. Many of the commercially available methods use one or more of the methods identified below.

5.3 Frequency domain separation

The Fourier transform of an individual PD pulse will contain frequencies from DC up to several hundred megahertz, if the PD sensor is in close proximity to the PD source. Many types of disturbances produce pulses, but the frequency content of the pulses at the PD sensor may be lower than stator winding PD. For example, sparking caused by poor electrical contacts or PD in other apparatus that is remote from the machine under test, often produce frequencies up to just a few megahertz. Thus one method of separating PD from disturbances is to use analogue or digital filters that preferentially respond to pulses in specific frequency ranges. The PD measuring system (sensor and detection electronics) will be described as having a lower cut-off frequency and an upper cut-off frequency. Typical frequency ranges for on-line PD measuring systems according to Clause 6 are in the high frequency range (HF: 3 MHz to 30 MHz), in the very high frequency range (VHF: 30 MHz to 300 MHz), or in the ultra high frequency range (UHF: 300 MHz to 3 GHz). When using measuring systems in the low frequency range (LF: below 3 MHz), the lower frequencies will be subject to the significant influence of power line carrier, converter fed motor switching and excitation system disturbances, which need to be suppressed.

Generally, the higher the upper cut-off frequency of the PD detection system, the greater will be the signal to noise ratio, and thus the lower will be the risk of false indications. However, the higher the lower cut-off frequency, then the lower is the likelihood of PD being detected that is remote from the sensor. Assuming the PD sensor is located at the high voltage terminals of the stator winding, a low frequency range PD system will be sensitive to PD in more coils than a high frequency range PD system. Note however that in on-line PD testing the coils near the high voltage terminal are the only ones likely to have high levels of PD activity.

AVA Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012

since the voltage is higher than for coils remote from the terminals. However, other sparking and arcing phenomena, which may significantly damage the insulation, can also be detected by PD measuring devices and can occur throughout the winding even at low potential sites close to the neutral.

5.4 Time domain separation

In some on-line PD monitoring systems, PD is separated from disturbances on the basis of time domain characteristics. Two types of time domain separation systems have been employed:

– Pulse shape analysis
– Time of pulse arrival

Both types can only be used with a high bandwidth detection system.

Pulse shape analysis is the time domain analogy of filtering. It is predicated on specific time domain pulse characteristics such as rise-time and decay-time. For example, a PD sensor located close to the source of the stator PD may result in a detected rise-time that is shorter than a specific time, whereas certain kinds of disturbances (types a) to k) in 5.2) may be characterized by a longer rise-time. Digital circuits can separate stator PD from such disturbance sources by measuring the rise-time. Generally, the further the PD or disturbance source is from the PD sensor, the longer will be the rise-time of the detected pulse, since series inductance and/or the travelling wave phenomena called dispersion (frequency dependent velocity) tends to suppress the higher frequency components of a pulse.

Disturbance suppression using the time of pulse arrival method requires at least two PD sensors per phase to be installed on bus or cable connecting the motor or generator to the power system. This method depends on the time it takes an individual disturbance or PD pulse to travel along the power cable or bus.



Figure 1 – Time domain disturbance separation by time of pulse arrival

As shown in Figure 1, pulses from the power system will arrive at “System” sensor (S) before it will arrive at the ‘Machine” PD sensor (M). The difference in the arrival time at each sensor depends on the distance between the two sensors, and the propagation velocity of the pulse along the bus or cable. Digital logic notes the relative time of arrival and categorizes the pulse as being from the power system, and thus assumed to be a disturbance. Similarly a pulse from the stator winding is assumed to be PD if the machine sensor detects the pulse before being detected by the system sensor. Note this separation method is only effective if the pulse arriving first at the machine sensor is stator PD, and not disturbances such as from slip

Documents
Document Sharing Hub
Full document details: PD IEC/TS 60034-27-2:2012