PD ISO/TR 8547:2024

BSI Standards Publication

# Corrosion of metals and alloys — Exposure test results in the Asian Monsoon region

Documents
Document Sharing Hub

Full document details: PD ISO/TR 8547:2024

# National foreword

This Published Document is the UK implementation of ISO/TR 8547:2024.

The UK participation in its preparation was entrusted to Technical Committee ISENFE/8.

A list of organizations represented on this committee can be obtained on request to its committee manager.

**Contractual and legal considerations**

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

This publication is not to be regarded as a British Standard.

© The British Standards Institution 2024
Published by BSI Standards Limited 2024

ISBN 978 0 539 26031 1

ICS 77.060

**Compliance with a Published Document cannot confer immunity from legal obligations.**

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 April 2024.

**Amendments/corrigenda issued since publication**

| Date | Text affected |
|---|---|

Documents
Document Sharing Hub

Full document details: PD ISO/TR 8547:2024

Technical Report

# ISO/TR 8547

First edition
2024-04

# Corrosion of metals and alloys — Exposure test results in the Asian Monsoon region

*Corrosion des métaux et alliages — Résultats des essais d'exposition dans la région de la mousson asiatique*

Reference number
ISO/TR 8547:2024(en)

© ISO 2024

Documents
Document Sharing Hub

Full document details: PD ISO/TR 8547:2024

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland



Documents
Document Sharing Hub
Full document details: PD ISO/TR 8547:2024

# Contents

Page

**Foreword** ..... **iv**
**Introduction** ..... **v**
**1 Scope** ..... **1**
**2 Normative references** ..... **1**
**3 Terms and definitions** ..... **1**
**4 Exposure tests** ..... **1**
**5 Climatic and environmental conditions[1][2]** ..... **3**
**6 Corrosion behaviours of carbon steel[1][2]** ..... **6**
6.1 Corrosion rate (CR[CS]) ..... 6
6.2 Effect of environmental factors on corrosion rate ..... 6
**7 Corrosion behaviours of zinc[3]** ..... **12**
7.1 Comparison with the previous or published study ..... 12
7.2 Corrosion rate (CR[Zn]) ..... 14
7.3 Effect of environmental factors on corrosion rate ..... 14
**8 Corrosion mapping[2][3]** ..... **21**
**9 Summary** ..... **22**
**Annex A** (informative) **Data sources** ..... **23**
**Bibliography** ..... **24**

© ISO 2024 – All rights reserved


Documents
Document Sharing Hub
Full document details: PD ISO/TR 8547:2024

# Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2024 – All rights reserved


Documents
Document Sharing Hub
Full document details: PD ISO/TR 8547:2024

# Introduction

At the time of publication, the mainstream method of classifying environmental corrosion is that specified in ISO 9223. This is a method in which the corrosion rates of various metals are classified in six levels based on the results of direct exposure tests conducted around the world. However, the exposure sites were located only in Japan for the exposure tests in Asian Monsoon region, in which East-Asia, South-Asia and East-South Asia are included and the climates are affected by monsoons. Thus, standardization of an evaluation/classification method suited to the Asian Monsoon region has been strongly desired. Therefore, exposure tests were conducted in three counties including Japan, Vietnam and Thailand, under the “e-Asia Project”.

This document summarizes the exposure test results for carbon steel and galvanized steel sheet.

© ISO 2024 – All rights reserved



Documents
Document Sharing Hub
Full document details: PD ISO/TR 8547:2024

Documents
Document Sharing Hub

# Corrosion of metals and alloys — Exposure test results in the Asian Monsoon region

## 1 Scope

This document provides the data of exposure test results for carbon steel and galvanized steel sheets in three countries, Japan, Vietnam and Thailand, under the "e-Asia Project" as valuable information on the corrosivity of atmospheres in the world.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9223:2012, *Corrosion of metals and alloys — Corrosivity of atmospheres — Classification, determination and estimation*

ISO 9225:2012, *Corrosion of metals and alloys — Corrosivity of atmospheres — Measurement of environmental parameters affecting corrosivity of atmospheres*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 9223 and ISO 9225 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at https://www.electropedia.org/

## 4 Exposure tests

The coupons of carbon steel and galvanized steel sheet were exposed in outdoor environments at 16 exposure test sites in Japan, 13 sites in Vietnam and 7 sites in Thailand as shown in Figure 1. Specimens of 3 mm thickness and 70 mm × 150 mm of carbon steel and specimens of 1 mm thickness and 70 mm × 150 mm of galvanized steel sheet were used for exposure tests. The specimens of carbon steel were exposed both sides. For the specimens of galvanized steel sheet, the backside and cut edge of the coupons were covered by polyethylene sheet after degreasing the specimen in acetone. The exposed surfaces of specimens were exposed to skyward and groundward as shown in Figure 2. The corrosion products on the exposed specimens were removed by using chemical solutions according to ISO 8407, and the weight losses were measured to determine the corrosion rate.

For the environmental factors, monthly amounts of airborne salinity and $SO_2$ were measured by "Dry gauze" and "$PbO_2$ cylinder", respectively, based on JIS Z 2382. The temperature, relative humidity, and ACM sensor output, I, were recorded in a microcomputer every 10 min.

For the annual average values of $Cl^-$ deposition, S, and $SO_2$ deposition, P, those values based on JIS Z 2382, S(JIS) and P(JIS), respectively, were converted to S and P based on ISO 9225:2012, Annex F:

$$S = 2{,}4\ S(JIS)$$

© ISO 2024 – All rights reserved



Documents
Document Sharing Hub
Full document details: PD ISO/TR 8547:2024

P = 0,67P(JIS)

NOTE Some of numerical data are available from data sources given in Annex A.




**Key**

| | | | | | | | |
|---|---|---|---|---|---|---|---|
| J1 | Asahikawa | J14 | Nishihara | V1 | Sơn La | T1 | Chiang Rai |
| J2 | Akkeshi | J15 | Uruma | V2 | Yên Bai | T2 | Khon Kaen |
| J3 | Sapporo | J16 | Miyakojima | V3 | Cua Ong | T3 | Pathum Thani |
| J4 | Niigata | | | V4 | Hà Nội | T4 | Bangkok |
| J5 | Fukui | | | V5 | Con Vanh | T5 | Chon Buri |
| J6 | Sendai | | | V6 | Đong Hoi | T6 | Rayong |
| J7 | Tsukuba | | | V7 | Dung Quat | T7 | Phangnga |
| J8 | Choshi | | | V8 | Pleiku | | |
| J9 | Yamanakako | | | V9 | Phan Rang | | |
| J10 | Shimizu | | | V10 | Bien Hoa | | |
| J11 | Fukuyama | | | V11 | Can Tho | | |
| J12 | Fukuoka | | | V12 | Rach Gia | | |
| J13 | Kagoshima | | | V13 | Ca Mau | | |

**Figure 1 — Exposure test sites in Japan, Vietnam and Thailand**

© ISO 2024 – All rights reserved

Documents
Document Sharing Hub
Full document details: PD ISO/TR 8547:2024




**Key**

1 skyward

2 groundward

**Figure 2 — Example of exposure test for galvanized steel at Miyakojima**

## 5 Climatic and environmental conditions[1][2]

The average temperature, T, at each site is shown in Figure 3. T value increases in the order Japan<Vietnam<Thailand. In Japan, the lowest T values, in the range of approximately 5 °C to 10 °C, can be seen at the test sites in Northern area or in the mountain (Asahikawa, Akkeshi, Sapporo and Yamanakako), the remain test sites have T of about 13 °C to 24 °C. In Vietnam, the average air temperatures are rather high, and almost all Vietnam test sites have T in range of 22 °C to 27 °C. Different from Japan and Vietnam, the air temperature of Thailand is very high with the annual average values of about 28 °C to 30 °C, except one site in the North (Chiang Rai) where T is lower (25 °C).

The average relative humidity, RH, at each site is shown in Figure 4. RH of all test sites are rather high, almost all of them have RH ≥ 70 %, except several sites with RH < 70 % (as Kagoshima and Miyakojima – Japan, Khon Kaen – Thailand), among them, there are many test sites with RH ≥ 80 %, especially in some areas, RH values reach approximately 85 % to 90 %.

The total of rainfalls in Asian area are very great as shown in Figure 5. Almost all test sites show the amount of rainfall in the range of approximately 1 000 mm/y to 2 500 mm/y, in particular, there are test sites with very high total of rainfall, approximately 2 500 mm/y to 3 000 mm/y.

Figure 6 shows the annual $Cl^-$ deposition rate, S, at each site during the exposure period. The inland sites have low S values (< 1 mmd), and the coastal sites have higher S values (> 1 mmd). Depending on the location of the test sites as well as the topography and wind regime, S values at coastal sites have different values in the range of about 1 mmd to 60 mmd. The high S values are observed at Miyakojima and Uruma (which belong to Okinawa islands, Japan) and Phangnga (which is located near Phuket, Thailand).

Figure 7 shows the annual $SO_2$ deposition rate, P, at each site during the exposure period. P values at almost all test sites are not significant (< 3 mmd) except only three sites in Thailand, Bangkok, Rayong and Pathum Thani.

© ISO 2024 – All rights reserved

Documents
Document Sharing Hub
Full document details: PD ISO/TR 8547:2024