

PPI TR-2

May 1, 2024

PPI PVC Range Composition Listing of Qualified Ingredients



105 Decker Court • Suite 825 • Irving, Texas 75062 • 469.499.1044 • www.plasticpipe.org

FOREWARD.....	4
SUMMARY OF CHANGES	5
I. Definitions Specific to PPI TR-2.....	7
II. INTRODUCTION	9
III. PPI PVC Range Composition.....	12
Part A. Pre-qualified Ingredients Exempted from Stress-Rupture Testing.....	13
Part A.1 PVC Resin	15
Part A.2 Calcium Stearate	16
Part A.3 Paraffinic Hydrocarbon Wax	17
Part A.4 Polyethylene Wax.....	18
Part A.5 Titanium Dioxide.....	19
Part A.6 Calcium Carbonate.....	20
Part B. PVC Resin, Functionally Equivalent and Other Ingredients Not Exempted from Stress-Rupture Testing - Data Requirements for Listing at 73°F (23°C).....	22
Part B.1 PVC Resin	23
Part B.2 Heat Stabilizer, Process Aid, Colorant and other Components Not Complying to Part A.....	24
Part C. Standard Industry Practice of High Intensity Mixing of PVC Pipe Compounds	24
Part D – Requirements for Obtaining a Dependent Listing Under the PPI PVC Range Composition.....	25
Part D.1 – Initial Data Requirements	25
IV. Listing of Pre-qualified and Functionally Equivalent Ingredients	26
TABLE 1 – PVC RESIN	27
TABLE 2.1 – HEAT STABILIZER (organotin).....	28
TABLE 2.2 – HEAT STABILIZER (calcium zinc).....	30
TABLE 3A – CALCIUM STEARATE	31
TABLE 3B – CALCIUM STEARATE FUNCTIONAL EQUIVALENT	31
TABLE 4A – PARAFFIN WAX	32
TABLE 4B – PARAFFIN WAX FUNCTIONAL EQUIVALENT	32
TABLE 5A – POLYETHYLENE WAX	33
TABLE 5B – POLYETHYLENE WAX FUNCTIONAL EQUIVALENT	33
TABLE 6A – TITANIUM DIOXIDE	33
TABLE 6B – TITANIUM DIOXIDE FUNCTIONAL EQUIVALENT – LIQUID DISPERSED	34
TABLE 6C – TITANIUM DIOXIDE FUNCTIONAL EQUIVALENT – DRY POWDERS	36
TABLE 7A – CALCIUM CARBONATE	36

TABLE 7B – CALCIUM CARBONATE FUNCTIONAL EQUIVALENT	37
TABLE 8 – PROCESSING AID	38
TABLE 9A – COLORANT – DRY POWDER	39
TABLE 9B – COLORANT – LIQUID DISPERSED	40
V. Listing of Pre-qualified and Functionally Equivalent Ingredient Packages	41
TABLE 10 – COMBINATION INGREDIENT PACKAGES	42
TABLE 11 – FUNCTIONALLY EQUIVALENT INGREDIENT PACKAGES	45

APPENDIXES

Appendix A – Example Listing Request(s) for the PPI PVC Generic Range Formulation	48
Appendix B – PMD Test Procedures & References for the Evaluation of Calcium Carbonate	49
Appendix C – Example to Convert PVC Compound Formulations from PHR to Weight Percent.....	51
Appendix D – List of Manufacturer Contacts.....	52

FOREWORD

This technical report was developed and published with the technical help of the members of the (Plastics Pipe Institute, Inc.) Hydrostatic Stress Board (PPI HSB). The members have shown their interest in quality products by assisting independent standards-making and user organizations in the development of standards, and also by developing reports on an industry-wide basis to help engineers, code officials, specifying groups, and users.

PPI's PVC range composition and all applicable policies are included in this technical report. This technical report lists of each of the ingredients that have been accepted by the Hydrostatic Stress Board (HSB) by its commercial designation as qualified for use in PPI's PVC Range Composition. Requirements for acceptance are covered by applicable PPI policy or, in cases for which there is no applicable policy, the HSB may determine these requirements through a "Special Case" consideration. The listings included in this report also show allowable use levels for each ingredient and any other applicable limitation.

This report was prepared by the PPI HSB as a service to the industry. The information in this report is offered in good faith and believed to be accurate at the time of its preparation but is offered "as is" without any express or implied warranty, including WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Each product manufacturer that lists compositions with the PPI HSB does so voluntarily and with the express agreement that PPI assumes no liability in regard to the lists, and that it will hold PPI harmless from any claims or liability in connection with its listed pipe compositions.

Additional information may be needed in some areas, especially with regard to unusual or special applications. Consult the manufacturer or material supplier for more detailed information. PPI does not endorse the proprietary products or processes of any manufacturer, and assumes no responsibility for compliance with applicable laws and regulations.

Questions, comments, and problems of interpretation should be referred to the PPI HSB Chair, Plastics Pipe Institute, 105 Decker Court, Suite 825, Irving, TX 75062. Copies of this report, as well as other publications, are available from the PPI website: www.plasticpipe.org.

This report was updated May 1, 2024.

© Copyright, The Plastics Pipe Institute, Inc. 2024

SUMMARY OF CHANGES

2024	
Heat Stabilizers (organotin) and Heat Stabilizers (calcium zinc)	A calcium zinc stabilizer qualified for listing in PPI TR-2. Revisions were made to the policies and listing tables to differentiate organotin and calcium zinc heat stabilizers. – Definitions: This section defines organotin and calcium zinc heat stabilizers. – Introduction: Updated to include mention of calcium zinc heat stabilizers listings and their differentiation from organotin heat stabilizers. – Section III Table 1: Heat Stabilizers include requirements for organotin and calcium zinc heat stabilizers. – Heat Stabilizer Listing Tables: Updated to differentiate between organotin heat stabilizers (Table 2.1) and approved non-organotin heat stabilizers (Table 2.2). – Table 10 and Table 11 Examples: Clarifies that only organotin heat stabilizer can be included in the packages.
Document	Editorial revisions: – Revised mentions of “TR-2” and “TR-3” to “PPI TR-2” and “PPI TR-3”. – Clarified language in Part B Introduction.
2023	
Table of Contents	Editorial revision: Separate packages from the ingredients. Packages appear in a new Section V.
Part A.3 Paraffinic Hydrocarbon Wax	Editorial revision: Revised the flash point in Celsius as 449°F converts to 232°C.
TABLE 6B – Titanium Dioxide Functional Equivalent -- Liquid Dispersed: NOTE 1, NOTE 2, NOTE 3 and NOTE 4	Editorial revision: Formatted the listings, appearing in NOTE 1, NOTE 2 and NOTE 4 into a table. Also, removed NOTE 3 as the ingredient is no longer listed.
TABLE 9A – Colorant – Dry Powder	Editorial revision: The historical PPI TR-2 documents allowed variation of the colorant (increase or decrease) in accordance with PPI TR-3 Part D.1. However, Part D.1 was revised during the years to allow colorant substitutions for materials with specific policies in PPI TR-3. As such, the PPI TR-2 Table 9A note is now revised to the policies allowing variation of the colorant (increase or decrease), which is PPI TR-3 Part D.1.1.1.1.
Table 10 – Combination Ingredient Package	Removed NOTE 1 as the ingredient is no longer listed.

2021	
Part B.1, Part B.2	HSBTG25-0219: Revisions to reflect new definition, commercially produced pipe.
Table 1	PVCTG14-0818: New NOTE 2 explaining that some allowable use levels were determined via an HSB Special Case and to reference the colorant tables for the levels.
2020	
Foreword	Editorial revision from "...technical help and financial support of the members of the PPI (Plastics Pipe Institute)." to "...technical help of the members of the (Plastics Pipe Institute, Inc.) Hydrostatic Stress Board (PPI HSB)."
Document	Editorial revision of "Chairman of the HSB" to "PPI HSB Chair".
Table of Contents	Editorial revision of Appendix A and Appendix D noting that the dependent listing request template and manufacturer contact information are now available online.
Section I Definitions	Editorial revision to reference the correct policy sections for Prequalified and Functional Equivalent Ingredients, Part A and Part B respectively.
Part A Table 1	Editorial revision from "Compliance to B.2 and Listing by PPI." to "Compliance to Part B.2 and Listing with the PPI HSB."
Part A.2 Ash	Editorial revision adding unit of measure (%).
Part A.4 Acid Number	Editorial revision adding reference to comment "(1)".
TABLE 1 – PVC Resin	Editorial revision to reference the correct policy section for PVC Resin, Part B.1.
TABLE 6B – Titanium Dioxide Functional Equivalent – Liquid Dispersed	Editorial revision to the notes to reflect the name changes in the products.
2018	
Part D (new)	Part D – Requirements for Obtaining a Dependent Listing Under the PPI PVC Range Composition
2017	
All policy language in the document	All policy language moved into PPI TR3 which converted PPI TR2 into a listing document such as PPI TR4.
TR-2/2014 to TR-2/2016	
Part B.2	Includes requirements when testing liquid dispersed colorants.

I. Definitions Specific to PPI TR-2

Vinyl Plastics — Compositions of polymers and ingredients that are based on polymers of vinyl chloride, or copolymers of vinyl chloride with other monomers, the vinyl chloride being in the greatest amount by mass. Within the context of TR-2 the term vinyl is limited to compositions of polyvinyl chloride (PVC).

Ingredient — Any chemical, mineral, polymer or other ingredient that has been added to a vinyl composition for the purpose of imparting certain desired processing or product performance properties.

Pre-qualified Ingredient— Any chemical, mineral, polymer, etc. having properties meeting the applicable requirements as set forth in Section III Part A.

Functionally Equivalent Ingredient— Any chemical, mineral, polymer, etc. not having properties meeting the applicable requirements as set forth in Section III Part B and shown to function in an equivalent manner through testing.

Combination Ingredient Package- A set ratio of a pre-blended combination of prequalified ingredients. As a service to formulators of PVC pipe compounders, some suppliers of ingredients make available “packages” of pre-blended combinations of Prequalified Ingredients provided: 1) each of its individual ingredients is qualified for such use; and 2) the net amount of each individual ingredient that is introduced into the composition, both through the “package” and by direct addition, is in compliance with the composition requirements for that ingredient. It is the responsibility of the formulator to make sure that the PPI PVC range composition is always prepared in accordance with the currently listed composition.

Functional Equivalent Ingredient Package- A set ratio of a pre-blended combination of ingredients containing an ingredient/ingredients that is not pre-qualified. This package will be accepted for listing upon completion of testing demonstrating that its use in PPI’s PVC Range Composition continues to yield a PVC compound that complies with the minimum property requirements for cell class 12454, in accordance with ASTM D1784, and that qualifies for a 4,000 psi HDB, for water, for 73.4°F, in accordance with ASTM D2837. There is no standard protocol, or policy for effecting this demonstration. Minimum data requirements are established by the HSB for each case, depending on the nature of the ingredients, and the information already available. Those seeking to qualify these kinds of combinations of ingredients should make a “Special Case” request of the PPI HSB Chair.

PPI PVC Range Composition - A PVC composition, classified as PVC 1120, Class 12454 in accordance with applicable ASTM requirements, that carries a PPI recommended hydrostatic design basis (HDB) of 4,000 psi (27.58 MPa) for water for 73.4°F (23°C), with such basis having been established in accordance with requirements stated in PPI Technical Reports TR-2 and TR-3. This composition is maintained by the HSB of PPI and is made available for use by the general public.

Privately held PVC Composition - A privately held PVC composition that carries a PPI recommended hydrostatic design basis (HDB) that has been established based on the requirements of PPI Technical Reports TR-2 and TR-3. This private composition is maintained by a specific company or organization and is not made available by PPI to the general public.

Standard Grade (S) - A PPI HSB recommended rating that is valid for a five-year period, given to those materials that comply with the full data requirements of TR-2 and TR-3.

Experimental Grade (E) - A PPI HSB recommended rating that is valid for a limited duration, given to those materials covered by data that do not yet comply with the full requirements of the Standard Grade, but satisfy the applicable minimum preliminary data requirements that are detailed in TR-2 and TR-3. The owner of an experimental listing must understand there is a potential risk in commercial sale of an experimental ingredient in case it does not meet all the TR-2 requirements.

Organotin stabilizer (n) – a thermal stabilizer consisting of a tin ingredient and diluent.

NOTE: Organotin stabilizers might include co-stabilizers.

CaZn stabilizer (n) – a thermal stabilizer consisting of a calcium zinc ingredient and diluent

II. INTRODUCTION

It was recognized early in the evolution of the thermoplastics pipe industry that in consequence of its viscoelastic nature, the fracture strength of a thermoplastic polymer is significantly influenced — for any given set of conditions of temperature and environment — by duration of loading. The longer a load is sustained; the lower is the fracture strength. It was also recognized that the long-term strength of a thermoplastics composition is not only determined by the primary ingredient, the base polymer, but can also be profoundly influenced by the nature and quantity of ingredients — such as property modifiers, processing aids, stabilizers, and colorants — that are used to enhance performance and facilitate processing, and to give product identification. But in those early days there existed no standard method by which reliable design stresses could be established for thermoplastic compositions intended for pressure pipe. All too often, design stresses were based on results of relatively short-term loading with **safety factors** that — based on experience, educated guess, limited experience, or other rationale — were said to adequately compensate for the reduction in long-term strength that characteristically occurs with all plastics when subjected to prolonged loading. Unfortunately, this approach was not only inconsistent from material to material, but oftentimes it was unreliable. The long-term strength of some materials was overestimated, while that of others was underestimated.

To remedy this situation, the Thermoplastics Pipe Division (subsequently named the Plastics Pipe Institute) of the Society of the Plastics Industry established in November 1958 the Working Stress Subcommittee, the predecessor to the Hydrostatic Stress Board (HSB), consisting of technical persons well versed in the state-of-the-art of the evaluation and forecast of the long-term strength of plastics. Two and half years later, in April 1961, this group agreed on a uniform Tentative Method for Estimating Long-Term Hydrostatic Strength and Hydrostatic Design Stress of Thermoplastic Pipe; and in July 1963, it issued its first hydrostatic design stress recommendations for compositions for which data had been submitted in accordance with this method.

A frequent challenge to the HSB was the evolutionary nature of the industry, particularly in the case of PVC pipe compositions. At first, each PVC composition was a fixed and very specific composition, with the use level and identity of each ingredient spelled out. The ingredient identification would often consist of a manufacturer's trade designation. In search of more effective and less costly sources of ingredients, companies holding listings for PVC compositions would often qualify alternative sources of a certain ingredient. To demonstrate qualification a company had to submit to the HSB extensive long-term data that showed the proposed change would not compromise a listed composition's long-term strength. From the knowledge learned by this work, policies were developed whereby a newly proposed ingredient, for example, a calcium carbonate — can qualify for that purpose provided it is demonstrated that its physical and chemical properties comply to requirements that have been established for that class of ingredient based on results of industry wide testing. These policies provided for prequalification of ingredients that greatly facilitated the process of determining equivalence.

Later on, during the seventies, the concept of "PVC range compositions" was introduced. As new and improved extrusion technology began to be used, it was discovered that fine-tuning the quantity of certain ingredients — particularly, so called "internal" and "external" lubricants — would greatly benefit production rate and product quality. To avoid the impracticality of having to qualify each composition variation, industry expanded their fixed content recipes into range compositions, whereby the allowable content of certain ingredients was defined not by a fixed amount but rather, by a minimum/maximum range. The acceptable ranges of ingredient content had also to be established by long-term data documentation.

To make it possible to use resins and other ingredients from different suppliers, extruders of PVC pipe had to qualify a number of “different” range PVC compositions — each provided by a different resin supplier — which in fact were often times quite the same except for source of resin, or some other key ingredient. For a manufacturer of a new ingredient, or of an alternative to an existing ingredient, having to qualify his product for inclusion in the many private PVC range compositions that then abounded was a costly and time-consuming process. In recognition of this situation, the HSB proposed in 1983 to establish a single, generic and public PVC range composition which then included all PVC resins and ingredients which had been qualified in privately held compositions of the same kind. These PVC pressure pipe compounds were formulated using organotin heat stabilizers. To accomplish this required the cooperation of all major holders of PVC compositions, including their willingness to share with the HSB their confidential recipes. This cooperation was obtained, the compositions of the many stress-rated compositions were compared, and a single, generic, state-of-the-art composition was established which allowed a wide choice in PVC resins and in ingredients.

The HSB next worked on defining the policies and procedures for qualifying new ingredients. In 1985 the PPI PVC range composition and related policies were agreed upon and are published in this report. Since that time many new alternate ingredients have been qualified for use in this composition.

One such alternative ingredient was calcium-zinc heat stabilizers which originated in Europe in 2000, driven by the Vinyl 2010-Vinyl Plus initiatives to replace lead and cadmium-based heat stabilizers with COS (organic-based and/or Calcium-Zinc) systems^{1,2}. Use of COS heat stabilizer systems expanded from Europe to South America to many countries in Asia and in multiple PVC applications to include thermoplastic pressure pipe. Use in North America began in non-pressure formulations³. In 2021, a range composition formulation using a CaZn heat stabilizer in lieu of an organotin heat stabilizer, confirmed a long-term strength performance of 4000-psi HDB at 73°F. The first PPI TR-2 listing for a calcium zinc heat stabilizer was approved in 2022.

¹ The European PVC Industry’s Experience in Replacing Lead and Cadmium-based Stabilizers. 2014. VinylPlus. Brussels, Belgium

² Hopfmann. Stoffelsma. Ryningen. Clucas. Pfaender. Organic Based Stabilizer Systems for PVC Pipes – A New Stabilizer Generation for PVC Pipes. 1998. PPX Sweden.

³ E. Flick. Plastic Additives. 1986. Noyes Data Corporation. New Jersey. USA. Pages 581.

The policies and procedures in this Technical Report (TR) are intended to cover ingredient listings for most PVC piping applications. PPI recognizes there may be unusual cases, issues or circumstances that are not covered in PPI TR-2, and that may justify an exception to the standard policies. To allow manufacturers an opportunity to have their ingredient(s) listed by PPI when this occurs, the HSB has provided a “Special Case” system. The manufacturer may present its “Case” to the HSB at one of their two annual meetings, usually in February and August, using the approved “Special Case” form in PPI TR-3. All information provided to HSB in these special cases will be made available for review only by HSB members and PPI staff, and will be held by them in strict confidence, in accordance with PPI’s written confidentiality procedures (available from the PPI HSB Chair). There is a PPI fee for each special case. You must contact the PPI HSB Chair well in advance of each meeting to arrange for your special case. A completed HSB submission form **must** be received at least two (2) weeks prior to the HSB meeting to permit HSB consideration at that meeting.

III. PPI PVC Range Composition

The PPI PVC Range Composition in PPI TR-2 Section III Table 1 is divided into categories which are detailed in Section I Definitions Specific to PPI TR-2.

Qualified ingredients are listed in accordance with the above categories.

Because the PPI PVC Range Composition has been established from a matrix of PPI listed range compositions – each of which has a 4,000-psi hydrostatic design basis at 73.4°F that has been established through extensive stress-rupture testing – a company may obtain a dependent listing under this composition by meeting the requirements set forth in Part D of PPI TR-2.

Part A. Pre-qualified Ingredients Exempted from Stress-Rupture Testing

An individual or combination ingredient that meets the allowable content range in Table 1 and the physical property requirements of Part A is a pre-qualified ingredient and is exempt from stress rupture testing for qualification. An ingredient manufacturer may still elect to publish this prequalified ingredient in the appropriate table in TR-2.

A PVC composition that complies with the minimum property requirements of cell class 12454 according to ASTM D 1784 and that satisfies the limitations of the PVC range formulation given in Table I, qualifies for a recommended hydrostatic design basis (HDB) of 4,000 psi at 73°F (23°C) without the need to submit the stress-rupture data. A manufacturer wishing to register this PVC range composition for use in his plant should apply to the PPI HSB Chair and identify the manufacturer's commercial designation for this composition. These PVC compositions are dependent on the PPI PVC range composition and are published in PPI TR-4.

Table 1
PPI PVC Range Composition for Listing at 73°F (23°C)

Ingredient	Qualification Requirements	Allowable Content Range (in parts per hundred parts of resin)	Applicable Table 1 Notes
PVC Resin	Compliance to B.1 and Listing with the PPI HSB	100	
Heat Stabilizer - Only one type of heat stabilizer is allowed in the formulation. - Mixing of heat stabilizers is not allowed.			
organotin	Compliance to B.2 and Listing in PPI TR-2 Table 2.1	0.3 – 1.0	NOTE 1 NOTE 2
calcium-zinc	HSB Special Case	See listings in PPI TR-2 Table 2.2 of qualified calcium zinc heat stabilizers	NOTE 1 NOTE 2 NOTE 3
Calcium Stearate	Compliance to A.2	0.4 – 1.5	NOTE 1
Paraffin Wax	Compliance to A.3	0.6 – 1.5	
Polyethylene Wax	Compliance to A.4	0.0 – 0.3	
Titanium Dioxide	Compliance to A.5	0.5 – 3.0	
Calcium Carbonate	Compliance to A.6	0.0 – 5.0	
Process Aid	Compliance to B.2 and Listing with the PPI HSB	0.0 – 2.0	
Colorant	Compliance to B.2 and Listing with the PPI HSB, or compliance to PPI TR-3 Part D.1 Listing with PPI HSB	See listings in PPI TR-2 of qualified colorants	

NOTE 1: See PPI TR-2 Section IV for listing of Prequalified and Functionally Equivalent Ingredients.

NOTE 2: Ingredient tables should be referenced for specific approved ranges. PHR levels outside of the general ranges shown are the result of HSB Special Case approvals. For more information on the HSB Special Case process, contact the PPI HSB Chair.

NOTE 3: The PPI PVC Range Composition was developed using organotin heat stabilizers. In 2021, calcium zinc heat stabilizers performance was approved for use in the PPI PVC Range Composition. Europe, South America, Asia and other countries have used calcium zinc heat stabilizers in PVC applications that include pressure pipe (refer to Section I Introduction for more details).

Calcium zinc heat stabilizers can contribute to the total lubricity of the compound. As such, consideration of the total lubricity contribution is needed when using a calcium-zinc stabilizer. The allowable use levels are not purported to address additional factors necessary for end-use such as durability, resistance to cracking, impact resistance, weatherability, cell classification, etc. Consult the manufacturer regarding the allowable use level that achieves the required long-term strength of 4,000-psi HDB at 73°F and performance required by the end-use application (see PPI TR-3 Notes to Reader).

The pipe manufacturer is encouraged to perform stress-rupture testing on any new combination of ingredients to ensure that the anticipated strength is realized under the selected processing conditions. One of the best means to check for proper processing is by use of either the Accelerated Regression Test (ASTM D 2241) or other long-term stress-rupture data generated in accordance with ASTM D 1598 and analyzed by the method of least squares as described in ASTM D 2837.

Part A.1 PVC Resin

This policy only applies to mass and suspension grades of PVC resins.

There are no pre-qualified PVC resins for the PPI PVC Generic Range Formulation. All PVC resins must be qualified according to Part B.

PVC Resin made in a new plant — For equivalent PVC resin that is currently listed in PPI TR-2 that is made in a new plant, a provisional listing will be granted based on manufacturer's data supporting equality of the resin through chemical and physical property analysis. E-2 level hydrostatic data is required for a standard grade listing.

Part A.2 Calcium Stearate

The following guidelines are not to be considered as specifications or standards to indicate the requirements for calcium stearates, nor is it intended that they describe all the commercial calcium stearates that are suitable for use in polyvinyl chloride (PVC) plastic pipe compounds. The intent is only to give guidelines for alternative use of members of a group of commercial calcium stearates that are apparently chemically identical and that have been found by physio- chemical analysis, by engineering pipe testing, and by use of pipe in the field to be sufficiently similar in nature to produce pipe and fittings that are basically the same in properties and performance. Consideration has been given to physio-chemical analysis of the calcium stearates, long-term hydrostatic pressure testing of pipe, and requirements of the applicable pipe standards.

Commercial calcium stearates may be substituted one for another in polyvinyl chloride (PVC) plastic pipe and fitting compounds without additional long-term pipe testing provided (1) the substitution is for the same amount, (2) the substitution in the compound is 1.5 parts or less per hundred parts of resin and (3) the properties fall within the ranges given below:

Property (see Note1)	Units	Test Methods	Requirements
Melting Point	°F (°C)	see NOTE 1	293 -329 (145 – 165)
Chlorides, as chloride ion	% max		0.3
Free fatty acid,	% max		1
Acid number			200 +/- 15 (see NOTE 2)
Iodine value	max		5 (see NOTE 2)
Volatile content, at 221°F (105°C)	% max		3.5
Ash (as CaO) at 1832°F (1000°C)	%		9.0 – 12.0
Iron	ppm max		100
Color			White to off-white
Particle Size			At least 95% through U.S. Standard 20 mesh

NOTE 1: The test methods shall be those commonly used in the calcium stearate industry.

NOTE 2: Acid number and iodine value apply to the stearic acid raw material.

Calcium stearates not meeting these guidelines may be evaluated as a functional equivalent in accordance with the policies and procedures in Part B of PPI TR-2. When sufficient data, background, and successful usage, both in production and service, have been developed with other calcium stearates, they may be considered for inclusion in a new group under these guidelines.