



AEROSPACE MATERIAL SPECIFICATION

AMS2515™**REV. H**

Issued	1961-01
Reaffirmed	2003-05
Revised	2013-01
Stabilized	2018-11

Superseding AMS2515G

Polytetrafluoroethylene (PTFE) Resin Coating, Low Build,
370 to 400 °C (698 to 752 °F) Fusion

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

AMS2515H has been declared "STABILIZED" by SAE AMS Committee P Polymeric Materials and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2018 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

Full document details: [SAE AMS2515H](#)

SAE values your input. To provide feedback on this Technical Report, please visit <http://standards.sae.org/AMS2515H>

Documents
Document Sharing Hub

1. SCOPE

1.1 Purpose

This specification establishes the engineering requirements for producing thin coatings of polytetrafluoroethylene (PTFE) resin on parts and the properties of such coatings.

1.2 Application

Primarily to provide dry lubrication, high heat stability, and corrosion protection on parts which operate at not higher than 275 °C (527 °F) for limited periods or not higher than 245 °C (473 °F) for extended periods. This coating may also be used as a release film for molds.

1.2.1 This coating should not be specified for use on parts made of, or coated with, metals, such as cadmium, lead, tin, and zinc, having melting points below or only slightly above the fusing temperature of 3.4.

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS5045 Steel, Sheet and Strip, 0.25 Carbon, Maximum, Hard Temper

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 108 Steel Bars, Carbon, Cold-Finished, Standard Quality

ASTM B 117 Salt Spray (Fog) Testing

2.3 U.S. Government Publications

Available from the Document Automation and Production Service (DAPS), Building 4/D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, Tel: 215-697-6257, <http://assist.daps.dla.mil/quicksearch/>.

MIL-STD-202 Test Methods for Electronic and Electrical Component Parts

3. TECHNICAL REQUIREMENTS

3.1 Material

The coating materials (primer and finish coating) shall be dispersions of polytetrafluoroethylene (PTFE) resin solids in a water medium. The primer may be either pigmented or unpigmented. The finish resin coating material shall be unpigmented unless colored material is specified by purchaser.

3.2 Preparation

3.2.1 Cleaning

Surfaces, other than anodized aluminum or magnesium, to be coated shall be degreased, chemically cleaned or lightly abrasive blasted, cleaned to remove abrasive particles, and air dried. Anodized aluminum or magnesium surfaces need only be degreased and dried.

3.2.2 Preheating

Immediately prior to coating, metals other than aluminum, magnesium, and copper, shall be preheated to $400\text{ }^{\circ}\text{C} \pm 5$ ($752\text{ }^{\circ}\text{F} \pm 9$) to produce a light oxide film and remove any organic contamination and air cooled. Preheating of aluminum, magnesium, and copper is not required. (See 8.2).

3.3 Coating

3.3.1 Primer

A primer resin coat of 0.0002 to 0.0007 inch (5 to 18 μm) dry film thickness shall be applied to the prepared surfaces and fused as in 3.4.