AEROSPACE MATERIAL SPECIFICATION

AMS3894™/3	REV. C

Issued 1972-11
Revised 1989-01
Reaffirmed 2005-06
Stabilized 2016-09

Superseding AMS3894/3B

Carbon Fiber Tape and Sheet
Epoxy Resin Impregnated
G 150000 (1034) Tensile, 19000000 (131) Modulus, 80 (176)

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by the SAE AMS P17 Composite Materials Committee and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2016 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: **Tel: 877-606-7323 (inside USA and Canada)**
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: http://www.sae.org

SAE values your input. To provide feedback on this Technical Report, please visit http://www.sae.org/technical/standards/AMS3894/3C

Documents Document Sharing Hub

Full document details: SAE AMS3894_3C

1. SCOPE:

1.1 Form: This specification covers one type of epoxy-resin-impregnated carbon fibers in the form of tape and sheet.

1.2 Application: Primarily for use in structural composites requiring high strength up to 80°C (176°F).

1.3 Classification: G 150,000 psi (1034 MPa) tensile strength, 19,000,000 psi (131 GPa) tensile modulus carbon fiber impregnated with epoxy resin for service up to 80°C (176°F).

2. APPLICABLE DOCUMENTS: See AMS 3894.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3894.

3.2 Material: The product shall be AMS 3892/3 high tensile strength carbon fibers impregnated with epoxy resin formulated to meet the requirements specified herein.

3.2.1 Storage Life: The product shall meet the requirements of this specification when tested at any time up to six months from date of receipt by purchaser provided it has been stored in the original unopened containers at not higher than -18°C (0°F).

Documents
Document Sharing Hub
Full document details: SAE AMS3894_3C