

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 4061

Issued 9- 1-65

Revised 7- 1-81

ALUMINUM ALLOY SHEET AND PLATE, ALCLAD
4.5Cu - 1.5Mg - 0.60 Mn (Alclad 2024-T36)
Width Over 60 Inches

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of 3-25-74. It is recommended that this specification not be specified for new designs.

This cover sheet should be attached to the original issue of the subject specification.

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of 7- 1-81. By this action, subject specification number and title will be deleted from the active specification index of Aerospace Material Specifications.

AEROSPACE MATERIAL SPECIFICATIONS

AMS 4061

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N.Y. 10017

Issued 9-1-65
Revised

ALUMINUM ALLOY SHEET AND PLATE, ALCLAD 4.5Cu - 1.5Mg - 0.60Mn (Alclad 2024-T36) Width Over 60 Inches

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **FORM:** Sheet and plate, produced in widths over 60 inches.
3. **APPLICATION:** Primarily for structural parts of good strength which are required to exhibit maximum corrosion resistance. This material, when re-solution heat treated by the user, may not have the tensile properties shown. Certain design and processing procedures may cause this material to be susceptible to stress corrosion cracking; ARP 823 recommends practices to minimize such conditions.

4. **COMPOSITION:**

	Core (2024)			Cladding (1230)	
	min	max		min	max
Copper	3.8	4.9	Iron + Silicon	--	0.7
Magnesium	1.2	1.8	Copper	--	0.10
Manganese	0.30	0.9	Zinc	--	0.10
Iron	--	0.50	Manganese	--	0.05
Silicon	--	0.50	Other Impurities, each	--	0.05
Zinc	--	0.25	Aluminum, by difference	99.30	--
Chromium	--	0.10			
Other Impurities, each	--	0.05			
Other Impurities, total	--	0.15			
Aluminum	remainder				

5. **CONDITION:** Solution heat treated and cold reduced approximately 6% in thickness.
6. **TECHNICAL REQUIREMENTS:** The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.
 - 6.1 **Cladding Thickness:** After rolling, the average cladding thickness shall be as shown. Routine measurements are not required.

Total Thickness of Composite Product Inch	Cladding Thickness Per Side % of Total Thickness	
	min	max
0.063 to 0.187, incl	2.0	--
Over 0.187 to 0.500, excl	1.2	--
0.500	1.2	3.0