



AEROSPACE MATERIAL SPECIFICATION

AMS4222™**REV. H**

Issued	1942-12
Revised	1984-04
Noncurrent	1991-01
Reaf. Nonc.	1991-01
Stabilized	2017-04

Superseding AMS4222G

Aluminum Alloy Castings, Sand, Moderate Heat Resistance
4.0Cu - 2.0Ni - 1.5Mg - 0.12Ti (242.0P)
Solution Heat Treated and Stabilized

(UNS A02420)

RATIONALE

AMS4222H has been declared "STABILIZED" by AMS Committee D because it contains mature technology that is not expected to change and thus no further revisions are anticipated.

STABILIZED NOTICE

AMS4222H has been declared "STABILIZED" by the SAE AMS D Nonferrous Alloys Committee. This document was stabilized because this document contains mature technology that is not expected to change and thus no further revisions are anticipated. Previously this document was non-current. The last technical update of this document occurred in April, 1984. Users of this document should refer to the cognizant engineering organization for disposition of any issues with reports/certifications to this specification; including exceptions listed on the certification.

NOTE: In many cases, the purchaser may represent a sub tier supplier and not the cognizant engineering organization.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2017 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:
Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

Full document details: SAE AMS4222H

SAE values your input. To provide feedback on this Technical Report, please visit <http://standards.sae.org/AMS4222H>

Documents
Document Sharing Hub

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of sand castings.

1.2 Application: Primarily for cylinder heads for air-cooled piston engines.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods
AMS 2360 - Room Temperature Tensile Properties of Castings
AMS 2635 - Radiographic Inspection
AMS 2645 - Fluorescent Penetrant Inspection
AMS 2646 - Contrast Dye Penetrant Inspection
AMS 2694 - Repair Welding of Aerospace Castings
AMS 2804 - Identification, Castings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B557 - Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
ASTM E10 - Brinell Hardness of Metallic Materials
ASTM E34 - Chemical Analysis of Aluminum and Aluminum Alloys
ASTM E155 - Reference Radiographs for Inspection of Aluminum and Magnesium Castings

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals: Test Methods

2.3.2 Military Standards:

MIL-STD.649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined
Ø by wet chemical methods in accordance with ASTM E34, by spectrographic methods in accordance with Federal Test Method Standard NO. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Copper	3.5	4.5
Nickel	1.7	2.3
Magnesium	1.2	1.8
Titanium	0.07	0.18
Iron	--	0.8
Silicon	--	0.6
Manganese	--	0.10
Zinc	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

- 3.2 Condition: Solution heat treated and stabilized.

- 3.3 Casting: Castings shall be produced in lots from metal conforming to 3.1. Metal remelted from previously analyzed ingot may be poured directly into castings. Furnace or ladle additions of grain-refining elements or alloys are permissible. Unless otherwise agreed upon by purchaser and vendor, molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted or unless the composition of a sample taken after the last addition to the melt conforms to 3.1.

- 3.3.1 A melt shall be the metal withdrawn from a batch-furnace charge of 2000 lb (900 kg) or less as melted for pouring castings or, when permitted by purchaser, a melt shall be 4000 lb (1800 kg) or less of metal withdrawn from one continuous furnace in not more than eight consecutive hours.

- 3.3.2 A lot shall be all castings poured from a single melt in not more than
Ø eight consecutive hours and solution heat treated and stabilized in the same heat treatment batch.

- 3.4 Cast Test Specimens: Chemical analysis specimens and tensile specimens shall be cast as follows:

- 3.4.1 Chemical Analysis Specimens: Shall be cast from each melt and shall be of a size and shape agreed upon by purchaser and vendor.