

AEROSPACE MATERIAL SPECIFICATION

Issued	NOV 1941
Revised	JUL 1982
Noncurrent	APR 1989
Reaf. Noncur.	APR 1994
Cancelled	FEB 2005
Superseding AMS 4240F	

Castings, Sand
10Mg
Solution Heat Treated and Naturally Aged

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of February, 2005. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications indicating that it has been cancelled.

Cancelled specifications are available from SAE.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2005 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:

Tel: 877-606-7323 (inside USA and Canada)

Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: custsvc@sae.org

<http://www.sae.org>

SAE WEB ADDRESS:

1. SCOPE:
 - 1.1 Form: This specification covers an aluminum alloy in the form of sand castings.
 - 1.2 Application: Primarily for components requiring a combination of maximum strength, elongation, and resistance to shock and where optimum resistance to stress-corrosion cracking is not required. Special foundry practices are necessary.
2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.
 - 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.
 - 2.1.1 Aerospace Material Specifications:
 - AMS 2350 - Standards and Test Methods
 - AMS 2360 - Room Temperature Tensile Properties of Castings
 - AMS 2635 - Radiographic Inspection
 - AMS 2645 - Fluorescent Penetrant Inspection
 - AMS 2646 - Contrast Dye Penetrant Inspection
 - AMS 2694 - Repair Welding of Aerospace Castings
 - AMS 2804 - Identification, Castings
 - 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.
 - ASTM B557 - Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
 - ASTM E34 - Chemical Analysis of Aluminum and Aluminum Alloys
 - ASTM E155 - Reference Radiographs for Inspection of Aluminum and Magnesium Castings, Series III
 - 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.
 - 2.3.1 Federal Standards:
 - Federal Test Method Standard No. 151 - Metals; Test Methods
 - 2.3.2 Military Specifications:
 - MIL-H-6088 - Heat Treatment of Aluminum Alloys
 - 2.3.3 Military Standards:
 - MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E34, by spectrographic methods in accordance with Federal Test Method Standard No. 151, or by other analytical methods approved by purchaser:

	min	max
Magnesium	9.5	10.6
Iron	--	0.30
Titanium	--	0.25
Copper	--	0.25
Silicon	--	0.25
Manganese	--	0.15
Zinc	--	0.15
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

- 3.2 Condition: Solution heat treated and naturally aged.

Ø

- 3.3 Castings: Castings shall be produced in lots from metal conforming to 3.1. Metal remelted from previously analyzed ingot may be poured directly into castings. Furnace or ladle additions of grain-refining elements or alloys are permissible. Unless otherwise agreed upon by purchaser and vendor, molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted or unless the composition of a sample taken after the last addition to the melt has been found to conform to 3.1.

- 3.3.1 A melt shall be the metal withdrawn from a batch-furnace charge of 2000 lb (900 kg) or less as melted for pouring castings, or, when permitted by purchaser, a melt shall be 4000 lb (1800 kg) or less of metal withdrawn from one continuous furnace in not more than 8 consecutive hours.

- 3.3.2 A lot shall be all castings poured from a single melt in not more than 8 consecutive hours.

- 3.4 Cast Test Specimens: Chemical analysis specimens and tensile test specimens shall be cast as follows and, when requested, shall be supplied with the castings:

- 3.4.1 Chemical Analysis Specimens: Shall be cast from each melt and shall be of a size and shape agreed upon by purchaser and vendor.