



AEROSPACE MATERIAL SPECIFICATION

AMS4533™**REV. F**Issued 1991-07
Revised 2026-01

Superseding AMS4533E

Copper-Beryllium Alloy, Bars and Rods,
98Cu - 1.9Be,
Solution and Precipitation Heat Treated (TF00, formerly AT)
(Composition similar to UNS C17200)

RATIONALE

AMS4533F results from a Five-Year Review and update of this specification with changes to clarify that metric values are primary for grain size measurements (see 3.4.3 and 8.3), relocate Definitions (see 2.3), update Form (see 1.1), Applicable Documents (see Section 2), Composition (see 3.1), Condition (see 3.2), Microstructure (see 3.4.4), and Ordering Information (see 8.5), and allow use of the immediate prior revision of this specification (see 8.4).

1. SCOPE

1.1 Form

This specification covers a copper-beryllium alloy in the form of bars and rods (see 8.5).

1.2 Application

These products have been used typically for parts requiring a combination of high strength, wear resistance, and corrosion resistance and where thermal conductivity, electrical conductivity, and low magnetic susceptibility may be important, but usage is not limited to such applications.

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards that may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2026 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 1-877-606-7323 (U.S. and Canada only)
Tel: 1-724-776-4970 (outside U.S. and Canada)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

Full document details: SAE AMS4533F

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4533F/>

Documents

Standard, visit Sharing Hub

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (U.S. and Canada only) or +1 724-776-4970 (outside U.S. and Canada), www.sae.org.

AMS2221 Tolerances, Copper and Copper Alloy Bars and Rods

AMS2750 Pyrometry

AS7766 Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B194 Copper-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar

ASTM B249/B249M General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, and Shapes

ASTM B601 Temper Designations for Copper and Copper Alloys—Wrought and Cast

ASTM E3 Preparation of Metallographic Specimens

ASTM E8/E8M Tension Testing of Metallic Materials

ASTM E18 Rockwell Hardness of Metallic Materials

ASTM E112 Determining Average Grain Size

ASTM E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness

2.3 Definitions

Terms used in AMS are defined in AS7766.

2.3.1 Hardness conversion tables for metals are presented in ASTM E140.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM B194 or by other analytical methods acceptable to the purchaser (see 8.5).

Table 1 - Composition

Element (see 3.1.1)	Min	Max
Beryllium	1.80	2.00
Cobalt + Nickel	0.20	--
Cobalt + Nickel + Iron	--	0.6
Aluminum	--	0.20
Silicon	--	0.20
Copper (see 3.1.2)	remainder	
Sum of Named Elements (see 3.1.3)	99.5	--

