



AEROSPACE MATERIAL SPECIFICATION

AMS4775™**REV. L**

Issued 1952-11
Reaffirmed 2000-08
Revised 2023-10

Superseding AMS4775K

Nickel Alloy, Brazing Filler Metal
73Ni - 0.75C - 4.5Si - 14Cr - 3.1B - 4.5Fe
1790 °F (977 °C) Solidus to 1970 °F (1077 °C) Liquidus
(Composition similar to UNS N99600)

RATIONALE

AMS4775L is the result of a Five-Year Review and update of the specification. The revision updates the prohibition on unauthorized exceptions to the specification (see 8.6).

1. SCOPE

1.1 Form

This specification covers a nickel alloy in the form of wire, rod, strip, foil, and powder and a viscous mixture (paste) of the powder in a suitable binder.

1.2 Application

This filler metal has been used typically for joining corrosion- and heat-resistant steels and alloys requiring corrosion- and oxidation-resistant joints with good strength at elevated temperatures, but usage is not limited to such applications. It also may be used as a corrosion- and oxidation-resistant hard coating.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AS7766 Terms Used in Aerospace Metals Specifications

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

Full document details: SAE AMS4775L

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4775L/>

Documents
Document Sharing Hub

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E18 Rockwell Hardness of Metallic Materials

ASTM E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness

2.3 AWS Publications

Available from American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33166-6672, Tel: 1-800-443-9353 or 305-443-9353, www.aws.org.

AWS A5.01M/A5.01 Welding and Brazing Consumables - Procurement of Filler Metals and Fluxes

AWS A5.8/A5.8M Specification for Filler Metals for Brazing and Braze Welding

2.4 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Product shall meet the requirements of AWS A5.8/A5.8M BNi-1 and the following:

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Wire and Strip

Powder bonded in a suitable binder.

3.2.2 Rod

As cast, with fins and projections removed.

3.2.3 Foil and Powder

As fabricated.

3.2.4 Paste

Shall consist of 84 to 90% by weight powder in a suitable binder and, unless otherwise ordered, shall not contain flux.

3.3 Properties

Filler metal shall conform to the following requirements:

3.3.1 Wire and Strip

3.3.1.1 Burn-Off of Binder

Organic binder used for bonding powder to form wire and strip shall be fully burnt off, leaving no adherent residue, when the product is heated to a temperature of 1000 °F (538 °C) in an inert or reducing atmosphere, or vacuum (10^{-3} torr or better).