



AEROSPACE MATERIAL SPECIFICATION

AMS4952™**REV. H**Issued 1988-07
Revised 2026-04

Superseding AMS4952G

Titanium Alloy, Welding Wire,
6Al - 2Sn - 4Zr - 2Mo
(Composition similar to UNS R54620)

RATIONALE

AMS4952H results from a Five-Year Review and update of this specification with changes to update wording related to exceptions (see 4.4.2), relocate Definitions (see 2.3), and update Applicable Documents (see Section 2), Fabrication (see 3.4), Sampling and Testing (see 4.3), Resampling and Retesting (see 4.5), and Ordering Information (see 8.5).

1. SCOPE

1.1 Form

This specification covers a titanium alloy in the form of welding wire (see 8.5).

1.2 Application

This wire has been used typically as filler metal for gas-metal-arc and gas-tungsten-arc welding, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (U.S. and Canada only) or +1 724-776-4970 (outside U.S. and Canada), www.sae.org.

AMS2249	Chemical Check Analysis Limits, Titanium and Titanium Alloys
AMS2813	Packaging and Marking of Packages of Welding Wire, Standard Method
AMS2814	Packaging and Marking of Packages of Welding Wire, Premium Quality
AMS2816	Identification, Welding Wire, Tab Marking Method

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2026 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 1-877-606-7323 (U.S. and Canada only)
Tel: 1-724-776-4970 (outside U.S. and Canada)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

Full document details: SAE AMS4952H

For more information on this standard, visit <https://www.sae.org/standards/content/AMS4952H/>

Documents

Standard, visit Sharing Hub

AMS2819	Identification, Welding Wire, Direct Color Code System
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP4926	Alloy Verification and Chemical Composition Inspection of Welding Wire
AS7766	Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E539	Analysis of Titanium Alloys by Wavelength Dispersive X-Ray Fluorescence Spectrometry
ASTM E1409	Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion
ASTM E1447	Determination of Hydrogen in Reactive Metals and Reactive Metal Alloys by Inert Gas Fusion with Detection by Thermal Conductivity or Infrared Spectrometry
ASTM E1941	Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis
ASTM E2371	Analysis of Titanium and Titanium Alloys by Direct Current Plasma and Inductively Coupled Plasma Atomic Emission Spectrometry (Performance-Based Test Methodology)
ASTM E2994	Analysis of Titanium and Titanium Alloys by Spark Atomic Emission Spectrometry and Glow Discharge Atomic Emission Spectrometry (Performance-Based Method)

2.3 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1; carbon shall be determined in accordance with ASTM E1941, hydrogen in accordance with ASTM E1447, oxygen and nitrogen in accordance with ASTM E1409, and other elements in accordance with ASTM E539, ASTM E2371, or ASTM E2994. Other analytical methods may be used if acceptable to the purchaser.

Table 1 - Composition

Element	Min	Max
Aluminum	5.50	6.50
Zirconium	3.60	4.40
Molybdenum	1.80	2.20
Tin	1.80	2.20
Oxygen (see 3.1.1.1)	--	0.15
Silicon	--	0.10
Iron	--	0.10
Copper	--	0.10
Carbon (see 3.1.1.1)	--	0.04
Nitrogen (see 3.1.1.1)	--	0.0400 (400 ppm)
Hydrogen (see 3.1.1.1)	--	0.0125 (125 ppm)
Yttrium (see 3.1.1.2)	--	0.0050 (50 ppm)
Boron	--	0.0030 (30 ppm)
Other Elements, each (see 3.1.1.2)	--	0.10
Other Elements, total (see 3.1.1.2)	--	0.40
Titanium	remainder	

3.1.1 Except for carbon, oxygen, nitrogen, and hydrogen, chemical analysis of initial bar or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure conformance to composition requirements.

3.1.1.1 Carbon, oxygen, nitrogen, and hydrogen shall be determined on each lot of finished wire.

3.1.1.2 Determination not required for routine acceptance.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2249.

3.2 Melting Practice

Alloy shall be multiple melted. The first melt shall be made by vacuum consumable electrode, nonconsumable electrode, electron beam cold hearth, or plasma arc cold hearth melting practice. The subsequent melt or melts shall be made using vacuum arc remelting (VAR) practice. Alloy additions are not permitted in the final melt cycle.

3.2.1 The atmosphere for nonconsumable electrode melting shall be vacuum or shall be argon and/or helium at an absolute pressure not higher than 1000 mm of mercury.

3.2.2 The electrode tip for nonconsumable electrode melting shall be water-cooled copper.

3.3 Condition

Cold drawn, bright finish, in a temper and with a surface finish that will provide proper feeding of the wire in machine-welding equipment.

3.4 Fabrication

3.4.1 Finished wire shall be formed from rod, bar, or wire descaled by a process that does not affect the composition of the wire. Surface irregularities without alpha case consistent with normal forming processes are acceptable provided the wire conforms to the tolerances of 3.7.

3.4.2 In-process annealing, if required between rolling or drawing operations, shall be performed after cleaning the material and in a vacuum or in a protective atmosphere to avoid surface oxidation and adsorption of other extraneous elements unless the contaminated surface is removed mechanically or chemically.