

AEROSPACE MATERIAL SPECIFICATION



AMS 5329F

Issued JUL 1963
Revised OCT 1987
Noncurrent JAN 1995
Cancelled JUL 2001

Superseding AMS 5329E

Steel Castings, Sand
0.80Cr - 1.8Ni - 0.35Mo (0.28 - 0.36C) (SAE 4330 Modified)
Annealed

UNS J23260

CANCELLATION NOTICE

This specification has been "CANCELLED" by the Aerospace Materials Division, SAE, as of July 2001. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications.

Cancelled specifications are available from SAE.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2001 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790



Documents
Document Sharing Hub

1. SCOPE:

1.1 Form:

This specification covers a low-alloy steel in the form of sand castings.

1.2 Application:

Primarily for light-to-medium-section castings requiring heat treatment to tensile strengths of 180,000 psi (1240 MPa) and higher.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350	Standards and Test Methods
AMS 2360	Room Temperature Tensile Properties of Castings
AMS 2369	Quality Assurance Sampling of Carbon and Low-Alloy Steel Castings
AMS 2635	Radiographic Inspection
AMS 2640	Magnetic Particle Inspection
AMS 2645	Fluorescent Penetrant Inspection
AMS 2694	Repair Welding of Aerospace Castings
AMS 2804	Identification, Castings

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370	Mechanical Testing of Steel Products
ASTM E350	Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
ASTM E446	Reference Radiographs for Steel Castings up to 2 in. (51 mm) in Thickness

2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

MIL-H-6875 Heat Treatment of Steel, Process for

2.3.2 Military Standards:

MIL-STD-794 Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350 or by spectrochemical or other analytical methods approved by purchaser:

	min	max
Carbon	0.28	0.36
Manganese	0.60	1.00
Silicon	0.50	0.90
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.65	1.00
Nickel	1.65	2.00
Molybdenum	0.30	0.45
Copper	--	0.35

3.2 Condition:

Annealed.

3.3 Castings:

A melt shall be the metal poured from a single furnace charge. A lot shall be all castings poured from a single melt, heat treated in the same furnace load, and presented for vendor's inspection at one time.