



AEROSPACE MATERIAL SPECIFICATION

AMS5629™/H1025

Issued 2023-03

Steel, Corrosion-Resistant, Bars, Wire, Forgings, Rings, and Extrusions
13Cr - 8.0Ni - 2.2Mo - 1.1Al
Vacuum Induction Plus Consumable Electrode Melted
Solution Heat Treated, Precipitation Hardened (H1025)
(Composition similar to UNS S13800)

RATIONALE

AMS5629/H1025 is a new specification for the purchase of corrosion resistant steel product in the solution and precipitation heat treated (H1025) condition.

1. SCOPE

1.1 Form

This specification covers a corrosion-resistant steel product 12 inches (305 mm) and under in nominal diameter, thickness, or for hexagons, least distance between parallel sides in the solution and precipitation heat treated (H1025) condition.

1.1.1 The aged product may be supplied directly by a producer or by another entity performing the functions of a producer as defined in AS6279. The latter can be accomplished by precipitation heat treatment of solution treated material previously certified to AMS5629. The entity assuming responsibility for the aging operation is designated the producer of AMS5629/H1025.

1.2 Application

These products have been used typically for parts requiring corrosion resistance and high strength up to 600 °F (316 °C) with good ductility and strength in the transverse direction in large sections sizes, but usage is not limited to such applications (see 8.1).

1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking after heat treatment. ARP1110 recommends practices to minimize such conditions, to the Application section as a subparagraph.

1.3 Classification

Classification shall be in accordance with AMS5629.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

Full document details: SAE AMS5629_H1025

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5629/H1025/>

Documents

Document Sharing Hub

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2241	Tolerances, Corrosion- and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS2759/3	Heat Treatment, Precipitation-Hardening Corrosion-Resistant and Maraging Steel Parts
AMS2761	Heat Treatment of Steel Raw Materials
AMS5629	Steel, Corrosion-Resistant, Bars, Wire, Tubing, and Rings, 16Cr - 4.0Ni - 0.30Cb (Nb) – 4.0Cu, Solution Heat Treated, Precipitation Hardenable
ARP1110	Minimizing Stress Corrosion Cracking in Wrought Forms of Steels and Corrosion Resistant Steels and Alloys
AS6279	Industry Standard Practices for Production, Distribution, and Procurement of Metal Stock
AS7766	Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A370	Mechanical Testing of Steel Products
-----------	--------------------------------------

2.3 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall be in accordance with AMS5629.

3.2 Melting Practice and Delta Ferrite Class

Shall be in accordance with AMS5629.

3.3 Condition

Shall be in accordance with AMS5629 and the following:

3.3.1 The product shall be supplied in the precipitation hardened (H1025) heat treat condition.

3.3.2 Bar shall not be cut from plate (see 4.3.3).