



AEROSPACE MATERIAL SPECIFICATION

AMS5766™**REV. G**

Issued 1972-05
Reaffirmed 2007-08
Revised 2026-04

Superseding AMS5766F

Alloy, Corrosion- and Heat-Resistant, Bars, Forgings, and Forging Stock,
21Cr - 32.5Ni - 0.38Ti - 0.38Al - 45Fe, (Alloy 800),
Solution Heat Treated
(Composition similar to UNS N08800)

RATIONALE

AMS5766G is the result of a Five-Year Review and update of the specification. The revision updates the Title to match the Scope and add the trade name (see 8.6), revises composition testing and reporting (see 3.1 and 3.1.1), adds strain rate control to tensile tests (see 3.3.1.1.1), removes reference to tubing as out of Scope (see 3.4.2), updates bar reporting requirements (see 4.4.2), provides for additional forging stock properties (see 4.4.3 and 8.7), and updates the exceptions requirements (see 4.4.4).

1. SCOPE

1.1 Form

This specification covers a corrosion- and heat-resistant iron-nickel-chromium alloy in the form of bars and forgings 4.0 inches (102 mm) and under and forging stock of any size.

1.2 Application

These products have been used typically for low-stressed parts requiring corrosion and oxidation resistance, particularly where such parts may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (U.S. and Canada only) or +1 724-776-4970 (outside U.S. and Canada), www.sae.org.

AMS2261 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire

AMS2269 Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2026 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 1-877-606-7323 (U.S. and Canada only)
Tel: 1-724-776-4970 (outside U.S. and Canada)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

Full document details: SAE AMS5766G

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5766G/>

Documents

Standard, visit Sharing Hub

AMS2283	Composition Testing Methods for Nickel- and Cobalt-Based Alloys
AMS2371	Quality Assurance Sampling and Testing, Corrosion- and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS2374	Quality Assurance Sampling and Testing, Corrosion- and Heat-Resistant Steel and Alloy Forgings
AMS2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification, Forgings
AS1182	Standard Stock Removal Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel, Bars and Mechanical Tubing
AS7766	Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E8/E8M Tension Testing of Metallic Materials

2.3 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Composition shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2283 or by other analytical methods acceptable to the purchaser.

Table 1 - Composition

Element	Min	Max
Carbon	--	0.10
Manganese	--	1.50
Silicon	--	1.00
Phosphorus	--	0.035
Sulfur	--	0.015
Chromium	19.00	23.00
Nickel	30.00	35.00
Titanium	0.15	0.60
Aluminum	0.15	0.60
Copper	--	0.75
Iron	remainder	

3.1.1 The producer may test for any element not listed in Table 1 and include this analysis in the report of 4.4. Reporting of any element not listed in the composition table is not a basis for rejection unless limits of acceptability are specified by the purchaser.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2269.