



AEROSPACE MATERIAL SPECIFICATION

AMS5928™

Issued	2010-10
Reaffirmed	2026-06

Steel, Corrosion-Resistant, Bars, Wire, and Forgings
12Cr - 9Ni - 2Mo - 0.7Al - 0.3Ti
Vacuum Induction Plus Vacuum Consumable Electrode Melted
Solution Heat Treated, Precipitation Hardenable

RATIONALE

AMS5928 has been reaffirmed to comply with the SAE Five-Year Review policy.

A reaffirmed status is given to technical reports that have been reviewed by the technical committee and deemed to be current with no need for immediate revision. No changes have been made to this document as a result of this review.

1. SCOPE

1.1 Form

This specification covers a corrosion-resistant steel in the form of bars, wire, forgings, and forging stock.

1.2 Application

These products have been used typically for heat-treated parts requiring a combination of high strength and high toughness up to 800 °F (427 °C) with good ductility and strength in the transverse direction, but usage is not limited to such applications.

1.2.1 Certain design, processing procedures, or environmental conditions may cause these products to become susceptible to stress-corrosion cracking; ARP1110 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2241	Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS2248	Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS2300	Steel Cleanliness, Premium Aircraft-Quality, Magnetic Particle Inspection Procedure
AMS2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2026 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 1-877-606-7323 (U.S. and Canada only)
Tel: 1-724-776-4970 (outside U.S. and Canada)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

Full document details: SAE AMS5928

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5928/>

Documents

Standard Sharing Hub

AMS2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS2750	Pyrometry
AMS2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification, Forgings
AS1182	Standard Stock Removal Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 370	Mechanical Testing of Steel Products
ASTM A 604	Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E 399	Plane-Strain Fracture Toughness of Metallic Materials

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	--	0.02
Manganese	--	0.25
Silicon	--	0.25
Phosphorus	--	0.015
Sulfur	--	0.010
Chromium	11.00	12.50
Nickel	8.00	10.00
Molybdenum	1.75	2.25
Titanium	0.2	0.5
Aluminum	0.60	0.80
Nitrogen	--	0.01

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248.

3.2 Melting Practice

Product shall be multiple melted using vacuum induction melting followed by vacuum consumable electrode remelt practice.

3.3 Condition

The product shall be supplied in the following condition:

3.3.1 Bars, Wire, and Forgings

3.3.1.1 Rounds

Hot finished, solution heat treated and turned, centerless ground, or polished.

3.3.1.2 Hexagons

Hot finished, solution heat treated and descaled.

3.3.1.3 Squares and Flats

Hot finished, solution heat treated, and machined or descaled.

3.3.1.4 Wire

Cold finished, solution treated and descaled.

3.3.1.5 Forgings

Solution heat treated and descaled.

3.3.2 Forging Stock

As ordered by the forging manufacturer.

3.4 Heat Treatment

Bars, wire, and forgings shall be solution heat treated by heating to $1545^{\circ}\text{F} \pm 25$ ($840^{\circ}\text{C} \pm 14$), holding at heat for a time commensurate with section thickness, heating equipment and procedure used, but not less than 30 minutes, and cooling as required to below 90°F (32°C). Pyrometry shall be in accordance with AMS2750.

3.5 Properties

The product shall conform to the following requirements; tensile and hardness testing shall be performed in accordance with ASTM A 370.

3.5.1 Bars, Billets and Forging Stock

3.5.1.1 Macrostructure

Visual examination of transverse full cross-sections from bars, billets, and forging stock, etched in hot hydrochloric acid in accordance with ASTM A 604, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections for product 36 squares inches (232 cm^2) and under in nominal cross-sectional area shall be no worse than the macrographs of ASTM A 604 shown in Table 2.

TABLE 2 - MACROSTRUCTURE LIMITS

Class	Condition	Severity
1	Freckles	A
2	White Spots	A
3	Radial Segregation	A
4	Ring Pattern	B