



AEROSPACE MATERIAL SPECIFICATION

AMS6452™**REV. E**

Issued	1984-10
Revised	2012-04
Reaffirmed	2007-09
Stabilized	2017-12

Superseding AMS6452D

Steel, Welding Wire
0.95Cr - 0.20Mo (0.38 - 0.43C)
Vacuum Melted, Environment Controlled Packaging
(Composition similar to UNS G41400)

RATIONALE

AMS6452E has been declared "STABILIZED" by SAE AMS Committee E Carbon and Low Alloy Steels as mature technology that is not expected to change and thus no further revisions are anticipated.

STABILIZED NOTICE

AMS6452E has been declared "STABILIZED" by SAE AMS Committee E Carbon and Low Alloy Steels. This document will no longer be updated and may no longer represent standard industry practice. This document was stabilized because the document contains mature technology that is not expected to change and thus no further revisions are anticipated. Previously this document was revised. The last technical update of this document occurred in April 2012. Users of this document should refer to the cognizant engineering organization for disposition of any issues with reports/certifications to this specification; including exceptions listed on the certification.

NOTE: In many cases, the purchaser may represent a sub tier supplier and not the cognizant engineering organization.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2017 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

Full document details: SAE AMS6452E

SAE values your input. To provide feedback on this Technical Report, please visit <http://standards.sae.org/AMS6452E>

Documents
Document Sharing Hub

1. SCOPE

1.1 Form

This specification covers a low-alloy steel in the form of welding wire.

1.2 Application

This wire has been used typically for filler metal for gas-metal-arc or gas-tungsten-arc welding of critical weldments of low-alloy steels requiring a joint capable of being heat treated to a strength level approximating that of the basis metal, but usage is not limited to such applications.

1.3 Classification

Wire shall be classified as follows:

Type 1 - Bare Wire

Type 2 - Copper Coated

1.3.1 Type 1 shall be supplied unless Type 2 is specified.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org

AMS2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
AMS2813	Packaging and Marking of Packages of Welding Wire, Standard Method
AMS2814	Packaging and Marking of Packages of Welding Wire, Premium Quality
AMS2816	Identification, Welding Wire, Tab Marking Method
AMS2819	Identification, Welding Wire, Direct Color Code System
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP4926	Alloy Verification and Chemical Composition Inspection of Welding Wire

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org

ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

3. TECHNICAL REQUIREMENTS

3.1 Wire Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon (3.1.1.1)	0.38	0.43
Manganese	0.75	1.00
Silicon	0.15	0.35
Phosphorus	--	0.008
Sulfur	--	0.008
Chromium	0.80	1.10
Molybdenum	0.15	0.25
Nickel	--	0.25
Copper (3.1.1.2)	--	0.35
Oxygen (3.1.1.1)	--	0.0100 (100 ppm)
Nitrogen (3.1.1.1)	--	0.0050 (50 ppm)
Hydrogen (3.1.1.1)	--	0.0010 (10 ppm)