



AEROSPACE MATERIAL SPECIFICATION

AMS6466™**REV. G**

Issued	1959-01
Revised	1997-06
Reaffirmed	2006-04
Noncurrent	2008-12
Reaf. Nonc.	2015-12
Stabilized	2017-12

Superseding AMS6466F

Steel, Corrosion-Resistant, Welding Wire
5.2Cr – 0.55Mo
(Composition similar to UNS S50280)

RATIONALE

AMS6466G has been designated stabilized based on results of a survey to aerospace users and producers.

STABILIZED NOTICE

AMS6466G has been declared "STABILIZED" by SAE AMS Committee E Carbon and Low Alloy Steels. This document will no longer be updated and may no longer represent standard industry practice. This document was stabilized because this document contains mature technology that is not expected to change, and other documents contain similar, but not necessarily equivalent requirements, and thus no further revisions are anticipated. Previously this document was non-current. The last technical update of this document occurred in June 1997. Users of this document should refer to the cognizant engineering organization for disposition of any issues with reports/certifications to this specification; including exceptions listed on the certification.

NOTE: In many cases, the purchaser may represent a sub tier supplier and not the cognizant engineering organization.

AMS Committee E recommends that the following similar but not identical specifications may be considered for future procurement. This listing does not constitute authority to substitute these specifications for the "STABILIZED" specification.

AWS A5.28/A5.28M Specification for Low-Alloy Steel Electrodes and Rods for Gas Shielded Arc Welding ER80S-B6
UNS S50280

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2017 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

Full document details: SAE AMS6466G

SAE values your input. To provide feedback on this Technical Report, please visit <http://standards.sae.org/AMS6466G>

Documents
Document Sharing Hub

1. SCOPE:

1.1 Form:

This specification covers a corrosion-resistant steel in the form of welding wire.

1.2 Application:

This wire has been used typically as filler metal for gas-tungsten-arc and gas-metal-arc welding of low-alloy steels where response to heat treatment is required in the weld, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2813	Packaging and Marking of Packages of Welding Wire, Standard Method
AMS 2814	Packaging and Marking of Packages of Welding Wire, Premium Quality
AMS 2816	Identification, Welding Wire, Tab Marking Method
AMS 2819	Identification, Welding Wire, Direct Color Code System
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP4926	Alloy Verification and Chemical Composition Inspection of Welding Wire

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 ANSI Publications:

Available from ANSI, 11 West 42nd Street, New York, NY 10036-8002.

ANSI B46.1 Surface Texture

3. TECHNICAL REQUIREMENTS:

3.1 Wire Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.10
Manganese	--	0.60
Silicon	0.25	0.60
Phosphorus	--	0.03
Sulfur	--	0.03
Chromium	4.50	6.00
Molybdenum	0.45	0.65
Nickel	--	0.60
Copper	--	0.35

3.1.1 Chemical analysis of initial ingot, bar, or rod stock before drawing, other than those analyses required to be done on the finished wire, is acceptable, provided processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements.

3.1.2 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.