



AEROSPACE MATERIAL SPECIFICATION

AMS6520™**REV. E**

Issued	1969-05
Revised	1995-06
Noncurrent	2001-10
Reaf. Noncur.	2011-11
Stabilized	2016-11

Superseding AMS6520D

Steel, Maraging, Sheet, Strip, and Plate
18Ni - 7.8Co - 4.9Mo - 0.40Ti - 0.10Al
Consumable Electrode Melted, Solution Heat Treated
UNS K92890

RATIONALE

AMS6520E is stabilized as there are not any users of the document.

STABILIZED NOTICE

AMS6520E has been declared "STABILIZED" by AMS E Carbon and Low Alloy Steels Committee. This document will no longer be updated and may no longer represent standard industry practice. This document was stabilized because Committee E cannot find users for this document. Previously this document was reaffirmed noncurrent.. The last technical update of this document occurred in June, 1995. Users of this document should refer to the cognizant engineering organization for disposition of any issues with reports/certifications to this specification; including exceptions listed on the certification.

NOTE: In many cases, the purchaser may represent a sub tier supplier and not the cognizant engineering organization.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2016 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

Full document details: SAE AMS6520E

SAE values your input. To provide feedback on this Technical Report, please visit <http://standards.sae.org/AMS6520E>

Documents
Document Sharing Hub

1. SCOPE:

1.1 Form:

This specification covers a premium aircraft-quality, maraging steel in the form of sheet, strip, and plate.

1.2 Application:

These products have been used typically for large booster rocket applications, pressure vessels, and other components requiring through-hardening, without quenching, to a yield strength of 245 ksi (1689 MPa) or higher, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchaser order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2248	Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2252	Tolerances, Low-Alloy Steel Sheet, Strip, and Plate
MAM 2252	Tolerances, Metric, Low-Alloy Steel Sheet, Strip, and Plate
AMS 2300	Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
MAM 2300	Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steels, Wrought Products and Forging Stock
AMS 2750	Pyrometry
AMS 2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 370 Mechanical Testing of Steel Products
ASTM A 604 Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
ASTM E 45 Determining the Inclusion Content of Steel
ASTM E 112 Determining the Average Grain Size
ASTM E 338 Sharp-Notch Tension Testing of High-Strength Sheet Materials
ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E 399 Plane-Strain Fracture Toughness of Metallic Materials

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.03
Manganese	--	0.10
Silicon	--	0.10
Phosphorus	--	0.010
Sulfur	--	0.010
Nickel	17.00	19.00
Cobalt	7.00	8.50
Molybdenum	4.60	5.20
Titanium	0.30	0.50
Aluminum	0.05	0.15

- 3.1.1 Prior to pouring, nominal additions of 0.05% calcium, 0.02% zirconium, and 0.003% boron shall be made to the melt but analysis for these elements need not be made.