



AEROSPACE MATERIAL SPECIFICATION

AMS6891™/4

Issued

2021-03

Carbon Fiber and Fiberglass Epoxy/Prepreg Products with 350 °F (177 °C) Cure for Aerospace Applications: Type 42, Class 4, Grade 48, Style 108

RATIONALE

Widely distributed and available industry material specifications are required for procurement of composite materials whose allowables data is published in CMH-17.

NOTICE

This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user.

1. SCOPE

The intent of this specification is for the procurement of the material listed on the QPL and, therefore, no qualification or equivalency threshold values are provided. Users that intend to conduct a new material qualification or equivalency program must refer to the Quality Assurance section of this base specification, AMS6891.

1.1 Form

This detail specification along with the base specification, AMS6891, establish the requirements for fiberglass fabric impregnated with a modified B-staged epoxy resin ("fabric prepreg").

1.2 Classification

All products qualified to this detail specification have the following classifications:

Form 4, Type 42, Class 4, Grade 48, Style 108

For an explanation of these classifications, please refer to the base specification.

2. APPLICABLE DOCUMENTS

See base specification.

3. MATERIAL REQUIREMENTS

3.1 General Requirements

In case of conflict between requirements of the base specification and this detail specification, requirements of this detail specification must govern.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2021 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

Full document details: SAE AMS6891_4

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS6891/4/>

Documents
Document Sharing Hub

3.2 Prepreg Material Requirements

3.2.1 Uncured Prepreg Physical and Chemical Properties

The uncured prepreg physical and chemical properties must be in accordance with Table 1 when tested in accordance with the designated method. Specific procedures must be identical, or equivalent, to those used in the original material qualification program. The material must be capable of being cut without disarray of the fibers and without other visible damage.

Table 1 - Uncured prepreg physical and chemical properties

Property	Test Method	Frequency	Requirement	
Resin Content ⁽²⁾	ASTM D3529, 4.4.1 of the Base Specification	Every Master Roll ⁽¹⁾	42.0% ± 3.0%	
Fiber Areal Weight ⁽²⁾	ASTM D3529, 4.4.1 of the Base Specification	Every Master Roll ⁽¹⁾	47.5 g/m ² ± 5.0 g/m ²	
Volatile Content	ASTM D3530, 4.4.2 of the Base Specification	Once per batch	2.0% maximum	
Infrared Spectroscopy (IR)	ASTM E1252 and ASTM E168, 4.4.5 of the Base Specification	Two specimens from the start and end of every batch	ATR: 0.99 correlation minimum	
High Performance Liquid Chromatography (HPLC) ⁽²⁾	SACMA SRM 20R-94, 4.4.7 of the Base Specification	One specimen from the start and end of every batch	P2/P1	0.97 to 1.37
			P3/P1	1.97 to 2.33
			P4/P1 ⁽³⁾	0.10 Max
Differential Scanning Calorimetry (DSC) (Sub-Ambient T _g)	ASTM E1356, 4.4.8 of the Base Specification	Start and end of every batch ⁽¹⁾	Maximum 14 °C	

⁽¹⁾ Three specimens should be taken across the width of the prepreg: left, center, right.

⁽²⁾ Key characteristic required for SPC control.

⁽³⁾ P4/P1 requirement reflects supplier out-of-storage allowance. For user verification of work life, requirement is 0.35 and is representative of the work life requirement of the prepreg.

4. QUALITY ASSURANCE PROVISIONS

See base specification.

5. ACKNOWLEDGMENTS

A user must mention this specification number and AMS6891 in all quotations and when acknowledging purchase orders.

6. REJECTIONS

Product not conforming to this specification and AMS6891, or to modifications authorized by the user, will be subject to rejection.

7. NOTES

7.1 Revision Indicator

A change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this document. An (R) symbol to the left of the document title indicates a complete revision of the document, including technical revisions. Change bars and (R) are not used in original publications, nor in documents that contain editorial changes only.