

AEROSPACE MATERIAL SPECIFICATION



AMS 7711D

Issued	SEP 1957
Revised	APR 1984
Noncurrent	DEC 1991
Cancelled	SEP 2000
Superseding AMS 7711C	

Steel Sheet and Strip, Flat-Rolled, Electrical, Non-Oriented
2.65(Si + Al)
Type 47S188 or Type 64S213, Semi-Processed

CANCELLATION NOTICE

This specification has been "CANCELLED" by the Aerospace Materials Division, SAE, as of September 2000. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications noting that it has been cancelled.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790



Reproduced By GLOBAL
ENGINEERING DOCUMENTS
With The Permission Of SAE
Under License Agreement

Documents
Document Sharing Hub

Distributed under license from the IHS Archive

1. SCOPE:

1.1 Form:

This specification covers two types of semi-processed silicon steel in the form of sheet and strip supplied in coils or cut lengths.

1.2 Application:

Primarily for 50 to 60 Hz power frequency applications in magnetic devices such as motors and generators, and in small transformers and similar apparatus where medium core losses are desired; where the purchaser anneals the product to develop the desired core loss and permeability characteristics.

1.3 Classification:

The steels covered by this specification are classified as follows:

Type 47S188 - Product 0.0185 in. (0.47 mm) thick

Type 64S213 - Product 0.025 in. (0.64 mm) thick

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other specifications shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 Standards and Test Methods

AMS 2370 Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products
Except Forgings and Forging Stock

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A343 Alternating-Current Magnetic Properties of Materials at Power Frequencies Using the
Wattmeter-Ammeter-Voltmeter Method and 25-cm Epstein Test Frame

2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall be a low carbon steel containing approximately 2.65% silicon and other alloying elements, usually aluminum, in such proportions as required to provide a product meeting the requirements of 3.3.

3.2 Condition:

Semi-processed (See 8.3) and, unless otherwise specified, uncoated.

3.3 Magnetic Properties:

The product shall conform to the following requirements (density of 7.70 g/cm³ is assumed):

3.3.1 Core Loss: Shall be not greater than the following, determined in accordance with ASTM A343 on 50/50 Epstein specimens as in 4.3.1, annealed by heating in a non-carburizing atmosphere to not lower than 1450°F (790°C) and furnace cooling:

Type	Maximum		
	W/lb 60 Hz	W/kg 60 Hz	W/kg 50 Hz
47S188	1.88	4.14	3.27
64S213	2.13	4.70	3.71

3.3.2 Permeability: Typical permeability shall be as high as possible consistent with the required core loss limits (See 3.3.1) that govern the grade. Typical permeability (μ_p) shall be as follows, calculated from measurements of peak exciting current at an induction of 15 kilogausses (1.5 T) in accordance with ASTM A343 on annealed 50/50 grain Epstein specimens.

Type	Typical μ_p
47S188	1300
64S213	1450