



400 COMMONWEALTH DRIVE WARRENDALE PA 15096

AEROSPACE MATERIAL SPECIFICATION

AMS 7715

Issued 9-15-57
Revised 10-1-82

STEEL SHEET AND STRIP, FLAT-ROLLED ELECTRICAL 4.25Si AISI Type M-15, Semiprocessed

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of 10-16-74. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the initial issue of the subject specification.

.....

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of 10-1-82. By this action, subject specification number and title will be deleted from the active specification index of Aerospace Material Specifications.

This specification is under the jurisdiction of AMS Committee "E".

SAE Technical Board rules provide that. "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

STEEL, FLAT-ROLLED ELECTRICAL

4.25Si

AISI Type M-15, Semiprocessed

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **FORM:** Sheet and strip in coils or cut lengths.
3. **APPLICATION:** Primarily for use in power, distribution, and specialty transformers. Not recommended for large retentative machines where the relatively low ductility of this steel might be deleterious.
4. **COMPOSITION:** Iron base, nominal 4.25% silicon.
5. **CONDITION:** Semiprocessed material, in which the specified core loss is developed by the purchaser. Unless otherwise specified, either cold rolled or hot rolled material may be supplied.
6. **TECHNICAL REQUIREMENTS:**
 - 6.1 **Magnetic Properties:** Material shall conform to the following requirements after annealing at not lower than 1450 F by means which will avoid carburization or excessive oxidation; tests shall be performed in accordance with the methods listed in ASTM A34-55, insofar as practicable, using assumed density of 7.55 g per cubic centimeter.
 - 6.1.1 **Core Loss at 60 Cycles w per lb, max:**
 - 6.1.1.1 Epstein specimens cut from material treated in accordance with 6.1 (fully processed) shall not exceed the following maximum core losses at either 10 or 15 kilogausses as specified on the purchase order. If no value is specified on the purchase order, requirements for 15 kilogausses shall apply.

Nominal Thickness Inch	Core Loss at 10 Kilogausses	Core Loss at 15 Kilogausses
0.0140	0.58	1.46
0.0155	0.61	1.54
0.0170	0.65	1.63
0.0185	0.68	1.71

Sect. n 8.3 of the SAE Technical Board rules provides that: "All technical information used in the preparation of this specification is the property of the Society of Automotive Engineers, Inc. and is not to be used by anyone engaged in industry or trade is entirely voluntary. There is no obligation on the part of the Society of Automotive Engineers, Inc. to defend or maintain the validity of this specification or to defend or maintain the validity of any patent which may apply to the subject matter. Prospective users of this specification are advised that they are responsible for protecting themselves against liability for infringement of patents."