

**TUNGSTEN CARBIDE-COBALT POWDER
Sintered and Crushed**

1. SCOPE:

1.1 Form: This specification covers tungsten carbide-cobalt in the form of powder.

1.2 Application: Primarily for producing plasma spray coatings to provide wear and fretting resistant surfaces.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B214 - Sieve Analysis of Granular Metal Powders

ASTM B215 - Sampling Finished Lots of Metal Powders

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by methods agreed upon by purchaser and vendor:

	min	max
Free Carbon (3.1.1)	--	0.10
Total Carbon	5.15	--
Cobalt	11.00 - 13.00	
Iron	--	1.50
Other Impurities, each (3.1.1)	--	1.00
Tungsten	81.00	--

3.1.1 Determination not required for routine acceptance.

3.2 Condition: As manufactured.

3.3 Properties: Powder shall conform to the following requirements:

3.3.1 Particle Size Distribution: Powder shall be supplied with the following particle size distribution. Sieve analysis shall be conducted in accordance with ASTM B214.

Mesh Size	% By Weight, Min
-200 mesh (75 μ m)	99.5
-325 mesh (45 μ m)	95.0

- indicates passing through sieve

3.3.2 Metallographic Inspection: Tungsten carbide particles in the cobalt matrix shall not exceed 20 microns and shall be predominantly 2 to 5 microns.

3.3.3 Plasma Spraying: Powder shall produce acceptable spray coatings; standards for acceptance and method of test shall be as agreed upon by purchaser and vendor.

3.4 Quality: Powder, as received by purchaser, shall be thoroughly blended, uniform in color and quality, dry, and free from foreign materials and from imperfections detrimental to its spraying qualities.