FEDERAL SUPPLY CLASS
6145

RATIONALE

TABLE 1 OF THE STANDARD NEEDS TO BE UPDATED TO SUPPORT CURRENT QUALIFICATION ACTIVITIES TO REFLECT THE SLIGHT WEIGHT INCREASE OF THE CONDUCTOR AS SPECIFIED IN AS29606 AND THE EFFECT THAT IT HAD ON THE FINISHED WIRE.

NOTICE

THE COMPLETE REQUIREMENTS FOR PROCURING THE PRODUCT DESCRIBED HEREIN SHALL CONSIST OF THIS DOCUMENT AND THE LATEST ISSUE OF AS22759.

THIS SPECIFICATION IS NOT INTENDED FOR USE IN NAVAL AIRCRAFT OR NAVAL AIR SYSTEMS APPLICATIONS.



FP - FLUOROCARBON POLYMER MODIFIED POLYTETRAFLUOROETHYLENE (PTFE)
CONDUCTOR - STRANDED NICKEL COATED EXTRA HIGH STRENGTH COPPER ALLOY

FIGURE 1 - AS22759/96 CONFIGURATION

TABLE 1 - CONSTRUCTION DETAILS FOR FINISHED WIRE

PART NO. 1/	WIRE SIZE	CONDUCTOR 3/ STRANDING (NUMBER OF STRANDS X SIZE GAUGE OF STRANDS)	CONDUCTOR DIAMETER (INCHES) MIN	CONDUCTOR DIAMETER (INCHES) MAX	CONDUCTOR RESISTANCE AT 20 °C (68 °F) (OHMS/1000 FEET MAX)	FINISHED WIRE DIAMETER (INCHES) MIN	FINISHED WIRE DIAMETER (INCHES) MAX	FINISHED WIRE WEIGHT (LB/1000 FEET) 2/ MIN	FINISHED WIRE WEIGHT (LB/1000 FEET) 2/ TARGET	FINISHED WIRE WEIGHT (LB/1000 FEET) 2/ MAX
M22759/96-30-*	30	7 X 38	.0117	.0134	129.6	.026	.029	.75	.88	.96
M22759/96-28-*	28	7 X 36	.0147	.0164	79.0	.029	.033	.97	1.10	1.23
M22759/96-26-*	26	19 X 38	.0184	.0204	49.4	.033	.037	1.34	1.58	1.71
M22759/96-24-*	24	19 X 36	.0231	.0254	30.1	.038	.042	1.87	2.24	2.40
M22759/96-22-*	22	19 X 34	.0293	.0314	18.6	.043	.047	2.70	3.16	3.36
M22759/96-20-*	20	19 X 32	.0373	.0404	11.4	.051	.055	4.25	4.80	5.00

1/ PART NUMBER: THE ASTERISKS IN THE PART NUMBER COLUMN OF TABLE 1 SHALL BE REPLACED BY COLOR CODE DESIGNATORS IN ACCORDANCE WITH MIL-STD-681. EXAMPLES: M22759/96-20-93 IS A 20 AWG WHITE WITH ORANGE STRIPE.

2/ THE ACCEPTABLE VALUE FOR THE CPK FOR THE FINISHED WIRE WEIGHT LISTED SHALL BE 1.3, USING A NORMAL (GAUSSIAN) DISTRIBUTION TO OBTAIN THOSE CPK VALUES.

3/ CONDUCTOR SHALL CONFORM TO AS29606 TYPE NCS SMALL DIAMETER NICKEL COATED EXTRA HIGH STRENGTH COPPER ALLOY CONDUCTOR.

For more information on this standard, visit
https://www.sae.org/standards/content/AS22759/96A

THIRD ANGLE PROJECTION



ISSUED 2016-07 REVISED 2021-08

CUSTODIAN: AE-8/AE-8D

PROCUREMENT SPECIFICATION: AS22759

AEROSPACE STANDARD

WIRE, ELECTRICAL, POLYTETRAFLUOROETHYLENE/ POLYMIDE INSULATED, NORMAL WEIGHT, NICKEL COATED, EXTRA HIGH STRENGTH COPPER ALLOY, 260 °C, 600 VOLT, ROHS

AS22759™/96
SHEET 1 OF 4

REV. A

SAE Executive Standards Committee Rules provide that: " This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2021 SAE International
All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.
TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada) Fax: 724-776-0790 Tel: +1 724-776-4970 (outside USA) Email: CustomerService@sae.org SAE WEB ADDRESS: http://www.sae.org

Documents Sharing Hub

Full document details: SAE AS22759_96A

REQUIREMENT: ALL REQUIREMENTS SHALL CONSIST OF THIS DOCUMENT AND THE LATEST ISSUE OF AS22759.

1. WIRE CONSTRUCTION: WIRE CONSTRUCTION SHALL BE IN ACCORDANCE WITH FIGURE 1 AND TABLES 1, 2, 3, AND 4.

TABLE 2 - WIRE INSULATION MATERIALS

TAPE CODE	THICKNESS (NOM)	MATERIAL
1	.0020	.0005 (FP)/.0010 (POLYIMIDE)/.0005 (FP)
2	.0020	FP (UNSINTERED)

TABLE 3 - TAPE OVERLAP REQUIREMENTS 1/

WIRE SIZE	WRAP 1			WRAP 2			NOMINAL WALL THICKNESS (MILS)
	TAPE CODE	PERCENT OVERLAP		TAPE CODE	PERCENT OVERLAP		
		MIN	MAX		MIN	MAX	
30	1	50.5	54.0	2	50.5	54.0	7.4
28	1	50.5	54.0	2	50.5	54.0	7.4
26	1	50.5	54.0	2	50.5	54.0	7.4
24	1	50.5	54.0	2	50.5	54.0	7.4
22	1	50.5	54.0	2	50.5	54.0	7.4
20	1	50.5	54.0	2	50.5	54.0	7.4

1/ WRAP 1 IS INNERMOST TAPE WHICH IS IN CONTACT WITH THE CONDUCTOR.

2. WIRE PERFORMANCE RATING:

   TEMPERATURE RATING: 260 °C (500 °F) MAXIMUM CONDUCTOR CONTINUOUS TEMPERATURE.

   VOLTAGE RATING: 600 VOLTS (RMS) AT SEA LEVEL. THIS INSULATION SYSTEM HAS BEEN USED IN AEROSPACE APPLICATIONS USING 115 VOLTS (PHASE TO NEUTRAL), 400 HERTZ AC, AND 28 VOLTS DC. VERIFICATION OF THE SUITABILITY OF THIS PRODUCT FOR USE IN OTHER ELECTRICAL SYSTEM CONFIGURATIONS IS THE RESPONSIBILITY OF THE USER.

3. MATERIALS AND PHYSICAL PROPERTIES: REFER TO AS22759 FOR MATERIAL REQUIREMENT. MATERIALS USED IN THE MANUFACTURE OF THESE PRODUCTS SHALL COMPLY WITH THE RESTRICTION OF HAZARDOUS SUBSTANCES DIRECTIVE 2002/95/EC.

4. FINISH WIRE INSULATION PROPERTIES: FINISH WIRE INSULATION PROPERTIES SHALL BE IN ACCORDANCE WITH TABLE 4.

TABLE 4 - FINISHED WIRE INSULATION PROPERTIES REQUIREMENTS

INSULATION PROPERTIES	
IMPULSE TEST VOLTAGE	8.0 KILOVOLTS (PEAK)
HIGH FREQUENCY TEST VOLTAGE	5.7 KILOVOLTS (RMS)
INSULATION STATE OF SINTER	3.0 JOULES PER GRAM MAXIMUM
TAPE OVERLAP	TABLE 3
LAMINATION SEALING	260 °C ± 2 °C (500 °F ± 3.6 °F), 6 HOURS
INSULATION BLOCKING	260 °C ± 2 °C (500 °F ± 3.6 °F)
SHRINKAGE	290 °C ± 2 °C (554 °F ± 3.6 °F)
	MAXIMUM CHANGE .091 INCH
ELECTRICAL RESISTANCE (IR)	5000 MEGOHMS (MIN)-1000 FEET
WET DIELECTRIC VOLTAGE	2500 VOLTS (RMS), 60 HERTZ
INSULATION STRIP FORCE	.25-6.0 POUNDS: WIRE SIZES 26-20
	NOT REQUIRED FOR WIRE SIZES 30-28
UV LASER MARKING	55% MINIMUM AVERAGE
CONTINUOUS LENGTH SCHEDULE	B

AVA Documents
Document Sharing Hub
Full document details: SAE AS22759_96A