

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

REV.
C

AS5166™

FEDERAL SUPPLY CLASS
4730

RATIONALE

OPTIONAL MATERIAL AND FINISH SPECIFICATIONS ADDED. QML STATEMENT REVISED. INTENDED USE NOTE REVISED, NEW NOTE 8 ADDED. GENERAL UPDATES INCORPORATED. CADMIUM WARNING NOTE ADDED.





FIGURE 1 - FITTING, TEE /13/

For more information on this standard, visit
<https://www.sae.org/standards/content/AS5166C>

THIRD ANGLE PROJECTION



CUSTODIAN: G-3/G-3B

PROCUREMENT SPECIFICATION: AS4875 /4/



AEROSPACE STANDARD

FITTING, TEE,
AIR PRESSURE GAUGE

AS5166™
SHEET 1 OF 3

REV.
C

Copyright © 2021 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Fax: 724-776-0790

Tel: +1 724-776-4970 (outside USA)
Email: CustomerService@sae.org

SAE WEB ADDRESS: <http://www.sae.org>




**FIGURE 2 - ALTERNATE CONFIGURATION
OF CENTER BODY SECTION /7/ /13/**

NOTES:

NOTICE

THIS DOCUMENT REFERENCES A PART WHICH CONTAINS CADMIUM AS A PLATING MATERIAL. CONSULT LOCAL OFFICIALS IF YOU HAVE QUESTIONS CONCERNING CADMIUM'S USE.

/1/ MATERIAL:

- a. DASH AS CODE LETTER: TYPE 4130 STEEL FORGING OR BAR PER AMS-S-6758 OR AMS6370 OR TYPE 4140 PER AMS6349 OR AMS6382. /2/
- b. CODE LETTER T: TYPE 6AL-4V TITANIUM ALLOY FORGING OR BAR PER AMS4928.
- c. CODE LETTER W: TYPE 7075-T73 ALUMINUM ALLOY FORGING PER AMS4141 OR AMS-QQ-A-367; OR 7075-T351 ALUMINUM ALLOY BAR PER AMS4124; OR 7075-T73 ALUMINUM ALLOY BAR PER AMS-QQ-A-225/9. /2/

/2/ HEAT TREATMENT:

- a. DASH AS MATERIAL CODE LETTER: REFER TO HARDNESS REQUIREMENT PER PROCUREMENT SPECIFICATION.
- b. MATERIAL CODE LETTER T: NONE.
- c. MATERIAL CODE LETTER W: REFER TO ELECTRICAL CONDUCTIVITY AND HARDNESS REQUIREMENT PER PROCUREMENT SPECIFICATION.

3. FINISH:

- a. DASH AS MATERIAL CODE LETTER: CADMIUM PLATE PER AMS-QQ-P-416, TYPE II, CLASS 2, DYE BLACK AND COAT WITH LIGHT FILM OF OIL PER PROCUREMENT SPECIFICATION.
- b. MATERIAL CODE LETTER T: ANODIZE PER AMS2488, TYPE 2 OR FLUORIDE PHOSPHATE CONVERSION COAT PER AMS2486 WITH COLOR PER PROCUREMENT SPECIFICATION.
- c. MATERIAL CODE LETTER W: ANODIZE PER AMS2472 OR MIL-A-8625, TYPE II, CLASS 2, DYE BROWN, DUPLEX SEAL PER PROCUREMENT SPECIFICATION.

/4/ PROCUREMENT SPECIFICATION: AS4875 EXCEPT AS SPECIFIED ON THIS STANDARD. PRODUCT MANUFACTURED TO THIS STANDARD SHALL MEET THE REQUIREMENTS SPECIFIED HEREIN AND THE PROCUREMENT SPECIFICATION. ORIGINAL COMPONENT MANUFACTURERS (OCM) AND VALUE ADDED DISTRIBUTORS (VAD) SHALL BE LISTED IN THE NADCAP QUALIFIED MANUFACTURER LIST (QML) FOR THIS PRODUCT TYPE. THE QML IS AVAILABLE AT www.eAuditNet.com.

	AEROSPACE STANDARD		AS5166™ SHEET 2 OF 3	REV. C
	FITTING, TEE, AIR PRESSURE GAUGE			



Document Sharing Hub