



SURFACE VEHICLE RECOMMENDED PRACTICE

J1691™

APR2019

Issued 1997-04
Revised 2019-04

Superseding J1691 FEB2007

Plastic Motor Vehicle Safety Glazing - Tolerances and Fabrication Details

RATIONALE

This Recommended Practice was reaffirmed to comply with the SAE's Five-Year Review policy.

1. SCOPE

This SAE Recommended Practice is intended to cover plastic safety glazing for use in motor vehicles and motor vehicle equipment. Nominal specifications for thickness, flatness, curvature, size, and fabrication details are presented principally for the guidance of body engineers and designers. For additional information on plastic safety glazing materials for use in motor vehicles and motor vehicle equipment, please refer to SAE J673.

2. REFERENCES

2.1 Applicable Documents

The following publication forms a part of this specification to the extent specified herein. Unless otherwise indicated, the latest issue of SAE publications shall apply.

2.1.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

SAE J673 Automotive Safety Glazing Materials

2.2 Related Publications

The following publications are provided for information purposes only and are not a required part of this SAE Technical Report.

2.2.1 United States National Highway Traffic Safety Administration (NHTSA) Publications

Available from the Superintendent of Documents, U.S. Government Printing Office, Mail Stop: SSOP, Washington, DC 20402-9320 or at www.cfr.gov.

CFR Title 49 Part 571.205: Glazing Materials (FMVSS 205)

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2019 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

Full document details: [SAE J1691_201904](http://www.sae.org/J1691_201904)

SAE values your input. To provide feedback on this Technical Report, please visit http://standards.sae.org/J1691_201904

2.2.2 Transport Canada Publications

Transport Canada documents are available from Transport Canada, Tower C, Place de Ville, 330 Sparks Street Ottawa, Ontario K1A 0N5, Tel: 1-800-305-2059, www.tc.gc.ca.

Canada Motor Vehicle Safety Standards (CMVSS) 205 Glazing Materials

3. SIZES

There are no standard sizes applicable to plastic safety glazing for use in motor vehicles and motor vehicle equipment. The feasibility of proposed plastic safety glazing sizes developed by the motor vehicle/motor vehicle equipment manufacturer must be determined by conference with the plastic glazing fabricator.

The various types of plastic safety glazing (flat or curved) are as follows: injection molded, extruded (formed), and cell cast.

4. TYPICAL COMMERCIAL TOLERANCE INFORMATION

4.1 Thickness

Commercially available flat or curved plastic safety glazing has thickness tolerance as follows in Table 1:

Table 1 - Thicknesses¹

Type of Plastic Safety Glazing	Typical Nominal Thickness
Injection Molded and Extruded	4.00, 5.00, and 6.00 ($\pm 5\%$ of total thickness) mm 0.157, 0.197, and 0.236 ($\pm 5\%$ of total thickness) inch
Cell Cast	4.00, 5.00, and 6.00 ($+10\%/-20\%$ of total thickness) mm 0.157, 0.197, and 0.236 ($+10\%/-20\%$ of total thickness) inch

¹ Other plastic safety glazing thicknesses may be acceptable for use in motor vehicles and motor vehicle equipment, provided they meet the requirements of all applicable laws, regulations, codes, and practices in effect.

4.2 Flatness

Flat safety plastic glazing of the types noted may have 0.8 mm (0.03 inch) maximum total bow per 305 mm (12 inches) length, and each part may have a maximum overall bow, in millimeters, of 0.0026 times the length of the part.

4.3 Curvature

Dimensional tolerances on the physical dimensions of curved injection molded, extruded (formed), or cell cast plastic automotive safety glazing parts shall be specified as follows, with reference to numeric design data or to a master die model derived from numeric data supplied by the automotive manufacturer.

- a. Size - Maximum size (plus zero) with specified minimum size. Allowances must be made for the thermal expansion and contraction of the material based upon design and installation. In addition, material stresses need to be accounted for in order to meet acceptable dimensional tolerance limits. These material stresses are both a function of the thermal deformation vector (i.e., CTE) and the material's elastic modulus. The coefficient of thermal expansion for several plastic glazing materials (e.g., polycarbonate and acrylic) is shown in Table 2, along with the modulus of elasticity for each material.