



SURFACE VEHICLE STANDARD

J443™

NOV2024

Issued 1952-01
Revised 2024-11

Superseding J443 AUG2017

Procedures for Determining and Verifying Peening Intensity

RATIONALE

Changed document category from “Recommended Practice” to “Standard.” Resolved conflicting text and added commonly used methods for the verification process. Added method for verifying intensity derived from a Type 2 saturation curve.

1. SCOPE

This SAE Standard defines the method for deriving and verifying the peening intensity exerted onto a part surface during shot peening or other surface enhancement processes.

1.1 Application

1.1.1 Almen test strips are used to generate saturation curves in order to determine intensity and as a means of verifying the repeatability of a peening process.

1.1.2 The process of shot peening or other peening processes cannot, at present, be adequately controlled by nondestructive inspection of the peened parts; therefore, it is necessary to control the process itself to achieve consistent, reliable results. The use of Almen test strips with this standard is a method of measuring and verifying the peening process.

2. REFERENCES

2.1 Applicable Documents

The following publications form a part of this specification to the extent specified herein. Unless otherwise indicated, the latest issue of SAE publications shall apply.

2.2 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2590 Rotary Flap Peening of Metal Parts

SAE J442 Test Strip, Holder, and Gage for Shot Peening

SAE Executive Standards Committee Rules provide that: “This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user.”

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

Full document details: SAE J443_202411

For more information on this standard, visit https://www.sae.org/standards/content/J443_202411/

Documents

Standard, visit Sharing Hub

SAE J2277 Shot Peening Coverage Determination
SAE J2597 Computer Generated Shot Peening Saturation Curves
SAE HS-84 SAE Manual on Shot Peening

3. DEFINITIONS

3.1 ARC HEIGHT

A measurement of the curvature of an Almen test strip is the “arc height,” not the “intensity.” Exposing a single Almen test strip does not reveal intensity. Intensity can only be determined from a saturation curve developed by the procedure described in Section 4.

3.2 PRE-BOW

The measurement, either positive or negative, of the arc height of an Almen test strip prior to peening.

3.2.1 PRE-BOW COMPENSATION

Subtraction of the measured pre-bow from the measured arc height, after peening, to obtain the net change in the arc height from the peening process.

4. TECHNICAL REQUIREMENTS

4.1 Peening Intensity

Intensity is a function of the mass, the hardness, the velocity and the impingement angle of the shot and the distance traveled by the shot stream to the peened surface of an Almen test strip. For each set of peening parameters with a given media, an intensity value can be derived and documented.

4.2 Saturation Curve

A saturation curve, which is a plot of Almen test strip arc heights versus the duration of the exposure to the shot stream, is used to derive the peening intensity for a set of peening parameters. The saturation curve is developed from data points obtained by peening a series of Almen test strips while varying only the exposure. The exposure may be time-based (minutes, seconds, or inverse feed rate) or increment-based (number of passes, rotations, or cycles). In general, these points define a typical curve with a shape as exemplified in Figure 1 (Type 1). In some cases, saturation curves can appear as exemplified in Figure 2 (Type 2) and occur only when process variables do not permit the attainment of earlier data points.

The arc height value on the curve that increases by 10% when the exposure time is doubled is declared to be the intensity. The exposure time associated with the intensity value is designated as “T.” The exposure time at which the arc height increases by 10% is designated as “2T.” See 6.5 for recommended documentation of peening intensity. The use of computer-generated saturation curves that comply with SAE J2597 is recommended.

In cases where it appears that a data point is erroneous, it is permissible to repeat that test. If the same erroneous value is achieved, then the machine parameters shall be evaluated and adjusted as needed and a new saturation curve shall be generated.

Almen test strips exposed for extended periods can exhibit arc heights significantly greater than the “intensity” value. This does not imply that extensively long duration peening treatments are in violation of intensity requirements. Intensity is a value derived from a saturation curve and is constant for a given set of machine parameters, regardless of peening time.




Figure 1 - Time based saturation curve (Type 1)




Figure 2 - Incremental based saturation curve (Type 2)