SEMI M1-0414
SPECIFICATIONS FOR POLISHED SINGLE CRYSTAL SILICON WAFERS

This Standard was technically approved by the Silicon Wafer Global Technical Committee. This edition was approved for publication by the global Audits and Reviews Subcommittee on December 23, 2013; available at www.semiviews.org and www.semi.org in April 2014. Originally published in 1978; previously published January 2014.

SUPERSEDED

Table of Contents

1 Purpose 3
2 Scope 3
3 Referenced Standards and Documents 4
4 Terminology 8
5 Ordering Information 8
6 Requirements 17
6.1 *General Characteristics* 17
6.2 *Electrical Characteristics* 19
6.3 *Chemical Characteristics* 19
6.4 *Structural Characteristics* 20
6.5 *Wafer Preparation Characteristics* 20
6.6 *Dimensional Characteristics* 21
6.7 *Front Surface Chemistry* 31
6.8 *Front and Back Surface Inspection Characteristics* 32
7 Specifications for the 32, 22, and 16 nm Technology Generations 33
8 Sampling 33
9 Test Methods 33
10 Certification 33
11 Product Labeling 33
12 Packing and Shipping Container Labeling 34
13 Related Documents 34
APPENDIX 1 Flatness Decision Tree 35
APPENDIX 2 RoHS Requirements 38
APPENDIX 3 Shape Decision Tree 40
RELATED INFORMATION 1 Specification Guides for Advanced Technology Generations 43
RELATED INFORMATION 2 Surface Metal Contamination 46
RELATED INFORMATION 3 Test Methods 47

List of Tables

Table 1 Silicon Wafer Specification Format for Order Entry, Parts 1 and 2 9
Table 2 Energy Ranges for Ion Implant Modeling 19
Table 3 Dimensional Characteristics of 2 inch and 3 inch Polished Single Crystal Silicon Wafers 23
Table 4 Dimensional Characteristics of 100 mm and 125 mm Polished Single Crystal Silicon Wafers with Secondary Flat 23
Table 5 Dimensional Characteristics of 150 mm Polished Single Crystal Silicon Wafers with Secondary Flat 24
Table 6 Dimensional Characteristics of 100 mm and 125 mm Polished Single Crystal Silicon Wafers Without Secondary Flat 25
Table 7 Dimensional Characteristics of 150 mm and 200 mm Polished Single Crystal Silicon Wafers Without Secondary Flat 25
Table 8 Dimensional Characteristics and Wafer ID Marking Requirements for Notched 200 mm and 300 mm Polished Single Crystal Silicon Wafers 26
Table 9 Specified Requirements for Notched 450 mm Polished Single Crystal Silicon Wafers 27

Documents Document Sharing Hub
Full document details: SEMI M1-0414

Table 10 Template-Coordinate Based Wafer Edge Profile Specifications (see Figure 6) 29
Table 11 Parameters for Use with Profile-Parameter Based Edge Profile Specifications 30
Table 12 Polished Wafer Defect Limits 31
Table A2-1 Tolerated Maximum Concentrations of Hazardous Materials in or on Silicon Wafers 39
Table A3-1 Variables in Shape Quantities 42
Table A3-2 Shape Code Summary 42
Table R1-1 Guide for the Specification of 300 and 450 mm Diameter Silicon Wafers for the 32, 22, and 16 nm Technology Generations 43
Table R2-1 Suggested Polished Wafer Surface Metal Contamination Limits Appropriate to Circuits and Devices with a Minimum Linewidth in the Range 0.8 µm to 1.2 µm 46

List of Figures

Figure 1 Fixed Quality Area 18
Figure 2 Orthogonal Misorientation of {111} Wafer 19
Figure 3 Optional A/N Code Field Location on Back Surface of Notched 300 mm Diameter Wafer (Categories 1.15 and 1.15.1) 21
Figure 4 Secondary Flat Locations 22
Figure 5 Notch Dimensions 22
Figure 6 SEMI Wafer Edge Profile Template 28
Figure 7 Examples of Acceptable and Unacceptable Wafer Edge Profiles 29
Figure A1-1 Flatness Decision Tree 36
Figure A1-2 Scanner Site and Subsite Flatness Elements 37
Figure A1-3 Subsite Center near Boundaries of Site and FQA 37
Figure A3-1 Four Branches of the Shape Decision Tree 41

SUPERSEDED

Documents
Document Sharing Hub
Full document details: SEMI M1-0414

1 Purpose

1.1 Single crystal silicon wafers are utilized for essentially all integrated circuits and many other semiconductor devices. To permit common processing equipment to be used in multiple device fabrication lines, it is essential for the wafer dimensions to be standardized.

1.2 In addition, as technology advances to smaller and smaller dimensions for the elements of high-density integrated circuits, it has become of interest to standardize additional properties of the wafers.

1.3 This Specification provides the essential dimensional and certain other common characteristics of silicon wafers, including polished wafers as well as substrates for epitaxial and certain other kinds of silicon wafers.

2 Scope

2.1 These specifications cover ordering information and certain requirements for high-purity (electronic grade), single crystal polished silicon wafers used in semiconductor device and integrated circuit manufacturing. Such wafers are usually sliced from cylindrical single-crystal ingots that have been ground to a uniform diameter prior to slicing. These specifications also cover ordering information and certain requirements for electronic grade silicon wafers intended for use as substrates (or starting wafers) for other kinds of wafers, including epitaxial, annealed, and SOI wafers.

2.2 Dimensional requirements are provided for the following categories of polished wafers:

Category 1.1	2 inch polished single crystal silicon wafers with secondary flat
Category 1.2	3 inch polished single crystal silicon wafers with secondary flat
Category 1.5	100 mm polished single crystal silicon wafers, 525 µm thick, with secondary flat
Category 1.6	100 mm polished single crystal silicon wafers, 625 µm thick, with secondary flat
Category 1.7	125 mm polished single crystal silicon wafers with secondary flat
Category 1.8.1	150 mm polished single crystal silicon wafers with secondary flat and T/3 edge profile template
Category 1.8.2	150 mm polished single crystal silicon wafers with secondary flat and T/4 edge profile template
Category 1.9.1	200 mm notched polished single crystal silicon wafers with T/3 edge profile template
Category 1.9.2	200 mm notched polished single crystal silicon wafers with T/4 edge profile template
Category 1.9.3	200 mm notched polished single crystal silicon wafers with parameter-specified edge profile
Category 1.10.1	200 mm flatted polished single crystal silicon wafers with T/3 edge profile template without secondary flat
Category 1.10.2	200 mm flatted polished single crystal silicon wafers with T/4 edge profile template without secondary flat
Category 1.11	100 mm flatted polished single crystal silicon wafers without secondary flat
Category 1.12	125 mm flatted polished single crystal silicon wafers without secondary flat
Category 1.13.1	150 mm flatted polished single crystal silicon wafers with T/3 edge profile template without secondary flat
Category 1.13.2	150 mm flatted polished single crystal silicon wafers with T/4 edge profile template without secondary flat
Category 1.15	300 mm notched polished single crystal silicon wafers with T/4 edge profile template
Category 1.15.1	300 mm notched polished single crystal silicon wafers with parameter-specified edge profile

SUPERSEDED

Documents Document Sharing Hub
Full document details: SEMI M1-0414

Category 1.16.1 450 mm polished single crystal silicon wafers with notch centered on <110> axis

Category 1.16.2 450 mm polished single crystal silicon wafers with notch centered on <100> axis

2.2.1 Values given for thickness, total thickness variation (TTV), bow, and warp apply only to wafers prior to application of back surface films, extrinsic gettering treatments, or other thermal treatments.

2.2.2 The dimensional characteristics of Category 1.10.1, 1.10.2, 1.11, 1.12, 1.13.1, and 1.13.2 wafers specified in this document are identical with those specified in JEITA EM-3602, and the dimensional characteristics of Category 1.15 wafers are essentially equivalent with those specified in JEITA EM-3602.

2.3 A complete purchase specification requires that additional physical properties be specified along with test methods suitable for determining their magnitude. This Standard provides a comprehensive listing of such properties and associated test methods. This listing provides a systematic basis for constructing the purchase specification for any kind of polished silicon wafer or substrate and is expected to be used for such purposes.

2.4 These specifications apply specifically to prime silicon wafers with at least one chem-mechanically polished surface. Ground, lapped, and unpolished wafers are not covered in this Specification but this Specification may provide guidance in connection with their procurement.

2.5 This Standard also provides guides for the specification of 300 and 450 mm diameter prime silicon wafers for the 32, 22, and 16 nm technology generations. These are included in Related Information 1.

2.6 These specifications do not cover the requirements for the following related silicon materials and wafers:

- Polycrystalline silicon (see SEMI M16 or JEITA EM-3601A),
- Epitaxial wafers (see SEMI M62),
- Epitaxial wafers with buried layer (see SEMI M61),
- Test wafers (see SEMI M8),
- Premium wafers (see SEMI M24),
- Reclaimed wafers (see SEMI M38),
- Annealed wafers (see SEMI M57),
- SOI wafers (see SEMI M41, SEMI M71, or JEITA EM-3603B), and
- Solar-grade silicon wafers (see SEMI PV22).

They do, however, provide the ordering information for test, premium, and reclaimed wafers, as well as the ordering information for the polished substrates and starting wafers used to prepare epitaxial, annealed, and SOI wafers.

2.7 For referee purposes, U.S. customary units shall be used for wafers of 2 inch and 3 inch nominal diameters, and SI (system international, commonly called metric) units for 100 mm and larger diameter wafers.

NOTICE: SEMI Standards and Safety Guidelines do not purport to address all safety issues associated with their use. It is the responsibility of the users of the documents to establish appropriate safety and health practices, and determine the applicability of regulatory or other limitations prior to use.

3 Referenced Standards and Documents

3.1 *SEMI Standards and Safety Guidelines*

SEMI M8 — Specification for Polished Monocrystalline Silicon Test Wafers

SEMI M12 — Specification for Serial Alphanumeric Marking of the Front Surface of Wafers

SEMI M13 — Specification for Alphanumeric Marking of Silicon Wafers

SEMI M16 — Specification for Polycrystalline Silicon

SEMI M18 — Guide for Developing Specification Forms for Order Entry of Silicon Wafers

SEMI M20 — Practice for Establishing a Wafer Coordinate System

SUPERSEDED

Documents
Document Sharing Hub

Full document details: SEMI M1-0414

SEMI M24 — Specification for Polished Monocrystalline Silicon Premium Wafers

SEMI M26 — Guide for the Re-Use of 100, 125, 150, and 200 mm Wafer Shipping Boxes Used to Transport Wafers

SEMI M33 — Test Method for the Determination of Residual Surface Contamination on Silicon Wafers by Means of Total Reflection X-Ray Fluorescence Spectroscopy (TXRF)

SEMI M35 — Guide for Developing Specifications for Silicon Wafer Surface Features Detected by Automated Inspection

SEMI M38 — Specification for Polished Reclaimed Silicon Wafers

SEMI M40 — Guide for Measurement of Roughness of Planar Surfaces on Silicon Wafers

SEMI M41 — Specification of Silicon-on-Insulator (SOI) for Power Device/ICs

SEMI M43 — Guide for Reporting Wafer Nanotopography

SEMI M44 — Guide to Conversion Factors for Interstitial Oxygen in Silicon

SEMI M45 — Specification for 300 mm Wafer Shipping System

SEMI M53 — Practice for Calibrating Scanning Surface Inspection Systems Using Certified Depositions of Monodisperse Reference Spheres on Unpatterned Semiconductor Wafer Surfaces

SEMI M57 — Guide for Specifying Silicon Annealed Wafers

SEMI M58 — Test Method for Evaluating DMA-Based Particle Deposition Systems and Processes

SEMI M59 — Terminology for Silicon Technology

SEMI M61 — Specification for Silicon Epitaxial Wafers with Buried Layers

SEMI M62 — Specifications for Silicon Epitaxial Wafers

SEMI M67 — Practice for Determining Wafer Near-Edge Geometry from a Measured Thickness Data Array Using the ESFQR, ESFQD and ESBIR Metrics

SEMI M68 — Practice for Determining Wafer Near-Edge Geometry from a Measured Height Data Array Using a Curvature Metric, ZDD

SEMI M70 — Practice for Determining Wafer-Near-Edge Geometry Using Partial Wafer Site Flatness

SEMI M71 — Specification for Silicon-on-Insulator (SOI) Wafers for CMOS LSI

SEMI M73 — Test Methods for Extracting Relevant Characteristics from Measured Wafer Edge Profiles

SEMI M77 — Practice for Determining Wafer Near-Edge Geometry Using Roll-off Amount, ROA

SEMI M78 — Guide for Determining Nanotopography of Unpatterned Silicon Wafers for the 130 nm to 22 nm Generations in High Volume Manufacturing

SEMI MF26 — Test Methods for Determining the Orientation of a Semiconductive Single Crystal

SEMI MF28 — Test Methods for Minority-Carrier Lifetime in Bulk Germanium and Silicon by Measurement of Photoconductive Decay

SEMI MF42 — Test Methods for Conductivity Type of Extrinsic Semiconducting Materials

SEMI MF81 — Test Method for Measuring Radial Resistivity Variation on Silicon Wafers

SEMI MF84 — Test Method for Measuring Resistivity of Silicon Wafers with an In-Line Four-Point Probe

SEMI MF391 — Test Methods for Minority Carrier Diffusion Length in Extrinsic Semiconductors by Measurement of Steady-State Surface Photovoltage

SEMI MF523 — Practice for Unaided Visual Inspection of Polished Silicon Wafer Surfaces

SEMI MF525 — Test Method for Measuring Resistivity of Silicon Wafers Using a Spreading Resistance Probe

SUPERSEDED

Documents Document Sharing Hub

Full document details: SEMI M1-0414

SEMI MF533 — Test Method for Thickness and Thickness of Variation of Silicon Wafers

SEMI MF534 — Test Method for Bow of Silicon Wafers

SEMI MF657 —Test Method for Measuring Warp and Total Thickness Variation on Silicon Wafers by Noncontact Scanning

SEMI MF671 — Test Method for Measuring Flat Length on Wafers of Silicon and Other Electronic Materials

SEMI MF673 — Test Methods for Measuring Resistivity of Semiconductor Slices or Sheet Resistance of Semiconductor Films with a Noncontact Eddy-Current Gage

SEMI MF847 — Test Methods for Measuring Crystallographic Orientation of Flats on Single Crystal Silicon Wafers by X-Ray Techniques

SEMI MF928 — Test Methods for Edge Contour of Circular Semiconductor Wafers and Rigid Disk Substrates

SEMI MF951 — Test Method for Determination of Radial Interstitial Oxygen Variation in Silicon Wafers

SEMI MF978 — Test Method for Characterizing Semiconductor Deep Levels by Transient Capacitance Techniques

SEMI MF1048 — Test Method for Measuring Reflective Total Integrated Scatter

SEMI MF1049 — Practice for Shallow Etch Pit Detection on Silicon Wafers

SEMI MF1152 — Test Method for Dimensions of Notches on Silicon Wafers

SEMI MF1188 — Test Method for Interstitial Oxygen Content of Silicon by Infrared Absorption with Short Baseline

SEMI MF1239 — Test Method for Oxygen Precipitation Characteristics of Silicon Wafers by Measurement of Interstitial Oxygen Reduction

SEMI MF1366 — Test Method for Measuring Oxygen Concentration in Heavily Doped Silicon Substrates by Secondary Ion Mass Spectrometry

SEMI MF1388 — Test Method for Generation Lifetime and Generation Velocity of Silicon Material by Capacitance-Time Measurements of Metal-Oxide-Silicon (MOS) Capacitors

SEMI MF1390 — Test Method for Measuring Warp on Silicon Wafers by Automated Non-contact Scanning

SEMI MF1391 — Test Method for Substitutional Atomic Carbon Content of Silicon by Infrared Absorption

SEMI MF1451 — Test Method for Measuring Sori on Silicon Wafers by Automated Non-contact Scanning

SEMI MF1528 — Test Method for Measuring Boron Contamination in Heavily Doped *n*-Type Silicon Substrates by Secondary Ion Mass Spectrometry

SEMI MF1530 — Test Method for Measuring Flatness, Thickness, and Total Thickness Variation on Silicon Wafers by Automated Non-contact Scanning

SEMI MF1535 — Test Method for Carrier Recombination Lifetime in Silicon Wafers by Noncontact Measurement of Photoconductivity Decay by Microwave Reflectance

SEMI MF1617 — Test Method for Measuring Surface Sodium, Aluminum, Potassium, and Iron on Silicon and Epi Substrates by Secondary Ion Mass Spectrometry

SEMI MF1619 — Test Method for Measurement of Interstitial Oxygen Content of Silicon Wafers by Infrared Absorption Spectroscopy with *p*-Polarized Radiation Incident at the Brewster Angle

SEMI MF1726 — Practice for Analysis of Crystallographic Perfection of Silicon Wafers

SEMI MF1727 — Practice for Detection of Oxidation Induced Defects in Polished Silicon Wafers

SEMI MF1809 — Guide for Selection and Use for Etching Solutions to Delineate Structural Defects in Silicon

SEMI MF1982 — Test Methods for Analyzing Organic Contaminants on Silicon Wafer Surfaces by Thermal Desorption Gas Chromatography

SUPERSEDED

Documents
Document Sharing Hub

Full document details: SEMI M1-0414

SEMI MF2074 — Guide for Measuring Diameter of Silicon and Other Semiconductor Wafers

SEMI PV13 — Test Method for Contactless Excess-Charge-Carrier Recombination Lifetime Measurement in Silicon Wafers, Ingots, and Bricks Using an Eddy-Current Sensor

SEMI PV22 — Specification for Silicon Wafers for Use in Photovoltaic Solar Cells

SEMI T3 — Specification for Wafer Box Labels

SEMI T7 — Specification for Back Surface Marking of Double-sided Polished Wafers with a Two-Dimensional Matrix Code Symbol

3.2 *ANSI Standards*[1]

ANSI/ASQ Z1.4 — Sampling Procedures and Tables for Inspection by Attributes

3.3 *ASTM Standards*[2]

ASTM D523 — Standard Test Method for Specular Gloss

ASTM E122 — Standard Practice for Calculating Sample Size to Estimate, With Specific Precision, the Average for a Characteristic of a Lot or Process

3.4 *DIN Standards*[3]

3.5 *European Community Directive*[4]

2002/95/EC — On the restriction of the use of certain hazardous substances in electrical and electronic equipment

3.6 *ISO Standard*[5]

ISO 14706 — Surface Chemical Analysis – Determination of Surface Elemental Contamination on Silicon Wafers by Total Reflection X-ray Fluorescence (TXRF) Spectroscopy

3.7 *JEITA Standards*[6]

JEITA EM-3401 — Terminology of Silicon Wafer Flatness

JEITA EM-3501 — Standard Methods for Determining the Orientation of a Semiconductor Silicon Single Crystal

JEITA EM-3502 — Test Method for Recombination Lifetime in Silicon Wafers by Measurement of Photoconductivity Decay by Microwave Reflectance

JEITA EM-3503 — Standard Test Method for Substitutional Atomic Carbon Content of Silicon by Infrared Absorption

JEITA EM-3504 — Standard Test Method for Interstitial Atomic Oxygen Content of Silicon by Infrared Absorption

JEITA EM-3508 — Test Method for Bulk Micro Defect Density and Denuded Zone Width in Annealed Silicon Wafers

JEITA EM-3601A — Standard Specification for High Purity Polycrystalline Silicon

JEITA EM-3602 — Standard Specification for Dimensional Properties of Silicon Wafers with Specular Surfaces

---

[1] American National Standards Institute, 25 West 43rd Street, New York, NY 10036, USA; Telephone: 212.642.4900, Fax: 212.398.0023, http://www.ansi.org

[2] American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, USA; Telephone: 610.832.9585, Fax: 610.832.9555, http://www.astm.org

[3] Deutsches Institut für Normung e.V., silicon standards are no available from Beuth Verlag GmbH, Burggrafenstrasse 4-10, D-10787 Berlin, Germany; http://www.din.de. Consequently these standards have been removed from this section and moved to the Related Documents section at the end of this Standard.

[4] *Official Journal of the European Union*, February 13, 2003 Available for downloading from the following URL: http://164.36.164.20/sustainability/pdfs/finalrohs.pdf

[5] International Organization for Standardization, ISO Central Secretariat, 1 rue de Varembé, Case postale 56, CH-1211 Geneva 20, Switzerland; Telephone: 41.22.749.01.11, Fax: 41.22.733.34.30, http://www.iso.ch

[6] Japan Electronics and Information Technology Industries Association, Ote Center Building, 1-1-3, Otemachi, Chiyoda-ku, Tokyo 100-0004, Japan; http://www.jeita.or.jp

SUPERSEDED

Documents Document Sharing Hub

Full document details: SEMI M1-0414

JEITA EM-3603B — Standard of SOI Wafers and Metrology

3.8 *JIS Standards*[7]

JIS H 0604 — Measuring of Minority-carrier Lifetime in Silicon Single Crystal by Photoconductive Decay Method

JIS H 0607 — Determination of Conductivity Type in Germanium by Thermoelectromotive Method

JIS H 0609 — Test methods of Crystalline Defects in Silicon by Preferential Etch Techniques

JIS H 0611 — Methods of Measurement of Thickness, Thickness Variation and Bow of Silicon Wafer

JIS H 0614 — Visual Inspection for Silicon Wafers with Specular Surfaces

JIS H 0615 — Test Method for Determination of Impurity Concentrations in Silicon Crystal by Photoluminescence Spectroscopy

JIS Z 8741 — Specular Glossiness – Methods of Measurement

3.9 *MHI Standard*[8]

CEA 556-C — Outer Shipping Container Bar Code Label Standard

NOTICE: Unless otherwise indicated, all documents cited shall be the latest published versions.

4 Terminology

4.1 Terms, acronyms, and symbols associated with silicon wafers and silicon technology are listed and defined in SEMI M59.

5 Ordering Information

5.1 Purchase orders for silicon wafers furnished to this specification shall include the following items. These items are indicated on the Silicon Wafer Specification Format for Order Entry, Parts 1 and 2, shown in Table 1, with a ♦ symbol in the left-most column.

- 2-1.1 Growth Method
- 2-1.3 Crystal Orientation
- 2-1.4 Conductivity Type
- 2-1.5 Dopant
- 2-1.8 Wafer Surface Orientation
- 2-2.1 Resistivity
- 2-6.1 Diameter
- 2-6.2 Fiducial Dimensions
- 2-6.3 Primary Flat/Notch Orientation
- 2-6.4 Secondary Flat Length
- 2-6.5 Secondary Flat Location
- 2-6.6 Edge profile
- 2-6.7 Thickness

5.2 In addition, the purchase order must indicate the test method to be used in evaluating each of those items for which alternate test procedures exist.

[7] Japanese Industrial Standards, Available through the Japanese Standards Association, 1-24, Akasaka 4-Chome, Minato-ku, Tokyo 107-8440, Japan. Telephone: 81.3.3583.8005; Fax: 81.3.3586.2014; http://www.jsa.or.jp

[8] Material Handling Institute, 8720 Red Oak Blvd., Suite 201, Charlotte, NC 28217, USA; Telephone: 704.676.1190; Fax: 704.676.1199; http://www.mhi.org

SUPERSEDED

Documents
Document Sharing Hub
Full document details: SEMI M1-0414

5.3 The following items must also be included in the purchase order:

5.3.1 Lot acceptance procedures,

5.3.2 Certification (if required) and

5.3.3 Packing and shipping container labeling requirements.

5.4 Finally, many other characteristics may also be specified in purchase orders for silicon wafers. These shall be selected from the other items listed in the Silicon Wafer Specification Format for Order Entry, Parts 1 and 2 (see Table 1).

5.5 The parameter values provided in the requirements tables in § 6 may be used to identify appropriate values in the specification without selecting a value for each line. However, even if these requirements table values are used, the desired test methodology must be selected in accordance with ¶ 5.2.

5.6 It is essential that all choices for the items selected to be specified be made in order not to have unspecified parameters that would lead to surprises between supplier and customer. This is particularly important in the specification of wafer site flatness, for which a variety of parameters must be selected as outlined in Appendix 1.

5.7 Of the various items listed, the following (listed in the order in which they appear in Table 1) are most often selected, especially for wafers to be used for advanced integrated circuit manufacture:

- 2-1.6 Nominal edge exclusion (to define the fixed quality area (FQA), see Figure 1.)
- 2-4 Structural characteristics
- 2-5.1 Wafer ID Marking
- 2-6.6 Edge Profile
- 2-6.8 Total Thickness Variation (TTV or GBIR, see ¶ R4-7.7)
- 2-6.10 Warp (and sometimes 2-6.9 Bow or 2-6.11 Sori)
- 2-6.13 Site Flatness (SFQR)
- 2-8.5 Localized Light Scatterers (LLS)

Table 1 Silicon Wafer Specification Format for Order Entry, Parts 1 and 2

Part 1 General Information			
ITEM		*INFORMATION*	*Date:*
Customer Name			
Purchase Order Number			
Line Number			
Item Number			
General Specification Number			
Revision Level			
Part Number/Revision			
Part 2 Polished Wafer or Substrate			
ITEM		*SPECIFICATION*	*MEASUREMENT METHOD*
2-1 GENERAL CHARACTERISTICS *(Note that ♦ indicates a required item for which a value or choice* ***must*** *be indicated in order to minimally specify a silicon wafer.)*			
♦	2-1.1	Growth Method	[ ] Cz; [ ] FZ; [ ] MCz; [ ] Supplier option of Cz or MCz	
	2-1.2	Use of Refined Polysilicon	[ ] Permitted; [ ] Not permitted	

SUPERSEDED
Documents Document Sharing Hub
Full document details: SEMI M1-0414

		ITEM	SPECIFICATION	MEASUREMENT METHOD
♦	2-1.3	Crystal Orientation	[ ] (100); [ ] (111); [ ] (110); [ ] Other: (specify) ( )	[ ] SEMI MF26 (X-ray); [ ] SEMI MF26 (Optical); [ ] JEITA EM-3501; [ ] Other: (specify)_____
♦	2-1.4	Conductivity Type	[ ] *p;* [ ] *n*	[ ] SEMI MF42; [ ] JIS H 0607; [ ] Other: (specify)_____
♦	2-1.5	Dopant	[ ] B; [ ] P; [ ] Sb; [ ] As; [ ] Neutron Transmutation Doped; [ ] Other: (specify) _____	
	2-1.6	Nominal Edge Exclusion[#1] (see Figure 1)	[ ] 2 mm; [ ] 3 mm; [ ] 5 mm; [ ] Other: (specify)_____mm	
	2-1.7	Co-dopant in Crystal	[ ] None; [ ] Nitrogen; [ ] Carbon; [ ] Nitrogen and Carbon; [ ] Argon; [ ] Other: (specify)_____	
♦	2-1.8	Wafer Surface Orientation (with respect to crystal orientation, see Item 2-1.3)	[ ] On-orientation: [ ] 0.00° ± 1.00°; [ ] 0.00° ± ____° [ ] Off-orientation: [ ] 0.6° ± 0.4° [ ] 2.50° ± 0.50°; [ ] 4.00° ± 0.50°; [ ] _____° ± _____°	[ ] SEMI MF26 (X-ray); [ ] SEMI MF26 (Optical); [ ] JEITA EM-3501; [ ] Other: (specify)_____
	2-1.9	Orthogonal Misorientation (see Figure 2)	[ ] ±5° max; [ ] Other: ± [ ]°, max	
2-2 ELECTRICAL CHARACTERISTICS *(Note that ♦ indicates a required item for which a value or choice **must** be indicated in order to minimally specify a silicon wafer.)*				
♦	2-2.1	Resistivity Measured at	Nominal [ ] ± Tolerance [ ] Ω·cm [ ] Center Point; [ ] Other: (specify)_____	[ ] SEMI MF84; [ ] SEMI MF673; [ ] Other: (specify)_____
	2-2.2	Radial Resistivity Variation (RRG)	Not greater than [ ]%	SEMI MF81 Figure 1 – [ ] A, [ ] B, [ ] C, [ ] D; [ ] Other: (specify) _____
	2-2.3	Resistivity Striations	Not greater than [ ]%	[ ] SEMI MF525; [ ] Other: (specify)_____
	2-2.4	Minority Carrier Lifetime	Greater than [ ] µs	SEMI MF28 [ ] A, [ ] B; SEMI MF391 [ ] A, [ ] B; [ ] SEMI MF1388; [ ] SEMI MF1535; [ ] JEITA EM-3502; [ ] JIS H 0604; [ ] SEMI PV13 [ ] Other: (specify)_____
2-3 CHEMICAL CHARACTERISTICS				
	2-3.1	Oxygen Concentration (Values using the following Calibration Factor, see SEMI M44)	Nominal [ ] ± Tolerance [ ]; [ ] 10^{17} cm^{-3}; [ ] ppma [ ] IOC-88; [ ] Old ASTM; [ ] New ASTM or DIN; [ ] Original JEITA; [ ] Other: (specify)_____	IR (Interstitial): [ ] SEMI MF1188; [ ] SEMI MF1619; [ ] JEIDA EM-3504; [ ] Other: (specify)_____ [ ] SIMS (Total): SEMI MF1366; [ ] GFA (Total)
	2-3.2	Radial Oxygen Variation	Not greater than [ ]%	SEMI MF951 Plan [ ] A1; [ ] A2; [ ] A3; [ ] B; [ ] B1; [ ] C; [ ] D; [ ] Other: (specify)_____
	2-3.3	Carbon Concentration (Background, cf. 2-1.7)	Not greater than [ ] [ ] ppma; [ ] × $10^{16}cm^{-3}$	[ ] SEMI MF1391; [ ] JEITA EM-3503; [ ] Other: (specify)_____

SUPERSEDED

Documents
Document Sharing Hub
Full document details: SEMI M1-0414

ITEM			SPECIFICATION	MEASUREMENT METHOD
	2-3.4	Boron Concentration in Heavily Doped *n*-type Silicon	Not greater than [ ] ppba	[ ] SEMI MF1528; [ ] Other: (specify)_____
	2-3.5	Bulk Iron Content	[ ] Not greater than [ ] × $10^{[\ ]}$ atoms/cm^3	[ ] SEMI MF978 (DLTS); [ ] SEMI MF391(SPV); [ ] SEMI MF1535; [ ] JEITA EM-3502 (μτ); [ ] SEMI PV13 [ ] Other (specify): _____
	2-3.6	Hazardous Substances Restrictions	[ ] EC Directive 2002/95/EC [ ] Other: (specify) _____	See Appendix 2 Specify: _____
2-4 STRUCTURAL CHARACTERISTICS				
	2-4.1	Dislocation Etch Pit Density	[ ] Not greater than [ ]/cm^2	[ ] SEMI MF1809; [ ] JIS H 0609; [ ] Other: (specify)_____
	2-4.2	Slip	[ ] None [ ] Other: (specify)_____	[ ] SEMI MF1809; [ ] JIS H 0609; [ ] Other: (specify)_____
	2-4.3	Lineage	[ ] None [ ] Other: (specify)_____	[ ] SEMI MF1809; [ ] JIS H 0609; [ ] Other: (specify)_____
	2-4.4	Twin Boundary	[ ] None [ ] Other: (specify)_____	[ ] SEMI MF1809; [ ] JIS H 0609; [ ] Other: (specify)_____
	2-4.5	Swirl	[ ] Not greater than [ ]% of wafer area	[ ] SEMI MF1809; [ ] JIS H 0609; [ ] Other: (specify)_____
	2-4.6	Shallow Pits	Not greater than [ ]/cm^2	[ ] SEMI MF1727; [ ] SEMI MF1049; [ ] Other: (specify)_____
	2-4.7	Oxidation Induced Stacking Faults (OSF)	Not greater than [ ]/cm^2	Test Cycle: [ ] SEMI MF1727; [ ] JIS H 0609; [ ] Other: (specify)_____ Observation Method: [ ] SEMI MF1726; [ ] JIS H 0609; [ ] Other: (specify)_____
	2-4.8	Oxide Precipitates	Range: [ ] to [ ] Unit: [ ] cm^{-2}; [ ] cm^{-3}	Test Cycle: SEMI MF1239 [ ] A, [ ] B; [ ] Other: (specify)_____
	2-4.9	Interstitial Oxygen Reduction ($\Delta[O_i]$)	Range: [ ] to [ ] [ ] ppma; [ ] × 10^{17} cm^{-3}	Test Cycle: SEMI MF1239 [ ] A, [ ] B; [ ] Other: (specify)_____
	2-4.10	Bulk defects by X-ray topography	[ ] Density:_____ cm^{-3}	[ ] Specify_____
	2-4.11	Bulk Micro Defects	[ ] Density:_____ cm^{-3}	[ ] JEITA EM-3508; [ ] Other: (specify)_____
2-5 WAFER PREPARATION CHARACTERISTICS				
	2-5.1	Wafer ID Marking	[ ] None; [ ] SEMI M12; [ ] SEMI M13; [ ] SEMI T7; [ ] SEMI T7 + optional alphanumeric mark (see Figure 3); [ ] Other: (specify) _____	
	2-5.2	Front Surface Thin Film(s)	[ ] None [ ] Description:	
	2-5.3	Denuded Zone	[ ] None [ ] Width: _____μm	[ ] JEITA EM-3508; [ ] Other: (specify)_____
	2-5.4	Extrinsic Gettering	[ ] None [ ] Description:	
	2-5.5	Backseal	[ ] None [ ] Description:	
	2-5.6	Annealing	[ ] None [ ] Description:	

SUPERSEDED

Documents Document Sharing Hub
Full document details: SEMI M1-0414

ITEM			SPECIFICATION	MEASUREMENT METHOD
	2-5.7	Edge Surface Condition	[ ] Ground; [ ] Etched; [ ] Polished[#2]	
	2-5.8	Back Surface Condition	[ ] Supplier Option; [ ] Caustic Etched; [ ] Acid Etched; [ ] Polished[#2] (see Item 2-9.8 for required gloss level)	
2-6 DIMENSIONAL CHARACTERISTICS *(Note that ♦ indicates a required item for which a value or choice **must** be indicated in order to minimally specify a silicon wafer.*				
	THE ITEMS LISTED IN THIS SECTION MAY BE SPECIFIED INDIVIDUALLY OR THEY MAY BE [ ] Specified According to Category 1.__ Polished Wafers (see Tables 3 through 9). If the items are specified according to a standard wafer Category, all the items in these tables need not be entered individually.			
♦ ➲	2-6.1	Diameter	[ ] Nominal [ ] ± Tolerance [ ] mm	[ ] SEMI MF2074; [ ] Other: (specify)_____
♦ ➲	2-6.2	Fiducial Dimensions	Flat [ ] Length or [ ] Diameter:[#3] [ ] Nominal [ ] ± Tolerance [ ] mm [ ] Notch Dimensions (see Figure 5)	[ ] SEMI MF671 (Flat Length); [ ] SEMI MF1152 (Notch Dimensions); [ ] Other: (specify)_____
♦ ➲	2-6.3	Primary Flat/Notch Orientation	[ ] (crystal axis) [_____]±____°	[ ] SEMI MF847 (Flat); [ ] Other: (specify)_____
♦ ➲	2-6.4	Secondary Flat Length	[ ] None; [ ] Other: _____±____mm	[ ] SEMI MF671; [ ] Other: (specify)_____
♦ ➲	2-6.5	Secondary Flat Location (see Figure 4)	[ ] None; [ ] Other: (θ) _____°	
♦ ➲	2-6.6	Template-Coordinate Based Edge Profile Specification	[ ] T/3 template [ ] T/4 template [ ] Other template (specify)_____	SEMI MF928: Method A [ ], Method B [ ] Other: (specify)_____
		Profile-Parameter-Based Edge Profile Specification	[ ] Front edge width ____µm ± ____µm [ ] Front bevel angle ____° ± ____° [ ] Front shoulder radius ____µm ± ___µm [ ] Back shoulder radius ____µm ± ___µm [ ] Back bevel angle ____° ± ____° [ ] Back edge width ____µm ± ___µm [ ] Front apex angle ____° ± ____° (optional)[#4] [ ] Back apex angle ____° ± ____° (optional)[#4]	SEMI M73:[#4] Method 1 [ ], Method 2 [ ]; [ ] Other: (specify)_____
♦ ➲	2-6.7	Thickness	[ ] Nominal [ ] ± Tolerance [ ] µm	[ ] SEMI MF533; [ ] SEMI MF1530; [ ] JIS H 0611; [ ] Other: (specify)_____
➲	2-6.8	Total Thickness Variation (TTV)	[ ] [ ] µm, max	[ ] SEMI MF533; [ ] JIS H 0611; [ ] SEMI MF657 (partial scan); [ ] SEMI MF1530 (full scan); [ ] Other: (specify)_____
➲	2-6.9	Bow	[ ] [ ] µm, max	[ ] SEMI MF534; [ ] JIS H 0611; [ ] Other: (specify)_____
➲	2-6.10	Warp	[ ] [ ] µm, max	[ ] SEMI MF657; [ ] SEMI MF1390; [ ] Other: (specify)_____
	2-6.11	Sori	[ ] [ ] µm, max	[ ] SEMI MF1451; [ ] JEITA EM-3401; [ ] Other: (specify)_____

SUPERSEDED

Documents
Document Sharing Hub
Full document details: SEMI M1-0414

ITEM			SPECIFICATION	MEASUREMENT METHOD
	2-6.12	Flatness, Global	Acronym:[#6] [ ] [ ] [ ] [ ] Value: [ ]µm	[ ] SEMI MF1530; [ ] JEITA EM-3401; [ ] Other: (specify)_____
	2-6.13	Flatness, Site	Acronym:[#6] [ ] [ ] [ ] [ ] Value: Not greater than [ ] µm Site Size ___ mm × ___ mm [ ]% Usable Area_____ [ ] Include partial sites; [ ] Do not include partial sites Offset: x = [ ] mm, y = [ ] mm	[ ] SEMI MF1530; [ ] Other: (specify)_____
	2-6.14	Nanotopography	[ ] as described in SEMI M43 (specify conditions):_____ [ ] ≤_____ nm for 2 mm analysis area [ ] ≤_____ nm for 10 mm analysis area	 SEMI M78 SEMI M78
	2-6.15	Near Edge Geometry	[ ] ESFQR, [ ] ESFQD. or [ ] ESBIR [ ] ZDD [ ] L-ROA, [ ] P-ROA [ ] PSFQR, [ ] PSFQD	SEMI M67 SEMI M68 SEMI M77 SEMI M70
2-7 FRONT SURFACE CHEMISTRY				
	2-7.1	Surface Metal Contamination		
	2-7.1.1	Sodium	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] Other: (specify)_____
	2-7.1.2	Aluminum	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] Other: (specify)_____
	2-7.1.3	Potassium	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.1.4	Chromium	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.1.5	Iron	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.1.6	Nickel	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.1.7	Copper	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____

SUPERSEDED

Documents Document Sharing Hub
Full document details: SEMI M1-0414

	ITEM		SPECIFICATION	MEASUREMENT METHOD
	2-7.1.8	Zinc	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.1.9	Calcium	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.2	Other Surface Metals (List Separately)		
	2-7.2.1	_____	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.2.2	_____	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.2.3	_____	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.2.4	_____	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.2.5	_____	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.2.6	_____	[ ] Not greater than [ ] × $10^{[\,]}$ atoms/cm^2	[ ] ICP/MS; [ ] AAS; [ ] SEMI MF1617 (SIMS); [ ] SEMI M33 (TXRF); [ ] ISO 14706 (TXRF); [ ] Other: (specify)_____
	2-7.3	Surface Organics	[ ] Not greater than [ ]ng/cm^2	[ ] SEMI MF1982; [ ] Other: (specify)_____
2-8 FRONT SURFACE INSPECTION CHARACTERISTICS				
	FOR ALL WAFER DIAMETERS, THE ITEMS LISTED IN THIS SECTION MAY BE SPECIFIED INDIVIDUALLY. ALTERNATIVELY, FOR WAFERS 150 mm OR LESS IN DIAMETER, WHICH CAN BE INSPECTED VISUALLY, THE ITEMS LISTED MAY BE [ ] Specified according to Table 12. If the items are specified according to Table 12, the items marked with the symbol ⮟ need not be entered individually.			
⮟	2-8.1	Scratches – Macro	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
⮟	2-8.1	Scratches – Macro	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____

SUPERSEDED

Documents
Document Sharing Hub
Full document details: SEMI M1-0414

ITEM			SPECIFICATION	MEASUREMENT METHOD
✓	2-8.2	Scratches – Micro	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.3	Pits	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.4	Haze	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.5	Localized Light Scatterers (LLS)	Size: ≥[ ] µm (LSE) Count: ≤[ ] [ ] per wafer; [ ] per cm^2 Size: ≥[ ] µm (LSE) Count: ≤[ ] [ ] per wafer; [ ] per cm^2 Size: ≥[ ] µm (LSE) Count: ≤[ ] [ ] per wafer; [ ] per cm^2 Size: ≥[ ] µm (LSE) Count: ≤[ ] [ ] per wafer; [ ] per cm^2 Size: ≥[ ] µm (LSE) Count: ≤[ ] [ ] per wafer; [ ] per cm^2	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.6	Contamination/Area	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.7	Edge Chips and Indents	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.8	Edge Cracks	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.9	Cracks, Crow's Feet	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.10	Craters	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.11	Dimples	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.12	Grooves	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.13	Mounds	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.14	Orange Peel	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
✓	2-8.15	Saw Marks	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS;[#7] [ ] Other: (specify)_____
	2-8.16	Dopant Striation Rings	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] Other: (specify)_____
	2-8.17	Stains	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] Other: (specify)_____

SUPERSEDED

Documents Document Sharing Hub
Full document details: SEMI M1-0414

ITEM			SPECIFICATION	MEASUREMENT METHOD
	2-8.18	rms Microroughness	[ ] Not greater than [ ] nm, over spectral range from [ ] μm^{-1} to [ ] μm^{-1}	[ ] SEMI MF1048; [ ] AFM; [ ] Other: (specify)_____
2-9 BACK SURFACE INSPECTION CHARACTERISTICS				
	FOR ALL WAFER DIAMETERS, THE ITEMS LISTED IN THIS SECTION MAY BE SPECIFIED INDIVIDUALLY. ALTERNATIVELY, FOR WAFERS 150 mm OR LESS IN DIAMETER, WHICH CAN BE INSPECTED VISUALLY, THE ITEMS LISTED MAY BE [ ] Specified according to Table 12. If the items are specified according to Table 12, the items marked with the symbol ⮟ need not be entered individually.			
⮟	2-9.1	Edge Chips	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] Other: (specify)_____
	2-9.2	Edge Cracks	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] Other: (specify)_____
⮟	2-9.3	Cracks, Crow's Feet	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] Other: (specify)_____
⮟	2-9.4	Contamination/Area	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] Other: (specify)_____
⮟	2-9.5	Saw Marks	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] Other: (specify)_____
	2-9.6	Stains	[ ] None; [ ] Other: (specify)_____	[ ] SEMI MF523; [ ] JIS H 0614; [ ] Other: (specify)_____
	2-9.7	Roughness	[ ] _____ nm rms	[ ] SEMI M40; [ ] Other: (specify)_____
	2-9.8	Brightness (Gloss)	[ ] _____	[ ] ASTM D523; [ ] JIS Z 8741; [ ] Other: (specify)_____
	2-9.9	Scratches – Macro	[ ] None; [ ] Cum Length =[ ] mm	[ ] SEMI MF523; [ ] JIS H 0614; [ ] Other: (specify)_____
	2-9.10	Scratches – Micro	[ ] None; [ ] Cum Length =[ ] mm	[ ] SEMI MF523; [ ] JIS H 0614; [ ] Other: (specify)_____
	2-9.11	Localized Light Scatterers	Size: ≥[ ] µm (LSE) Count: ≤[ ] [ ] per wafer; [ ] per cm^2 Size: ≥[ ] µm (LSE) Count: ≤[ ] [ ] per wafer; [ ] per cm^2	[ ] SEMI MF523; [ ] JIS H 0614; [ ] SSIS[#7]; [ ] Other: (specify)_____
2-10 OTHER (as required)				

#1 The nominal edge exclusion, *EE*, specifies the diameter of the FQA, which is given by the nominal diameter (see Item 2-6.1) minus 2*EE* (see Figure 1). This quantity provides a center referenced property. Although use of edge referenced properties is discouraged, some equipments and procedures are based on edge referenced dimensions. When this occurs, the quality area is not fixed and some part of the fixed quality area may fall outside the evaluated area, which is generally not a desirable situation.

#2 If specified as polished, this term is meant to imply a surface condition and not a particular processing technique. If desired, a quantitative measure of surface finish may optionally be indicated by specifying the rms microroughness over a specified spatial frequency (or wavelength) range. Because a standardized test method has not yet been developed for this metric, both values and test procedures, including sampling plan and detrending procedures, shall be agreed upon between supplier and customer.

#3 Note that in the case of {100} *n*-type wafers, 125 mm or smaller in diameter, with a secondary flat (Categories 1.1, 1.2, 1.5, 1.6, and 1.7) the primary and secondary flats are opposing and the concept of flat diameter does not apply because the diameter perpendicular to the flats does not intersect the wafer circumference.

#4 Thickness reported by parameter based edge profile measurement is typically different from the actual wafer thickness reported by standard dimensional metrology equipment used for flatness and shape. Users are cautioned not to assume the edge profile reported thickness is a valid wafer dimension.

#5 Flatness Acronyms are defined in the Flatness Decision Tree in Appendix 1.

#6 In today's technology, it may be possible to inspect for some of these items using automated surface scanning inspection systems (SSIS). Such systems should be calibrated according to SEMI M53 using polystyrene latex spheres deposited in accordance with SEMI M58. Some indication of the defects separable by such instruments is provided in SEMI M35; however, a standard test procedure has yet to be developed. Application of automated inspection with the use of an SSIS must be agreed upon between supplier and customer.

SUPERSEDED

Documents
Document Sharing Hub
Full document details: SEMI M1-0414

6 Requirements

6.1 *General Characteristics*

6.1.1 The crystal growth method shall be modified Czochralski (Cz), float zone (FZ), or magnetic Czochralski (MCz) as specified on the purchase order. In some cases, the supplier is given the option of selecting Cz or MCz.

6.1.1.1 If the Cz or MCz method is used for crystal growth, it may be permissible to utilize refined (previously melted) polysilicon in the growth charge; when this is the case, the appropriate box should be checked.

6.1.2 The crystal orientation shall be as specified on the purchase order. Usually either (100) or (111) is specified, but (110) is sometimes specified for polished wafers to be used for making SOI wafers. Occasionally, another orientation, such as (311) or (511), is specified.

6.1.3 The conductivity type shall be either *n* or *p*.

6.1.4 The dopant shall be specified to match the conductivity type. In general, boron (B) is used for *p*-type material, while phosphorus (P) is most commonly used for *n*-type material. For some applications, antimony (Sb) or arsenic (As) are used to obtain *n*-type wafers. For high power applications, neutron transmutation doping is often used to obtain high resistivity *n*-type wafers.

6.1.5 The nominal edge exclusion, *EE*, specifies the diameter of the fixed quality area (FQA), which is given by the nominal diameter minus $2 \cdot EE$ (see Figure 1). The fixed quality area is a center-referenced region that is independent in size from the tolerances of both wafer diameter and flat length. For the purposes of defining the FQA, the periphery of a wafer of nominal dimensions at a location with a notch is assumed to follow the circumference of a circle with diameter equal to the nominal wafer diameter.

6.1.5.1 The nominal edge exclusion is usually specified as 2 mm or 3 mm, but some advanced wafer processing technologies are moving in the direction of 1 mm. However, it should be noted that not all processes and metrology can work as close to the wafer edge as implied by the nominal edge exclusion.

6.1.5.2 In addition, it is sometimes necessary to specify additional exclusion zones, such as those for wafer identification marks or wafer holding areas.

6.1.5.3 Although use of edge-referenced properties is discouraged, some equipments and procedures are based on edge referenced dimensions. When this occurs, the quality area is not fixed and some part of the fixed quality area may fall outside the evaluated area, which is generally not a desirable situation.

6.1.6 A co-dopant may be required for polished wafers intended to be processed into annealed wafers. Some co-dopants may also be used in connection with control of oxygen precipitation characteristics even when the wafer is not annealed.

6.1.7 *Wafer Surface Orientation* — The wafer shall conform to the surface orientation as specified in the purchase order.

6.1.7.1 For on-orientation wafers, the angular tolerance from the plane perpendicular to the growth axis shall be specified.

6.1.7.2 For off-orientation wafers, both the misorientation angle from the growth axis and its angular tolerance shall be specified.

6.1.7.2.1 A misorientation angle between 0.2° and 1° (0.6° ± 0.4°) from a (100) plane is frequently used for some epitaxial substrates.

6.1.7.2.2 A misorientation angle of 2.50° or 4° ± 0.5° from a (111) plane is often used for other epitaxial substrates.

6.1.7.3 Orthogonal misorientation is the tilt angle of the normal to a (111) wafer surface toward nearest <110> direction in a plane parallel with the primary flat as indicated in Figure 2.

6.1.7.3.1 The contribution of 5° of orthogonal misorientation to the total off-orientation angle is less than 0.5°.

6.1.7.4 For ion implant applications, the following tolerance issues should be considered:

SUPERSEDED

Documents Document Sharing Hub
Full document details: SEMI M1-0414