SEMI M23.5-0211 (Reapproved 0218)
SPECIFICATION FOR ROUND 100 mm POLISHED MONOCRYSTALLINE INDIUM PHOSPHIDE WAFERS FOR ELECTRONIC AND OPTOELECTRONIC DEVICE APPLICATIONS (V-GROOVE OPTION)

This Standard was technically approved by the Compound Semiconductor Materials Global Technical Committee. This edition was approved for publication by the global Audits and Reviews Subcommittee on June 28, 2017. Available at www.semiviews.org and www.semi.org in February 2018; originally published October 2000; previously published February 2011.

SUPERSEDED

1 Purpose

1.1 This Specification defines properties of round 100 mm monocrystalline indium phosphide wafers, in agreement with presently established industry practice. It uniquely defines those mechanical parameters that do not need, for technical reasons, a choice of different values.

2 Scope

2.1 The parameters defined include the values and tolerances of wafer diameter, thickness and surface orientation.

2.2 The complete specification for this product includes all requirements of SEMI M23, excluding those that are not relevant to this Specification.

NOTICE: SEMI Standards and Safety Guidelines do not purport to address all safety issues associated with their use. It is the responsibility of the users of the Documents to establish appropriate safety and health practices, and determine the applicability of regulatory or other limitations prior to use.

3 Referenced Standards and Documents

3.1 *SEMI Standards and Safety Guidelines*

SEMI M23 — Specification for Polished Monocrystalline Indium Phosphide Wafers

NOTICE: Unless otherwise indicated, all documents cited shall be the latest published versions.

Table 1 Dimension and Tolerance Requirements

Property	*Dimension*	*Tolerance*	*Units*
Diameter[#1]	100.0	±0.5	mm
Thickness, Center Point	625	±25	µm
Primary Flat Length	32.5	±2	mm
Secondary Flat Length	18	±2	mm

#1 The diameter standard means that the dimension is centered to this value.

Table 2 Orientation and Flat Location Requirements

Property	*Requirement*
Primary Flat Orientation	$(01\bar{1})$ ± 0.5°,[#1] under a Phosphorus facet. The primary flat shall be perpendicular to the 'V' etch figure.[#2]
Secondary Flat Orientation	(011), 90° ± 5° counterclockwise from the primary flat.
Surface Orientation[#3]	
A.	{100}[#1] ± 0.5° (see SEMI M23, Figure 2)
B.	{100}[#1] off 2° ± 0.5° toward the (110) plane which is between the primary and secondary flats (see SEMI M23, Figure 4)

Documents Document Sharing Hub
Full document details: SEMI M23.5-0211-0218R

Property	*Requirement*
ORTHOGONAL MISORIENTATION	±5° (see SEMI M23, Figure 5)

#1 See Table 1 in SEMI M23.

#2 See Figure 2 in SEMI M23, which shows the orientation of the V-groove figure relative to crystallographically anisotropic pits (see Note 4).

#3 The frame of reference is the (100) plane of the crystal. It is the wafer normal that is tilted toward the (110) plane of the crystal.

#4 Relating to the etchant used for identifying V-groove and/or dovetail direction, see ¶ 13.1 of SEMI M23: "HBr-$K_2Cr_2O_7$-H_2O etching system for indium phosphide."

NOTICE: SEMI makes no warranties or representations as to the suitability of the Standards and Safety Guidelines set forth herein for any particular application. The determination of the suitability of the Standard or Safety Guideline is solely the responsibility of the user. Users are cautioned to refer to manufacturer's instructions, product labels, product data sheets, and other relevant literature, respecting any materials or equipment mentioned herein. Standards and Safety Guidelines are subject to change without notice.

By publication of this Standard or Safety Guideline, SEMI takes no position respecting the validity of any patent rights or copyrights asserted in connection with any items mentioned in this Standard or Safety Guideline. Users of this Standard or Safety Guideline are expressly advised that determination of any such patent rights or copyrights and the risk of infringement of such rights are entirely their own responsibility.

SUPERSEDED

Copyright by SEMI®, 673 S. Milpitas Blvd., Milpitas, CA 95035. Reproduction of the contents in whole or in part is forbidden without express written consent of SEMI.

Documents Document Sharing Hub

Full document details: SEMI M23.5-0211-0218R