

SEMI M9-0822

SPECIFICATION FOR POLISHED MONOCRYSTALLINE GALLIUM ARSENIDE WAFERS

This Standard was technically approved by the Compound Semiconductor Materials Global Technical Committee. This edition was approved for publication by the global Audits and Reviews Subcommittee on July 21, 2016. Available at www.semiviews.org and www.semi.org in August 2022; originally published in 1986; previously published August 2016.

NOTICE: The designation of SEMI M9 was updated during the 0822 publishing cycle to reflect the revision of SEMI M9.5, and the withdrawal of SEMI M9.1 and SEMI M9.6.

1 Purpose

1.1 This Specification covers two groups of substrate requirements for monocrystalline high-purity gallium arsenide wafers used in semiconductor and electronic device manufacture. Dimensional and crystallographic orientation characteristics and limits on surface defects are the only standardized properties set forth below.

2 Scope

2.1 A complete purchase specification may require that additional physical, electrical, and bulk properties be defined. These properties are listed, together with test methods suitable for determining their magnitude where such procedures are documented.

2.2 This Specification is directed specifically to gallium arsenide wafers with one or both sides polished. Unpolished wafers or wafers with epitaxial films are not covered; however, purchasers of such wafers may find this Specification helpful in defining their requirements.

2.3 The material is single crystal gallium arsenide (GaAs) having a cubic zinc blende structure and having the following properties. The following properties are for use as guidelines:

- *Density* — 5.316 gm/cm³
- *Melting Point* — 1238°C
- *Dielectric Constant* — 13.1
- *Lattice Parameter* — 5.654 Å
- *Energy Gap* — 1.42 eV

2.4 For reference purposes, SI (System International, commonly called metric) units shall be used.

NOTICE: SEMI Standards and Safety Guidelines do not purport to address all safety issues associated with their use. It is the responsibility of the users of the Documents to establish appropriate safety and health practices, and determine the applicability of regulatory or other limitations prior to use.

3 Referenced Standards and Documents

3.1 SEMI Standards and Safety Guidelines

SEMI MF26 — Test Method for Determining the Orientation of a Semiconductive Single Crystal

SEMI MF154 — Guide for Identification of Structures and Contaminants Seen on Specular Silicon Surfaces

SEMI MF523 — Practice for Unaided Visual Inspection of Polished Silicon Wafer Surfaces

SEMI MF533 — Test Method for Thickness and Thickness Variation of Silicon Wafers

SEMI MF671 — Test Method for Measuring Flat Length on Wafers of Silicon and Other Electronic Materials

SEMI MF928 — Test Method for Edge Contour of Circular Semiconductor Wafers and Rigid Disk Substrates

SEMI MF1390 — Test Method for Measuring Bow and Warp on Silicon Wafers by Automated Noncontact Scanning

SEMI MF1530 — Test Method for Measuring Flatness, Thickness, and Total Thickness Variation on Silicon Wafers by Automated Noncontact Scanning

SEMI MF2074 — Guide for Measuring Diameter of Silicon and Other Semiconductor Wafers

3.2 *ANSI® Standards*¹

ANSI/ASQ Z1.4-1993 — Sampling Procedures and Tables for Inspection by Attributes

3.3 *ASTM® Standards*²

ASTM E122 — Standard Practice for Calculating Sample Size to Estimate, with Specified Precision, the Average for a Characteristic of a Lot or Process

ASTM F76 — Standard Test Methods for Measuring Resistivity and Hall Coefficient and Determining Hall Mobility in Single-Crystal Semiconductors

NOTICE: Unless otherwise indicated, all documents cited shall be the latest published versions.

4 Terminology

4.1 Definitions

4.1.1 *bow* — of a semiconductor slice or wafer, a measure of concave or convex deformation of the median surface of a slice or wafer, independent of any thickness variation which may be present. Bow is a bulk property of the test specimen, not a property of an exposed surface. Generally, bow is determined with a test specimen in a free, unclamped condition. Units of bow are generally micrometers or inches.

4.1.2 *dopant* — a chemical element, usually from the second, fourth, or sixth columns of the periodic table for the case of III-V compounds, incorporated in trace amounts in a semiconductor crystal to establish its conductivity type and resistivity.

4.1.3 *edge contouring* — on slices whose edges have been shaped by mechanical and/or chemical means, a description of the profile of the boundary of the slice joining the front and back sides.

4.1.4 *flat diameter* — the linear dimension across the surface of a semiconductor wafer from the center of the flat through the wafer center to the circumference of the wafer on the opposite edge along the diameter perpendicular to the flat. (Refer to Figure 6.)

NOTE 1: The flat diameter may be associated with the primary orientation flat, with a secondary flat, if present, or with any other flat, if present. In such cases, the terms may be modified as primary orientation flat diameter, secondary flat diameter, etc.

4.1.5 *lot* — for the purpose of this Document, (a) all of the wafers of nominally identical size and characteristics contained in a single shipment, or (b) subdivisions of large shipments consisting of wafers as above which have been identified by the supplier as constituting a lot.

4.1.6 *orthogonal misorientation* — in {100} wafers cut intentionally ‘off-orientation’, the angle between the projection of the vector normal to the slice surface onto the {100} plane and the projection on that plane of the nearest direction. (Refer to Figure 5.)

4.1.7 *total thickness variation (TTV)* — the difference between the maximum and minimum thickness values of a slice or wafer encountered during a scan pattern or a series of point requirements. TTV is generally expressed in micrometers or mils (thousandths of an inch).

4.1.8 *warp* — of a semiconductor slice or wafer, the difference between the maximum and minimum distances of the median surface of the slice or wafer from a reference plane, encountered during a scan pattern. Warp is a bulk property of the test specimen, not a property of an exposed surface. Warp is generally expressed in micrometers or mils (thousandths of an inch).

¹ American National Standards Institute, 25 West 43rd Street, New York, NY 10036, USA; Telephone: +1.212.642.4900, Fax: +1.212.398.0023, <http://www.ansi.org>. ANSI trademark is owned by American National Standards Institute.

² ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, USA; Telephone: +1.610.832.9585, Fax: +1.610.832.9555, <http://www.astm.org>. ASTM trademark is owned by ASTM International.

5 Ordering Information

5.1 Purchase orders for gallium arsenide wafers furnished to this specification shall include the following items:

5.1.1 Nominal diameter (refer to applicable SEMI Standard for polished GaAs wafers),

5.1.2 Thickness (refer to applicable SEMI Standard for polished GaAs wafers),

5.1.3 Total Thickness Variation (refer to applicable SEMI Standard for polished GaAs wafers),

5.1.4 Surface orientation (refer to applicable SEMI Standard for polished GaAs wafers). There are two options of flat location for 2 inch and 3 inch diameter polished monocrystalline GaAs wafers for integrated circuit and optoelectronic applications. They are V-Groove (as illustrated in Figures 1 and 3) and Dove-Tail (as illustrated in Figures 2 and 4). These designations describe the shape of groove that can be etched perpendicular to the primary flat.

5.1.5 The following are the options of wafer surface orientation:

A. $(100) \pm 0.5^\circ$ as shown in Figures 1 and 2.

B. For V-Groove option: (100) off 2° toward the (110) plane which is located between the primary and secondary flats as shown in Figure 3. Figure 5 illustrates orthogonal misorientation.

C. For Dove-Tail option: (100) off 2° toward any of the nearest (110) planes as shown in Figure 4. Figure 5 illustrates orthogonal misorientation.

5.1.6 Lot Acceptance Procedures (refer to § 8),

5.1.7 Certification (refer to § 11),

5.1.8 Packing and Marking (refer to § 12).

5.2 *Optional Criteria* — The following items may be specified optionally in addition to those listed above:

5.2.1 Crystal Growth Method,

5.2.2 Etch Pit Density (EPD) of Crystal,

5.2.3 Crystal Growth Perfection,

5.2.4 Impurity Type,

5.2.5 Surface Condition of Wafer,

5.2.6 Edge Contour,

5.2.7 Mobility,

5.2.8 Resistivity,

5.2.9 Carrier Concentration,

5.2.10 Thermal Conversion Characteristics.

6 Dimensions and Permissible Variations

6.1 The material shall conform to the dimensions and dimensional tolerances as specified in the applicable polished gallium arsenide wafer standard.

6.2 If edge contoured wafers are specified on the purchase order, the profile shall conform to the following requirements at all points on the wafer periphery.

6.2.1 When the wafer is aligned with the SEMI Wafer Edge Profile Template (refer to Figure 6) so that the x -axis of the template is coincident with the wafer surface and the y -axis of the template is tangent with the outermost radial portion of the contour, the wafer edge profile must be contained within the clear region of the template (refer to Figure 7 for example of acceptable and unacceptable contours).

6.2.2 No sharp points or protrusions are permitted anywhere on the wafer edge contour.

6.2.3 Cosmetic attributes of the edge contour are not covered by this Specification. They shall be agreed upon between supplier and purchaser.

7 Materials and Manufacture

7.1 The material shall consist of wafers from ingots grown to the material definition specified in the purchase order or contract.

8 Physical Requirements

8.1 The material shall conform to the crystallographic orientation details as specified in the applicable polished gallium arsenide wafer standard.

8.2 The material shall conform to the details specified in the purchase order or contract as follows:

8.2.1 Conduction Type,

8.2.2 Dopant,

8.2.3 Carrier Concentration,

8.2.4 Resistivity,

8.2.5 Thermal Conversion Characteristics,

8.2.6 Etch Pit Density,

8.2.7 Mobility,

8.2.8 Surface Characteristics,

8.2.9 Growth Methods.

9 Sampling

9.1 Unless otherwise specified, ASTM E122 shall be used. When so specified, appropriate sample sizes shall be selected from each lot in accordance with ANSI/ASQ Z1.4. Each quality characteristic shall be assigned an acceptable quality level (AQL) or lot total percent defective (LTPD) value in accordance with ANSI/ASQ Z1.4 definitions for critical, major and minor classifications. If desired and so specified in the contract or order, each of these classifications may alternatively be assigned cumulative AQL or LTPD values. Inspection levels shall be agreed upon between the supplier and the purchaser.

10 Test Methods

10.1 *Diameter* — Determined by SEMI MF2074.

10.2 *Thickness, Center Point* — Determined by SEMI MF533.

NOTE 2: GaAs wafers are extremely fragile. While the mechanical dimensions of a slice can be measured by use of tools such as a micrometer calipers and other conventional techniques, the slice may be damaged physically in ways that are not immediately evident. Special care must therefore be used in the selection and execution of measurement methods.

10.3 *Flat Length* — Determined by SEMI MF671.

10.4 *Flat Orientation* — Determined by etching method identified in the appropriate polished GaAs wafer standard.

10.5 *Bow and Warp* — Determined in accordance with SEMI MF1390.

10.6 *Total Thickness Variation* — Determined by SEMI MF533 or SEMI MF1530.

10.7 *Surface Orientation* — Determined by SEMI MF26.

10.8 *Orthogonal Misorientation* — Determined by a method agreed upon between the supplier and purchaser.

10.9 *Surface Defects and Contamination* — Determined by a method agreed upon between the supplier and purchaser.

10.10 *Mobility* — Determined by ASTM F76.

10.11 *Crystal Perfection* — Determined by a method agreed upon between the supplier and purchaser.