

DEP SPECIFICATION

WET H₂S REQUIREMENTS FOR DOWNSTREAM PRESSURE VESSELS AND PIPING

DEP 30.10.02.17-Gen.

February 2014

ECCN EAR99

DESIGN AND ENGINEERING PRACTICE

DEM1



© 2014 Shell Group of companies

All rights reserved. No part of this document may be reproduced, stored in a retrieval system, published or transmitted, in any form or by any means, without the prior written permission of the copyright owner or Shell Global Solutions International BV.

This document contains information that is classified as EAR99 and, as a consequence, can neither be exported nor re-exported to any country which is under an embargo of the U.S. government pursuant to Part 746 of the Export Administration Regulations (15 C.F.R. Part 746) nor can be made available to any national of such country. In addition, the information in this document cannot be exported nor re-exported to an end-user or for an end-use that is prohibited by Part 744 of the Export Administration Regulations (15 C.F.R. Part 744).

PREFACE

DEP (Design and Engineering Practice) publications reflect the views, at the time of publication, of Shell Global Solutions International B.V. (Shell GSI) and, in some cases, of other Shell Companies.

These views are based on the experience acquired during involvement with the design, construction, operation and maintenance of processing units and facilities. Where deemed appropriate DEPs are based on, or reference international, regional, national and industry standards.

The objective is to set the standard for good design and engineering practice to be applied by Shell companies in oil and gas production, oil refining, gas handling, gasification, chemical processing, or any other such facility, and thereby to help achieve maximum technical and economic benefit from standardization.

The information set forth in these publications is provided to Shell companies for their consideration and decision to implement. This is of particular importance where DEPs may not cover every requirement or diversity of condition at each locality. The system of DEPs is expected to be sufficiently flexible to allow individual Operating Units to adapt the information set forth in DEPs to their own environment and requirements.

When Contractors or Manufacturers/Suppliers use DEPs, they shall be solely responsible for such use, including the quality of their work and the attainment of the required design and engineering standards. In particular, for those requirements not specifically covered, the Principal will typically expect them to follow those design and engineering practices that will achieve at least the same level of integrity as reflected in the DEPs. If in doubt, the Contractor or Manufacturer/Supplier shall, without detracting from his own responsibility, consult the Principal.

The right to obtain and to use DEPs is restricted, and is typically granted by Shell GSI (and in some cases by other Shell Companies) under a Service Agreement or a License Agreement. This right is granted primarily to Shell companies and other companies receiving technical advice and services from Shell GSI or another Shell Company. Consequently, three categories of users of DEPs can be distinguished:

- 1) Operating Units having a Service Agreement with Shell GSI or another Shell Company. The use of DEPs by these Operating Units is subject in all respects to the terms and conditions of the relevant Service Agreement.
- 2) Other parties who are authorised to use DEPs subject to appropriate contractual arrangements (whether as part of a Service Agreement or otherwise).
- 3) Contractors/subcontractors and Manufacturers/Suppliers under a contract with users referred to under 1) or 2) which requires that tenders for projects, materials supplied or - generally - work performed on behalf of the said users comply with the relevant standards.

Subject to any particular terms and conditions as may be set forth in specific agreements with users, Shell GSI disclaims any liability of whatsoever nature for any damage (including injury or death) suffered by any company or person whomsoever as a result of or in connection with the use, application or implementation of any DEP, combination of DEPs or any part thereof, even if it is wholly or partly caused by negligence on the part of Shell GSI or other Shell Company. The benefit of this disclaimer shall inure in all respects to Shell GSI and/or any Shell Company, or companies affiliated to these companies, that may issue DEPs or advise or require the use of DEPs.

Without prejudice to any specific terms in respect of confidentiality under relevant contractual arrangements, DEPs shall not, without the prior written consent of Shell GSI, be disclosed by users to any company or person whomsoever and the DEPs shall be used exclusively for the purpose for which they have been provided to the user. They shall be returned after use, including any copies which shall only be made by users with the express prior written consent of Shell GSI. The copyright of DEPs vests in Shell Group of companies. Users shall arrange for DEPs to be held in safe custody and Shell GSI may at any time require information satisfactory to them in order to ascertain how users implement this requirement.

All administrative queries should be directed to the DEP Administrator in Shell GSI.

TABLE OF CONTENTS

1.	INTRODUCTION	4
1.1	SCOPE.....	4
1.2	DISTRIBUTION, INTENDED USE AND REGULATORY CONSIDERATIONS	4
1.3	DEFINITIONS	5
1.4	CROSS-REFERENCES	5
1.5	SUMMARY OF MAIN CHANGES.....	6
1.6	COMMENTS ON THIS DEP	7
1.7	DUAL UNITS.....	7
1.8	NON NORMATIVE TEXT (COMMENTARY).....	7
2.	REQUIREMENTS FOR CARBON STEEL PRESSURE VESSELS AND PIPING IN WET H₂S SERVICE.....	8
2.1	GENERAL	8
2.2	DEFINITION OF WET H ₂ S SERVICE, SUSCEPTIBILITY TO WET H ₂ S.....	8
2.3	GENERAL REQUIREMENTS.....	10
2.4	PRESSURE VESSELS - REQUIREMENTS FOR SSC POTENTIAL	14
2.5	PRESSURE VESSELS - REQUIREMENTS FOR HIC/SOHIC POTENTIAL	15
2.6	PRESSURE VESSELS - REQUIREMENTS FOR CARBONATE CRACKING POTENTIAL	18
2.7	PIPING – SPECIFIC REQUIREMENTS	19
3.	OTHER METALLIC MATERIALS	21
3.1	INTRODUCTION	21
3.2	ALLOY STEEL, CAST IRON AND DUCTILE IRON	21
3.3	ALLOYED STEELS AND NON FERROUS MATERIAL	21
4.	FABRICATION REQUIREMENTS, BOLTING, PLATING, COATINGS, AND DIFFUSION PROCESSES, SPECIAL COMPONENTS, VALVES, COMPRESSORS AND PUMPS.....	21
4.1	REQUIREMENTS	21
5.	REFERENCES	22

APPENDICES

APPENDIX A	ENHANCED PWHT REQUIREMENTS.....	24
-------------------	--	-----------

1. INTRODUCTION

1.1 SCOPE

This DEP specifies requirements and gives recommendations for the selection and qualification of cracking resistant metallic materials for service in wet H₂S containing environments for downstream based equipment and piping systems. It also specifies the requirements and gives recommendations for the selection and qualification of metallic material exposed to conditions that may lead to carbonate stress corrosion cracking (wet H₂S service is often associated to high pH streams containing carbonate and cyanides).

This DEP addresses all mechanisms of cracking that can be caused by wet H₂S and wet carbonate, including:

- Sulphide stress cracking
- Hydrogen induced cracking and stepwise cracking
- Stress-oriented hydrogen induced cracking
- Carbonate cracking

Excluded from the scope of this DEP are:

- Hydrogen charging cracking in non-wet H₂S environments
- Other alkaline stress corrosion cracking mechanisms (e.g., caustic stress cracking)
- Amine stress cracking
- Loss of material (mass loss) corrosion or localized corrosion

This DEP is also based on NACE MR0103.

This DEP contains mandatory requirements to mitigate process safety risks in accordance with Design Engineering Manual (DEM) 1 – Application of Technical Standards.

This is a revision of the DEP of the same number dated February 2013; see (1.5) regarding the changes.

1.2 DISTRIBUTION, INTENDED USE AND REGULATORY CONSIDERATIONS

Unless otherwise authorised by Shell GSI, the distribution of this DEP is confined to Shell companies and, where necessary, to Contractors and Manufacturers/Suppliers nominated by them. Any authorised access to DEPs does not for that reason constitute an authorization to any documents, data or information to which the DEPs may refer.

This DEP is intended for use in facilities related to oil refining, chemical processing, gasification, distribution and supply/marketing. This DEP may also be applied in other similar facilities.

When DEPs are applied, a Management of Change (MOC) process shall be implemented; this is of particular importance when existing facilities are to be modified.

If national and/or local regulations exist in which some of the requirements could be more stringent than in this DEP, the Contractor shall determine by careful scrutiny which of the requirements are the more stringent and which combination of requirements will be acceptable with regards to the safety, environmental, economic and legal aspects. In all cases the Contractor shall inform the Principal of any deviation from the requirements of this DEP which is considered to be necessary in order to comply with national and/or local regulations. The Principal may then negotiate with the Authorities concerned, the objective being to obtain agreement to follow this DEP as closely as possible.

1.3 DEFINITIONS

1.3.1 General definitions

The **Contractor** is the party that carries out all or part of the design, engineering, procurement, construction, commissioning or management of a project or operation of a facility. The Principal may undertake all or part of the duties of the Contractor.

The **Manufacturer/Supplier** is the party that manufactures or supplies equipment and services to perform the duties specified by the Contractor.

The **Principal** is the party that initiates the project and ultimately pays for it. The Principal may also include an agent or consultant authorised to act for, and on behalf of, the Principal.

The word **shall** indicates a requirement.

The capitalised term **SHALL [PS]** indicates a process safety requirement.

The word **should** indicates a recommendation.

1.3.2 Specific definitions

Term	Definition
ASCC	Alkaline Stress Corrosion Cracking
ASME	American Society of Mechanical Engineers
ASTM	American Society for Testing and Materials
AWS	American Welding Institute
CE	Carbon Equivalent
[CN_{Free}]	Free cyanide in aqueous solution = $\text{HCN}_{\text{aq}} + \text{CN}^-$
FCAW	Flux Core Arc Welding
[H₂S]	Total Sulphide in aqueous solution = $\text{H}_2\text{S}_{\text{aq}} + \text{HS}^- + \text{S}^{2-}$
HAZ	Heat Affected Zone
HB	Hardness Brinell (hardness Brinell with a carbide ball indenter according to ASTM E 10 is noted HBW)
HIC	Hydrogen Induced Cracking
HV	Hardness Vickers
NACE	National Association of Corrosion Engineers
PWHT	Post Weld Heat Treatment
SOHIC	Stress Oriented Hydrogen Induced Cracking
SSC	Sulfide Stress Cracking
TMCP	Thermal/Mechanical Controlled Process
WFMT	Wet Fluorescent Magnetic Test
WPQT	Welding Procedure Qualification Test
PQR	Procedure Qualification Record

1.4 CROSS-REFERENCES

Where cross-references to other parts of this DEP are made, the referenced section number is shown in brackets (). Other documents referenced by this DEP are listed in (5).

1.5 SUMMARY OF MAIN CHANGES

This DEP is a full revision of the DEP of the same number dated February 2013. The following are the main, non-editorial changes.

Section/Clause	Change
1.3.2	Changed WPQT and added PQR
2.2.1, item 1.	Removed "As defined in this DEP" at the end of this section
2.2.3.6, item 2	Added last sentence.
2.3.1	Added item c)
2.3.2.1, item 1	Split this section and added the sentence, now starting with "Also refer to...."
2.3.2.1, item 2	Added NACT condition. Relocated "The acceptability of hot finished material shall be subject to the approval of the Principal".
2.3.2.2.2 item 1	Added "of plate material" in section above Table 2
2.3.2.2.2, Table 2	Notes 1, 2 removed from Table
2.3.2.5	Changed sequence of title/section header, now starting with Fittings
2.3.4.1, item 1	SHALL [PS] changed to shall. Added (required for the PQR)
2.3.4.1, item 2	Complemented WPQT with PQR
2.3.4.3	Modified this section to allow FCAW to be considered.
2.3.6, item 1	Deleted last section "unless otherwise specified by the Principal"
2.5.2.3.1, item 1	Removed SHALL [PS] requirement. It is now "shall"
2.5.2.3.1 Table 5	Added to title (plate material)
2.5.4.2, item 1	reworded.
2.3.6, item 5	changed PWHT temperature
2.7.1, item 1	Added item e; PWHT and hardness testing as per NACE SP0472
2.7.2, item 4	Added; system (so including welded fittings and forgings). Note this also applies for piping systems in High SSC severity categorie (so as per Table 8)
4.1.2	Changed SHALL [PS] into shall
5. References	Changed: - A 106 into A106/A106M. - A105N into A105 - JB 4726, -27 and -30 into JB/T 4726, -27 and -30

1.6 COMMENTS ON THIS DEP

Comments on this DEP may be submitted to the Administrator using one of the following options:

Shell DEPs Online (Users with access to Shell DEPs Online)	Enter the Shell DEPs Online system at https://www.shelldeps.com Select a DEP and then go to the details screen for that DEP. Click on the "Give feedback" link, fill in the online form and submit.
DEP Feedback System (Users with access to Shell Wide Web)	Enter comments directly in the DEP Feedback System which is accessible from the Technical Standards Portal http://swwww.shell.com/standards . Select "Submit DEP Feedback", fill in the online form and submit.
DEP Standard Form (Other users)	Use DEP Standard Form 00.00.05.80-Gen. to record feedback and email the form to the Administrator at standards@shell.com .

Feedback that has been registered in the DEP Feedback System by using one of the above options will be reviewed by the DEP Custodian for potential improvements to the DEP.

1.7 DUAL UNITS

This DEP contains both the International System (SI) units, as well as the corresponding US Customary (USC) units, which are given following the SI units in brackets. When agreed by the Principal, the indicated USC values/units may be used.

1.8 NON NORMATIVE TEXT (COMMENTARY)

Text shown in italic style in this DEP indicates text that is non-normative and is provided as explanation or background information only.

Non-normative text is normally indented slightly to the right of the relevant DEP clause.

2. REQUIREMENTS FOR CARBON STEEL PRESSURE VESSELS AND PIPING IN WET H₂S SERVICE

2.1 GENERAL

1. All carbon steel pressure vessels and piping operating in downstream applications and exposed to process streams that result in potential cracking mechanisms caused by wet H₂S service environment, shall be designed and fabricated in accordance with the requirements of this DEP.

2.2 DEFINITION OF WET H₂S SERVICE, SUSCEPTIBILITY TO WET H₂S

2.2.1 General

"Wet H₂S" service is the term commonly used for refinery and gas plant (downstream) environments containing water and H₂S (plus other corrosives or contaminants). The term "sour service" is also used. The approach to materials selection and testing has been standardised and is described in the applicable sections of this DEP.

1. The materials selection, testing, and PWHT requirements SHALL [PS] be based upon an assessment of the severity of the environment and susceptibility of materials to each potential damage mechanism anticipated or experienced.

2.2.2 Definition – H₂S content, cyanide content, carbonate content

1. The 'H₂S content of water' in the context of this DEP shall be understood to mean the sum of the dissolved (molecular) H₂S, bisulphide ion (HS⁻¹), and sulphide ion (S⁻²) concentrations in the water phase, that result from the presence of H₂S in the process system.
2. The 'cyanide content of water' shall be understood to mean the concentration of 'free' cyanide [CN_{Free}], expressed in ppmw, in the sour water that results from the presence of HCN and CN⁻ in the process stream.
3. The carbonate ion (CO₃⁻²) concentration used to determine the susceptibility to carbonate cracking shall be understood to mean the actual carbonate ion concentration.

2.2.3 Susceptibility to cracking and severity categories

2.2.3.1 General

1. Carbon steel susceptibility to each different cracking mechanism is determined based on the process environment (Water, [H₂S], [CN_{Free}], CO₃⁻²) and material properties (chemistry, mechanical properties, and thermal history).

2.2.3.2 Process severity category

1. Four severity categories are defined for each mechanism for the purposes of setting the material and fabrication requirements. These categories are Negligible, Low, Moderate and High severity.
2. Tables 1a, 1b and 1c shall be used to assess the severity of the process environment as applicable to the type of damage mechanism being considered. When using these tables, the environment being considered should be present during normal operations. Short-term upsets should only be considered if the damage mechanism anticipated or experienced is also likely to occur in the short term (e.g., sulphide stress cracking).
3. Potential mechanisms are not exclusive, i.e., if there is more than one mechanism active, the materials and PWHT requirements may have to be combined to address the severity of more than one environment.
4. If this DEP is used to specify replacement of any in-service equipment (or equipment in a directly comparable service) and the in-service equipment has been damaged by significant hydrogen blistering and/or HIC, the replacement equipment should be assessed as being in a "Moderate" or "High" severity environment. Equipment that has