

UL 13

Power-Limited Circuit Cables

Document Was Downloaded By Rice, Shi SHIMISHENG
For Use By KUANTECH CO LTD
12039 : 7/30/2007 - 3:10 AM

UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL



Documents

Document Sharing Hub

Document Was Downloaded By Rice, Shi SHIMISHENG
For Use By KUANTECH CO LTD
12039 : 7/30/2007 - 3:10 AM

UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL



Documents
Document Sharing Hub

Underwriters Laboratories Inc. (UL)
333 Pfingsten Road
Northbrook, IL 60062-2096

UL Standard for Safety for Power-Limited Circuit Cables, UL 13

Third Edition, Dated July 23, 2007

SUMMARY OF TOPICS

The third edition of the Standard for Power-Limited Circuit Cables, UL 13, has been issued to include the addition of provision for silver plated steel conductors, as well as reflect the latest ANSI approval date and to incorporate formatting and editorial revisions.

The new requirements are substantially in accordance with UL's Proposal(s) on this subject dated May 18, 2007.

As indicated on the title page (page 1), this UL Standard for Safety is an American National Standard. Attention is directed to the note on the title page of this Standard outlining the procedures to be followed to retain the approved text of this ANSI/UL Standard.

The UL Foreword is no longer located within the UL Standard. For information concerning the use and application of the requirements contained in this Standard, the current version of the UL Foreword is located on ULStandardsInfoNet at: <http://ulstandardsinfo.net/ulforeword.html>

The master for this Standard at UL's Northbrook Office is the official document insofar as it relates to a UL service and the compliance of a product with respect to the requirements for that product and service, or if there are questions regarding the accuracy of this Standard.

UL's Standards for Safety are copyrighted by UL. Neither a printed copy of a Standard, nor the distribution diskette for a Standard-on-Diskette and the file for the Standard on the distribution diskette should be altered in any way. All of UL's Standards and all copyrights, ownerships, and rights regarding those Standards shall remain the sole and exclusive property of UL.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form by any means, electronic, mechanical photocopying, recording, or otherwise without prior permission of UL.

Revisions of UL Standards for Safety are issued from time to time. A UL Standard for Safety is current only if it incorporates the most recently adopted revisions.

UL provides this Standard "as is" without warranty of any kind, either expressed or implied, including but not limited to, the implied warranties of merchantability or fitness for any purpose.

In no event will UL be liable for any special, incidental, consequential, indirect or similar damages, including loss of profits, lost savings, loss of data, or any other damages arising out of the use of or the inability to use this Standard, even if UL or an authorized UL representative has been advised of the possibility of such damage. In no event shall UL's liability for any damage ever exceed the price paid for this Standard, regardless of the form of the claim.

UL will attempt to answer support requests concerning electronic versions of its Standards. However, this support service is offered on a reasonable efforts basis only, and UL may not be able to resolve every support request. UL supports the electronic versions of its Standards only if they are used under the conditions and operating systems for which it is intended. UL's support policies may change from time-to-time without notification.

UL reserves the right to change the format, presentation, file types and formats, delivery methods and formats, and the like of both its printed and electronic Standards without prior notice.

Purchasers of the electronic versions of UL's Standards for Safety agree to defend, indemnify, and hold UL harmless from and against any loss, expense, liability, damage, claim, or judgement (including reasonable attorney's fees) resulting from any error or deviation introduced while purchaser is storing an electronic Standard on the purchaser's computer system.

If a single-user version electronic Standard was purchased, one copy of this Standard may be stored on the hard disk of a single personal computer, or on a single LAN file-server or the permanent storage device of a multiple-user computer in such a manner that this Standard may only be accessed by one user at a time and for which there is no possibility of multiple concurrent access.

If a multiple-user version electronic Standard was purchased, one copy of the Standard may be stored on a single LAN file-server, or on the permanent storage device of a multiple-user computer, or on an Intranet server. The number of concurrent users shall not exceed the number of users authorized.

Electronic Standards are intended for on-line use, such as for viewing the requirements of a Standard, conducting a word search, and the like. Only one copy of the Standard may be printed from each single-user version of an electronic Standard. Only one copy of the Standard may be printed for each authorized user of a multiple-user version of an electronic Standard. Because of differences in the computer/software/printer setup used by UL and those of electronic Standards purchasers, the printed copy obtained by a purchaser may not look exactly like the on-line screen view or the printed Standard.

An employee of an organization purchasing a UL Standard can make a copy of the page or pages being viewed for their own fair and/or practical internal use.

The requirements in this Standard are now in effect, except for those paragraphs, sections, tables, figures, and/or other elements of the Standard having future effective dates as indicated in the note following the affected item. The prior text for requirements that have been revised and that have a future effective date are located after the Standard, and are preceded by a "SUPERSEDED REQUIREMENTS" notice.

New product submittals made prior to a specified future effective date will be judged under all of the requirements in this Standard including those requirements with a specified future effective date, unless the applicant specifically requests that the product be judged under the current requirements. However, if the applicant elects this option, it should be noted that compliance with all the requirements in this Standard will be required as a condition of continued Listing and Follow-Up Services after the effective date, and understanding of this should be signified in writing.

Copyright © 2007 Underwriters Laboratories Inc.

This Standard consists of pages dated as shown in the following checklist:

Page	Date
1-80.....	July 23, 2007

UL COPYRIGHTED MATERIAL –

NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL



Documents

Document Sharing Hub

JULY 23, 2007

1



ANSI/UL 13-2007

UL 13

Standard for Power-Limited Circuit Cables

First Edition – November, 1990
Second Edition – February 29, 1996

Third Edition

July 23, 2007

The most recent designation of ANSI/UL 13 as an American National Standard (ANSI) occurred on July 9, 2007. The ANSI approval for this standard does not include the Cover Page, Transmittal Pages, or Title Page.

This ANSI/UL Standard for Safety, which consists of the Third Edition, is under continuous maintenance, whereby each revision is ANSI approved upon publication.

Revisions of this Standard will be made by issuing revised or additional pages bearing their date of issue. A UL Standard is current only if it incorporates the most recently adopted revisions, all of which are itemized on the transmittal notice that accompanies the latest set of revised requirements. Comments or proposals for revisions on any part of the Standard may be submitted to UL at any time. Proposals should be submitted via a Proposal Request in UL's On-Line Collaborative Standards Development System (CSDS) at <http://csds.ul.com>.

COPYRIGHT © 2007 UNDERWRITERS LABORATORIES INC.

Document Was Downloaded By Rice, Shi SHIMISHENG
For Use By KUANTECH CO LTD
12039 : 7/30/2007 - 3:10 AM

UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL



Documents

Document Sharing Hub

No Text on This Page

Document Was Downloaded By Rice, Shi SHIMISHENG
For Use By KUANTECH CO LTD
12039 : 7/30/2007 - 3:10 AM

UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL



Documents

Document Sharing Hub

CONTENTS

INTRODUCTION

1 Scope	5
2 Units of Measurement	7
3 References and Terms	7

CONSTRUCTION

4 Materials	7
5 Conductors	8
6 Metal Coating	11
7 Insulation	12
7.1 Material and application	12
7.2 Properties	12
7.3 Thicknesses	17
8 Coaxial and Optical-Fiber Members	25
9 Individual Covering	26
10 Electromagnetic Shield(s)	27
11 Binder(s)	28
12 Assembly of Multiple-Conductor Cable	28
13 Cable Jacket	30
14 Metal Covering	33
14.1 General	33
14.2 Smooth metal sheath	34
14.3 Welded and corrugated metal sheath	35
14.4 Extruded and corrugated metal sheath	35
14.5 Interlocked armor	35
15 Jacket over Metal Covering	37

PERFORMANCE

16 Continuity Test of Conductors and Shields	38
17 D-C Resistance Test of Copper Conductors	38
18 Cold Bend Test of Insulation	43
19 Cold Bend Test of Complete Cable	44
20 Impact Test for Type PLTC Cable Marked "-ER"	45
21 Crushing Test for Type PLTC Cable Marked "-ER"	46
22 Smoke and Fire Testing of Type CL3P and CL2P Cables	48
23 Fire Testing of Type CL3R and CL2R Cables	48
24 VW-1 (Vertical-Specimen) Flame Test	48
25 Alternative Vertical-Tray Flame Tests on Type CL3, CL2, and PLTC Cables	49
25.1 General	49
25.2 UL Test	49
25.3 FT4/IEEE 1202 test	50
26 Sunlight Resistance Test	50
27 Spark and Dielectric Withstand Test Alternatives for Class 2 Cables	50
28 Spark Test after Insulating for Class 3 and Type PLTC Cables	51
29 Dielectric Voltage-Withstand Test for Class 3 and Type PLTC Cables	51
30 Long Term Insulation-Resistance Test in Water	52
31 Insulation Resistance Test at 60.0°F (15.6°C)	54

32 Test Procedure for Determining the Multiplying-Factor Column for Adjusting Insulation Resistance	57
33 Shrinkback Test on Thermoplastic Insulation from Class 3 and Type PLTC Cables	59
34 Crushing Resistance Test of Insulation	60
35 Crushing Test for Cable Marked for Direct Burial	61
36 Mechanical Water Absorption Test of Insulation in Direct-Burial Cable	62
37 Copper Sulphate Test of Zinc Coating on Steel Strip for and from Interlocked Steel Armor ..	64
38 Tension Test of Interlocked Armor	66
39 Flexibility Test for Cable Having Interlocked Armor or a Smooth or Corrugated Metal Sheath ..	69
40 Tests for Oil Resistance	70
41 Circuit Integrity	70
42 Durability Test of Ink Printing	70
43 Limited Combustible	71

MARKINGS

44 Intervals	71
45 Coding	72
46 Information on or in the Cable	72
47 Information on the Tag, Reel, or Carton	76
48 Multiple Markings	78
49 Date of Manufacture	79

Document Was Downloaded By Rice, Shi SHIMISHENG
 For Use By KUANTECH CO LTD
 12039 : 7/30/2007 - 3:10 AM
 UL COPYRIGHTED MATERIAL –

NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
 DISTRIBUTION WITHOUT PERMISSION FROM UL



Documents

Document Sharing Hub

INTRODUCTION

1 Scope

1.1 These requirements cover 60 – 250°C (140 – 482°F) single- and multiple-conductor power-limited circuit cables for use as fixed wiring within buildings (some are also marked for direct burial) principally for Class 3 and Class 2 circuits as described in Article 725 and other applicable parts of the National Electrical Code (NEC). Cables covered by these requirements are:

- a) Types CL3P and CL2P (plenum cables),
- b) Types CL3R and CL2R (riser cables),
- c) Types CL3 and CL2 (commercial cables for other than plenum, riser, or tray uses),
- d) Types CL3X and CL2X (cables for limited use), and
- e) Type PLTC (cable for non-plenum and non-riser Class 3 and Class 2 circuits in general and in trays).

1.2 Cables for Class 3 circuits are rated for 300 volts but are not so marked. Cables for Class 2 circuits do not have a voltage rating. See 46.1 (h).

1.3 A cable that contains one or more electromagnetic shields may be surface marked or have a marker tape to indicate that it is "shielded ". A cable that contains one or more optical-fiber members has "-OF " supplementing the type letters and is marked in accordance with 47.1 (d). A cable may consist of or contain one or more coaxial members.

1.4 The overall jacket on a cable that has "sun res " or "sunlight resistant " in a surface marking or on a marker tape complies with a 720-h sunlight-resistance test. The overall jacket on all Type PLTC cable is required to comply with this 720-h test, so Type PLTC cable may be marked "sun res " or "sunlight resistant " but is not required to be so marked.

1.5 A cable that has "dir bur ", "direct burial ", or "for direct burial " in a surface marking or on a marker tape complies with a 1000-lbf crushing test. Direct-burial cable with wire armor, a metal braid, interlocked metal armor, or a smooth or corrugated metal sheath has a jacket over the metal covering.

1.6 Smoke and fire considerations are as follows for the cables covered in these requirements:

- a) TYPE CL3P and CL2P CABLES – Cables that are intended for installation in accordance with section 725.82 (A) of the National Electrical Code, ANSI/NFPA 70, in a duct, plenum, or other space used to transport environmental air without the cables being enclosed in a raceway in that space are to be tested for smoke and flame characteristics in accordance with the National Fire Protection Association Standard Method of Test for Flame Travel and Smoke of Wires and Cables for Use in Air-Handling Spaces, ANSI/NFPA 262. A cable that complies exhibits a maximum flame-propagation distance that is not greater than 5 ft, 0 in or 152 cm, a peak optical density of smoke produced of 0.50 or less (32 percent light transmission), and an average optical density of smoke produced of 0.15 or less.
- b) TYPE CL3R and CL2R CABLES – Cables that are intended for use in vertical runs in a shaft, or for installations in which the cables penetrate more than one floor, as specified in Section 725.82 (B) of the National Electrical Code, ANSI/NFPA 70, are to be tested for flame-propagation characteristics in accordance with the Standard for Test for Flame-Propagation

UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL



Documents

Document Sharing Hub

Height of Electrical and Optical-Fiber Cables Installed Vertically in Shafts, UL 1666. A cable that complies has a flame-propagation height less than 12 ft, 0 in or 366 cm and temperatures are 850.0°F (454.4°C) or less at a height of 12 ft, 0 in or 366 cm.

c) TYPE CL3 and CL2 CABLES – Type CL3 and CL2 general-use cables comply with a 70,000 Btu/h (20.5 kW) vertical-tray flame test. The cable manufacturer chooses one of the following tests:

1) THE UL TEST REFERENCED IN 25.2.1 – This paragraph applies the test method described as the UL Flame Exposure (smoke measurements are not applicable) in the Standard for Vertical-Tray Fire-Propagation and Smoke-Release Test for Electrical and Optical-Fiber Cables, UL 1685, to cable that is surface marked or designated by a marker tape as "CL3 " or "CL2 ". For compliance, this test damages less than 8 feet (244 cm) of cable.

2) THE FT4/IEEE 1202 TEST REFERENCED IN 25.3.1 – This paragraph applies the test method described as the FT4/IEEE 1202 Type of Flame Exposure (smoke measurements are not applicable) in the Standard for Vertical-Tray Fire-Propagation and Smoke-Release Test for Electrical and Optical-Fiber Cables, UL 1685. This test differs from the UL test in loading (more cables are used, with small cables bundled, and the spacing between cables is limited), burner angle, and failure criterion. For compliance, this test damages less than 150 cm (59 in) of cable. A cable that complies either is not marked or it bears the designation "FT4/IEEE 1202" or "FT4 " legible on or through the outer surface or on a marker tape [see marking in 46.1 (i)].

d) TYPE CL3X and CL2X CABLES – Type CL3X and CL2X cables comply with the VW-1 vertical-specimen flame test. The cable is not marked "VW-1 ".

e) TYPE PLTC CABLE – Type PLTC tray cable complies with a 70,000 Btu/h (20.5 kW) vertical-tray flame test. The cable manufacturer chooses the test in (c)(1) or (c)(2). This test is applied to cable that is surface marked or designated by a marker tape as "PLTC ".

1.7 The overall jacket on Type PLTC cable is a "gas/vapor-tight continuous sheath" in the sense discussed in sections 501.15 (D) and 501.15 (E) of the National Electrical Code, ANSI/NFPA 70. Cables that are surface marked "-ER" are for use as exposed runs between a cable tray and utilization equipment where the cables are continuously supported and protected against physical damage using mechanical protection such as struts, angles, or channel.

1.8 With certain exceptions, as noted in 1.9, Type CL3X and CL2X cables are required by the NEC to be used with protection such as raceway. The Type CL3 and CL2 and other cables covered in these requirements that are not required by the NEC to be used in raceway are capable of use without the physical protection of raceway but may be pulled into conduit or installed in other raceway.

1.9 Type CL3X and CL2X cables are limited by the NEC to use in unconcealed spaces in which the exposed length of cable does not exceed 10 ft or 3.05 m, and in raceway. These NEC limitations do not apply to Type CL3X and CL2X cables that are smaller in diameter than 0.25 in or 6.35 mm and are used in a one-, two-, or multi-family dwelling.

UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL



Documents

Document Sharing Hub

1.10 These requirements do not cover cables that contain conductors for electric-light, power, or Class 1 circuits. These requirements do not cover optical-fiber cables that do not contain any electrical conductors. These requirements do not cover communication cables (see the Standard for Communications Cables, UL 444) or cables for power-limited fire-alarm circuits (see the Standard for Cables for Power-Limited Fire-Alarm Circuits, UL 1424). These requirements do not cover vault-lacing cable, which is for use in concrete as part of a theft-alarm system.

1.11 These requirements do not cover the optical or other performance of any optical-fiber member or group of such members. See 8.3.

2 Units of Measurement

2.1 In addition to being stated in the inch/pound units that are customary in the USA, each of the requirements is also stated in units that make the requirement conveniently usable in countries employing the various metric systems (practical SI and customary). Equivalent – although not necessarily exactly identical – results are to be expected from applying a requirement in USA or metric terms. Equipment calibrated in metric units is to be used when a requirement is applied in metric terms.

3 References and Terms

3.1 Wherever the designation "UL 1581 " is used in this wire standard, reference is to be made to the designated part(s) of the Reference Standard for Electrical Wires, Cables, and Flexible Cords, UL 1581.

3.2 Any undated reference to a code or standard appearing in the requirements of this standard shall be interpreted as referring to the latest edition of that code or standard.

3.3 Nylon designates a thermoplastic material whose characteristic constituent is a polyamide formed by the condensation of dibasic organic acids and diamines. Nylon used as a covering is unfilled and without reinforcement but may contain stabilizers, flame retardants, pigment, and/or other additives.

3.4 PBT designates a thermoplastic polyester material whose characteristic constituent is polybutylene terephthalate. PBT used as a covering is unfilled and without reinforcement but may contain flame retardants, pigment, and/or other additives.

CONSTRUCTION

4 Materials

4.1 Each material used in a cable shall be compatible with all of the other materials used in the cable.

4.2 Power-limited circuit cable shall comply in all respects with the applicable requirements for construction details, test performance, and markings.

5 Conductors

5.1 Conductors shall comply in size (see 5.2) and material with Table 5.1. The nominal diameters of solid and stranded conductors that are indicated in Table 5.2 are to be used in calculating the dimensions required for various parts of the cable when using Tables 13.1, 13.2, 13.3, 14.1, 14.2, 15.1, and 18.1. The length of lay of the wires (strands) of a stranded conductor shall not exceed 20 times the calculated diameter over the assembled conductor for 19 – 6 AWG conductors and shall not exceed 30 times the calculated diameter over the assembled conductor for 30 – 20 AWG conductors.

Table 5.1
Conductors

Cable types	AWG sizes of thermocouple-extension wire ^a	AWG sizes of soft-annealed copper conductors ^b	AWG sizes of solid or stranded copper-clad steel conductors	AWG sizes of solid or stranded silver plated steel conductors
CL3P, CL3R, CL3, CL3X	24 – 12	24 ^c , 23 – 12, 11 ^f , 10 ^f	28 ^{c, f} , (27 – 10) ^f	None
CL2P, CL2R, CL2, CL2X	24 – 12	30 ^{c, d} , (29 – 25) ^d , 24 – 12, (11 – 6) ^e	28 ^c , (27 – 6) ^e	30 ^{c, d, e} , (29 – 25) ^{d, e} , (24 – 12) ^e
PLTC	22 – 12	22 – 12	None	None

^a The sizes of thermocouple-extension wire are nominal and are intended only for use in the cable marking that is specified in 46.1 (b)(5) or (b)(6). The conductor in a thermocouple-extension wire is not required to comply with a diameter or resistance value.

^b A copper conductor shall be round and shall be solid or stranded. A stranded conductor shall consist of round strands with a right- or left-hand direction of lay. Seven strands, concentric, is the stranding assumed in these requirements, however, individual strand diameter, any mix or different strand diameters, the number of strands, and the stranding type are not specified. A solid copper conductor and the individual wires (strands) of a stranded copper conductor shall comply with ASTM B 3. See 6.1 – 6.4 (metal coating) and 17.1 – 17.9 (d-c resistance).

^c Where conductors are smaller than the minimum size indicated for copper or copper-clad steel, the cable is to be shown by test to have a breaking strength of at least 25 lbf or 111 N or 11.3 kgf.

^d 25 AWG and smaller copper conductors are only for either of the following:

a) In a cable that has a breaking strength shown by test to be at least 25.0 lbf or 111 N or 11.3 kgf. 30 – 25 AWG copper conductors are acceptable without the strength test in a cable that contains four or more conductors.

b) As the central conductor in a coaxial member.

^e For Class 2: 11 – 6 AWG copper conductors are only for multiple-conductor jacketed cables (integral or nonintegral) employing the surface marking AUDIO ONLY or as the central conductor in a coaxial member. 6 AWG and smaller copper-clad steel conductors are only for the central conductor in a coaxial member. Copper-clad steel conductors shall have 21 percent or higher conductivity in accordance with ASTM B 869. Silver plated steel conductors shall have 12 percent or higher conductivity.

^f For Class 3: 11 and 10 AWG copper conductors and 10 AWG and smaller copper-clad steel conductors are only for the central conductor in a coaxial member. Copper-clad steel conductors shall have 21 percent or higher conductivity in accordance with ASTM B 869.

Table 5.2
Conductor diameters

AWG size of conductor	Solid conductor				Nominal diameter of stranded conductor	
	Nominal diameter		Minimum diameter			
	inch	mm	inch	mm	inch	mm
30	0.0100	0.254	0.0099	0.251	0.0113	0.287
29	0.0113	0.287	0.0112	0.284	0.0128	0.325
28	0.0126	0.320	0.0125	0.318	0.0143	0.363
27	0.0142	0.361	0.0141	0.358	0.0161	0.409
26	0.0159	0.404	0.0151 ^b	0.384 ^b	0.0180	0.457
25	0.0179	0.455	0.0170 ^b	0.432 ^b	0.0203	0.516
24	0.0201	0.511	0.0191 ^b	0.485 ^b	0.0228	0.579
23	0.0226	0.574	0.0215 ^b	0.546 ^a	0.0256	0.650
22 PLTC	0.0253	0.643	0.0250 ^a	0.635 ^a	0.0287	0.729
Others			0.0240 ^b	0.610 ^b		
21 PLTC	0.0285	0.724	0.0282 ^a	0.717 ^a	0.0323	0.820
Others			0.0271 ^b	0.688 ^b		
20 PLTC	0.0320	0.813	0.0317 ^a	0.805 ^a	0.0362	0.919
Others			0.0304 ^b	0.772 ^b		
19 PLTC	0.0359	0.912	0.0355 ^a	0.902 ^a	0.0407	1.03
Others			0.0341 ^b	0.866 ^b		
18	0.0403	1.020	0.0399	1.013	0.0456	1.16
17	0.0453	1.150	0.0448	1.138	0.0513	1.30
16	0.0508	1.290	0.0503	1.278	0.0576	1.46
15	0.0571	1.450	0.0565	1.435	0.0647	1.64
14	0.0641	1.630	0.0635	1.613	0.0727	1.85
13	0.0720	1.83	0.0713	1.81	0.0816	2.07
12	0.0808	2.05	0.0800	2.03	0.0915	2.32
11	0.0907	2.30	0.0900	2.28	0.103	2.62
10	0.1019	2.59	0.101	2.56	0.116	2.95
9	0.1144	2.906	0.113	2.88	0.130	3.30
8	0.1285	3.264	0.127	3.23	0.146	3.71
7	0.1443	3.665	0.143	3.63	0.164	4.17
6	0.1620	4.115	0.160	4.07	0.184	4.67

^a Minimum diameter (0.99 x nominal) of a solid conductor of this size in a Type PLTC cable. See corresponding resistance (1.02 x nominal) in Table 17.1.

^b Minimum diameter (0.95 x nominal) of a solid conductor of this size in all cables other than Type PLTC. See corresponding resistance (1.1 x nominal) in Table 17.1.

5.2 All solid and stranded conductors are to be identified in the cable, tag, reel, or carton size markings as a particular AWG size. The size of a solid conductor shall be verified either by determination of the d-c resistance or, as described in 5.6, by determination of the diameter. The size of a stranded conductor shall be verified either by determination of the d-c resistance or by determination of the cross-sectional area as described in 5.6. Determination of the conductor size by measurement of the d-c resistance is to be as described in D-C Resistance Test of Copper Conductors, Section 17, and is the referee method in all cases.

5.3 Each conductor shall be continuous throughout the entire length of the finished cable – see test in 16.1 and 16.2.

5.4 A joint in a solid conductor or in one of the individual wires of a stranded conductor shall be made in a workmanlike manner, shall be smooth, and shall not have any sharp projections. A joint in a stranded conductor is to be made by separately joining each individual wire, or is to be made by machine brazing or welding of the conductor as a whole provided that the resulting solid section of the stranded conductor is not longer than 1/2 in or 13 mm, there are no sharp points, and the distance between brazes or welds in a single conductor does not average less than 3000 ft or 915 m in any reel length of insulated single conductor. A joint made before insulation is applied to a conductor shall not increase the diameter of the solid conductor or individual wire (strand). A joint made after insulating shall not increase the diameter of the solid conductor or individual wire (strand) by more than 20 percent. Joints made after insulating shall be made prior to further processing and shall be insulated by heat-shrinkable tubing or by applying the original or investigated comparable insulation by means of a bonded patch or molding, and shall comply with the requirements in this Standard. A jacket that is damaged to the point that the underlying assembly is exposed or that is opened for the purpose of repairing a conductor either:

- a) Shall be stripped and replaced in its entirety, or
- b) A second, duplicate jacket shall be applied over the first for the entire length of the cable.

The total jacket thickness shall not exceed any limitation determined for a particular cable in an applicable flame or smoke-and-flame test or other test specified in this Standard.

5.5 Any section of conductor that includes a factory joint shall have a tensile strength that is not less than 85 percent of the tensile strength of an adjacent section of the conductor without a joint.

5.6 In place of complying with the d-c resistance requirement in Section 17, at the cable manufacturer's option, a copper conductor shall instead comply with the following requirement:

a) **SOLID CONDUCTOR** – The diameter of a solid conductor shall not be smaller than the minimum diameter indicated for the size in Table 5.2 (see 5.2) when the diameter of the conductor is determined from measurements as follows:

- 1) Measurements of the diameter of a solid copper conductor, a copper-clad steel conductor or silver plated steel conductor are to be made by optical means or by means of a machinist's micrometer caliper having flat surfaces both on the anvil and on the end of the spindle. In either case, the equipment is to be calibrated to read directly to at least 0.001 in or 0.01 mm, with each division of a width that facilitates estimation of each measurement to 0.0001 in or 0.001 mm. The maximum and minimum diameters at a given point on the solid conductor are each to be recorded to the nearest 0.0001 in or 0.001 mm, added together, and divided by 2 without any rounding off of the sum or resulting average.

UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM



Documents

Document Sharing Hub

2) Each minimum diameter indicated in Table 5.2 is an absolute minimum. The unrounded average of the two diameter readings is therefore to be compared directly with the minimum in the table for the purpose of determining whether the solid conductor does or does not comply with the diameter requirement.

b) **STRANDED CONDUCTOR** – The cross-sectional area of a stranded copper conductor, copper-clad steel conductor or silver plated steel conductor of a standard (see 5.2) AWG size and having only round strands shall not be smaller than the minimum area indicated for the size in the 0.98 × nominal column in Table 20.1 of UL 1581. The cross-sectional area of the stranded conductor is to be determined as the sum of the areas of its component round strands. However, when the sum of the strand areas does not comply, the result of a determination of the conductor area by the weight method specified in 210.1 – 210.4 of UL 1581 is to be taken as conclusive.

6 Metal Coating

6.1 If the insulation adjacent to the copper conductor is of a material that corrodes unprotected copper in the test described in paragraph 500.1 of UL 1581, the conductor shall be covered with a coating of tin complying with ASTM B 33, of a tin/lead alloy complying with ASTM B 189, of nickel complying with ASTM B 355), of silver complying with ASTM B 298, or of another metal or alloy (evaluation required).

6.2 For silver plated steel conductors of a specific diameter, the plating thickness of silver or combined silver over nickel plating shall not be less than that specified for silver coating thickness of 1.25 percent as defined in ASTM B 501 – 93, Standard Specification for Silver-Coated, Copper-Clad Steel Wire for Electronic Application, Table 1.

6.3 It is acceptable to metal-coat a conductor or the individual wires (strands) of a stranded conductor on which a coating is not needed for corrosion protection.

6.4 The maximum temperature rating of the cable is not specified relative to the diameter of copper wires used in the serving, wrap, or braid shielding described in accordance with 10.2 (c). Otherwise, copper strands and solid copper conductors shall not be used in a cable with a temperature rating higher than indicated in Table 6.1.

Table 6.1
Maximum temperature rating of cable relative to diameter and coating of solid copper conductor or of copper conductor strands

Metal coating of copper strands or of solid copper conductor	Diameter of each strand or of the solid conductor	
	Smaller than 0.015 in or 0.38 mm	At least 0.015 in or 0.38 mm
Uncoated or coated with tin or a tin/lead alloy	150°C (302°F)	200°C (392°F)
Coated with silver	200°C (392°F)	200°C (392°F)
Coated with nickel	over 200°C (392°F)	over 200°C (392°F)

7 Insulation

7.1 Material and application

7.1.1 Each conductor shall be insulated for its entire length with one or more of the insulation materials indicated in Table 7.1 or referenced in note ^a to Table 7.1. The insulation shall be solid or, in the cases indicated in the second column of Table 7.1, may be expanded (foamed). In any case, a solid dielectric skin (a thin, solid, extruded layer that may or may not be separable) of the same or other material from Table 7.1 may be applied over the solid insulation or over the foam. The material insulation in an air-gap coaxial member shall consist of a solid tube over a solid spacer (thread) that has a nominally circular cross section and is applied to the conductor helically in a continuous length (length of lay is not specified). Otherwise, the insulation shall be applied directly to the conductor, shall have a circular cross section, and shall fit tightly to the conductor but shall not adhere excessively (no test). The insulation shall be uniform and shall not have any defects (bubbles, open spots, rips, tears, cuts, or foreign material) that are visible with normal or corrected vision without magnification.

7.1.2 Either of the following materials that the manufacturer wishes to use as insulation or a jacket shall be evaluated for the requested temperature rating as described in Long-Term Aging, Section 481 of UL 1581:

- a) Material generically different from any insulation or jacket material that is named in Table 7.1 for the construction (new material).
- b) Material that is named in Table 7.1 yet does not comply with the short-term tests specified for the material in Specific Materials, Section 50 of UL 1581.

The temperature rating of materials (a) and (b) shall be the temperature rating for the cable determined as specified in 13.1. The thicknesses of insulation and/or jacket using materials (a) and/or (b) shall be as required for the specific cable type. Investigation of the electrical, mechanical, and physical characteristics of the cable using material (a) and/or (b) shall show the material(s) to be comparable in performance to an insulation or jacket material named in Table 7.1 for the required temperature rating. The investigation shall include tests such as crushing, impact, abrasion, deformation, heat shock, insulation resistance, and dielectric voltage-withstand.

7.2 Properties

7.2.1 Unaged and heat-aged requirements for insulation on conductors rated 60°C in all cables except Type PLTC

7.2.1.1 Specimens of unaged solid single-layer insulation removed from finished insulated conductors shall have a minimum tensile strength of 1200 lbf/in² or 8.27 MN/m² or 827 N/cm² or 0.844 kgf/mm² and a minimum elongation of 100 percent when tested in accordance with the test procedures in UL 1581. There shall be no cracks on either the inside or the outside surface of solid, foamed, or multi-layered insulation after flexing around a mandrel after air-oven aging. Specimens of the insulated conductors approximately 12 in or 300 mm long shall be placed in a circulating air oven conforming to ASTM D 5423 (Type II ovens) and D 5374 and maintained at a temperature of 100 ±2°C (212 ±3.6°F) for 7 d (168 h) or 121 ±2°C (249.8 ±3.6°F) for 48 h at the manufacturer's option. After removal from the oven, the specimens shall be allowed to cool to room temperature and then wound tightly, for six close turns, around a mandrel having a diameter no greater than that of the insulated conductor under test. The insulation shall be examined for cracks using a lens having magnification of 5X. The insulated conductor shall then be straightened, one side of the tube of insulation sliced off with a knife or razor-blade, and the conductor removed to permit examination of the inner surface of the insulation.

7.2.2 Unaged and heat-aged insulation requirements for all cables to be rated 75°C or greater, and PLTC to be rated 60°C or greater

7.2.2.1 Specimens of solid single-layered insulations removed from finished insulated conductors shall comply with the values of unaged elongation and tensile strength shown in the applicable physical-properties table for the material referenced in Table 7.1 when tested in accordance with the test procedures in UL 1581. Specimens of solid single-layered insulations except PVDF rated 125°C shall comply with the values of aged retention of elongation and tensile strength shown in the applicable physical-properties table for the material referenced in Table 7.1 when tested in accordance with the test procedures in UL 1581. PVDF rated 125°C, foamed, and multi-layered insulations shall comply with 7.2.2.2.

7.2.2.2 Specimens of PVDF rated 125°C, foamed, or multiple-layered insulations approximately 300 mm (12 in) long shall be placed in a circulating-air oven conforming to ASTM D 5423 (Type II ovens) and D 5374 and aged for the appropriate time and temperature shown in Table 7.1 in UL 13 and Table 47.1 in UL 1581 for the insulation adjacent to the conductor. When the insulation is foamed, the aging shall be as specified for the solid insulation. After removal from the oven, the specimens shall be allowed to cool to room temperature and then wound tightly, for six close turns, around a mandrel having a diameter no greater than that of the insulated conductor under test. The insulation shall be examined for cracks using a lens having magnification of 5X. The insulated conductor shall then be straightened, one side of the tube of insulation sliced off with a knife or razor-blade, and the conductor removed to permit examination of the inner surface of the insulation. There shall be no cracks on either the inside or the outside surface of the insulation.

Table 7.1
Index to insulations and jackets

Material(s) ^a	Temperature Rating of Insulation	Temperature Rating of Jacket	Applicable table of physical properties in UL 1581 (see 7.2.1.1 and 7.2.1.2)
CP	90°C (194°F) solid	90°C (194°F) solid	50.1
	75°C (167°F) solid	75°C (167°F) solid	50.1
Thermoplastic CPE	—	90°C (194°F) solid	50.28
Thermoset CPE	—	90°C (194°F) solid	50.29
	—	75°C (167°F) solid	50.30
ECTFE ETFE	150°C (302°F) solid	150°C (302°F) solid	50.83
	foamed	—	—
FEP	200°C (392°F) ^b solid	200°C (392°F) solid	50.70
	foamed	—	—
NBR/PVC	—	90°C (194°F) solid	50.83

Table 7.1 Continued

Material(s) ^a	Temperature Rating of Insulation	Temperature Rating of Jacket	Applicable table of physical properties in UL 1581 (see 7.2.1.1 and 7.2.1.2)
	—	75°C (167°F) solid	50.80
Neoprene	—	90°C (194°F) solid	50.124
	—	75°C (167°F) solid	50.123
HDFRPE LDFRPE	75°C (167°F) solid foamed	75°C (167°F) solid —	50.133 —
HDPE	75°C (167°F) solid foamed	— —	50.136 —
LDPE	75°C (167°F) solid foamed	— —	50.136 —
PFA, MFA	200°C (392°F) ^b solid foamed	200°C (392°F) solid —	50.137 —
	250°C (482°F)	250°C (482°F)	50.137
Polypropylene: PP, FRPP	75°C (167°F) solid foamed	— — —	50.139 —
		75°C (167°F) — —	50.139 —
PTFE TFE	250°C (482°F) ^b solid foamed	250°C (482°F) solid —	50.219 —
PVC	105°C (221°F) solid	105°C (221°F) solid	50.182
	90°C (194°F) solid	90°C (194°F) solid	50.182
	75°C (167°F) solid	75°C (167°F) solid	50.182
		60°C (140°F) solid	50.182
SRPVC (semirigid PVC)	105°C (221°F)		

UL COPYRIGHTED MATERIAL -

NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL

Table 7.1 Continued on Next Page



Documents

Document Sharing Hub

Table 7.1 Continued

Material(s) ^a	Temperature Rating of Insulation	Temperature Rating of Jacket	Applicable table of physical properties in UL 1581 (see 7.2.1.1 and 7.2.1.2)
	solid	—	50.183
	90°C (194°F) solid	—	50.183
	75°C (167°F) solid	75°C (167°F) solid	50.183
		60°C (140°F) solid	50.183
PVDF and PVDF copolymer	150°C (302°F) solid foamed	150°C (302°F) solid —	50.185 —
	125°C (257°F) solid foamed	125°C (257°F) solid —	50.185 —
Silicone rubber	200°C (392°F) ^b solid 150°C (302°F) solid		50.210 50.210
TPE	105°C (221°F) solid	105°C (221°F) solid	50.223
	90°C (194°F) solid	90°C (194°F) solid	50.224
XL: XLPE XLPVC XLEVA blends of these	105°C (221°F) solid 90°C (194°F) solid	105°C (221°F) solid 90°C (194°F) solid	50.245 50.237
	75°C (167°F) solid foamed	75°C (167°F) solid —	50.241 —
XLPO	105°C (221°F) solid	105°C (221°F) solid	50.233

^a See 7.1.2 for the long-term evaluation of an insulation or jacket material not named in the first column or not complying with the short-term tests referenced in the last column.

^b 150°C (302°F) is the limit for the cable temperature rating [see 13.1 (b)] where a solid conductor or conductor strands are used that are smaller in diameter than 0.015 in or 0.38 mm and are uncoated or are coated with tin or a tin/lead alloy. The indicated rating higher than 150°C (302°F) applies where, regardless of diameter the strands are coated with silver [200°C (392°F)] or nickel [250°C (482°F)]. A 200°C or 392°F rating applies where silicone rubber is used on a small-diameter solid conductor or small-diameter conductor strands that are coated with silver) – See 6.4 and Table 6.1.

7.2.3 Unaged and heat-aged jacket requirements for all cables, except PLTC, to be rated 60°C

7.2.3.1 Specimens of jacket removed from completed cable shall comply with the unaged values shown in the applicable physical-properties table for the material referenced in Table 7.1 when tested in accordance with the test procedures in UL 1581. For all jacketed types, except PLTC, jacket material removed from a length of finished cable shall comply with the aging test as follows: 7 d (168 hr) 100 ±2°C (212 ±3.6°F), and at least 50 percent retention of the unaged elongation and 75 percent retention of unaged tensile strength when tested in accordance with the test procedures in UL 1581 with the following modifications:

- a) Jackets thinner than 0.46 mm (0.018 in) average, 0.36 mm (0.014 in) minimum at any point shall be buffed only to remove imperfections, not natural indentations.
- b) Cables with an overall diameter not greater than 5.1 mm (0.200 in) may have their jackets tested as tubular specimens rather than as die-cut specimens. Tubular specimens shall not be used for larger cables.

7.2.4 Unaged and heat-aged jacket requirements for all cables to be rated 75°C or greater, and PLTC to be rated 60°C or greater

7.2.4.1 Specimens of jacket removed from completed cable shall comply with the unaged values shown in the applicable physical-properties table for the material referenced in Table 7.1 when tested in accordance with the test procedures in UL 1581 with the modifications shown in 7.2.3.1. Specimens shall be aged for the length of time and at the temperature shown in the applicable physical-properties table for the material referenced in Table 7.1 and tested in accordance with the relevant procedures in UL 1581. Minimum retention of elongation and tensile strength requirements in the applicable physical-properties table referenced in Table 7.1 shall be used to determine compliance. This shall apply to all jacket materials except PVDF and PVDF copolymers rated 125°C. For these materials, the flexibility test described in 7.2.4.2 shall be used.

7.2.4.2 Aged specimens of PVDF and PVDF copolymer jackets rated 125°C in place on the cable shall not show any cracks on either the inside or outside surface after specimens are wound onto a cylindrical mandrel of the diameter indicated in 7.2.4.3.

7.2.4.3 The specimens that are to be aged shall be conditioned in accordance with UL 1581 for the length of time and at the temperature indicated for the jacket material in Table 7.1 and the applicable table of physical properties in UL 1581. The conditioning shall be followed by 16–96 h of rest in still air at room temperature before the specimens are wound onto a mandrel. The aged specimens shall be wound at room temperature for six complete turns (adjacent turns touching) onto a circular mandrel having a diameter twice that of the diameter over the overall jacket. Each specimen shall be unwound before being examined.

UL COPYRIGHTED MATERIAL –

NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM



Documents

Document Sharing Hub

7.3 Thicknesses

7.3.1 The dimensions of the spacer (thread) portion of the material insulation in an air-gap coaxial member are not specified. The average thickness and the minimum thickness at any point of the tube portion of an air-gap coaxial member shall not be less than indicated in Table 7.3. The thicknesses of the integral insulation (solid) and jacket on a flat, parallel cable shall not be less than indicated in Table 7.2. The average thickness and the minimum thickness at any point of solid insulation (including any skin) on single-conductor cable for Class 2 circuits and on any conductor in an unjacketed ribbon cable (before and after separation) and in a twisted pair or other twisted multiple-conductor cable that is without an overall jacket and is for Class 2 circuits shall not be less than indicated in Table 7.4. The average thickness and the minimum thickness at any point of solid insulation (including any skin) in a coaxial member, on a thermocouple-extension wire, and on every other conductor, including each conductor in jacketed ribbon cable before and after separation and in nonintegral flat cable, shall not be less than indicated in Table 7.3. The average thickness and the minimum thickness at any point of solid insulation (including any skin) on conductors in single-conductor and twisted-pair or other twisted multi-conductor Type CL3 cable without an overall jacket shall be not less than indicated in Table 7.5. The thicknesses of foamed insulation (including any skin) shall be evaluated based on the performance of the finished cable when tested in accordance with this Standard. In any case, the thicknesses of solid and foamed insulations (including any skin) are to be determined by means of measurements made as described in Section 250 of UL 1581, with the following modifications for stranded conductors that leave one or more strand impressions in the insulation that are too small to accommodate the smaller pin referred to in 250.11 of UL 1581, which is to be 0.0200 in (20.0 mils) or 0.508 mm in diameter:

- a) The 0.003-in (3-mil) or 0.08-mm thickness-reduction allowance mentioned in 250.5 of UL 1581 is to be applied only to insulation that is from a stranded conductor as mentioned above and has an average thickness (including any skin) of at least 0.015 in or 0.38 mm.
- b) Only an optical method as applicable from 7.3.2 is to be used for thickness measurements of insulation that is from a stranded conductor as mentioned above and has an average thickness (including any skin) less than 0.015 in or 0.38 mm.

7.3.2 Thickness measurements of a nylon or similar covering (see note ^b to Table 7.3, Table 7.4, and Table 7.5) of insulation having an average thickness or minimum thickness at any point of not more than 0.0060 in or 0.152 mm (including any skin) are to be made by means of a micrometer microscope or other optical instrument that is calibrated to read directly to at least 0.0001 in (0.1 mil) or 0.001 mm. Each of these measurements is to be recorded to the nearest 0.0001 in or 0.001 mm. Otherwise, under 7.3.1 (b), a simply manipulated optical device that is accurate to 0.001 in (1 mil) or 0.01 mm may be used for insulation, with each measurement recorded to the nearest 0.001 in or 0.01 mm.

7.3.3 For 7.3.1 (b), the conductor and any covering over the insulation or skin are to be removed from the finished insulated conductor, wire, or member. A thin slice of the insulation plus any skin is then to be cut perpendicular to the longitudinal axis of the resulting hollow tube. Measurements are to be taken of the maximum and minimum wall thicknesses of the slice. The recorded maximum and minimum thicknesses are to be added together and divided by 2 without any rounding off of the sum but with the resulting average rounded off (see Sections 7.3.4 – 7.3.7) to the same degree as stated in 7.3.2 for the recorded measurements. The average thickness so determined and the recorded minimum thickness are to be taken as the average and minimum-at-any-point thicknesses that are to be compared with Table 7.3 or with whatever lesser thicknesses are established for the construction as the result of the insulation-crushing test described in Crushing Resistance Test of Insulation, Section 31.

7.3.4 Rounding off to the nearest 0.0001 in:

A figure in the fourth decimal place is to remain unchanged if the figure in the fifth decimal place is 0 – 4 and the figure in the fourth decimal place is odd or even, or if the figure in the fifth decimal place is 5 and the figure in the fourth decimal place is even (0, 2, 4, and so forth). A figure in the fourth decimal place is to be increased by 1 if the figure in the fifth decimal place is 6 – 9 and the figure in the fourth decimal place is odd or even, or if the figure in the fifth decimal place is 5 and the figure in the fourth decimal place is odd (1, 3, 5, and so forth).

7.3.5 Rounding off to the nearest 0.001 in:

A figure in the third decimal place is to remain unchanged if the figure in the fourth decimal place is 0 – 4 and the figure in the third decimal place is odd or even, or if the figure in the fourth decimal place is 5 and the figure in the third decimal place is even (0, 2, 4, and so forth). A figure in the third decimal place is to be increased by 1 if the figure in the fourth decimal place is 6 – 9 and the figure in the third decimal place is odd or even, or if the figure in the fourth decimal place is 5 and the figure in the third decimal place is odd (1, 3, 5, and so forth).

7.3.6 Rounding off to the nearest 0.001 mm:

A figure in the third decimal place is to remain unchanged if the figure in the fourth decimal place is 0 – 4 and the figure in the third decimal place is odd or even, or if the figure in the fourth decimal place is 5 and the figure in the third decimal place is even (0, 2, 4, and so forth). A figure in the third decimal place is to be increased by 1 if the figure in the fourth decimal place is 6 – 9 and the figure in the third decimal place is odd or even, or if the figure in the fourth decimal place is 5 and the figure in the third decimal place is odd (1, 3, 5, and so forth).

7.3.7 Rounding off to the nearest 0.01 mm:

A figure in the second decimal place is to remain unchanged if the figure in the third decimal place is 0 – 4 and the figure in the second decimal place is odd or even, or if the figure in the third decimal place is 5 and the figure in the second decimal place is even (0, 2, 4, and so forth). A figure in the second decimal place is to be increased by 1 if the figure in the third decimal place is 6 – 9 and the figure in the second decimal place is odd or even, or if the figure in the third decimal place is 5 and the figure in the second decimal place is odd (1, 3, 5, and so forth).

Document Was Downloaded By Rice, Shi SHIMISHENG
For Use By KUANTECH CO LTD
12039 : 7/30/2007 - 3:10 AM
UL COPYRIGHTED MATERIAL –

NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM



Documents


Document Sharing Hub

Table 7.2
Thicknesses of integral insulation (solid) and jacket on 2-, 3-, or 4-conductor flat, parallel cable and distance between conductors

Cable types and sizes	Nominal thickness away from tear area(s) (vertical dashed line through web or webs in Figure 7.1) and outside point P or X (defined in Figure 7.2) A ^a (Information only – not a requirement)		Minimum thickness at any point before separation measured outside point P or X (defined in Figure 7.2) B ^a		Minimum thickness at any point after separation C ^a		Minimum distance between copper conductors D ^a	
	inch	mm	inch	mm	inch	mm	inch	mm
Types CL2P, CL3P, CL2R, CL3R, CL2, CL3, CL2X, and CL3X 24 – 12 AWG	0.020	0.51	0.018	0.46	0.010	0.25	0.030	0.76
11 – 8 AWG	0.030	0.76	0.027	0.69	0.013	0.33	0.047	1.19
7 – 6 AWG	0.045	1.14	0.040	1.02	0.027	0.69	0.080	2.03

^a Dimension A – D are illustrated in Figure 7.1

Figure 7.1
Integral flat cable
See Table 7.2 for dimensions A – D



SB0636-2

Document Was Downloaded By Rice, Shi SHIMISHENG
For Use By KUANTECH CO LTD
12039 : 7/30/2007 - 3:10 AM


UL COPYRIGHTED MATERIAL -
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL



Documents


Document Sharing Hub

Figure 7.2
Definition of regions of valley slopes on which thickness measurements are not to be made in integral flat cables



SB0636-5

Constructions with a Cross Section Having a Definite Point P at the Outer End of Each Valley Slope OP in each case is a straight line from the center O of a conductor to P on the same segment of the cross section. Thickness measurements are not to be made on any valley slope.



SB0636-6

Constructions with a Cross Section not Having a Definite Point to Mark the Outer End of Each Valley Slope OT in each case is a straight line from the center O of a conductor to T, the point of tangency, on the adjacent segment of the cross section. Thickness measurements are not to be made deeper on a valley slope than point X, which is the intersection of the line OT with the valley slope. Thickness measurements are to be made on each slope segment TX.

Table 7.3
Thicknesses^a of solid insulation (including any skin) in jacketed ribbon cable and in nonintegral round and flat multiple-conductor cable

Cable Types	AWG size of conductor	Insulation whose unaged tensile strength is less than 2000 lbf/in ² or 13.79 MN/m ² or 1379 N/cm ² or 1.41 kgf/mm ²						PVC (1) with an unaged tensile strength of at least 2000 lbf/in ² or 13.79 MN/m ² or 1379 N/cm ² or 1.41 kgf/mm ² , and (2) with or without a covering ^b of nylon (see 3.3), PBT (see 3.4), or similar thermoplastic material or ECTFE, ETFE, FEP, HDPE,s , MFA, PFA, PTFE (TFE), PVDF, PVDF Copolymer, Semirigid PVC, PP, or XLPO	
		CP or silicone rubber		LDPE, PVC, or TPE (all without a nylon or similar covering)		PVC with a covering ^b of nylon (see 3.3), PBT (see 3.4), or similar thermoplastic material or TPE with a covering ^b of nylon or XL (without a nylon or similar covering)			
		A		B		C			
		Minimum acceptable average thickness	Minimum acceptable thickness at any point	Minimum acceptable average thickness	Minimum acceptable thickness at any point	Minimum acceptable average thickness	Minimum acceptable thickness at any point	Minimum acceptable average thickness	Minimum acceptable thickness at any point
PLTC (not 28 – 23 AWG), CL3P, CL3R, CL3, CL3X	28 – 20 19 – 15 14 – 12, 11 ^d , 10 ^d	inch						0.009 0.006	0.008 PLTC 0.005 Others
		0.015	0.013	0.012	0.011	0.009	0.008		
		0.015	0.013	0.015	0.013	0.009	0.008		
		0.020	0.018	0.020	0.018	0.012	0.011		
CL2P, CL2R, CL2, CL2X	30 – 12, 11 ^c , 10 ^c 9 ^c , 8 ^c 7 ^c , 6 ^c	0.009	0.008	0.009	0.008	0.0060	0.0050	0.0050	0.0040
		0.015	0.013	0.012	0.011	0.009	0.008		
		0.020	0.018	0.020	0.018	0.012	0.011		
PLTC (not 28 – 23 AWG), CL3P, CL3R, CL3, CL3X	28 – 20 19 – 15 14 – 12, 11 ^d , 10 ^d	mm						0.23 0.152	0.20 PLTC 0.127 Others
		0.38	0.33	0.30	0.28	0.23	0.20		
		0.38	0.33	0.38	0.33	0.23	0.20		
		0.51	0.46	0.51	0.46	0.30	0.28		
CL2P, CL2R, CL2, CL2X	30 – 12, 11 ^c , 10 ^c 9 ^c , 8 ^c 7 ^c , 6 ^c	0.23	0.20	0.23	0.20	0.152	0.127	0.127	0.102
		0.38	0.33	0.33	0.28	0.23	0.20		
		0.51	0.46	0.51	0.46	0.30	0.28		

UL COPYRIGHTED MATERIAL –

NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
 DISTRIBUTION WITHOUT PERMISSION FROM UL

Table 7.3 Continued on Next Page



Documents

Document Sharing Hub