

UL 1655

0-7629-0229-9

Community-Antenna Television Cables



*UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL*



Documents

Document Sharing Hub

Underwriters Laboratories Inc. (UL)
333 Pfingsten Road
Northbrook, IL 60062-2096

UL Standard for Safety for Community-Antenna Television Cables, UL 1655

First Edition, Dated November 14, 1997

Revisions: This Standard contains revisions through and including June 25, 2004.

Summary of Topics

The revisions to ANSI/UL 1655 include revised Energy Markings for Optical-Fiber Cables, option added for Reduced Non-Integral Jacket Thicknesses, addition of new Air-Gap Insulated Constructions, and other editorial revisions.

UL Standards for Safety are developed and maintained in the Standard Generalized Markup Language (SGML). SGML -- an international standard (ISO 8879-1986) -- is a descriptive markup language that describes a document's structure and purpose, rather than its physical appearance on a page. Due to formatting differences resulting from the use of UL's new electronic publishing system, please note that additional pages (on which no requirements have been changed) may be included in revision pages due to relocation of existing text and reformatting of the Standard.

Text that has been changed in any manner is marked with a vertical line in the margin. Changes in requirements are marked with a vertical line in the margin and are followed by an effective date note indicating the date of publication or the date on which the changed requirement becomes effective.

The following table lists the future effective dates with the corresponding reference:

Future Effective Date	References
December 27, 2004	Paragraphs 1.10, 10.3, and 36.1

In the revisions dated June 25, 2004, pages 12, 13, and 43 – 46 have been intentionally deleted from the Standard due to the deletion or relocation of text. Please discard any previous versions of these pages from your paper copy of the Standard.

The new and/or revised requirements are substantially in accordance with UL's Bulletin(s) on this subject dated April 1, 2004. The bulletin(s) is now obsolete and may be discarded.

The revisions dated June 25, 2004 include a reprinted title page (page1) for this Standard.

As indicated on the title page (page 1), this UL Standard for Safety is an American National Standard. Attention is directed to the note on the title page of this Standard outlining the procedures to be followed to retain the approved text of this ANSI/UL Standard.

The UL Foreword is no longer located within the UL Standard. For information concerning the use and application of the requirements contained in this Standard, the current version of the UL Foreword is located on ULStandardsInfoNet at: <http://ulstandardsinfo.net.ul.com/ulforeword.html>

The master for this Standard at UL's Northbrook Office is the official document insofar as it relates to a UL service and the compliance of a product with respect to the requirements for that product and service, or if there are questions regarding the accuracy of this Standard.

UL's Standards for Safety are copyrighted by UL. Neither a printed copy of a Standard, nor the distribution diskette for a Standard-on-Diskette and the file for the Standard on the distribution diskette should be altered in any way. All of UL's Standards and all copyrights, ownerships, and rights regarding those Standards shall remain the sole and exclusive property of UL.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form by any means, electronic, mechanical photocopying, recording, or otherwise without prior permission of UL.

Revisions of UL Standards for Safety are issued from time to time. A UL Standard for Safety is current only if it incorporates the most recently adopted revisions.

UL provides this Standard "as is" without warranty of any kind, either expressed or implied, including but not limited to, the implied warranties of merchantability or fitness for any purpose.

In no event will UL be liable for any special, incidental, consequential, indirect or similar damages, including loss of profits, lost savings, loss of data, or any other damages arising out of the use of or the inability to use this Standard, even if UL or an authorized UL representative has been advised of the possibility of such damage. In no event shall UL's liability for any damage ever exceed the price paid for this Standard, regardless of the form of the claim.

UL will attempt to answer support requests concerning electronic versions of its Standards. However, this support service is offered on a reasonable efforts basis only, and UL may not be able to resolve every support request. UL supports the electronic versions of its Standards only if they are used under the conditions and operating systems for which it is intended. UL's support policies may change from time-to-time without notification.

UL reserves the right to change the format, presentation, file types and formats, delivery methods and formats, and the like of both its printed and electronic Standards without prior notice.

Purchasers of the electronic versions of UL's Standards for Safety agree to defend, indemnify, and hold UL harmless from and against any loss, expense, liability, damage, claim, or judgement (including reasonable attorney's fees) resulting from any error or deviation introduced while purchaser is storing an electronic Standard on the purchaser's computer system.

If a single-user version electronic Standard was purchased, one copy of this Standard may be stored on the hard disk of a single personal computer, or on a single LAN file-server or the permanent storage device of a multiple-user computer in such a manner that this Standard may only be accessed by one user at a time and for which there is no possibility of multiple concurrent access.

If a multiple-user version electronic Standard was purchased, one copy of the Standard may be stored on a single LAN file-server, or on the permanent storage device of a multiple-user computer, or on an Intranet server. The number of concurrent users shall not exceed the number of users authorized.

Electronic Standards are intended for on-line use, such as for viewing the requirements of a Standard, conducting a word search, and the like. Only one copy of the Standard may be printed from each single-user version of an electronic Standard. Only one copy of the Standard may be printed for each authorized user of a multiple-user version of an electronic Standard. Because of differences in the computer/software/printer setup used by UL and those of electronic Standards purchasers, the printed copy obtained by a purchaser may not look exactly like the on-line screen view or the printed Standard.

An employee of an organization purchasing a UL Standard can make a copy of the page or pages being viewed for their own fair and/or practical internal use.

The requirements in this Standard are now in effect, except for those paragraphs, sections, tables, figures, and/or other elements of the Standard having future effective dates as indicated in the note following the affected item. The prior text for requirements that have been revised and that have a future effective date are located after the Standard, and are preceded by a "SUPERSEDED REQUIREMENTS" notice.

New product submittals made prior to a specified future effective date will be judged under all of the requirements in this Standard including those requirements with a specified future effective date, unless the applicant specifically requests that the product be judged under the current requirements. However, if the applicant elects this option, it should be noted that compliance with all the requirements in this Standard will be required as a condition of continued Listing and Follow-Up Services after the effective date, and understanding of this should be signified in writing.

Copyright © 2004 Underwriters Laboratories Inc.

This Standard consists of pages dated as shown in the following checklist:

Page	Date
1-11	June 25, 2004
14	November 14, 1997
15-22	June 25, 2004
23	November 14, 1997
24-25	February 21, 2001
26-28B	June 25, 2004
29	November 14, 1997
30	February 21, 2001
31-35	June 25, 2004
36	February 21, 2001
37-42	June 25, 2004
46A-46B	April 30, 1998
47-48	June 25, 2004
49-51	November 14, 1997
52-54A	June 25, 2004
54B	April 30, 1998
55	February 21, 2001
56-62	June 25, 2004
SR1-SR2	June 25, 2004

No Text on This Page



NOVEMBER 14, 1997
(Title Page Reprinted: June 25, 2004)



ANSI/UL 1655-2004

1

UL 1655

Standard for Community-Antenna Television Cables

First Edition

November 14, 1997

The most recent designation of ANSI/UL 1655 as an American National Standard (ANSI) occurred on June 3, 2004.

This ANSI/UL Standard for Safety, which consists of the First edition with revisions through June 25, 2004, is under continuous maintenance, whereby each revision is ANSI approved upon publication. Comments or proposals for revisions on any part of the Standard may be submitted to UL at any time. Written comments are to be sent to UL-RTP Standard Department, 12 Laboratory Dr., P.O. Box 13995, Research Triangle Park, NC, 27709-3995.

An effective date included as a note immediately following certain requirements is one established by Underwriters Laboratories Inc.

Revisions of this Standard will be made by issuing revised or additional pages bearing their date of issue. A UL Standard is current only if it incorporates the most recently adopted revisions, all of which are itemized on the transmittal notice that accompanies the latest set of revised requirements.

ISBN 0-7629-0229-9

COPYRIGHT © 1997, 2004 UNDERWRITERS LABORATORIES INC.

**UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL**



Documents

Document Sharing Hub

No Text on This Page

*UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL*



Documents

Document Sharing Hub

CONTENTS

INTRODUCTION

1 Scope	4C
2 Units of Measurement	5
3 References	6

CONSTRUCTION

4 Materials	6
5 Center Conductor of Coaxial Members	6
6 Metal Coating of Center Conductor	9
7 Insulation	10
7.1 Material and application	10
7.2 Thicknesses	14
8 Coaxial Members	15
9 Electromagnetic Shields	16
10 Optical-Fiber Members	17
11 Binders	18
12 Communications Conductor	18
13 Core Wrap	18
14 Assembly of a Multiple-Member Cable	18
15 Overall Cable Jacket	19
15.1 General	19
15.2 Flexibility test	20
15.3 Physical properties test	20
15.4 Jacket	21
16 Metal Covering (Armor)	26
16.1 General	26
16.2 Smooth metal sheath	27
16.3 Welded and corrugated metal sheath	28
16.4 Extruded and corrugated metal sheath	28
16.5 Interlocked armor	28A
17 Jacket over Armor	31

PERFORMANCE

18 Continuity Test of Center and Outer Conductors and Shields	32
19 D-C Resistance Test of Center Conductors	32
19.1 Requirements	32
19.2 General method	37
19.3 Kelvin-bridge referee method	37
20 Cold Bend Test of the Complete Cable	38
21 Smoke and Flame Testing of Plenum Cables	39
22 Flame Testing of Riser Cables	40
23 VW-1 (Vertical-Specimen) Flame Test of Limited-Use Cables	40
24 Alternative Vertical-Tray Flame Tests of General-Purpose Cables	41
24.1 Choice of test by the manufacturer	41
24.2 Changes in construction	41
24.3 UL test	41
24.4 FT4/IEEE 1202 test	42

25	Sunlight-Resistance Test	42
26	Alternative Spark and Dielectric Voltage-Withstand Tests of All Coaxial Members	46A
26.1	Choice of test by the manufacturer	46A
26.2	Spark test of members before cable assembly	46A
26.3	Dielectric voltage-withstand test of members after cable assembly	47
27	Crushing Resistance Test of Center-Conductor Insulation	47
28	Crushing Test of Cable Marked for Direct Burial	48
29	Copper Sulphate Test of Zinc Coating on Steel Strip for and from Interlocked Steel Armor ..	49
30	Tension Test of Interlocked Steel or Aluminum Armor	51
31	Flexibility Test of Cable Having Interlocked Armor or a Smooth or Corrugated Metal Sheath ..	54
32	Durability Test of Ink Printing	55
32A	Limited Combustible	55

MARKINGS

33	Intervals	56
34	Coding	56
35	Information on or in the Cable	56
36	Information on the Tag, Reel, or Carton	59
37	Multiple Markings	60
38	Date of Manufacture	61

**UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL**



Documents

Document Sharing Hub

No Text on This Page



This page intentionally left blank.

*UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL*



Documents

Document Sharing Hub

INTRODUCTION

1 Scope

1.1 This Standard states the construction, test, and marking requirements covering the safety of single and multiple coaxial and coaxial/optical-fiber cables for the distribution of radio frequency signals such as employed in a community antenna television system, and for supplying low-energy power at a potential not exceeding 60 volts to equipment directly associated with the signal distribution. These are power-limited cables and are of the following types for installation and use as the CATV cables specified in Article 820 and other applicable parts of the National Electrical Code (NEC), NFPA 70. Electrically nonconductive material separates each optical-fiber member from the rest of the cable.

a) PLENUM CABLES – Type CATVP (coaxial) and Type CATVP-OF (coaxial/optical-fiber). These cables are for installation as specified in Section 820.51(A) of the National Electrical Code, ANSI/NFPA 70 in a duct, plenum, or other space used to transport environmental air without the cable being enclosed in raceway in that space.

b) RISER CABLES – Type CATVR (coaxial) and Type CATVR-OF (coaxial/optical-fiber). These cables are for installation as specified in Section 820.51(B) of the National Electrical Code, ANSI/NFPA 70 in vertical runs in a shaft or for vertical runs that penetrate more than one floor.

c) GENERAL-PURPOSE CABLES – Type CATV (coaxial) and Type CATV-OF (coaxial/optical-fiber). These cables are general-applications commercial cables for use as specified in Section 820.51(C) of the National Electrical Code, ANSI/NFPA 70.

d) LIMITED-USE CABLES – Type CATVX (coaxial) and Type CATVX-OF (coaxial/optical-fiber). These are limited use cables as specified in Section 820.51(D) and Section 820.53(D) of the National Electrical Code, ANSI/NFPA 70.

e) *Deleted*

1.1 revised June 25, 2004

1.2 This Standard does not specify the impedance or other signal-carrying characteristics of these cables. This Standard does not cover tests for the signal-carrying performance of these cables.

1.3 *Deleted June 25, 2004*

1.4 Armored cables are covered by interlocked metal strip or a smooth or corrugated metal sheath) with or without a jacket over the armor. Cables for encasement in concrete, mortar, other masonry, plaster, or the like have metal armor and a jacket over the armor. Cables for direct burial in the earth (see markings in 1.8) are subject to a 1000-pound crushing test. Cables for direct burial are not required to be armored. Cables for direct burial that are armored have a jacket over the armor. All other cables (unarmored, flat or round) have an overall jacket. Some overall jackets incorporate a nonmetallic messenger.

1.3 revised and relocated as 1.4 April 30, 1998

1.5 Cables of a CATV type do not have a voltage rating.

1.5 revised June 25, 2004

1.6 Cables of materials that qualify for temperatures above 60°C (140°F) are marked with a temperature rating of 75, 90, 105, 125, 150, or 200°C (167, 194, 221, 257, 302, or 392°F). Temperature marking is not required for cables that qualify for a temperature rating of 60°C (140°F).

1.7 Cables that contain one or more electromagnetic shields in addition to the outer conductors of the coaxial members (these shields are identified as "additional" in 9.1) are not required to be marked to indicate the presence of the additional shielding. A shielded cable that is marked has "shielded" on the tag and either on the overall cable jacket or legible through the jacket.

1.7 revised April 30, 1998

1.8 Cables that qualify for exposure to sunlight (720-hour sunlight-resistance test – see 23.1) have the designation "sun res" or "sunlight resistant" on the tag and either on the overall cable jacket or legible through the jacket.

1.9 Cables that qualify for burial directly in the earth (1000-pound crushing test – see 28.1) have the designation "dir bur", "direct burial", or "for direct burial" on the tag and either on the overall cable jacket or legible through the jacket.

1.10 Optical performance is not evaluated. Cables with optical fibers are to have a tag marking in accordance with 10.3 and 36.1(d). Where there are conductive parts in an optical-fiber member or in a group of such members, a tag marking [36.1(e)] indicates the presence of these parts.

Revised 1.10 effective December 27, 2004

1.11 Deleted June 25, 2004

1.12 Deleted June 25, 2004

1.13 Deleted June 25, 2004

1.14 These requirements do not cover antenna-rotator or other coaxial/electrical cables - that is, coaxial cables with additional conductors for electric-light, power, control, non-power-limited fire-alarm, Class 1, Class 2, or Class 3 circuits.

1.15 Deleted June 25, 2004

1.16 Deleted June 25, 2004

1.17 Smoke and flame tests are as follows for the cables covered in these requirements:

- a) PLENUM CABLES – All Type CATVP and Type CATVP-OF cables are tested for smoke and flame characteristics as specified in Smoke and Flame Testing of Plenum Cables, Section 21, which references the National Fire Protection Association Standard Method of Test for Flame Travel and Smoke of Wires and Cables for Use in Air-Handling Spaces, ANSI/NFPA 262. A cable that complies exhibits a maximum flame-propagation distance that is not greater than 5 ft, 0 inch or 152 cm, a peak optical density of smoke produced of 0.50 or less (32 percent light transmission), and an average optical density of smoke produced of 0.15 or less.

b) RISER CABLES – Jacketed Type CATVR and Type CATVR-OF cables are tested for flame-propagation characteristics as specified in Flame Testing of Riser Cables, Section 22, which references the Standard Test for Flame-Propagation Height of Electrical and Optical-Fiber Cables Installed Vertically in Shafts, UL 1666. A cable that complies exhibits a flame-propagation height under 12 ft, 0 inch or 366 cm and attains a temperature no higher than 850.0°F (454.4°C) at a height of 12 ft, 0 inch or 366 cm.

c) GENERAL-PURPOSE CABLES – Jacketed Type CATV and Type CATV-OF cables are to comply with one of the two 70,000 Btu/h (20.5 kW) vertical-tray flame tests specified in Alternative Vertical-Tray Flame Tests of General-Purpose Cables, Section 24. The cable manufacturer is to choose one of the following tests:

1) The UL test referenced in 24.1.1 –24.3.2. These paragraphs apply the test method described as the UL Flame Exposure (smoke measurements are not applicable) in the Standard Vertical-Tray Fire-Propagation and Smoke-Release Test for Electrical and Optical-Fiber Cables, UL 1685.

2) The FT4/IEEE 1202 test referenced in 24.1.1 and 24.4.1. These paragraphs apply the test method described as the FT4/IEEE 1202 Type of Flame Exposure (smoke measurements are not applicable) in the Standard Vertical-Tray Fire-Propagation and Smoke-Release Test for Electrical and Optical-Fiber Cables, UL 1685. A cable that complies is eligible to be marked "FT4/IEEE 1202" or "FT4" on the surface or on a marker tape as indicated in 35.1(h).

d) LIMITED-USE CABLES – All Type CATVX and Type CATVX-OF cables are subjected to the VW-1 flame test specified in VW-1 (Vertical-Specimen) Flame Test of Limited-Use Cables, Section 23, which references the test method described as the VW-1 (Vertical-Specimen) Flame Test in Section 1080 of UL 1581. These cables are not marked "VW-1".

1.17 revised June 25, 2004

1.18 Deleted June 25, 2004

2 Units of Measurement

2.1 In addition to being stated in the inch/pound units that are customary in the USA, each of the requirements is also stated in units that make the requirement conveniently usable in countries employing the various metric systems (practical SI and customary). Equivalent - although not exactly identical - results are to be expected from applying a requirement in USA or metric terms. Equipment calibrated in metric units is to be used when a requirement is applied in metric terms.

UL COPYRIGHTED MATERIAL –
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM UL



Documents

Document Sharing Hub

3 References

3.1 Wherever the designation "UL 1581" is used in this wire standard, reference is to be made to the designated part(s) of the Reference Standard for Electrical Wires, Cables, and Flexible Cords, UL 1581.

CONSTRUCTION

4 Materials

4.1 Each material used in a cable shall be compatible with all of the other materials used in the cable.

4.2 Cables of a CATV type shall comply in all respects with the applicable requirements for construction details, test performance, and markings.

5 Center Conductor of Coaxial Members

5.1 The center conductor of each coaxial member shall be round and of solid 30 – 1 AWG soft-annealed copper, of stranded 30 AWG – 500 kcmil soft-annealed copper, of solid 30 – 6 AWG medium-drawn or hard-drawn copper, of solid 30 – 6 AWG copper-clad steel, of solid 30 – 1 AWG copper-clad aluminum, or of a smooth or corrugated copper tube. A stranded conductor shall consist of round strands with a right- or left-hand direction of lay. Seven strands, concentric, is the stranding assumed in these requirements; however, individual strand diameter, the number of strands, and the stranding type are not specified. See Metal Coating of Center Conductor, Section 6.

5.1 revised June 25, 2004

5.2 The nominal diameters indicated in Table 5.1 for solid and stranded center conductors are to be used in calculating the dimensions needed for various parts of the cable when using Tables 15.2, 15.3, 16.1, and 16.2. The length of lay of the wires (strands) of a stranded center conductor is not specified.

5.3 All solid, stranded, and tubular center conductors are to be identified as a particular AWG or circular-mil size in the marking on or in the cable and on the tag, reel, or carton. The size of a solid center conductor shall be verified either by determination of the d-c resistance or by determination of the diameter as described in 5.4. The size of a stranded or tubular center conductor shall be verified either by determination of the d-c resistance, as described in 5.5, or by determination of the cross-sectional area. Determination of the conductor size by measurement of the d-c resistance as described in D-C Resistance Test of Center Conductor, Section 19, is the referee method in all cases.

5.3 revised June 25, 2004

5.4 Where measured as the means of size verification (see 5.3), the diameter of a solid center conductor shall not be smaller than the minimum diameter indicated for the size in Table 5.1 when the diameter of the conductor is determined from measurements made as follows:

- a) Measurements of the diameter of a solid conductor are to be made over the metal-coated or uncoated conductor by optical means or by means of a machinist's micrometer caliper having flat surfaces both on the anvil and on the end of the spindle. In either case, the equipment is to be calibrated to read directly to at least 0.001 inch or 0.01 mm, with each division of a width that facilitates estimation of each measurement to 0.0001 inch or 0.001 mm. The maximum and minimum diameters at a given point on the solid conductor are each to be recorded to the nearest 0.0001 inch (0.1 mil) or 0.001 mm, added together, and divided by 2 without any rounding of the sum or resulting average.

b) Each minimum diameter indicated in Table 5.1 is an absolute minimum. The unrounded average of the two diameter readings is therefore to be compared directly with the minimum in the table for the purpose of determining whether the solid conductor does or does not comply with the diameter requirement.

5.5 Where measured as the means of size verification (see 5.3), the cross-sectional area of a stranded or tubular center conductor shall not be smaller than the minimum area indicated for the size in Table 5.1. The cross-sectional area of a stranded conductor is to be determined as the sum of the areas of its component round strands. However, where the sum of the strand areas does not comply, the conductor area is to be determined by the weight method outlined in Conductor Cross-Sectional Area by the Weight Method, Section 210 of UL 1581.

5.5 revised June 25, 2004

Table 5.1
Dimensions of center conductor of a coaxial member

Table 5.1 revised June 25, 2004

Size of conductor	Diameter of solid conductor				Cross-sectional area of tubular or stranded conductor				Nominal diameter of stranded conductor (7 strands)	
	Nominal See 5.2		Minimum See 5.4(b) mils are 0.99 x nominal except where note ^a applies		Nominal		Minimum cmil = 0.98 x nominal			
	mils	mm	mils	mm	cmil	mm ²	cmil	mm ²	mils	mm
30 AWG	10.0	0.254	9.5 ^a	0.241 ^a	100	0.0507	98	0.0497	11.3	0.287
29	11.3	0.287	10.7 ^a	0.272 ^a	128	0.0647	125	0.0633	12.8	0.325
28	12.6	0.320	12.0 ^a	0.305 ^a	159	0.0840	156	0.0790	14.3	0.363
27	14.2	0.361	13.5 ^a	0.343 ^a	202	0.102	198	0.100	16.1	0.409
26	15.9	0.404	15.1 ^a	0.384 ^a	253	0.128	248	0.126	18.0	0.457
25	17.9	0.455	17.0 ^a	0.432 ^a	320	0.162	314	0.159	20.3	0.516
24	20.1	0.511	19.1 ^a	0.485 ^a	404	0.205	396	0.201	22.8	0.579
23	22.6	0.574	21.5 ^a	0.546 ^a	511	0.259	501	0.254	25.6	0.650
22	25.3	0.643	24.0 ^a	0.610 ^a	640	0.324	627	0.318	28.7	0.729
21	28.5	0.724	27.1 ^a	0.688 ^a	812	0.412	796	0.404	32.3	0.820
20	32.0	0.813	30.4 ^a	0.772 ^a	1020	0.519	1000	0.509	36.2	0.919
19	35.9	0.912	34.1 ^a	0.866 ^a	1290	0.653	1264	0.641	40.7	1.03
18	40.3	1.02	40.2	1.016	1620	0.823	1588	0.807	45.6	1.16
17	45.3	1.15	44.9	1.140	2050	1.04	2009	1.02	51.3	1.30
16	50.8	1.29	50.3	1.278	2580	1.31	2528	1.28	57.6	1.46
15	57.1	1.45	56.5	1.435	3260	1.65	3195	1.62	64.7	1.64
14	64.1	1.63	63.5	1.613	4110	2.08	4028	2.04	72.7	1.85
13	72.0	1.83	71	1.81	5180	2.63	5076	2.58	81.6	2.07
12	80.8	2.05	80	2.03	6530	3.31	6399	3.24	91.5	2.32
11	90.7	2.30	90	2.28	8230	4.17	8065	4.09	103	2.62
10	101.9	2.588	101	2.56	10380	5.261	10172	5.16	116	2.95

Table 5.1 Continued

Size of conductor	Diameter of solid conductor				Cross-sectional area of tubular or stranded conductor				Nominal diameter of stranded conductor (7 strands)	
	Nominal See 5.2		Minimum See 5.4(b) mils are 0.99 x nominal except where note ^a applies		Nominal		Minimum cmil = 0.98 x nominal			
	mils	mm	mils	mm	cmil	mm ²	cmil	mm ²	mils	mm
9	114.4	2.906	113	2.88	13090	6.631	12828	6.50	130	3.30
8	128.5	3.264	127	3.23	16510	8.367	16180	8.20	146	3.71
7	144.3	3.665	143	3.63	20820	10.55	20404	10.34	164	4.17
6	162.0	4.115	160	4.07	26240	13.30	25715	13.03	184	4.67
5	181.9	4.620	180	4.57	33090	16.77	32428	16.43	206	5.23
4 AWG	204.3	5.189	202	5.14	41740	21.15	40905	20.73	232	5.89
3	229.4	5.827	227	5.77	52620	26.67	51568	26.14	260	6.60
2	257.6	6.543	255	6.48	66360	33.62	65033	32.95	292	7.42
1	289.3	7.348	286	7.27	83690	42.41	82016	41.56	332	8.43
1/0	—	—	—	—	105600	53.49	103488	52.42	372	9.45
2/0	—	—	—	—	13310	67.43	130438	66.08	418	10.62
3/0	—	—	—	—	167800	85.01	164444	83.31	470	11.94
4/0	—	—	—	—	211600	107.2	207368	105.1	528	13.41
250 kcmil	—	—	—	—	250 kcmil	127	245	124.1	575	14.61
300	—	—	—	—	300	152	294	149.0	630	16.00
350	—	—	—	—	350	177	343	173.8	681	17.30
400	—	—	—	—	400	203	392	198.6	728	18.49
450	—	—	—	—	450	228	441	223.5	772	19.61
500	—	—	—	—	500	253	490	248.3	813	20.65

^a Minimum diameter (0.95 x nominal) of a reduced-diameter solid conductor. See corresponding resistance (1.1 x nominal) in Table 19.1.

5.6 Each center and outer conductor and each shield shall be continuous throughout the entire length of the finished cable as determined by the Continuity Test of Center and Outer Conductors and Shields, Section 18.

5.7 A joint in a solid center conductor or in one of the individual wires of a stranded center conductor shall be made in a workmanlike manner, shall be smooth, and shall not have any sharp projections. A joint in a stranded conductor is to be made by separately joining each individual wire or by machine brazing or welding of the conductor as a whole so that the resulting solid section of the stranded conductor is not longer than 1/2 inch or 13 mm, there are no sharp points, and the distance between brazes or welds in a single conductor does not average less than 3000 ft or 915 m in any reel length of insulated single conductor. A joint made before insulation is applied to a center conductor shall not increase the diameter of the solid conductor or individual wire (strand). A joint made after insulating shall not increase the diameter of the solid conductor or individual wire (strand) by more than 20 percent. Joints made after insulating shall be insulated by applying a bonded patch or by molding. The insulation shall comply with the requirements in this Standard. An individual member jacket or an overall cable jacket that is damaged

UL COPYRIGHTED MATERIAL -

NOT AUTHORIZED FOR FURTHER REPRODUCTION OR
DISTRIBUTION WITHOUT PERMISSION FROM



Documents

Document Sharing Hub

to the point of exposing the underlying assembly or that is opened for the purpose of making any repair under the jacket either shall be stripped and replaced in its entirety or a second, duplicate jacket shall be applied over the first for the entire length of the member or cable. The total thickness of the two jackets shall not exceed any limitation determined for a particular cable in an applicable flame or smoke-and-flame test or other test specified in this Standard.

5.8 Any section of a center conductor that includes a factory joint shall have a tensile strength that is not less than 85 percent of the tensile strength of an adjacent section of the conductor not having a joint.

6 Metal Coating of Center Conductor

6.1 Where the insulation adjacent to the copper center conductor or copper cladding on the steel or aluminum center conductor is of a material that corrodes unprotected copper in the test described in Conductor Corrosion, Section 500 of UL 1581, the copper conductor or copper cladding shall be covered with a coating of tin, a tin/lead alloy, nickel, silver, or of another (evaluation required) metal or alloy.

6.2 Use of a metal coating is not specified on a solid center conductor or the individual wires (strands) of a stranded center conductor on which a coating is not required for corrosion protection.

6.3 The maximum temperature rating of the cable is not specified relative to the small-diameter copper wires used in the outer conductor. The temperature rating of a cable in which the center conductor is of copper shall not exceed the temperature indicated in Table 6.1 for the diameter and coating of the solid conductor or individual strands (see 15.3.1 regarding application of Table 6.1).

6.3 revised June 25, 2004

Table 6.1
Maximum temperature rating of cable relative to diameter and coating of solid copper center conductor or of copper center-conductor strands

Metal coating of copper strands or of solid copper conductor	Diameter of each strand or of the solid conductor	
	Smaller than 0.015 inch or 0.38 mm	At least 0.015 inch or 0.38 mm
Uncoated or coated with tin or a tin/lead alloy	150°C (302°F)	200°C (392°F)
Coated with silver	200°C (392°F)	200°C (392°F)
Coated with nickel	over 200°C (392°F)	over 200°C (392°F)

7 Insulation

7.1 Material and application

7.1.1 The center conductor of each coaxial member shall be insulated for its entire length. An air-gap dielectric shall be permitted. The insulation material is not specified. The insulation shall be solid or expanded (foamed) with or without a solid dielectric skin (a thin, solid, extruded layer that is or is not separable) applied over the solid or foamed insulation. A skin is not required to be of the same material as the insulation. An air-gap coaxial member shall consist of a solid spacer (thread) that has a nominally circular cross section and is applied to the center conductor helically in a continuous length (the length and direction of lay are not specified) with or without a solid insulating tube overall. Otherwise, the insulation shall be applied directly to the center conductor, shall have a circular cross section, and shall fit tightly to the conductor with no more than nominal adherence (a test is not specified). The insulation shall be uniform and shall not have any defects (bubbles, open spots, rips, tears, cuts, or foreign material) that are visible with normal or corrected vision without magnification.

7.1.1 revised June 25, 2004

7.1.2 Neither flexibility nor physical properties testing is specified for 60°C (140°F) insulation. Flexibility or physical properties testing in accordance with 7.1.4 – 7.1.6 is required for all insulations rated 75°C (167°F) or greater.

7.1.2 revised June 25, 2004

7.1.3 Relocated as 7.1.6 June 25, 2004

7.1.4 Specimens of solid single-layered insulations removed from finished insulated conductors shall comply with the values of unaged elongation and tensile strength shown in the applicable physical-properties table for the material referenced in Section 50 of UL 1581, and when tested in accordance with the test procedures in UL 1581. Specimens of solid single-layered insulations except PVDF rated 125°C shall comply with the values of aged retention of elongation and tensile strength shown in the applicable physical-properties table for the material referenced in Section 50 of UL 1581, and when tested in accordance with the test procedures in UL 1581. PVDF rated 125°C, foamed, and multi-layered insulations shall comply with 7.1.5.

7.1.4 added June 25, 2004

7.1.5 Solid or foamed 125°C (257°F) PVDF and PVDF copolymer insulations with or without a skin and other insulations with a skin shall comply with the flexibility test in 15.2 (conditioning per Table 50.185 of UL 1581) using specimens consisting of the insulated center conductor and wound onto a mandrel having a diameter equal to the diameter over the insulation (1 x DOD). Solid or foamed 150°C (302°F) PVDF and PVDF copolymer insulations without a skin and all other solid insulations without a skin shall comply with the tensile strength and ultimate elongation requirements for unaged and aged specimens of the particular material in the applicable table of physical properties in Specific Materials, Section 50 of UL 1581. All specimens are to be prepared from samples taken from the finished cable.

7.1.5 added June 25, 2004

7.1.6 Insulation that is of material generically different from any insulation material for which there is a table of physical properties in Specific Materials, Section 50 of UL 1581 (new material), or that is of material for which physical properties are tabulated in UL 1581 yet does not comply with the applicable short-term tests in the UL 1581 table, shall be of a material and in thicknesses and with a temperature rating appropriate for a CATV-series cable. The material shall be evaluated for the requested temperature rating as described in Long-Term Aging, Section 481 of UL 1581. Investigation of the electrical,

mechanical, and physical characteristics of the cable using either material shall show the material to be comparable in performance to the insulation materials in UL 1581 through tests such as crushing, impact, abrasion, deformation, heat shock, and dielectric voltage-withstand.

7.1.3 relocated as 7.1.6 June 25, 2004

7.2 Thicknesses

7.2.1 General

7.2.1.1 The dimensions of the spacer (thread) portion of the material insulation in an air-gap coaxial member are not specified. The average thickness and the minimum thickness at any point of solid or foamed insulation on the center conductor of a coaxial member are not specified but the thicknesses used shall be measured. The thicknesses used shall be adequate to result in compliance with the tests specified or referenced in this Standard. The thicknesses of solid and foamed insulations (including any skin) are to be determined by means of measurements made as described in Thicknesses of Insulation on Flexible Cord and on Fixture Wire, Section 250 of UL 1581, with the following modifications for a stranded conductor that leaves one or more strand impressions in the insulation that are too small to accommodate the smaller pin referred to in 250.11 of UL 1581. For this application, the pin is to be 0.0200 inch (20.0 mils) or 0.508 mm in diameter:

- a) The 0.003-inch (3-mil) or 0.08-mm thickness-reduction allowance in 250.5 of UL 1581 is to be applied only to insulation that is from a stranded center conductor that leaves the impressions described above in this paragraph and has an average thickness (including any skin) of at least 0.015 inch or 0.38 mm.
- b) Only an optical method as applicable from 7.2.1.2 and 7.2.1.3 is to be used for thickness measurements of insulation that is from a stranded center conductor that leaves the impressions described above in this paragraph and has an average thickness (including any skin) less than 0.015 inch or 0.38 mm.

7.2.1.2 A simply manipulated optical device that is accurate to 0.001 inch (1 mil) or 0.01 mm is to be used for measuring the insulation, with each measurement recorded to the nearest 0.001 inch or 0.01 mm.

7.2.1.3 The center conductor is to be removed from the insulation before measuring the thicknesses of the insulation as discussed in 7.2.1.1(b). A thin slice of the insulation plus any skin is then to be cut perpendicular to the longitudinal axis of the resulting hollow tube. Measurements are to be made of the maximum and minimum wall thicknesses of the slice. The recorded maximum and minimum thicknesses are to be added together and then divided by 2 without any rounding of the sum. The resulting average is to be rounded (see 7.2.2.1 - 7.2.5.1, which apply the American Society of Testing and Materials Standard Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications, ASTM E 29-93a) to the same degree as stated in 7.2.1.2 for the recorded measurements. The average thickness so determined and the recorded minimum thickness are to be taken as the average and minimum-at-any-point thicknesses that are established for the construction as the result of the Crushing Resistance Test of Center-Conductor Insulation, Section 27.

7.2.2 Rounding to the nearest 0.0001 inch

7.2.2.1 A figure in the fourth decimal place is to remain unchanged where the figure in the fifth decimal place is 0 - 4 and the figure in the fourth decimal place is odd or even, or where the figure in the fifth decimal place is 5 and the figure in the fourth decimal place is even (0, 2, 4, and so forth). A figure in the fourth decimal place is to be increased by 1 where the figure in the fifth decimal place is 6 - 9 and the figure in the fourth decimal place is odd or even, or where the figure in the fifth decimal place is 5 and the figure in the fourth decimal place is odd (1, 3, 5, and so forth).

7.2.3 Rounding to the nearest 0.001 inch

7.2.3.1 A figure in the third decimal place is to remain unchanged where the figure in the fourth decimal place is 0 - 4 and the figure in the third decimal place is odd or even, or where the figure in the fourth decimal place is 5 and the figure in the third decimal place is even (0, 2, 4, and so forth). A figure in the third decimal place is to be increased by 1 where the figure in the fourth decimal place is 6 - 9 and the figure in the third decimal place is odd or even, or where the figure in the fourth decimal place is 5 and the figure in the third decimal place is odd (1, 3, 5, and so forth).

7.2.4 Rounding to the nearest 0.001 mm

7.2.4.1 A figure in the third decimal place is to remain unchanged where the figure in the fourth decimal place is 0 - 4 and the figure in the third decimal place is odd or even, or where the figure in the fourth decimal place is 5 and the figure in the third decimal place is even (0, 2, 4, and so forth). A figure in the third decimal place is to be increased by 1 where the figure in the fourth decimal place is 6 - 9 and the figure in the third decimal place is odd or even, or where the figure in the fourth decimal place is 5 and the figure in the third decimal place is odd (1, 3, 5, and so forth).

7.2.5 Rounding to the nearest 0.01 mm

7.2.5.1 A figure in the second decimal place is to remain unchanged where the figure in the third decimal place is 0 - 4 and the figure in the second decimal place is odd or even, or where the figure in the third decimal place is 5 and the figure in the second decimal place is even (0, 2, 4, and so forth). A figure in the second decimal place is to be increased by 1 where the figure in the third decimal place is 6 - 9 and the figure in the second decimal place is odd or even, or where the figure in the third decimal place is 5 and the figure in the second decimal place is odd (1, 3, 5, and so forth).

8 Coaxial Members

8.1 Each coaxial member shall consist of a single central conductor covered in turn with solid or foamed insulation (with or without a skin) complying with 7.1.1 or of the air-gap construction complying with 7.1.1 and 7.2.1.1; a shield(s) (outer conductor) complying with Electromagnetic Shields, Section 9; and a jacket, which is required on a cable consisting of a single coaxial member, and is not required (see the last sentence of 5.8 regarding the maximum total thickness of two jackets on any member) on a coaxial member inside a multiple-member cable. The jacket on a coaxial member shall comply with Overall Cable Jacket, Section 15, where the jacket on the member constitutes the overall cable jacket.