

UL 444

ISBN 0-7629-0771-1

Communications Cables

Underwriters Laboratories Inc. (UL)
333 Pfingsten Road
Northbrook, IL 60062-2096

UL Standard for Safety for Communications Cables, UL 444

Third Edition, Dated March 29, 2002

Revisions: This Standard contains revisions through and including March 1, 2005.

UL Standards for Safety are developed and maintained in the Standard Generalized Markup Language (SGML). SGML – an international standard (ISO 8879-1986) – is a descriptive markup language that describes a document's structure and purpose, rather than its physical appearance on a page. Due to formatting differences resulting from the use of UL's new electronic publishing system, please note that additional pages (on which no requirements have been changed) may be included in revision pages due to relocation of existing text and reformatting of the Standard.

Text that has been changed in any manner is marked with a vertical line in the margin.

The new and revised requirements are substantially in accordance with UL's Bulletin(s) on this subject dated February 14, 2003, April 8, 2003, and October 26, 2004. The bulletin(s) is now obsolete and may be discarded.

The revisions dated March 1, 2005 include a reprinted title page (page 1) for this Standard.

As indicated on the title page (page 1), this UL Standard for Safety is an American National Standard. Attention is directed to the note on the title page of this Standard outlining the procedures to be followed to retain the approved text of this ANSI/UL Standard.

The master for this Standard at UL's Northbrook Office is the official document insofar as it relates to a UL service and the compliance of a product with respect to the requirements for that product and service, or if there are questions regarding the accuracy of this Standard.

UL's Standards for Safety are copyrighted by UL. Neither a printed copy of a Standard, nor the distribution diskette for a Standard-on-Diskette and the file for the Standard on the distribution diskette should be altered in any way. All of UL's Standards and all copyrights, ownerships, and rights regarding those Standards shall remain the sole and exclusive property of UL.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form by any means, electronic, mechanical photocopying, recording, or otherwise without prior permission of UL.

Revisions of UL Standards for Safety are issued from time to time. A UL Standard for Safety is current only if it incorporates the most recently adopted revisions.

UL provides this Standard "as is" without warranty of any kind, either expressed or implied, including but not limited to, the implied warranties of merchantability or fitness for any purpose.

In no event will UL be liable for any special, incidental, consequential, indirect or similar damages, including loss of profits, lost savings, loss of data, or any other damages arising out of the use of or the inability to use this Standard, even if UL or an authorized UL representative has been advised of the possibility of such damage. In no event shall UL's liability for any damage ever exceed the price paid for this Standard, regardless of the form of the claim.

UL will attempt to answer support requests concerning electronic versions of its Standards. However, this support service is offered on a reasonable efforts basis only, and UL may not be able to resolve every support request. UL supports the electronic versions of its Standards only if they are used under the conditions and operating systems for which it is intended. UL's support policies may change from time-to-time without notification.

UL reserves the right to change the format, presentation, file types and formats, delivery methods and formats, and the like of both its printed and electronic Standards without prior notice.

Purchasers of the electronic versions of UL's Standards for Safety agree to defend, indemnify, and hold UL harmless from and against any loss, expense, liability, damage, claim, or judgement (including reasonable attorney's fees) resulting from any error or deviation introduced while purchaser is storing an electronic Standard on the purchaser's computer system.

If a single-user version electronic Standard was purchased, one copy of this Standard may be stored on the hard disk of a single personal computer, or on a single LAN file-server or the permanent storage device of a multiple-user computer in such a manner that this Standard may only be accessed by one user at a time and for which there is no possibility of multiple concurrent access.

If a multiple-user version electronic Standard was purchased, one copy of the Standard may be stored on a single LAN file-server, or on the permanent storage device of a multiple-user computer, or on an Intranet server. The number of concurrent users shall not exceed the number of users authorized.

Electronic Standards are intended for on-line use, such as for viewing the requirements of a Standard, conducting a word search, and the like. Only one copy of the Standard may be printed from each single-user version of an electronic Standard. Only one copy of the Standard may be printed for each authorized user of a multiple-user version of an electronic Standard. Because of differences in the computer/software/printer setup used by UL and those of electronic Standards purchasers, the printed copy obtained by a purchaser may not look exactly like the on-line screen view or the printed Standard.

An employee of an organization purchasing a UL Standard can make a copy of the page or pages being viewed for their own fair and/or practical internal use.

The requirements in this Standard are now in effect, except for those paragraphs, sections, tables, figures, and/or other elements of the Standard having future effective dates as indicated in the preface. The prior text for requirements that have been revised and that have a future effective date are located after the Standard, and are preceded by a "SUPERSEDED REQUIREMENTS" notice.

New product submittals made prior to a specified future effective date will be judged under all of the requirements in this Standard including those requirements with a specified future effective date, unless the applicant specifically requests that the product be judged under the current requirements. However, if the applicant elects this option, it should be noted that compliance with all the requirements in this Standard will be required as a condition of continued Listing and Follow-Up Services after the effective date, and understanding of this should be signified in writing.

Copyright © 2005 Underwriters Laboratories Inc.

This Standard consists of pages dated as shown in the following checklist:

Page	Date
1-12B.....	March 1, 2005
13-15.....	March 29, 2002
16-17.....	March 1, 2005
18-28.....	March 29, 2002
29.....	March 1, 2005
30-34.....	March 29, 2002
35-48.....	March 1, 2005
A1-A2	March 1, 2005
B1-B2	March 1, 2005
SR1-SR2.....	March 1, 2005

No Text on This Page

Canadian Standards Association
CSA C22.2 No. 214-02
Sixth Edition

Underwriters Laboratories Inc.
UL 444
Third Edition



Communications Cables

March 29, 2002

(Title Page Reprinted: March 1, 2005)

Approved
by
Standards Council
of Canada



Commitment for Amendments

This Standard is issued jointly by Canadian Standards Association (CSA) and Underwriters Laboratories Incorporated (UL). Amendments to this Standard will be made only after processing according to the Standards writing procedures by CSA and UL.

Revisions of this Standard will be made by issuing revised or additional pages bearing their date of issue. A UL Standard is current only if it incorporates the most recently adopted revisions, all of which are itemized on the transmittal notice that accompanies the latest set of revised requirements.

ISBN 1-55324-438-9

Copyright © 2002
Canadian Standards Association
All rights reserved. No part of this publication may be reproduced in any form whatsoever without the prior permission of the publisher.

ISBN 0-7629-0771-1

Copyright © 2002, 2005
Underwriters Laboratories Inc.

CONTENTS

Preface	5
Foreword (CSA)	7
Foreword (UL)	8
Communication Cables	
1 Scope	9
2 Definitions	9
3 General	10
3.1 Reference publications	10
3.2 Units of measurement	12
3.3 General requirements	12
4 Construction	12
4.1 Conductors	12
4.2 Insulation	13
4.3 Optical fibre members	14
4.4 Core assembly	14
4.5 Spare pairs	15
4.6 Core binders	15
4.7 Core wrap	15
4.8 Shields	15
4.9 Jackets	16
4.10 Metallic sheaths	17
5 Manufacturing and production tests	17
5.1 Spark test after insulating	17
5.2 Continuity	19
5.3 Dielectric strength	19
6 Capability tests	20
6.1 Corrosion resistance of uncoated copper conductors	20
6.2 Crush resistance of insulation	21
6.3 Insulation unaged and heat-aged requirements	22
6.4 Insulation shrinkback	23
6.5 Insulation cold bend	23
6.6 AC leakage current through overall jacket	23
6.7 Durability of printing	24
6.8 Unaged and heat-aged requirements of jacket	24
6.9 Flexibility (PVDF jackets rated 125°C only)	25
6.10 Cable cold bend	26
6.11 Jacket peel test	26
6.12 Sunlight resistance of jacket of outdoor Type CMX cable	27
6.13 Cold impact of outdoor Type CMX cable	28
6.14 Flame and smoke requirements	29
6.15 Measuring thickness of insulation and rounding off the results	30
6.16 Conductor resistance	31
6.17 Conductor diameter	31
6.18 Compressive loading test for Type CMUC	32
6.19 Heat shock test for cross-connect wire	32
6.20 Deformation test for cross-connect wire	33

6.21 Dielectric tests for cross-connect wire 33

7 Marking of Cables 34

7.1 General 34

7.2 Type of marking 34

7.3 Required marking 34

7.4 Optional marking 36

7.5 Intervals 37

8 Marking on tag, reel, or carton 37

8.1 General requirements 37

8.2 Other marking 38

9 Date of manufacture 38

TABLES

Appendix A

Guidelines for sample selection for flame and smoke test requirements

Appendix B

Cable substitutions

Preface

This is the common UL and CSA Standard for Communications Cables. It is the sixth edition of CSA C22.2 No. 214 and the third edition of UL 444. This edition of CSA C22.2 No. 214 supersedes the previous editions, published in 1994, 1990, 1988, 1986, and 1984. This UL edition supersedes the previous editions published in 1994 and 1990.

This common standard was prepared by Canadian Standards Association and Underwriters Laboratories Inc. The effort of UL 444/CSA 214 Harmonization Committee is greatly appreciated.

The previous Tables 2A, 2B, 3A, 3B, 10 and 11 have been deleted, and Table 10 and a new Table 13 have been added. Tables have been renumbered.

This standard was reviewed by the CSA Subcommittee on C22.2 No. 214, under the jurisdiction of the Technical Committee on Wiring Products and the Strategic Resource Group, and has been formally approved by the Technical Committee.

This standard will be submitted to the American National Standards Institute (ANSI) for publication as an American National Standard.

Note: Although the intended primary application of this standard is stated in its Scope, it is important to note that it remains the responsibility of the users of the standard to judge its suitability for their particular purpose.

Level of harmonization

This standard uses an IEC format, but is not based on, nor shall it be considered equivalent to, an IEC standard. This standard is published as an identical standard. An identical standard is a standard that is the same in technical content except for conflicts in Codes and Governmental Regulations. Presentation shall be word for word except for editorial changes.

Interpretations

The interpretation by the SDO of an identical standard shall be based on the literal text to determine compliance with the standard in accordance with the procedural rules of the SDO. If more than one interpretation of the literal text has been identified, a revision shall be proposed as soon as possible to each of the SDOs to more accurately reflect the intent.

CSA Effective Date

The effective date for CSA will be announced through CSA *Informs* or a CSA Certification Notice.

UL Effective Date

As of March 1, 2005 all products Listed or Recognized by UL must comply with the requirements in this standard except for Clause 8.1.5 which is effective September 1, 2005.

Between March 1, 2005 and September 1, 2005, new product submittals to UL may be evaluated under all requirements in this standard or, if requested in writing, evaluated under presently effective requirements only. The presently effective requirements are contained in the third edition of UL 444.

A UL effective date is one established by Underwriters Laboratories Inc. and is not part of the ANSI approved standard.

The most recent designation of UL 444 as an American National Standard (ANSI) occurred on February 15, 2005.

This ANSI/UL Standard for Safety, which consists of the Third Edition with revisions through March 1, 2005 is under continuous maintenance, whereby each revision is ANSI approved upon publication. Comments or proposals for revisions on any part of the Standard may be submitted to UL at any time. Proposals should be submitted via a Proposal Request in UL's On-Line Collaborative Standards Development System (CSDS) at <http://csds.ul.com>.

Foreword (CSA)

The Canadian Standards Association (CSA) develops standards under the name Canadian Standards Association, and provides certification and testing under the name CSA International. CSA International provides certification services for manufacturers who, under license from CSA, wish to use the appropriate registered CSA Marks on certain products of their manufacture to indicate conformity with CSA Standards.

CSA Certification for a number of products is provided in the interest of maintaining agreed-upon standards of quality, performance, interchangeability and/or safety, as appropriate. Where applicable, certification may form the basis for acceptance by inspection authorities responsible for enforcement of regulations. Where feasible, programs will be developed for additional products for which certification is desired by producers, consumers, or other interests. In performing its functions in accordance with its objectives, CSA does not assume or undertake to discharge any responsibility of the manufacturer or any other party. The opinions and findings of the Association represent its professional judgement given with due consideration to the necessary limitations of practical operation and state of the art at the time the Standard is processed.

Products in substantial accord with this Standard but which exhibit a minor difference or a new feature may be deemed to meet the Standard providing the feature or difference is found acceptable utilizing appropriate CSA International Operating Procedures. Products that comply with this Standard shall not be certified if they are found to have additional features which are inconsistent with the intent of this Standard. Products shall not be certifiable if they are discovered to contravene applicable laws or regulations.

Testing techniques, test procedures, and instrumentation frequently must be prescribed by CSA International in addition to the technical requirements contained in Standards of CSA. In addition to markings specified in the Standard, CSA International may require special cautions, markings, and instructions that are not specified by the Standard.

Some tests required by CSA Standards may be inherently hazardous. The Association neither assumes nor accepts any responsibility for any injury or damage that may occur during or as the result of tests, wherever performed, whether performed in whole or in part by the manufacturer or the Association, and whether or not any equipment, facility, or personnel for or in connection with the test is furnished by the manufacturer or the Association.

Manufacturers should note that, in the event of the failure of CSA International to resolve an issue arising from the interpretation of requirements, there is an appeal procedure: the complainant should submit the matter, in writing, to the Secretary of the Canadian Standards Association.

If this Standard is to be used in obtaining CSA Certification please remember, when making application for certification, to request all current Amendments, Bulletins, Notices, and Technical Information Letters that may be applicable and for which there may be a nominal charge. For such information or for further information concerning CSA Certification, please address your inquiry to Applications and Customer Service, CSA International, 178 Rexdale Boulevard, Toronto, Ontario, Canada M9W 1R3.

Foreword (UL)

A. This Standard contains basic requirements for products covered by Underwriters Laboratories Inc. (UL) under its Follow-Up Service for this category within the limitations given below and in the Scope section of this Standard. These requirements are based upon sound engineering principles, research, records of tests and field experience, and an appreciation of the problems of manufacture, installation, and use derived from consultation with and information obtained from manufacturers, users, inspection authorities, and others having specialized experience. They are subject to revision as further experience and investigation may show is necessary or desirable.

B. The observance of the requirements of this Standard by a manufacturer is one of the conditions of the continued coverage of the manufacturer's product.

C. A product which complies with the text of this Standard will not necessarily be judged to comply with the Standard if, when examined and tested, it is found to have other features which impair the level of safety contemplated by these requirements.

D. A product employing materials or having forms of construction which conflict with specific requirements of the Standard cannot be judged to comply with the Standard. A product employing materials or having forms of construction not addressed by this Standard may be examined and tested according to the intent of the requirements and, if found to meet the intent of this Standard, may be judged to comply with the Standard.

E. UL, in performing its functions in accordance with its objectives, does not assume or undertake to discharge any responsibility of the manufacturer or any other party. The opinions and findings of UL represent its professional judgment given with due consideration to the necessary limitations of practical operation and state of the art at the time the Standard is processed. UL shall not be responsible to anyone for the use of or reliance upon this Standard by anyone. UL shall not incur any obligation or liability for damages, including consequential damages, arising out of or in connection with the use, interpretation of, or reliance upon this Standard.

F. Many tests required by the Standards of UL are inherently hazardous and adequate safeguards for personnel and property shall be employed in conducting such tests.

Communication Cables

1 Scope

1.1 This standard applies to 60 – 250°C single- or multiple-conductor jacketed or unjacketed, integral or nonintegral cables and single or multiple coaxial cables for telephone and other communication circuits such as voice, data, and audio for on-premise customer systems. These cables are not prohibited from containing one or more optical fibre members. For the purpose of this standard, a coaxial cable or coaxial member conductor is a single conductor with a shield. For the purpose of this standard, a single- or multiple-conductor unjacketed cable is a cross-connect wire.

1.2 This standard applies to communications cables that are intended primarily for installation in accordance with Section 60 of the *Canadian Electrical Code*(CEC), *Part I*, and Article 800 of the *National Electrical Code*(NEC). They are rated for 300 V applications but are not so marked.

1.3 This standard does not apply to communication cords.

1.4 In Canada, Type CMUC and cross-connect communications cables are not recognized by the Canadian Electrical Code, Part I.

2 Definitions

2.1 The following definitions apply in this standard:

2.2 **BONDED METAL SHIELD** – A covering over the cable core assembly consisting of a metal tape whose outer surface is adhesively bound to a polymeric jacket over it.

2.3 **CAPABILITY TEST** – A test that is conducted periodically on a cable component, or on a completed cable, intended to be proof of adequate construction and processing, and that is repeated for verification.

2.4 **COAXIAL CABLE** – A cable having one or more coaxial members, each consisting of a conductor centered inside one or more outer conductors consisting of metal tubes or shields, separated from the central conductor by a dielectric material.

2.5 **COVERING** – A jacket, sheath, or armour.

2.6 **CROSS-CONNECT WIRE (CABLE)** – A single- or multiple-conductor construction consisting of insulated conductors without an overall jacket.

2.7 **DIELECTRIC** – An insulating (nonconducting) medium.

2.8 **EQUIVALENT GAUGE** – A round conductor AWG number used to designate a flat conductor that has a cross-sectional area equal to that of the round conductor.

2.9 **GROUND PLANE** – A partially encompassing shield provided to reduce stray electrical fields.

2.10 **INTEGRAL** – A single extruded layer that serves as both insulation and jacket.

2.11 **JACKET** – A continuous nonmetallic outer covering.

2.12 **MANUFACTURING AND PRODUCTION TEST** – A test performed on a length of wire before further processing and/or on a completed cable before shipment.

Note: Where in-line packaging is used, and where conformity of the packaged product can be demonstrated, the tests may be performed on a master reel of the assembled cable prior to application of the final jacket.

2.13 SEMICONDUCTING – A material whose resistivity at room temperature is in the range of 10^{-2} – $10^9 \Omega \cdot \text{cm}$.

2.14 SHIELD – A conducting layer consisting of tape, braid, wire, or sheath, or a semiconducting layer.

2.15 THERMOPLASTIC – An insulation or jacket material that is capable of being repeatedly softened by heating and hardened by cooling through a temperature range characteristic of the material, and which in its softened state is capable of being shaped through the application of force.

Note: Examples of thermoplastic materials are polyethylene (PE), poly (vinyl chloride) (PVC), nylon, and polyethylene terephthalate (PET).

2.16 THERMOSET – A cross-linked insulating or jacketing compound that does not soften and flow on subsequent heating.

3 General

3.1 Reference publications

Where reference is made to other publications, such reference shall be considered to refer to the latest edition and all amendments published to that edition up to the time when the referencing standard is approved.

CSA Standards

C22.1-2002,
Canadian Electrical Code, Part I;

CAN/CSA-C22.2 No. 0-M91 (R1997),
General Requirements – Canadian Electrical Code, Part II;

C22.2 No. 0.3-01,
Test Methods for Electrical Wires and Cables

UL Standards

UL 1581-2001,
Reference Standard for Electrical Wires, Cables, and Flexible Cords;

UL 1666-2000,
Test for Flame Propagation Height of Electrical and Optical-Fiber Cables Installed Vertically in Shafts;

UL 1685-1997,
Vertical-Tray Fire-Propagation and Smoke-Release Test for Electrical and Optical-Fiber Cables.

ANSI¹ Standard

Z136 Series-1996/2000,
Safe Use of Lasers.

ANSI/NFPA² Standard

70-2002,
National Electric Code.

ASTM³ Standards

B 33-00,
Specification for Tinned Soft or Annealed Copper Wire for Electrical Purposes;

B 189-95,
Specification for Lead-Coated and Lead-Alloy-Coated Soft Copper Wire for Electrical Purposes;

B 286-95,
Specification for Copper Conductors for Use in Hookup Wire for Electronic Equipment;

B 298-99,
Specification for Silver-Coated Soft or Annealed Copper Wire;

B 355-95,
Specification for Nickel-Coated Soft or Annealed Copper Wire;

B 452-98,
Specification for Copper-Clad Steel Wire for Electronic Application;

B 869-96,
Specification for Copper-clad Steel Electrical Conductor for CATV Drop Wire;

D 573-99 ,
Standard Test Method for Rubber-Deterioration in an Air Oven;

D 5374-99,
Test Methods for Forced-Convection Laboratory Ovens for Evaluation of Electrical Insulation;

D 5423-99,
Specification for Forced-Convection Laboratory Ovens for Evaluation of Electrical Insulation;

G 151-00,
Standard Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources;

G 153-00,
Standard Practice for Operating Enclosed Carbon Arc Light Apparatus for Exposure of Nonmetallic Materials.

NFPA⁴ Standard

NFPA 262-1999
Standard Method of Test for Fire and Smoke Characteristics of Wire and Cables.

¹ American National Standards Institute

² American National Standards Institute/National Fire Protection Association.

³ American Society for Testing and Materials.

⁴ National Fire Protection Association.

3.2 Units of measurement

If a value for measurement is followed by a value in other units in parenthesis, the second value may be only approximate. The first stated value is the requirement.

3.3 General requirements

The requirements of CAN/CSA-C22.2 No. 0, when appropriate, apply to this standard.

4 Construction

4.1 Conductors

4.1.1 The conductors shall be solid or stranded, annealed, bare or metal-coated copper. The centre conductor of CMP, CMR, CMG, CM, CMH and CMX coaxial cables made of copper-clad steel shall have 21 percent or higher conductivity in accordance with ASTM Standard B 869. If the insulation adjacent to the copper conductor is of a material that corrodes unprotected copper in the test described in Clause 6.1, the conductor shall be covered with a coating of tin complying with ASTM Standard B 33, of lead or lead-alloy complying with ASTM Standard B 189, of nickel complying with ASTM Standard B 355, of silver complying with ASTM Standard B 298, or of another metal or alloy (evaluation shall be required). Metal-coating a conductor on which the coating is not required for corrosion protection shall be permitted. When this is done, the 100 per cent coverage requirement of the relevant ASTM Standard shall be waived.

The maximum temperature rating of cables relative to the diameter and coating of solid copper conductors or copper conductor strands shall not be higher than those shown in Table 1.

4.1.2 For stranded conductors, the length of lay of the strands shall not exceed 20 times the calculated diameter over the assembled conductor for No. 19 – 6 AWG conductor, or 30 times for No. 30 – 20 AWG conductor. The direction of lay of the strands may be right- or left-hand.

4.1.3 The conductors shall be continuous when tested in accordance with Clause 5.2.

4.1.4 The size of the copper conductor shall be determined either by means of the resistance shown in Tables 2 and 3, or by means of the dimensions shown in Table 4. In case of dispute, the resistance method shall be the referee method. Applications for various AWG sizes and conductor compositions are shown in Table 3A.

4.1.5 Resistance shall be determined in accordance with Clause 6.16.

4.1.6 Dimensions shall be determined in accordance with Clause 6.17.

4.1.7 A joint in a solid conductor or in one of the individual wires of a stranded conductor shall be made in a skillful manner, shall be essentially smooth, and shall not have any sharp projections.

A joint in a stranded conductor may be made by:

- a) Separately joining each individual wire; or

No Text on This Page